



Showcasing research from Professor Matsuura's laboratory,  
Graduate School of Engineering, Tottori University,  
Tottori, Japan.

An artificial viral capsid decorated with a DNA aptamer  
internalizing into lymphoma cells

Burkitt lymphoma-specific DNA aptamer-decorated artificial  
viral capsid self-assembled from  $\beta$ -annulus peptide bearing  
DNA aptamer was selectively internalized into Daudi cells,  
and doxorubicin complexed with the capsid selectively killed  
cells.

As featured in:



See Kazunori Matsuura *et al.*,  
*J. Mater. Chem. B*, 2023, 11, 6053.

Cite this: *J. Mater. Chem. B*, 2023, 11, 6053Received 29th January 2023,  
Accepted 22nd May 2023

DOI: 10.1039/d3tb00169e

rsc.li/materials-b

# An artificial viral capsid decorated with a DNA aptamer internalizing into lymphoma cells†

Kentarou Sakamoto,<sup>a</sup> Kohsuke Uchiyama,<sup>a</sup> Takashi Iwasaki,<sup>b</sup> Hiroshi Inaba<sup>id</sup><sup>ac</sup> and Kazunori Matsuura<sup>id</sup><sup>\*ac</sup>

Tumor-specific drug-delivering nanocarriers could be a promising modality for next-generation tumor therapy. Here we developed a Burkitt lymphoma-specific DNA aptamer-labeled nanocarrier using the  $\beta$ -Annulus peptide, which forms a spherical nanoassembly called artificial viral capsid. Dynamic light scattering and transmission electron microscopy of the DNA aptamer-decorated artificial viral capsid showed the formation of spherical assemblies with a diameter of approximately 50–150 nm. The artificial viral capsid was selectively internalized into the Burkitt lymphoma cell line, Daudi, and doxorubicin complexed with the capsid selectively killed Daudi cells.

## 1. Introduction

Aptamers have received attention as artificial biomolecular elements that specifically recognize the special structure of a target molecule specifically.<sup>1</sup> DNA aptamers are short sequences of artificial DNA that bind to a specific target and are mainly obtained *via* an *in vitro* selection method, which is also known as SELEX (Systematic Evolution of Ligands by EXponential enrichment).<sup>2</sup> Using this method, more specific DNA sequences are obtained by repeating (1) selection of sequences bound to target molecules from the randomized DNA library, (2) polymerase chain reaction amplification, and (3) condensing sequences with higher affinity. DNA aptamers recognize target molecules by forming their own conformation determined by their sequence; for example, thrombin-binding DNA aptamers form a G-quadruplex structure that recognizes their target, thrombin.<sup>3,4</sup>

Burkitt lymphoma is one of the most aggressive human cancers, and a drug delivery system (DDS) for the treatment of Burkitt lymphoma is highly desired. Tan *et al.* developed a DNA aptamer that can selectively bind to the Burkitt lymphoma cell line, Ramos cells.<sup>5</sup> Among their selected DNA aptamers, TE02 (43 base) showed the highest binding affinity toward Ramos cells with a dissociation constant of  $0.76 \pm 0.13$  nM. Using TE02 they developed a circular bispecific aptamer which can

bind to both Ramos cells and T cells to induce T cell-mediated tumor-specific killing,<sup>6</sup> and an aptamer-nanoparticle strip biosensor to detect Ramos cells for rapid and low-cost detection.<sup>7</sup> Its further application as a probe for early diagnosis of Burkitt lymphoma is anticipated.

The conjugation of aptamers to various nanomaterials, such as liposomes, inorganic nanoparticles, and viral capsids enables highly selective cell-targeted drug delivery.<sup>8,9</sup> For example, Kang *et al.* reported that liposomes decorated with the sgc8 aptamer, which specifically binds to leukemia cells, did not bind to nontarget cells but did bind to CCRF-CEM cells, the target leukemia cancer cells.<sup>10</sup> In addition, Francis *et al.* developed aptamer-decorated MS2 viral capsids that target the tyrosine kinase receptor on Jurkat T cells.<sup>11</sup>

Natural spherical viral capsids with icosahedral symmetry self-assembled from protein subunits have gained attention as nanomaterials with specific sizes, aggregation numbers, and inner cavities.<sup>12</sup> These properties enhance the possibility of using viral capsids as DDS carriers.<sup>13,14</sup> Recently, the artificial design of symmetrical assembled protein/peptide subunits has enabled the construction of virus-like nanocapsules.<sup>15–18</sup> To date, there have been several reports in that the protein/peptide nanocapsules are applied to in-cell experiments. Plasmid DNA was intracellularly delivered using viral capsid-like nanospheres self-assembled from *de novo* designed peptides.<sup>19–21</sup> Hilvert *et al.* recently demonstrated that *Aquifex aeolicus* lumazine synthase spontaneously forms self-assembled capsid-like protein shells in *E. coli* that efficiently encapsulate its own mRNA by laboratory evolution.<sup>22–24</sup> We also succeeded in creating an “artificial viral capsid” with a size of around 30–50 nm in water from self-assembly of a 24 a.a.  $\beta$ -Annulus peptide, which participates in the formation of the inner skeleton of the tomato bushy stunt virus.<sup>15,25</sup> Small angle x-ray scattering


<sup>a</sup> Department of Chemistry and Biotechnology, Graduate School of Engineering, Tottori University, Tottori 680-8552, Japan. E-mail: ma2ra-k@tottori-u.ac.jp

<sup>b</sup> Department of Bioresources Science, Graduate School of Agricultural Sciences, Tottori University, Tottori 680-8553, Japan

<sup>c</sup> Centre for Research on Green Sustainable Chemistry, Tottori University, Tottori 680-8552, Japan

† Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d3tb00169e>





**Fig. 1** A schematic view of (A) formation of a DNA aptamer-decorated artificial viral capsid and (B) Burkitt lymphoma-specific internalization of the DNA aptamer-decorated artificial viral capsid.

measurements revealed that the interior of the capsid is hollow.<sup>25</sup>  $\zeta$  potential measurements revealed that the N- and C-termini of the peptide direct to the inner and outer surfaces of the capsid, respectively.<sup>26</sup> By using these features, we succeeded in encapsulating DNA,<sup>26</sup> mRNA,<sup>27</sup> and His-tagged protein<sup>28,29</sup> into the artificial viral capsid *via* N-terminal modification. We also created capsids decorated with gold nanoparticles,<sup>30</sup> coiled-coil peptides,<sup>31</sup> single strand DNA,<sup>32</sup> human serum albumin,<sup>33</sup> and RNase S protein.<sup>34,35</sup>

In this study, we developed a DNA aptamer-decorated artificial viral capsid and utilized it as a Burkitt lymphoma cell line-specific DDS carrier. A Burkitt lymphoma cell-recognizing DNA aptamer TE02 was conjugated to the C-terminus of the  $\beta$ -Annulus peptide *via* a maleimide-activated carboxylic acid linker (Fig. 1). This conjugate ( $\beta$ -Annulus-TE02) self-assembled into the TE02-decorated artificial viral capsid and this capsid specifically internalized into the Burkitt lymphoma cell line, Daudi.

## 2. Materials and methods

### General methods

All reagents, including chemicals, materials, and cell culture media were obtained from commercial sources and used without further purification. 5'-H<sub>2</sub>N-(CH<sub>2</sub>)<sub>6</sub>-DNA was synthesized and purchased from BEX Co. Ltd. Ultrapure water with a high resistivity (> 18 M $\Omega$  cm) was purified using a Millipore Purification System (Milli-Q water) and was used as a solvent for the peptides and conjugates. Reversed-phase high performance liquid chromatography (RP-HPLC) was performed at ambient temperature using a Shimadzu LC-6AD liquid chromatography

system equipped with a UV/vis detector (220 nm, Shimadzu SPD-10AVvp) and Inertsil WP300 C18 (GL Science) columns (250  $\times$  4.6 mm or 250  $\times$  20 mm). Matrix-assisted laser desorption ionization-time-of-flight mass spectra were obtained using an Autoflex T2 instrument (Bruker Daltonics) in linear/positive mode with  $\alpha$ -cyano-4-hydroxy cinnamic acid ( $\alpha$ -CHCA) or 3-hydroxypicolinic acid/diammonium hydrogen citrate = 8/1 as the matrix.

### Solid-phase peptide synthesis

The peptide Ile-Asn(Trt)-His(Trt)-Val-Gly-Gly-Thr(*t*Bu)-Gly-Gly-Ala-Ile-Met-Ala-Pro-Val-Ala-Val-Thr(*t*Bu)-Arg(Pbf)-Gln(Trt)-Leu-Val-Gly-Ser-Gly-Gly-Gly-Cys(Trt)-Gly-Alko-PEG resin was synthesized on Fmoc-Gly-Alko-PEG resin (500 mg, 0.125 mmol, Watanabe Chemical Ind. Ltd.) using Fmoc-based coupling reactions (4 equiv. of Fmoc amino acids). An *N*-methylpyrrolidone (NMP) solution containing (1-cyano-2-ethoxy-2-oxoethylideneaminoxy)dimethylamino-morpholino-carbenium hexafluorophosphate (COMU) and diisopropylamine was used as the coupling reagent. Fmoc deprotection was performed using 20% piperidine in *N,N*-dimethylformamide (DMF). The coupling reaction and Fmoc deprotection were monitored using TNBS and a chloranil test kit (Tokyo Chemical Industry Co, Ltd). Peptidyl-resin was washed with NMP and dried *in vacuo*. Peptides were deprotected and cleaved from the resin using a cocktail of trifluoroacetic acid (TFA)/1,2-ethanedithiol/triisopropylamine/thioanisole/water = 8.25/0.25/0.1/0.5/0.5 (mL) at room temperature for 3 h. The reaction mixtures were filtered from the resins, and the peptide was precipitated by adding methyl *tert*-butyl ether (MTBE). The supernatant was decanted, and the precipitated peptide was dried *in vacuo* after three times of repetitive washing with MTBE. The crude peptide was purified using RP-HPLC on a C18 column eluting with a linear gradient of CH<sub>3</sub>CN/water containing 0.1% TFA (5/95 to 100/0 over 95 min). The mass of the purified peptide,  $\beta$ -Annulus-GGGCG, was confirmed using matrix-assisted laser desorption ionization-time-of-flight mass spectrometry (MALDI-TOF MS, matrix;  $\alpha$ -CHCA,  $m/z$  = 2637 ([M+H]<sup>+</sup><sub>calc.</sub> = 2638)).

### Synthesis of DNA-maleimide

DNA with an amino group *via* a hexamethylene chain at the 5' end (TE02-NH<sub>2</sub>-(5'-H<sub>2</sub>N-(CH<sub>2</sub>)<sub>6</sub>-TAGGCAGTGGTTTGCAGTCCGCATGTTGGGAATAGCCACGCCT-3') or random DNA-NH<sub>2</sub> (5'-H<sub>2</sub>N-(CH<sub>2</sub>)<sub>6</sub>-AAAAAAAACCCCCCCCCCGGGGGGGGGGGGGGGGTTTTTTTTTTTTT-3'), 0.9 mM in 20  $\mu$ L deionized water) was coupled with *N*-(4-maleimidobutyryloxy) sulfosuccinimide (Sulfo-GMBS, 120 equiv.) in the presence of 100 mM NaHCO<sub>3</sub> at 25  $^{\circ}$ C for 4 h. The solution was then dialyzed using a dialysis tube (Spectra/por7, molecular weight cut off (MWCO) 1 kDa, SPECTRUM) to remove excess Sulfo-GMBS, and the concentrations of TE02-maleimide and random DNA-maleimide were quantified using UV spectroscopy (JASCO FP-8200).

### Synthesis of the $\beta$ -annulus-DNA conjugate

The Michael reaction between DNA-maleimide and Cys residue in  $\beta$ -Annulus-GGGCG was performed as follows: DNA-maleimide and  $\beta$ -Annulus-GGGCG (16 equiv.) were mixed in 50%







for 24 h (final concentration; peptide, 25  $\mu\text{M}$ ; DOX, 0.167  $\mu\text{M}$ ). After incubation, 10  $\mu\text{L}$  WST-8 solution (Cell Counting Kit-8, DOJINDO) was added to each well and incubated at 37  $^{\circ}\text{C}$  for 1 h and absorbance at 450 nm was measured using microplate reader (Infinite 200 F Plex, TECAN).

### 3. Results and discussion

#### Synthesis of $\beta$ -annulus-DNA conjugates

$\beta$ -Annulus-TE02 was synthesized by conjugating  $\beta$ -Annulus-GGGCG (INHVGTTGGAIMAPVAVTRQLVGGGGCG-OH) and TE02 bearing an amino group *via* a hexamethylene chain at the 5' end (TE02-NH<sub>2</sub>) using Sulfo-GMBS, maleimide-activated carboxylic acid linker (Fig. 1A). In brief, the amino group of TE02-NH<sub>2</sub> was first coupled with Sulfo-GMBS (120 eq.) in the presence of sodium bicarbonate to produce TE02-maleimide. The Michael reaction proceeded between TE02-maleimide and the thiol group of Cys in  $\beta$ -Annulus-GGGCG. As a control,  $\beta$ -Annulus-random conjugate was prepared as well as  $\beta$ -Annulus-TE02 using random DNA-NH<sub>2</sub>. To visualize cellular localization of the conjugate, TAMRA- $\beta$ -Annulus was synthesized by labeling Cys- $\beta$ -Annulus with TAMRA-5-maleimide. Labelling of TE02 with TAMRA was conducted using TE02-NH<sub>2</sub> and 5-TAMRA, SE to produce TAMRA-TE02. The products were purified using RP-HPLC and the masses were identified using MALDI-TOF MS (Sup. Fig. 1).

#### Self-assembly of $\beta$ -Annulus-TE02 into the TE02-decorated artificial viral capsid

The formation of nanoparticles by self-assembly of  $\beta$ -Annulus-TE02 was confirmed using DLS (Fig. 2A) and TEM (Fig. 2B).  $\beta$ -Annulus-TE02 was dissolved in 10 mM phosphate buffer (pH 7.0) to produce 50, 25 and 5  $\mu\text{M}$   $\beta$ -Annulus-TE02 solutions. The solutions were sonicated for 5 min and incubated for 1 h at 25  $^{\circ}\text{C}$ . Assemblies were observed around 50 nm (25  $\mu\text{M}$ ; 55  $\pm$  16 nm, 5  $\mu\text{M}$ ; 53  $\pm$  12 nm) in the 25 and 5  $\mu\text{M}$  solutions, which are similar to artificial viral capsid reported in the previous studies.<sup>25–35</sup> However, in the 50  $\mu\text{M}$  solution, nanostructures with the size of 222  $\pm$  46 nm were observed, indicating aggregation of multiple capsids probably due to the interaction among DNAs on the capsids. These results suggest that at 25  $\mu\text{M}$  and 5  $\mu\text{M}$   $\beta$ -Annulus-TE02 forms discrete artificial viral capsids. In the TEM images, individual spherical assemblies with sizes of around 50–150 nm were observed in 25  $\mu\text{M}$  (see also Fig. S2A, ESI<sup>†</sup>) and 5  $\mu\text{M}$  solutions, whereas spherical assemblies with sizes of around 200 nm aggregates were observed in 50  $\mu\text{M}$  solution. These results are consistent with DLS measurements, indicating the formation of a spherical artificial viral capsid structure similar to that of  $\beta$ -Annulus (Fig. S2B, ESI<sup>†</sup>). TE02 only did not form any structure that could be observed by TEM (Fig. S2C, ESI<sup>†</sup>).

Furthermore, the secondary structure of TE02 decorating the artificial viral capsid was analyzed using CD spectra (Fig. 3). The CD spectrum of  $\beta$ -Annulus-TE02 showed typical B-type DNA double-helical structure similar to TE02 alone, implying




Fig. 2 Nanoparticle formation of  $\beta$ -Annulus-TE02. (A) Size distribution (left) and autocorrelation curve (right) obtained from DLS and (B) TEM images of  $\beta$ -Annulus-TE02 in 10 mM phosphate buffer.

that TE02 on the artificial viral capsid retains its original B-type DNA double-helical hairpin structure (Fig. 3A). We measured CD spectra at various temperatures to investigate the thermostability of the helical hairpin structure of TE02 and  $\beta$ -Annulus-TE02 (Fig. 3B). The increase in temperature decreased the molecular ellipticity at 270 nm in both samples, indicating denaturation of the double-helical hairpin. The difference spectrum between  $\beta$ -Annulus-TE02 and TE02 suggests that the peptide part of  $\beta$ -Annulus-TE02 partly retains its original secondary structure similar to  $\beta$ -Annulus-GGGCG (Fig. S3, ESI<sup>†</sup>): the difference between them may be due to the effect of the maleimido linker or steric hindrance between  $\beta$ -Annulus and TE02. The  $T_m$  values of TE02 and  $\beta$ -Annulus-TE02 were determined to be 40  $^{\circ}\text{C}$  and 45  $^{\circ}\text{C}$ , respectively, and these results suggested that TE02 on the artificial viral capsid was more stable than TE02 alone because of the dense display of TE02 on the capsid.






Fig. 3 (A) CD spectra of 20  $\mu\text{M}$   $\beta$ -Annulus-TE02 (red),  $\beta$ -Annulus-GGGCG (green), and TE02 (blue) in 10 mM phosphate buffer at 25  $^{\circ}\text{C}$ . (B) Temperature dependence in ellipticity at 270 nm of TE02 (blue) and  $\beta$ -Annulus-TE02 (red).

### Internalization of TE02-decorated artificial viral capsid into Burkitt lymphoma cells

The internalization of the TE02-decorated capsid was evaluated using coassembly of TAMRA-conjugated  $\beta$ -Annulus (TAMRA- $\beta$ -Annulus) and  $\beta$ -Annulus-TE02 (1 : 10 (mol:mol)). The formation of the assembled nanoparticles was confirmed using DLS (Fig. S4, ESI<sup>†</sup>). Daudi, a Burkitt lymphoma cell line, was treated by the TE02-decorated capsid co-assembled from 2.5  $\mu\text{M}$  TAMRA- $\beta$ -Annulus and 25  $\mu\text{M}$   $\beta$ -Annulus-TE02 (TAMRA/ $\beta$ -Annulus-TE02) in PBS(+) for 1 h. Cells were then washed twice with PBS(-) in a centrifugation step, and resuspended cells in PBS(+) were seeded on glass bottom dishes. TAMRA fluorescence in cells was observed using a CLSM (Fig. 4). As controls, cells were treated with the capsid co-assembled from 2.5  $\mu\text{M}$  TAMRA- $\beta$ -Annulus and 25  $\mu\text{M}$   $\beta$ -Annulus (TAMRA/ $\beta$ -Annulus) or 2.5  $\mu\text{M}$  TAMRA- $\beta$ -Annulus and 25  $\mu\text{M}$   $\beta$ -Annulus-random DNA (TAMRA/ $\beta$ -Annulus-random DNA) or 2.5  $\mu\text{M}$  TAMRA-TE02 and 25  $\mu\text{M}$  TE02 (TAMRA/TE02). In cells treated with the TE02-decorated capsid (TAMRA/ $\beta$ -Annulus-TE02), the fluorescence of TAMRA was located in the cell interior. The fluorescence of cells treated with control samples was also detected, but the intensity was weaker than that of cells with TAMRA/ $\beta$ -Annulus-TE02. The selectivity of TE02-decorated capsid toward Burkitt lymphoma cells was also investigated in comparison to Daudi and HeLa cells using CLSM (Fig. 4E). HeLa cells treated with TAMRA/ $\beta$ -Annulus-TE02 showed a subtle punctate signal, whereas Daudi cells treated with TAMRA/ $\beta$ -Annulus-TE02 showed strong fluorescence signals in the cytosol, indicating that TAMRA/ $\beta$ -Annulus-TE02 has the selectivity toward Burkitt lymphoma cells because of the




Fig. 4 (A)–(D) CLSM images of Daudi cells treated using (A) TE02-decorated capsid (TAMRA/ $\beta$ -Annulus-TE02), (B) random DNA-decorated capsid (TAMRA/ $\beta$ -Annulus-random DNA), (C) unmodified capsid (TAMRA/ $\beta$ -Annulus) and (D) TAMRA/TE02. (E) CLSM image of HeLa cells treated using TE02-decorated capsid (TAMRA/ $\beta$ -Annulus-TE02). TAMRA fluorescence was shown as white. Yellow dashed lines; cellular boundaries. Scale bars; 20  $\mu\text{m}$ .

binding selectivity of the TE02 aptamer. Since the surface of cells is negatively charged and the TE02-decorated capsid is also negatively charged, it can be thought that TE02-decorated capsid cannot interact with nontarget cells. Therefore, the off-target effect *e.g.*, cytotoxicity and cellular uptake toward normal cells in terms of the DDS carrier might be negligible.

We used flow cytometry analysis to quantify internalization efficiency (Fig. 5). The Daudi cells were treated in the same method for microscopic examination, and the pellet of the cells was resuspended in PBS(-) containing 2% FBS before the flow cytometry analysis was conducted. When treated with TAMRA/ $\beta$ -Annulus-TE02, many cell groups showed a higher fluorescence intensity than that of TAMRA/ $\beta$ -Annulus-random DNA,








Fig. 5 Flow cytometry analysis of Daudi cells treated with (A) TE02-decorated capsid (TAMRA/ $\beta$ -Annulus-TE02), (B) random DNA-decorated capsid (TAMRA/ $\beta$ -Annulus-random DNA), (C) unmodified capsid (TAMRA/ $\beta$ -Annulus) and (D) TAMRA-TE02.

indicating that the secondary structure of TE02 is important for binding to the Burkitt lymphoma cells. In contrast, TAMRA-TE02-treated cells did not have such a cell group with higher fluorescence intensity, implying the advantage of artificial viral capsids in terms of multivalent binding to lymphoma cells.

To investigate the applicability of the TE02-decorated artificial viral capsid as a lymphoma cell-specific drug carrier, we treated HeLa or Daudi cells with doxorubicin (DOX), one of the most used anticancer drugs, complexed with the TE02-decorated capsid and performed cell viability assay (Fig. 6).




Fig. 6 Cell viability assay of (A) HeLa cells and (B) Daudi cells treated with DOX (0.167  $\mu$ M) complexed with  $\beta$ -Annulus or  $\beta$ -Annulus-TE02 (25  $\mu$ M).

While at HeLa cells DOX showed no cytotoxicity, at Daudi cells DOX showed moderate cytotoxicity ( $\sim$ 25% cell death). In addition, half of Daudi cells was killed by DOX complexed with the TE02-decorated capsid, whereas DOX complexed with the unmodified capsid was not so effective. This result indicates the *in vitro* applicability of the TE02-decorated capsid for Burkitt lymphoma-specific cell killing.

## 4. Conclusions

In this study, we created a Burkitt lymphoma cell-specific TE02 aptamer-decorated artificial viral capsid. The capsid was formed in phosphate buffer, and the TE02 aptamer retained its original B-type DNA double-helical hairpin structure on the capsid. The TAMRA-labeled TE02-decorated capsid was internalized into its target cell, Daudi, and the fluorescence of TAMRA was located in the cell interior. The specific cell killing toward Burkitt lymphoma cells was also demonstrated compared with HeLa cells.

Since Burkitt lymphoma is a highly aggressive cancer, a new type of treatment methodology is urgently needed. Targeting Burkitt lymphoma using a DDS carrier would be a promising therapeutic method with a high cure rate and low toxicity,<sup>36</sup> and the Burkitt lymphoma-targeting TE02 aptamer-decorated nanoparticles that we developed could be one answer for the DDS carrier toward Burkitt lymphoma. Compared to other polymer- and lipid-based DDS carriers, this peptide/DNA-based nanocarrier has higher biocompatibility compared to polymer-based DDS carriers and reduces accumulation in the liver compared to lipid-based DDS carriers because of complexation of lipid with Apolipoprotein E in the blood.<sup>37</sup> This report indicates the applicability of a cell-specific aptamer-coated peptide-based nanocarrier toward the cell-specific internalization. This strategy could also be applied to other peptide/protein-based nanocarriers mentioned above.<sup>19–21</sup> We are now considering encapsulating other drugs or nucleic acid therapeutics in a tumor-selective aptamer-decorated capsid to achieve tumor-specific cell killing *in vitro* in the future.

## Author contributions

K. S. performed cellular experiment and wrote the paper with K. M. K. U. synthesized the peptide and performed *in vitro* experiments. T. I. distributed the Daudi cells to us and supervised the flow cytometry experiment. H. I. supervised whole experiment with K. M. K. M. directed the project, designed the experiments and wrote the manuscript with K. S.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This research was supported by a Grant-in-Aid for Scientific Research (B) (JSPS KAKENHI Grant No. JP 22H02199), a



Grant-in-Aid for Scientific Research (S) (JSPS KAKENHI Grant No. JP22H04975), a Grant-in-Aid for JSPS Fellows (JSPS KAKENHI Grant No. JP21J01604), and AGC Research Collaboration System.

## Notes and references

- X. Fang and W. Tan, *Acc. Chem. Res.*, 2010, **43**, 48–57.
- M. Blind and M. Blank, *Mol. Ther. – Nucleic Acids*, 2015, **4**, e223.
- L. C. Bock, L. C. Griffin, J. A. Latham, E. H. Vermaas and J. J. Toole, *Nature*, 1992, **355**, 564–566.
- R. F. Macaya, P. Schultze, F. W. Smith, J. A. Roe and J. Feigon, *Proc. Natl. Acad. Sci. U. S. A.*, 1993, **90**, 3745–3749.
- Z. Tang, D. Shangguan, K. Wang, H. Shi, K. Sefah, P. Mallikratchy, H. W. Chen, Y. Li and W. Tan, *Anal. Chem.*, 2007, **79**, 4900–4907.
- G. J. Tong, S. C. Hsiao, Z. M. Carrico and M. B. Francis, *J. Am. Chem. Soc.*, 2009, **131**, 11174–11178.
- Y. Yang, X. Sun, J. Xu, C. Cui, H. Safari Yazd, X. Pan, Y. Zhu, X. Chen, X. Li, J. Li and W. Tan, *ACS Nano*, 2020, **14**, 9562–9571.
- Y. Zhang, H. Hong and W. Cai, *Curr. Med. Chem.*, 2011, **18**, 4185–4194.
- X. Li, Q. Zhao and L. Qiu, *J. Controlled Release*, 2013, **171**, 152–162.
- H. Kang, M. B. O'Donoghue, H. Liu and W. Tan, *Chem. Commun.*, 2010, **46**, 249–251.
- G. Liu, X. Mao, J. A. Phillips, H. Xu, W. Tan and L. Zeng, *Anal. Chem.*, 2009, **81**, 10013–10018.
- Y. Khudyakov and P. Pumpens, *Viral Nanotechnology*, CRC Press, Boca Raton, FL, USA, 2016.
- P. van Rijn and R. Schirhagl, *Adv. Healthcare Mater.*, 2016, **5**, 1386–1400.
- A. M. When and N. F. Steinmetz, *Chem. Soc. Rev.*, 2016, **45**, 4074–4126.
- K. Matsuura, *Chem. Commun.*, 2018, **54**, 8944–8959.
- Q. Luo, C. Hou, Y. Bai, R. Wang and J. Liu, *Chem. Rev.*, 2016, **116**, 13571–13632.
- S. L. Kuan, F. R. G. Bergamini and T. Weil, *Chem. Soc. Rev.*, 2018, **47**, 9069–9105.
- S. Lou, X. Wang, Z. Yu and L. Shi, *Adv. Sci.*, 2019, **6**, 1802043.
- M. Cao, Z. Zhang, X. Zhang, Y. Wang, J. Wu, Z. Liu, L. Sun, D. Wang, T. Yue, Y. Han, Y. Wang, Y. Wang and M. Wang, *J. Colloid Interface Sci.*, 2022, **615**, 395–407.
- J. E. Noble, E. De Santis, J. Ravi, B. Lamarre, V. Castelletto, J. Mantell, S. Ray and M. G. Ryadnov, *J. Am. Chem. Soc.*, 2016, **138**, 12202–12210.
- J. Kong, Y. Wang, J. Zhang, W. Qi, R. Su and Z. He, *Angew. Chem., Int. Ed.*, 2018, **57**, 14032–14036.
- Y. Azuma, T. G. W. Edwardson, N. Terasaka and D. Hilvert, *J. Am. Chem. Soc.*, 2018, **140**, 566–569.
- N. Terasaka, Y. Azuma and D. Hilvert, *Proc. Natl. Acad. Sci. U. S. A.*, 2018, **115**, 5432–5437.
- S. Tetter, N. Terasaka, A. Steinauer, R. J. Bingham, S. Clark, A. J. P. Scott, N. Patel, M. Leibundgut, E. Wroblewski, N. Ban, P. G. Stockley, R. Twarock and D. Hilvert, *Science*, 2021, **372**, 1220–1224.
- K. Matsuura, K. Watanabe, T. Matsuzaki, K. Sakurai and N. Kimizuka, *Angew. Chem., Int. Ed.*, 2010, **49**, 9662–9665.
- K. Matsuura, K. Watanabe, Y. Matsushita and N. Kimizuka, *Polym. J.*, 2013, **45**, 529–534.
- Y. Nakamura, Y. Sato, H. Inaba, T. Iwasaki and K. Matsuura, *Appl. Sci.*, 2020, **10**, 1–10.
- K. Matsuura, T. Nakamura, K. Watanabe, T. Noguchi, K. Minamihata, N. Kamiya and N. Kimizuka, *Org. Biomol. Chem.*, 2016, **14**, 7869–7874.
- K. Sakamoto, H. Furukawa, J. V. V. Arafiles, M. Imanishi, K. Matsuura and S. Futaki, *Bioconjugate Chem.*, 2022, **33**, 311–320.
- K. Matsuura, G. Ueno and S. Fujita, *Polym. J.*, 2015, **47**, 146–151.
- S. Fujita and K. Matsuura, *Org. Biomol. Chem.*, 2017, **15**, 5070–5077.
- Y. Nakamura, S. Yamada, S. Nishikawa and K. Matsuura, *J. Pept. Sci.*, 2017, **23**, 636–643.
- K. Matsuura and T. Honjo, *Bioconjugate Chem.*, 2019, **30**, 1636–1641.
- K. Matsuura, J. Ota, S. Fujita, Y. Shiomi and H. Inaba, *J. Org. Chem.*, 2020, **85**, 1668–1673.
- Y. Liang, H. Furukawa, K. Sakamoto, H. Inaba and K. Matsuura, *ChemBioChem*, 2022, **23**, e202200220.
- E. M. Molyneux, R. Rochford, B. Griffin, R. Newton, G. Jackson, G. Menon, C. J. Harrison, T. Israels and S. Bailey, *Lancet*, 2012, **379**, 1234–1244.
- X. Yan, F. Kuipers, L. M. Havekes, R. Havinga, B. Dontje, K. Poelstra, G. L. Scherphof and J. A. A. M. Kamps, *Biochem. Biophys. Res. Commun.*, 2005, **328**, 57–62.

