

ChemComm

Chemical Communications

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: L. de Jonge, I. Hazenberg, H. Singh, T. Loman, A. P. Prakasham and A. Palmans, *Chem. Commun.*, 2026, DOI: 10.1039/D5CC06993A.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

COMMUNICATION

Consequences of Encapsulated vs Covalently Attached Pd-NHC Amphiphilic Polymeric Nanocatalysts in Bioorthogonal Catalysis

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

A comparison between novel Pd-NHC (N-heterocyclic carbene) catalysts covalently and non-covalently attached to polymeric nanoparticles reveals that hydrophobic domains in the vicinity of the Pd catalysts aid catalytic activity, and covalent attachment reduces cytotoxicity, opening new avenues to tune bioorthogonal reactivity of TMC-based nanocarriers.

The field of bioorthogonal chemistry and catalysis has conveniently opened up numerous novel directions in biology, such as protein conjugation, cell engineering, drug delivery, antibody-drug conjugates, and *in situ* prodrug activation, to name a few.^{1–3} Typically, these non-natural reactions are performed in living systems without interfering with native biological processes, which uniquely distinguishes them as ‘bioorthogonal’ reactions. Transition metal catalysts (TMCs) hold tremendous potential in this field by the manifold of intriguing organic transformations they catalyse.^{4,5} However, their potential in complex biological environments has been hampered by toxicity, instability and deactivation, and poor solubility in aqueous media.⁶ As a result, nanocarriers have been engineered to incorporate TMCs and thereby enhance their stability and improve their biocompatibility in biological media.^{7,8} Of particular interest are amphiphilic heterograft polymers that collapse in water to form nanometer-sized nanoparticles (NPs) with hydrophobic interiors.^{9,10} These NPs carry the TMCs within their hydrophobic core, improving water compatibility and limiting exposure of TMCs to complex media.

Recently, several advanced nanocarriers have been developed for the Pd(0/II)-mediated bioorthogonal prodye and prodrug activation in complex environments (Table S12).^{11–14} We have previously developed amphiphilic heterograft polymers with PPh_3 and bipyridine pendants that complex Pd(II) and found that the resulting NPs were capable of activating prodyes and prodrugs in water as well as in complex media.¹⁵ However, the polymers with pendant PPh_3 were highly sensitive to oxidation to the corresponding oxide, requiring demanding formulation conditions to obtain the Pd(II)-based NPs. Both the


nature of the ligand and the polymer's microstructure proved important for the catalyst's activity and stability, but activity was reduced in cell culture growth media. As part of our interest in using polymeric nanoparticles as carriers for bioorthogonal catalysts,^{16–18} we here focus on NHC ligands for the preparation of Pd(II) catalysts for bond cleavage activation of prodyes. Pd-NHC catalysts are highly effective in various C–X (X = C, N, O, S) bond forming reactions,¹⁹ and also function in water.²⁰ Wegner *et al* showed that incorporation of a Pd-NHC complex in the membrane of *E. coli* allowed the bioorthogonal cleavage of propargyl ethers.²¹ Their simple synthesis, stability, divergent structural motifs and high metal affinity make NHC a ligand of choice in organometallic chemistry. NHC-ligands were recently used by us in combination with Cu(I), showing excellent CuAAC activity in presence of 15 mM glutathione.²² Moreover, Cu(I)-NHC embedded in a polymer showed bioorthogonal activity in cellular media and mouse models.²³ Here, we apply NHC ligands for complexing to Pd(II) and evaluate the activity in aqueous and complex media, and compatibility with mammalian cells to assess their suitability for bioorthogonal catalysis. Particularly, we unveil the intriguing differences between physically encapsulated and covalently attached Pd-NHC to polymeric NPs, highlighting the effect of the hydrophobic micro-environment on catalyst activity, toxicity and stability.

We designed our NHC ligand with the following features: i) presence of a fused bicyclic motif for strong coordination and steric shielding for Pd ii) azide moiety for covalent ('click') attachment to amphiphilic polymer and iii) $-\text{CF}_3$ label for easy NMR characterization within the polymer matrix. The $-\text{N}_3$ and $-\text{CF}_3$ group appended bicyclic 1,2,4-triazole based NHC ligand precursor (**1**) was synthesized from L-pyroglutamic acid through a sequence of manipulations (see ESI for details, Scheme S1, Fig. S1–S4).²⁴ Pd-NHC complex (**2**) was synthesized by reacting (**1**) with PdBr_2 in presence of KBr , K_2CO_3 as base and pyridine as solvent for the reaction (Scheme 1). The pyridine in complex **2** is a labile, throw away ligand, which aids the incoming substrates during the catalysis process.²⁵ The formation of complex **2** was confirmed by the disappearance of the characteristic NCHN resonance of the precarbene in the ^1H NMR while the $^{19}\text{F}\{^1\text{H}\}$ signal was observed at -62.51 ppm for the $-\text{CF}_3$ group (Fig. S5–S11).

Department of Chemical Engineering & Chemistry and Institute for Complex Molecular Systems, Eindhoven University of Technology, P.O. Box 513, 5600 MB Eindhoven, The Netherlands. E-mail: a.palmans@tue.nl, a.p.prakasham@tue.nl

In order to reinforce the Pd center further by the combined effect of both the phosphine and NHC ligands, complex **(3)** was made by replacing the Py ligand with a PPh_3 ligand in complex **(2)** (Fig. S12-S19). The typical Pd coordinated *cis*- PPh_3 signal was

observed at 26.20 ppm in the $^{31}\text{P}\{^1\text{H}\}$ NMR (Fig. S17, Table S14). The presence of $-\text{N}_3$ in Pd complexes **(2)** and **(3)** was confirmed using IR spectroscopy where the azido stretch appeared around 2113 cm^{-1} (Fig. S10 and S18).²⁶



Scheme 1. Synthesis of Pd(II)-NHC complexes **(2)**, **(3)** and covalently Pd-NHC functionalized amphiphilic **(P2)** polymers.





Figure 1. A) $^{19}\text{F}\{^1\text{H}\}$ and $^{31}\text{P}\{^1\text{H}\}$ NMR of **P2@12% Pd-PPPh₃**; B) Pd quantification by ICP-OES measured in milliQ water (*) or 2 % THF in milliQ water (#); C) Experimental SAXS curves (symbols) and worm-like chain form factor fits (lines) for Pd-based NPs.

We incorporated the Pd complexes **2** and **3** into the amphiphilic nanoparticles by physical encapsulation as well as attached them to the heterograft polymers via a click reaction. For encapsulation, **P1** polymer was used, which contained 20% *n*-dodecyl chains for hydrophobic collapse and 80% Jeffamine®M1000 for water solubility. For the covalent linking, we prepared polymer **P2** with strained alkyne containing dibenzocyclooctyne (DBCO) grafts (12%) and dodecyl (22%) and Jeffamine (66%) as hydrophobic and hydrophilic graft, respectively. Polymers **P1,2** were made by post functionalization modification of the poly(pentafluorophenylacrylate) using previously optimized procedures and fully characterized (Fig. S20-S31).¹⁵ Using a strain promoted azide-alkyne cycloaddition (SPAAC) the azide functional Pd complexes were readily attached to the DBCO linked polymer backbone. Complete functionalization (12%) of **P2** was done with Pd complexes **(2)** and **(3)** to obtain polymers **P2@12% Pd-Py** and **P2@12% Pd-PPPh₃**. In order to check the effect of catalyst concentration and polymer microstructure, half of the DBCO groups were functionalized, i.e., 6%, with **(3)** affording polymer **P2@6% Pd-PPPh₃** (Scheme 1). Here, we also aimed to study the synergistic effect of NHC and PPh_3 ligands on Pd, which is expected to enhance stability and activity in catalysis.²⁷⁻²⁹ After post functionalization, all polymers were purified using dialysis to remove unbound grafts/Pd/free pentafluorophenol and fully characterized (Fig. S32-S40).

The presence of polymer bound Pd was confirmed by NMR where, for instance, the $-\text{CF}_3$ group signal was observed at -62.48 ppm and the Pd bound PPh_3 signal was observed at 26.69 ppm for **P2@12% Pd-PPPh₃** in their respective $^{19}\text{F}\{^1\text{H}\}$ and $^{31}\text{P}\{^1\text{H}\}$ NMR (Fig. 1A). The Pd concentration in the polymer samples was quantified using inductively coupled plasma optical emission spectroscopy (ICP-OES). The measured Pd concentrations were in good agreement with the calculated Pd concentration. The higher concentration measured for **P2@12% Pd-PPPh₃** suggests that the excess Pd complex used in the click reaction was not completely removed by dialysis (Fig. 1B). After formulating the obtained **P1,2**-based polymers into NPs in water, dynamic light scattering (DLS) showed hydrodynamic radii (R_H) of the NPs around $6.5\text{--}11.6\text{ nm}$, similar to the ones previously reported (Table S1 and Fig. S41).¹⁵



Scheme 2. Model prodyne activation using Pd nanoparticles.

More detailed insights into the nature of the NPs were obtained from small angle X-ray scattering (SAXS) analysis in water (ESI section 4.4). The experimental SAXS curves (Fig. 1C)

show global shapes indicative of conformationally stretched chains with limited flexibility for all NPs, similar to our previously studied copolymers lacking Pd complexes.³⁰ The experimental data were fit to the previously applied semiflexible worm-like chain model.²⁹ Comparison of the two encapsulated **P1** NPs revealed that the form factor fits (details in ESI, Table S4) were in good agreement with the experimental data. The Kuhn length l_k , i.e. the distance over which the polymer is rigid, was around 9 nm for **P1**-based NPs containing encapsulated Pd catalysts, similar to the previously studied Jeffamine-based NPs with only hydrophobic grafts.³⁰

The shape of the scattering curve obtained for **P2@12% Pd-Py** closely resembled that of **P1-Pd-Py**, indicating that




Figure 2. A) Kinetic profiles of encapsulated **P1** and covalently attached **P2** NPs in a pro-DNP (4) (100 μ M) to DNP (5) conversion monitored by UV-Vis over time at $\lambda = 400$ nm in water at 37 °C using 30 μ M of Pd; B) $T_{1/2}$ comparison of the **P1** and **P2** NPs in the formation of DNP (5); $T_{1/2}$ (time taken for 50 % formation of DNP (5) by UV-Vis, mean of multiple runs); C) HPLC conversion of DNP (5) after 24 h.

The hydrophobic interior of the NPs not only comprise the hydrophobic catalysts, but also sequester hydrophobic substrates in water.³¹ We applied two different dyes, pro-2,4-dinitro phenol (4) and pro-coumarin (6) to test the TMC activation strategy as this allows real time monitoring of the catalytic process by absorption or fluorescence spectroscopy, respectively. To start with, we studied the depropargylation reaction of *O*-propargylated 2,4-dinitro phenol (4) using the new Pd-NHC NPs (Scheme 2). The reactions were performed in water (37 °C) using a substrate to catalyst S/C ratio of 10/3 (100 μ M substrate, 30 μ M Pd). The formation of the dye, 2,4-dinitro phenol (5) was monitored using UV-Vis spectroscopy at $\lambda = 400$ nm. The encapsulated **P1** particles steadily cleaved the *O*-propargyl group of the pro-DNP in water over 12 h. **P1-Pd-Py** NPs showed slightly better activity than the **P1-Pd-PPPh₃** NPs (Fig. 2A). Also the **P2**-based NPs showed good activity in water and both the covalently attached **P2@12% Pd-Py** and **P2@12% Pd-PPPh₃** NPs showed similar behavior. Interestingly, increasing the polymer concentration while keeping the S/C ratio constant by comparing **P2@12% Pd-PPPh₃** to **P2@6% Pd-PPPh₃** (Fig. 2B) revealed notable differences, with the latter system showing a higher activity. This indicated that the presence of more hydrophobic compartments in **P2@6% Pd-PPPh₃** benefits the rate of the deprotection reaction while keeping the overall Pd concentration constant. This is also obvious from the Pd to polymer (P) ratio, where Pd:P is 24:1 for **P2@12% Pd-PPPh₃** while it is 12:1 for **P2@6% Pd-PPPh₃** with an overall [Pd] of 30 μ M in both cases (Table S5). The enhanced activity observed for the **P2@6% Pd-PPPh₃** NPs suggests that more hydrophobic domains are more beneficial than a higher local concentration of Pd.

nanoparticle shape and compactness are not significantly affected by physical encapsulation or covalent attachment.³² **P2**-based NPs showed some aggregation as evidenced by the upturn at low q values. This effect was more pronounced for the 12% functionalized particles and the PPh₃ comprising polymers. To account for the aggregation, we adapted our fitting strategy by combining a power-law model with the flexible cylinder model to extract data from the scattering curves for **P2**-based polymers (Fig. 1C). This afforded good fits. Notably, the Kuhn lengths l_k of **P2**-based polymers were comparable to the **P1**-based polymers, albeit that l_k was slightly higher (\approx 16.0 nm) for **P2@12% Pd-PPPh₃**, suggesting a lower flexibility (Table S4).

Additionally, the higher Kuhn length observed for **P2@12% Pd-PPPh₃** suggested a less dynamic polymer chain adopting more compact conformations. Such rigidity can restrict segmental motion and diffusion pathways, partially shielding catalytic sites and reducing substrate accessibility, eventually leading to diminished catalytic activity. All the experiments were repeated at least four times to ensure reproducibility and consistency of the observed trend.

The average catalytic activity of different polymeric NPs was compared against $T_{1/2}$, the time it takes to reach 50% formation of DNP (5), approximated by an absorbance of 0.3 at 400 nm in the UV-Vis spectrum (see ESI section 5.1 for details). Fig. 2B showed that encapsulated **P1-Pd-Py** is the fastest and covalent **P2@6% Pd-PPPh₃** is faster than **P2@12% Pd-PPPh₃** when keeping the S/C ratio constant. Additionally, the formation of DNP (5) was quantified by HPLC after 24 h (ESI section 5.2; Table S7). Analyzing all reactions after 24 h with a S/C ratio of 10/3 showed higher amounts of DNP formed for the covalent systems compared to the encapsulated systems (Fig. 2C). In fact, after 24 h, the best performing covalent system, **P2@6% Pd-PPPh₃** showed full conversion, whereas the best performing encapsulated **P1-Pd-Py** had a conversion of 87% to DNP. In addition, **P1-Pd-PPPh₃** showed a 58% formation of DNP. The results show that the covalent systems outperformed the encapsulated system. This aligns with our previous observations where a PdPPPh₃ complex encapsulated into NPs was slower than covalently crosslinked PdPPPh₃ complexes.¹⁵ However, the observed activity of these novel NHC-Pd-based NPs was lower (full conversion after 24 h) than our previous NPs (full conversion after 3.3 h, for same S/C 10/3), confirming the

COMMUNICATION

ChemComm

important role of the ligand and polymer microstructure for better catalytic activity.³² The differences between **P1** and **P2** extend beyond the mode of catalyst attachment and also include variations in P:Pd ratio, polymer graft composition and hydrophobic domain content, all of which may contribute to the observed differences in catalytic activity.

To assess the cytotoxicity of the novel catalytic systems, important for bioorthogonal reactivity, all NPs were incubated with HeLa cells for 24 h. The cell viability was tested using the CCK-8 assay. The results showed that the encapsulated **P1** NPs exhibited more pronounced toxicity than the covalently attached **P2** NPs. **P2@12% Pd-PPh₃** NPs was the least toxic after 24 h of incubation (Fig. S61). Even at high Pd concentrations of 100 μ M, the cell viability remained high. This finding emphasizes the beneficial effect of having covalently attached Pd catalysts in the polymer chain for better biocompatibility.

Having established that some of the novel catalytic NPs show good compatibility with mammalian cells, we finally tested the reactivity of the new catalysts in complex media. To this end, all reactions were repeated in PBS and the cell culture media, RPMI (preferred growth media for suspension cell lines) and DMEM (preferred for adherent cell lines). Cell culture media are a good predictor for catalyst activity in *in vitro* conditions.³³ The catalytic activity was mostly retained in PBS with **Pd-Py** containing NPs showing enhanced activity. Unfortunately, activity was mostly lost in RPMI and DMEM (Fig. S47), also for the most active **P2@6% Pd-PPh₃**. Changing the substrate from pro-DNP to pro-cou (**6**) (ESI section 5.3) containing a carbamate protecting group showed a similar trend in water, whereas in presence of cell culture media did not result in the formation of fluorescent dye (**7**). The loss of Pd activity in cell culture media prompted the investigation of deactivation pathways. Substrate activation studies in presence of 30 μ M of various biomolecules revealed strong inhibition by L-histidine, L-cysteine and glutathione for both **P1** and **P2** NPs, consistent with Pd catalyst poisoning by amine and sulfur nucleophiles (Fig. S48). This is in line with the results of Wegner *et al* where the catalytic reactions worked when performed in buffered conditions with *E. coli*, but failed for mammalian cells.²¹ Lastly, the reusability of the Pd NPs was evaluated by re-adding the substrate after the first run (15 h), and the Pd NPs remained active even after 30 h continuously cleaving the substrate in water (Fig. S49).

In summary, we developed novel Pd-NHC based polymeric nanoparticles and investigated their potential for bioorthogonal bond cleavage reactions. Covalently Pd-NHC attached NPs performed better than the encapsulated ones and the **P2@6% Pd-PPh₃** NPs with more hydrophobic micro-environment performed the best for prodye activation reactions in water. Additionally, the covalently linked **P2** NPs were less toxic to HeLa cells than the physically encapsulated **P1** NPs. Despite improved aqueous activity and reduced toxicity, Pd nanoparticles remained susceptible to deactivation by biological nucleophiles. Strategies such as the incorporation of chelate stabilizing ligands, polymer compartmentalization and cross-linking to enhance catalyst protection are underway in our laboratory.

Conflicts of interest

[View Article Online](#)
DOI: 10.1039/D5CC06993A

There are no conflicts to declare.

Data availability

† Electronic supplementary information (ESI) available: Experimental procedures, characterization and spectroscopic data; ¹H, ¹³C{¹H}, ¹⁹F{¹H}, ³¹P{¹H} NMR, MALDI-ToF-MS spectra of Pd-NHCs, GPC, DLS, ICP-OES, SAXS data of polymers, UV-Vis and fluorescence spectra, HPLC traces of the kinetics runs are available in the electronic supplementary information. See DOI: 10.1039/x0xx00000x. The SAXS data related to this article is available in DOI: 10.15151/ESRF-ES-2010314049.

Acknowledgements

The project has received funding from the European Union's Horizon 2020 research and innovation program under the Marie Skłodowska-Curie grant agreement no. 899987. We gratefully acknowledge support by The Dutch Research Council (NWO Gravitation; IPM program), the TU/e and Peter Lipman for ICP-OES analysis. We thank the staff of the ESRF and EMBL Grenoble for assistance and support in using beamline BM29 under proposal number MX-2677.

References

- 1 F. M. Zielke and F. P. J. T. Rutjes, *Top. Curr. Chem.*, 2023, **381**, 35.
- 2 W. Wang, X. Zhang, R. Huang, C.-M. Hirschbiegel, H. Wang, Y. Ding and V. M. Rotello, *Adv. Drug Deliv. Rev.*, 2021, **176**, 113893.
- 3 E. M. Sletten and C. R. Bertozzi, *Angew. Chem. Int. Ed.*, 2009, **48**, 6974–6998.
- 4 J. H. Docherty, T. M. Lister, G. McArthur, M. T. Findlay, P. Domingo-Legarda, J. Kenyon, S. Choudhary and I. Larrosa, *Chem. Rev.*, 2023, **123**, 7692–7760.
- 5 U. Bin Kim, D. J. Jung, H. J. Jeon, K. Rathwell and S. Lee, *Chem. Rev.*, 2020, **120**, 13382–13433.
- 6 J. Miguel-Ávila, M. Tomás-Gamasa and J. L. Mascareñas, *Trends Chem.*, 2023, **5**, 474–485.
- 7 A. A. H. Laporte and J. N. H. Reek, *Chem. Rev.*, 2025, **125**, 7223–7274.
- 8 F. Huang, J. Liu, M. Li and Y. Liu, *J. Am. Chem. Soc.*, 2023, **145**, 26983–26992.
- 9 A.-S. Glaive, C. Le Cœur, J.-M. Guigner, C. Amiel and G. Volet, *Langmuir*, 2024, **40**, 2050–2063.
- 10 J. Odrobińska, M. Skonieczna and D. Neugebauer, *Int. J. Mol. Sci.*, 2021, **22**, 1202.
- 11 R. Martínez, C. Carrillo-Carrión, P. Destito, A. Alvarez, M. Tomás-Gamasa, B. Pelaz, F. Lopez, J. L. Mascareñas and P. del Pino, *Cell Rep. Phys. Sci.*, 2020, **1**, 100076.
- 12 E. Indrigo, J. Clavadetscher, S. V. Chankeshwara, A. Megia-Fernandez, A. Lilienkampf and M. Bradley, *Chem. Commun.*, 2017, **53**, 6712–6715.
- 13 J. Li, J. Yu, J. Zhao, J. Wang, S. Zheng, S. Lin, L. Chen, M. Yang, S. Jia, X. Zhang and P. R. Chen, *Nat. Chem.*, 2014, **6**, 352–361.
- 14 B. J. Stenton, B. L. Oliveira, M. J. Matos, L. Sinatra and G. J. L. Bernardes, *Chem. Sci.*, 2018, **9**, 4185–4189.



Journal Name

COMMUNICATION

15 A. Sathyan, S. Croke, A. M. Pérez-López, B. F. M. de Waal, A. Unciti-Broceta and A. R. A. Palmans, *Mol. Syst. Des. Eng.*, 2022, **7**, 1736–1748.

16 A. Sathyan, E. Archontakis, A. J. H. Spiering, L. Albertazzi and A. R. A. Palmans, *Molecules*, 2024, **29**, 1850.

17 L. Deng, A. Sathyan, C. Adam, A. Unciti-Broceta, V. Sebastian and A. R. A. Palmans, *Nano Lett.*, 2024, **24**, 2242–2249.

18 A. Sathyan, T. Loman, L. Deng and A. R. A. Palmans, *Nanoscale*, 2023, **15**, 12710–12717.

19 N. Muniyappan and S. Budagumpi, *Inorg. Chim Acta*, 2026, **589**, 122915.

20 E. Levin, E. Ivry, C. E. Diesendruck and N. G. Lemcoff, *Chem. Rev.*, 2015, **115**, 4607–4692.

21 T. Wegner, A. Dombovski, K. Gesing, A. Köhrer, M. Elinkmann, U. Karst, F. Glorius and J. Jose, *Chem. Sci.*, 2023, **14**, 11896–11906.

22 A. P. Prakasham, H. Singh and A. R. A. Palmans, *Chem. Commun.*, 2025, **61**, 9697–9700.

23 D. Zheng, J. Tao, L. Jiang, X. Zhang, H. He, X. Shen, Y. Sang, Y. Liu, Z. Yang and Z. Nie, *J. Am. Chem. Soc.*, 2025, **147**, 998–1007.

24 J. Brand, J. Siles and J. Waser, *Synlett*, 2010, 881–884.

25 M. Kumar Gangwar, S. Dey, Prakasham. A. P and P. Ghosh, *Polyhedron*, 2021, **197**, 115011. DOI: 10.1039/D5CC06993A

26 J. Y. Park, H.-J. Kwon, S. Mondal, H. Han, K. Kwak and M. Cho, *Phys. Chem. Chem. Phys.*, 2020, **22**, 19223–19229.

27 E. Bortolamiol, G. Isetta, I. Caligiuri, N. Demitri, S. Paganelli, F. Rizzolio, T. Scattolin and F. Visentini, *Eur. J. Inorg. Chem.*, 2023, **26**, e202300084.

28 A. Kumar, M. K. Gangwar, A. P. Prakasham, D. Mhatre, A. Ch. Kalita and P. Ghosh, *Inorg. Chem.*, 2016, **55**, 2882–2893.

29 T. E. Schmid, D. C. Jones, O. Songis, O. Diebolt, M. R. L. Furst, A. M. Z. Slawin and C. S. J. Cazin, *Dalton Trans.*, 2013, **42**, 7345.

30 S. Wijker, D. Dellemme, L. Deng, B. Fehér, I. K. Voets, M. Surin and A. R. A. Palmans, *ACS Macro Lett.*, 2025, **14**, 428–433.

31 M. Artar, E. R. J. Souren, T. Terashima, E. W. Meijer and A. R. A. Palmans, *ACS Macro Lett.*, 2015, **4**, 1099–1103.

32 J. Willenbacher, O. Altintas, V. Trouillet, N. Knöfel, M. J. Monteiro, P. W. Roesky and C. Barner-Kowollik, *Polym. Chem.*, 2015, **6**, 4358–4365.

33 Y. Liu, S. Pujals, P. J. M. Stals, T. Paulöhrl, S. I. Presolski, E. W. Meijer, L. Albertazzi and A. R. A. Palmans, *J. Am. Chem. Soc.*, 2018, **140**, 3423–3433.



† Electronic supplementary information (ESI) available: Experimental procedures, characterization and spectroscopic data; ^1H , ^{13}C { ^1H }, ^{19}F { ^1H }, ^{31}P { ^1H } NMR, MALDI-ToF-MS spectra of Pd-NHCs, GPC, DLS, ICP-OES, SAXS data of polymers, UV-Vis and fluorescence spectra, HPLC traces of the kinetics runs are available in the electronic supplementary information. See DOI: 10.1039/x0xx00000x. The SAXS data related to this article is available in DOI: 10.15151/ESRF-ES2010314049

[View Article Online](#)
DOI: 10.1039/D5CC06993A