

Cite this: *J. Mater. Chem. A*, 2023, 11, 26519

The N, P co-doped carbon-loading Ni₃P@Ni heterojunction nanocomposites derived from polybenzimidazoles grafted with oxygen-phosphorus group as high-efficiency electrocatalyst for oxygen evolution reaction†

Gang Wang,^{id}*^a Wenshuai Tang,^a Shuai Yang,^a Mingxia Lu,^a Hongliang Wei,^{id}^a Lifeng Cui^{*b} and Xiaodong Chen^{id}*^c

Interfacial engineering-induced structural optimization is considered an expectant strategy to elevate the electrochemical activities of earth-abundant electrocatalysts. Herein, the pioneering architecture of Ni₃P@Ni heterojunctions embedded onto N, P co-doped C substrates was effectuated by a combination of the wet-impregnation process of Ni/polybenzimidazoles containing an oxygen-phosphorus group (PBI-OP) precursor and phosphating/carbonization treatment to obtain the Ni₃P@Ni/CNP electrocatalyst. It provides substantial Ni₃P@Ni heterojunction interfacial sites, and the strong interaction between Ni₃P@Ni nanosheets and CNP microspheres promotes the rearrangement of the electronic configuration to modify the electrochemically active sites while enhancing the structural stability and promoting interfacial electron transfer, thus improving the electrocatalytic activity of OER. In addition, the large number of pyridine N species on the electrocatalyst accelerated the diffusion of O₂, further reducing the overpotential of OER. DFT calculation unveiled that Ni₃P@Ni/CNP has a lower activation energy than IrO₂, indicating its extremely positive electrocatalytic effect on the OER kinetics. Ni₃P@Ni/CNP-M exhibits a low overpotential of 239 mV, a low Tafel slope of 52 mV dec⁻¹, and good stability at a current density of 10 mA cm⁻² in 1 M KOH electrolyte. Therefore, interfacial engineering through multi-component structures can provide new inspiration for designing advanced OER electrocatalysts.

Received 6th September 2023
Accepted 14th November 2023

DOI: 10.1039/d3ta05422e

rsc.li/materials-a

1. Introduction

The increasing energy crisis and environmental pollution brought on by the overconsumption of traditional fossil fuels have made it imperative to find eco-friendly and cost-effective renewable energy sources. Hydrogen is gaining attention globally as a clean and renewable energy source. The electrocatalytic decomposition of water to produce hydrogen is considered as a method to alleviate the current energy and environmental difficulties.¹⁻⁴ The anodic oxygen evolution reaction (OER), rather than the hydrogen evolution reaction (HER), is a complicated quadrielectron transfer reaction, and its sluggish reaction kinetics is a bottleneck in water electrolysis

technology.⁵ Despite numerous measures taken to improve OER kinetics, the results are still unsatisfactory, and there is an urgent need to push forward the exploration of high-efficiency OER electrocatalysts. At present, iridium, ruthenium, and the corresponding oxides (Ir, Ru, IrO₂, and RuO₂) are well-known for the benchmarked OER electrocatalysts, but their large-scale commercialization is limited due to their scarce reserves.^{6,7} Accordingly, the development of low-cost, earth-abundant, and high-performance OER electrocatalysts is still the key to realizing large-scale hydrogen production by electrochemical water electrolysis.

Currently, the investigation for efficacious and cost-effective nanomaterials as OER electrocatalysts has motivated a great deal of investment in transition metal phosphides,⁸⁻¹¹ nitrides,¹²⁻¹⁴ carbides,^{15,16} and other earth-abundant alternatives. Among these, nickel phosphide (Ni₃P) with suitable d-electron configurations and metallic properties has been extensively considered as a promising non-precious-metal OER electrocatalyst on account of its advantages of desirable intrinsic activity, chemical stability, and especially low polarization.¹⁷⁻²⁰ Nevertheless, the practical application of the Ni₃P electrocatalyst has been severely restricted by several

^aCollege of Chemistry and Chemical Engineering, Henan University of Technology, Zhengzhou 450001, PR China. E-mail: gwang198@gmail.com

^bCollege of Smart Energy, Shanghai Jiao Tong University, Shanghai 200240, PR China. E-mail: lcui@usst.edu.cn

^cDepartment of Mechanical Engineering, City University of Hong Kong, Tat Chee Avenue, Kowloon, Hong Kong SAR, China. E-mail: chenxd19891115@163.com

† Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d3ta05422e>

obstacles, such as the poor apparent activity, terrible conductivity, and insufficient exposure of electrocatalytically active sites triggered by the uncontrollable aggregation and metastable ability during the long-term OER proceedings.²¹ To respond to these challenges, multiple strategies have been executed to accelerate the electrocatalytic OER performance of Ni₃P nanomaterials, including the architecture of heterostructure interfaces,²² heteroatom doping,²³ nanostructure tailoring,²⁴ and hybridization.²⁵ Among them, refining ultrafine heterojunctions has been widely confirmed as one of the most approvable and feasible methods for optimizing local electronic structures, enhancing electrical conductivity, boosting charge transformation, and strengthening structural stability, which comprehensively facilitates majorizations in the adsorption energy of OER intermediates (O*, OH*, and OOH*) and thus giving rise to the increased intrinsic activity.²⁶ In particular, the controlled integration of Ni₃P with metals at the atomic/nano dimension to generate Janus-type metal/semiconductor heterojunctions enabled not only a favorable inheritance of the electrochemical properties of both contiguous components but also exerted significant charge redistribution and interface modification between them, which initiated the amelioration of electrocatalytically active sites and the compositional synergistic synergy, thus contributing to the enhancement of OER kinetics.²² Therefore, the integrated electrochemical performance of hetero-structured electrocatalysts was generally better than that of single-component counterparts or physical mixtures.²⁷ Aside from electrocatalytic activity promotion *via* heterostructure engineering, the compositing active components with the carbonaceous nanomaterial would upgrade the conductivity while also further anchoring, decentralizing, and assembling the electrocatalytically active sites, leading to the improvement of electron transfer ability, reinforcement of structural ability, and increment in the quantity of accessible active sites.²⁸ Accordingly, the controlled fabrication of composites of well-defined Janus-structured metal/Ni₃P heterostructures with carbonaceous materials as high-efficiency OER electrocatalysts is feasible, even though it is challenging.

Enlightened by the aforementioned statement, we legitimately synthesized the well-defined and neatly distributed Janus-architected Ni/Ni₃P heterojunction nanosheets immobilized over the N, P co-doped carbon substrate (Ni₃P@Ni/CNP) through a wet-impregnation treatment of Ni/polybenzimidazoles containing an oxygen-phosphorus group (PBI-OP) precursor, followed by thermal annealing. The well-refined heterojunction formed by the robust bonding of Ni₃P and Ni could inherit exclusive chemical properties of both phases well to strengthen the synergistic effect and structural stability and simultaneously could effectively induce electron rearrangement to modify the electrocatalytically active sites, thus contributing to the enhancement of overall OER performance. In addition, the introduction of N, P co-doped C nanomaterial by the self-consumption of PBI-OP as a substrate for the Ni₃P@Ni heterojunction encouraged the dispersion and exposure of electrocatalytically active sites and also increased the electrical conductivity. It was also demonstrated that a significant amount of pyridinic N species survive in the

Ni₃P@Ni/CNP electrocatalysts, which could favor the release of O₂ molecules to further bring down the OER overpotential.²⁹ After the electrochemical test, our synthesized Ni₃P@Ni/CNP electrocatalyst displayed better performance than similar products and even commercial IrO₂, particularly Ni₃P@Ni/CNP-M, which only needed a low overpotential of 239 mV to reach the current density of 10 mA cm⁻² in 1 M KOH electrolyte solution, and the Tafel slope was only 52 mV dec⁻¹. Moreover, the current density of Ni₃P@Ni/CNP-M remained almost unchanged after 20 h of continuous operation at 10 mA cm⁻², demonstrating its excellent stability.

2. Experiments

2.1. Materials

3,3'-Diaminobenzidine (DAB) and bis(4-carboxyphenyl) phenyl phosphine oxide (BCPPO) were purchased from ACROS ORGANICS and SCIENTIFIC COMPASS, respectively. Nickel(II) chloride hexahydrate (NiCl₂·6H₂O, 98%) was purchased from Alab (Shanghai, China). Polyphosphoric acid (PPA, 80%) and other chemicals were purchased from Nanjing Chemical Reagent Co. The chemicals used in the study were used without any further purification.

2.2. Preparation of PBI-OP

P₂O₅ and PPA were added to a three-neck flask with a mechanical stirrer and N₂ inlet and outlet. Under the N₂ atmosphere, the contents were warmed to 175 °C, stirred to dissolve P₂O₅ completely, and then cooled down to room temperature. DAB was added and stirred at 80 °C and 120 °C for 1 h each and then cooled to room temperature. BCPPO was added and stirred at 120 °C, 150 °C, 170 °C, and 190 °C for 12 h. The resulting mixture was cooled slightly and then poured into deionized water to obtain a brown product. The product was washed several times with deionized water to neutral and then soaked in 5 wt% Na₂CO₃ solution for 24 h. After washing with deionized water, the product was dried under vacuum at 100 °C for 36 h. PBI-OP was characterized by ¹H NMR, and as shown in Fig. 1, all H ions in the PBI-OP structure could be matched to the corresponding signal peaks, which proved the successful synthesis of PBI-OP in our preparation conditions (yield: 97%. ¹H NMR



Fig. 1 ¹H NMR spectrum and the corresponding chemical structure of PBI-OP.

(DMSO- d_6 , ppm): 13.31, 8.40, 7.88, 7.87, 7.76, 7.74, 7.67, 7.61, 7.59).

2.3. Preparation of Ni₃P@Ni/CNP samples

Nickel(II) chloride hexahydrate (NiCl₂·6H₂O) was dissolved in deionized water and sonicated for 15 min to form a homogeneous solution. Then, the PBI-OP powder was added to the NiCl₂ solution, stirred at 75 °C until the water was completely evaporated, and dried at 100 °C for 24 h using a vacuum drying oven to obtain the Ni/PBI-OP precursor. Next, the precursor was calcined in a tube furnace and roasted under N₂ atmosphere at a set annealing temperature of 700 °C, 800 °C, and 900 °C for 3 h with a heating rate of 5 °C min⁻¹, respectively, and the obtained samples were denoted as Ni₃P@Ni/CNP-L, Ni₃P@Ni/CNP-M, and Ni₃P@Ni/CNP-H.

2.4. Material characterization

The FTIR spectra of samples were obtained by Thermo Scientific Nicolet iS20 in the range of 400–4000 cm⁻¹. The Raman spectra of samples were recorded with HORIBA Scientific LabRAM HR Evolution using a 532 nm laser diode as the excitation source. XRD patterns were obtained at 2θ values between 10° and 90° using a Japanese Rigaku Ultima IV with Cu K α radiation ($\lambda = 0.15418$ nm) at a current of 40 mA and voltage of 40 kV. The morphology of samples was observed by scanning electron microscopy (SEM, Zeiss Gemini 300) and transmission electron microscopy (TEM, JEM 2100F). XPS analysis was performed on a Thermo ESCALAB 250XI instrument. Curve fitting and background subtraction were performed using Advantage software. The specific surface area of the powder samples was calculated using the BET model on a Micromeritics ASAP 2460 3.01 instrument. Based on the nitrogen adsorption data, the pore size distribution was calculated using the non-local density functional theory (NLDFT) equilibrium model. The thermal decomposition of ~6 mg powder samples was carried out with a thermogravimetric analysis (STA 449F3) instrument under a flowing nitrogen atmosphere (20 cm³ min⁻¹) at a heating rate of 10.0 °C min⁻¹ up to 1000 °C. The first-principles method was utilized to perform density functional theory (DFT) calculations within the generalized gradient approximation (GGA) using the Perdew–Burke–Ernzerhof (PBE) formulation, which could quantitatively calculate the reaction energy barrier of the elementary step of the OER process, thus further exploring the OER mechanism of Ni₃P@Ni/CNP electrocatalysts.

2.5. Electrocatalytic measurements

All the samples were tested for electrocatalytic activity using a Corrtest CS350M Electrochemical workstation with a standard three-electrode system. The electrocatalyst ink was obtained by dispersing 5 mg of the sample into 650 μ L of ethanol and 95 μ L of Nafion solution (5% mass fraction) through ultrasonication treatment for 30 min. Hg/HgO electrodes, graphite rods, and polished glassy carbon electrodes were selected as reference, counter, and working electrodes, respectively, for the electrochemical tests. The glassy carbon electrodes need to be cleaned before they can be used for electrochemical testing. Firstly, the

glassy carbon electrodes were polished with 0.3 μ m polishing powder, then put into an ultrasonic water bath for 2–3 min each time and repeated three times, and finally cleaned in anhydrous ethanol and deionized water. After cleaning, the glassy carbon electrode was activated using cyclic voltammetry in 0.5 M H₂SO₄ solution with a scanning range of 1.0 to –1.0 V until a stable pattern was obtained before use. 5 μ L of the catalyst ink was deposited on a polished glass carbon electrode with a diameter of 3 mm with a catalyst loading of 0.475 mg cm⁻², dried at room temperature and tested.

Linear sweep voltammetry (LSV) was used to record polarization curves at a scan rate of 10 mV s⁻¹. The electrochemical impedance spectroscopy (EIS) measurements were measured at 0.005 V vs. RHE over a frequency range of 0.1–10⁶ Hz. The double layer capacitance (C_{dl}) of the samples was measured by cyclic voltammetry (CV) at different scan rates in the non-Faraday region. Electrochemical surface area (ECSA) was calculated by recording j ($j = j_a - j_c$) curves at different scan rates at 1.26 V (vs. RHE) using a linear slope (equivalent to $2C_{dl}$). The stability of PBI-OP and Ni₃P@Ni/CNP catalysts was tested by the chronopotentiometry method, in which the voltage values of PBI-OP, Ni₃P@Ni/CNP-L, Ni₃P@Ni/CNP-M, and Ni₃P@Ni/CNP-H were set as 1.794 V, 1.589 V, 1.469 V, and 1.566 V, respectively. Their current densities can reach 10 mA cm⁻² at the corresponding voltage values, and then they were run continuously for 48 h to observe the changes in the period current density.

3. Results and discussion

The categories of Ni₃P@Ni/CNP samples could be successfully fabricated by a combination of the wetness-impregnation method and thermal annealing treatment. Briefly stated, the trailblazing PBI-OP was first synthesized by the copolymerization of DAB and BCPPO in the mixed liquids of P₂O₅ and PPA, and then the Ni²⁺ of NiCl₂·6H₂O was immobilized on its surface through Ni–N coordination bonds to form the Ni/PBI-OP precursor.³⁰ Eventually, going through the phosphating/carbonization processes, the Ni/PBI-OP precursor could be transformed into the Ni₃P@Ni/CNP samples as expected (Fig. 2a). The XRD patterns of the synthesized PBI-OP, Ni/PBI-OP precursor, and Ni₃P@Ni/CNP samples are depicted in Fig. 2b. More concretely, the PBI-OP presented a non-crystallinity peak at 21.8°, which indicated the periodicity and parallelism of the PBI-OP backbone and also proved its amorphous structure.^{30,31} In contrast, the Ni/PBI-OP precursor also exhibited a similar but weak diffraction peak, suggesting that the polymer chain of PBI-OP did not suffer any damage when PBI-OP was successfully anchored with Ni²⁺ ions during the wet-impregnation process. No other diffraction peaks were observed for the Ni/PBI-OP precursor, suggesting that the Ni²⁺ ions were highly decentralized without forming crystal species over the PBI-OP substrate. Whereas for Ni₃P@Ni/CNP samples, there were no peaks mentioned above, but several novel distinctive diffraction peaks appeared in the XRD spectrum, disclosing that the structure of PBI-OP has been decomposed and carbonized during the annealing process. The three prominent peaks



Fig. 2 (a) Schematic illustration of the preparation process of $\text{Ni}_3\text{P@Ni/CNP}$ samples. (b) XRD patterns of PBI-OP, Ni/PBI-OP precursor, $\text{Ni}_3\text{P@Ni/CNP-L}$, $\text{Ni}_3\text{P@Ni/CNP-M}$, and $\text{Ni}_3\text{P@Ni/CNP-H}$. (c) FT-IR spectrum, (d) Raman spectrum, and (e) N_2 adsorption–desorption isotherms of PBI-OP, $\text{Ni}_3\text{P@Ni/CNP-L}$, $\text{Ni}_3\text{P@Ni/CNP-M}$, and $\text{Ni}_3\text{P@Ni/CNP-H}$.

located at 44.50° , 51.85° , and 76.38° corresponded to the (111), (200), and (220) crystal planes of metallic Ni (JCPDS No. 87-0712), respectively, while the cognizable peaks at 41.76° , 42.82° , 43.63° , 46.32° , 47.14° , 50.44° , 52.52° , and 75.24° respectively, were indexed to the (231), (330), (112), (202), (141), (222), (132), and (233) crystal planes of Ni_3P (JCPDS No. 34-0501). The diffraction peak detected at about 25° for the $\text{Ni}_3\text{P@Ni/CNP}$ samples indicated the formation of a carbon substrate.³¹ Realistically, these results manifested that the annealing

temperatures set at 700°C , 800°C , and 900°C were reasonable and capable for the generation of Ni, Ni_3P , and carbon phase, which were further confirmed by the TG/DTA analysis (Fig. S2†). This consequence could be perceived as a prerequisite for the fabrication of the targeted $\text{Ni}_3\text{P@Ni/CNP}$ heterojunction samples.²²

The chemical structures of PBI-OP and $\text{Ni}_3\text{P@Ni/CNP}$ samples were further characterized by FTIR and Raman spectroscopies. As displayed in Fig. 2c, several prominent FTIR

characteristic peaks of PBI-OP were detected at 1605 cm^{-1} , 1432 cm^{-1} , 1285 cm^{-1} , 1169 cm^{-1} , and 823 cm^{-1} respectively, which were ascribed to the C=C/C=N stretching vibration of the benzimidazole ring, C=C stretching vibration of the benzene ring, respiratory vibration of the imidazole ring, oxygen phosphorus group, and C-H out of plane bending vibration in the aromatic ring, thus confirming the successful synthesis of PBI-OP in our preparation conditions.^{32–34} Nevertheless, the FTIR characteristic peak belonging to PBI-OP was not observed in the $\text{Ni}_3\text{P@Ni/CNP}$ samples, which was mainly attributed to the fact that the structure of PBI-OP was subjected to complete decomposition during the annealing proceedings. Noticeably, a new emergent characteristic peak was recognized at 609 cm^{-1} and assigned to the stretching vibration of the Ni–P bond, thus confirming the successful synthesis of the Ni_3P phase, which was consistent with XRD results.^{35–37} The Raman spectra of the synthesized PBI-OP and $\text{Ni}_3\text{P@Ni/CNP}$ samples are shown in Fig. 2d. It is illustrated that there are no obvious characteristic peaks in the Raman spectra of PBI-OP. Whereas for $\text{Ni}_3\text{P@Ni/C}$ samples, two dominant peaks at 1342 cm^{-1} (D band) and 1588 cm^{-1} (G-band) were well recognized, corresponding to the graphite structural defects and tangential vibrations of the graphite phase.^{38,39} These confirmed the formation of a microcrystalline graphite structure, which could impart the $\text{Ni}_3\text{P@Ni/CNP}$ samples with high electrical conductivity. It was worth noting that the I_D/I_G value of $\text{Ni}_3\text{P@Ni/CNP-M}$ was calculated to be as high as about 1.17, much larger than those of $\text{Ni}_3\text{P@Ni/CNP-L}$ (1.04) and $\text{Ni}_3\text{P@Ni/CNP-H}$ (1.08). This disclosed the generation of more crystal defects over $\text{Ni}_3\text{P@Ni/CNP-M}$, which could effectively excite the conductivity band to elevate the electronic conductivity. This is of great importance as it would be dedicated to the enhancement of OER electrocatalytic performance.⁴⁰

The N_2 adsorption–desorption isotherms were employed to determine the specific surface area, total pore volume, and pore size distribution for PBI-OP and $\text{Ni}_3\text{P@Ni/CNP}$ samples. As shown in Fig. 2e, all samples presented type IV isotherms with a significant H_3 hysteresis loop, thus revealing the abundant existence of mesopores and macropores in these samples.²² The pore size profiles of all the samples (Fig. S3†) indicated that their pore size distributions were mainly concentrated in the 2–10 nm range. Correspondingly, the BET specific surface area of PBI-OP, $\text{Ni}_3\text{P@Ni/CNP-L}$, $\text{Ni}_3\text{P@Ni/CNP-M}$, and $\text{Ni}_3\text{P@Ni/CNP-H}$ was calculated to be $12.03\text{ m}^2\text{ g}^{-1}$, $345.60\text{ m}^2\text{ g}^{-1}$, $374.01\text{ m}^2\text{ g}^{-1}$, and $370.29\text{ m}^2\text{ g}^{-1}$, respectively (Table S1†). To be noted, the BET specific surface area of PBI-OP was much lower than those of the $\text{Ni}_3\text{P@Ni/CNP}$ samples, suggesting that during the phase transformation process from PBI-OP to $\text{Ni}_3\text{P@Ni/CNP}$, the samples underwent giant morphological changes, and large amounts of mesopores and micropores were generated after the annealing treatment. $\text{Ni}_3\text{P@Ni/CNP-M}$ possessed the largest BET specific surface area, which originated from its abundant generation of mesoporous and microporous nanostructures at the appropriate annealing temperature of $800\text{ }^\circ\text{C}$.^{22,41} On these grounds, it was more sensible to infer that there were more intersecting micropores surviving in $\text{Ni}_3\text{P@Ni/CNP-M}$, which could furnish more available channels for the

diffusion and permeation of the electrolyte, formation of exposed active sites, and release of O_2 bubbles during the OER process, hence guaranteeing highly efficient OER electrochemical behavior.⁴²

The microscopic morphologies and structural features of PBI-OP and $\text{Ni}_3\text{P@Ni/CNP}$ samples were determined by SEM and TEM characterizations. As shown in Fig. 3a and b, the microscopic morphology of PBI-OP was made up of a large number of wrinkled and clustered nanosheets. When PBI-OP was loaded with Ni^{2+} ions, there was no conspicuous variation in its morphologies, and no distinguishable species resulting from Ni^{2+} aggregation was detected over the Ni/PBI-OP precursor (Fig. S4–S6†). Nevertheless, from the SEM images of $\text{Ni}_3\text{P@Ni/CNP}$ samples, as depicted in Fig. 3c and S7,† it could be discerned that when compared to PBI-OP and Ni/PBI-OP precursors, their nanostructures have changed significantly, exhibiting aggregated microspheres. In addition, the corresponding TEM, selected electron diffraction (SAED), high-resolution TEM (HRTEM), and EDS element mapping images of $\text{Ni}_3\text{P@Ni/C}$ are shown in Fig. 3d–i, respectively. From the HRTEM, SAED, and AFM images of $\text{Ni}_3\text{P@Ni/CNP-M}$ (Fig. 3d–g), it could be clearly observed that the $\text{Ni}_3\text{P@Ni}$ nanosheets are regularly immobilized in the CNP matrix, and their sizes and thicknesses are systematically measured to be about 20–30 nm and 1.5–2 nm (Fig. S8†) respectively, considerably smaller than those of counterparts, allowing more exposed active sites to be easily generated and permeated in the electrolyte.⁴³ Besides, combined with the SAED results, the discernible lattice fringes with spacings of 1.97 \AA and 2.03 \AA , also recognized in the HRTEM image of $\text{Ni}_3\text{P@Ni/CNP-M}$, belonged to the (202) plane of Ni_3P phase and the (111) plane of Ni phase, respectively, which proved the coexistence of Ni and Ni_3P phases,⁴⁰ as also confirmed by XRD results. Furthermore, it was also indisputable proof that the Ni and Ni_3P components were contiguous to each other, affirming the generation of Janus-type structures of the ultrafine heterointerfaces. Moreover, the corresponding EDS element mapping (Fig. 3h and i) demonstrated that the Ni element was completely distributed on the $\text{Ni}_3\text{P@Ni}$ nanosheets while the P element is mainly distributed on a portion of $\text{Ni}_3\text{P@Ni}$ nanosheets, further identifying the existence of $\text{Ni}_3\text{P@Ni}$ hetero interface structures. Besides, there were similar $\text{Ni}_3\text{P@Ni}$ heterostructures that could also be observed over $\text{Ni}_3\text{P@Ni/CNP-L}$ (Fig. S9†) and $\text{Ni}_3\text{P@Ni/CNP-H}$ (Fig. S10†), suggesting the effectiveness of the phosphating strategy with a polymeric compound with low phosphorus content for generating the $\text{Ni}_3\text{P@Ni}$ heterojunction in our preparation conditions, which is more advantageous to inheriting the electrochemical properties of both constituent components, while also triggering charge redistribution and interface modification between them, thus integrally bringing on the compositional synergy effect for the promotion of OER kinetics.⁴⁴ Noticeably, the EDS mapping results also manifested that the C, N, and P elements have the same distribution profiles, indicating the successful formation of a CNP substate as expected due to the effective doping of N, P heteroatoms into the C matrix, which could offer the functionalities to modulate the electronic structure, improve the electrical conductivity, and optimize the




Fig. 3 SEM images of (a) PBI-OP, (b) Ni/PBI-OP precursor, and (c) $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$. (d) TEM image of $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$, (e) SAED pattern of $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$, (f) AFM image of $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$, (g) HRTEM images of $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$, (h) and (i) EDS elemental mapping images of C, N, Ni, and P elements of $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$.

adsorption energy of reactants and intermediates, thus accelerating the electrochemical reactions kinetics. Moreover, as can be seen from the results of the elemental and ICP-OES analyses (Table S2[†]), $\text{Ni}_3\text{P}@Ni/\text{CNP-L}$, $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$ and $\text{Ni}_3\text{P}@Ni/\text{CNP-H}$ have basically the same content of each element, and the most abundant one is Ni, which is 47.82%, 48.28%, and 48.03%, respectively.

XPS was employed to investigate further the composition and chemical states of PBI-OP and $\text{Ni}_3\text{P}@Ni/\text{CNP}$ samples. As depicted in Fig. 4a, S11a, and S12a,[†] the obtained XPS survey spectra clearly demonstrated the signals of C, N, O, and P for PBI-OP, while the signals of C, N, O, P, and Ni were found for $\text{Ni}_3\text{P}@Ni/\text{CNP}$ samples. The high-resolution Ni2p XPS spectrum of $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$ (Fig. 4b, S11b, and S12b[†]) could be well deconvoluted into six prominent peaks attributed to $\text{Ni}^{\delta+}$ (855.1 eV, 872.6 eV) in the Ni_3P phase, Ni^0 (852.2 eV, 868.9 eV) in the Ni phase, and satellite peaks (860.1 eV and 878.3 eV).^{23,36,45,46} The high-resolution C1s XPS spectrum of PBI-OP (Fig. S13a[†]) contained four main peaks centered at 284.1 eV, 284.9 eV, 285.9 eV, and 290.7 eV, representing C-C/C=C, C-N, C-O-C and satellite peaks, respectively.⁴⁷ In striking contrast, the high-resolution C1s XPS spectra of $\text{Ni}_3\text{P}@Ni/\text{CNP-L}$, $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$, and $\text{Ni}_3\text{P}@Ni/\text{CNP-H}$ (Fig. 4c, S11c, and S12c[†]) were also divided into four individual component peaks at 284.8 eV, 285.9 eV, 286.8 eV and 289.1 eV, which corresponded to C-C/C=C, C-N, C-P, and satellite peaks,^{23,24} further testifying the

successful introduction of both N and P heteroatoms into the C matrix, which corroborated with the TEM results.^{48–50} In the high-resolution N1s XPS spectrum of PBI-OP (Fig. S13b[†]), two peaks at 397.3 eV and 398.1 eV were attributed to $-\text{N}=\text{}$ and $-\text{NH}-$, while the other two peaks at 399.4 eV and 400.5 eV were assigned to positively charged imines. The high-resolution N1s XPS spectrum of $\text{Ni}_3\text{P}@Ni/\text{CNP}$ samples could be fitted into four distinctive peaks (Fig. 4d, S11d, and S12d[†]). Apart from the three peaks at 397.8 eV for pyridinic-N species, 400.1 eV for pyrrolic-N species, and 401.1 eV for graphite-N species, respectively,⁴⁰ a crucial peak at 399.3 eV could be observed indexed to the Ni-N species, disclosing that covalent bonds were generated at the interface between the $\text{Ni}_3\text{P}@Ni$ heterojunction nanosheets and CNP microspheres, which significantly strengthened the interaction of these two components.⁵¹ More impressively, the content of Ni-N species of $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$ was measured to be about 28.31%, much higher than those of $\text{Ni}_3\text{P}@Ni/\text{CNP-H}$ and $\text{Ni}_3\text{P}@Ni/\text{CNP-L}$ (Table S3[†]), manifesting the existence of the strongest chemical interactions among them, which was expected to further reinforcing the structural durability and enhancing electrochemical performances.⁴⁶ In addition, the content of pyridinic-N species in $\text{Ni}_3\text{P}@Ni/\text{CNP-M}$ was calculated to be as high as 43.1%, higher than those in $\text{Ni}_3\text{P}@Ni/\text{CNP-L}$ (40.15%) and $\text{Ni}_3\text{P}@Ni/\text{CNP-H}$ (32.81%), which is of great significance to accelerate the OER electrocatalytic activity because the pyridinic-N species are believed to encourage the




Fig. 4 (a) XPS survey, (b) Ni2p, (c) C1s, (d) N1s, (e) O1s, and (f) P2p spectra of Ni₃P@Ni/CNP-M.

release of O₂ molecules for the reduction of OER overpotential.²⁹ The high-resolution O1s XPS spectra of Ni₃P@Ni/CNP samples (Fig. 4e, S11e, and S12e[†]) could be fitted to four distinctive peaks at 528.7 eV, 530.3 eV, 531.4 eV, and 532.6 eV, respectively, which are associated with the M–O bond, OH[−] species, O₂ and H₂O adsorbed on the surface.⁴⁷ In the high-resolution P2p XPS spectrum of PBI-OP (Fig. S13d[†]), only one peak appeared at 132.9 eV, representing the P–O bond. In striking contrast, in the high-resolution P2p XPS spectra of Ni₃P@Ni/CNP samples (Fig. 4f, S11f, and S12f[†]), besides the existing peak of the P–O bond, there were two additional peaks of P2p_{1/2} and P2p_{3/2} recognized at 129.8 eV and 128.9 eV, which were brought on by the presence of the P–Ni bond in Ni₃P, also further validating the existence of the Ni₃P phase.^{37,52}

Linear scanning voltammetry (LSV) tests were performed using a 3 mm diameter glassy carbon electrode as the working electrode at a scanning rate of 10 mV s^{−1} and corrected using

ohmic drop compensation. During testing, magnets were added to the electrolytic cell and slowly stirred to remove the O₂ bubbles generated on the glassy carbon electrode. All potentials in this work were converted to reversible hydrogen electrode (RHE) through the equation of $E_{\text{RHE}} = E_{\text{Hg}/\text{HgO}} + 0.059 \text{ pH} + 0.098$. As illustrated in Fig. 5a and S14,[†] the polarization curves of Ni₃P@Ni/CNP-M gave a much lower onset potential of 1.20 V vs. RHE than those of PBI-OP (1.56 eV), Ni₃P@Ni/CNP-L (1.25 eV), Ni₃P@Ni/CNP-H (1.30 eV), and even IrO₂ (1.46 eV). Besides, Ni₃P@Ni/CNP-M only needed an overpotential of 239 mV to achieve a current density of 10 mA cm^{−2}, significantly lower than those of PBI-OP (564 mV), Ni₃P@Ni/CNP-L (359 mV), Ni₃P@Ni/CNP-H (336 mV), and IrO₂ (347 mV), thus declaring a prominent enhancement in OER electrocatalytic performance. This consequence suggested that the formation and optimization of well-defined Ni₃P@Ni heterojunction structures by adjusting the phosphating temperature could indeed accelerate




Fig. 5 (a) Polarization curves of PBI-OP, IrO₂, Ni₃P@Ni/CNP-L, Ni₃P@Ni/CNP-M, and Ni₃P@Ni/CNP-H, (b) comparing the overpotential of Ni₃P@Ni/CNP-M with the literature values. (c) The corresponding Tafel plots of PBI-OP, IrO₂, Ni₃P@Ni/CNP-L, Ni₃P@Ni/CNP-M, and Ni₃P@Ni/CNP-H. (d) The current density as a function of the scan rate. (e) Time-dependent current density curves of PBI-OP and Ni₃P@Ni/CNP electrocatalyst; LSV curves of Ni₃P@Ni/CNP-M before and after a 48 h test.

electron transfer and significantly speed up the OER dynamics.^{26,53,54} It was pleasing to note that the electrocatalytic performance of Ni₃P@Ni/CNP electrocatalysts was comparable to or even superior than those of the representative NiP_x containing OER electrocatalysts reported recently (Fig. 5b and Table S4[†]), such as Ni/Ni₂P@N-CNF (285 mV),²² N-Ni₃P-Ni/N-CNTs/NF (270 mV),²³ Ni₃P/MnOOH (300 mV),²⁵ Ni₂P/Co-NF (316 mV),²⁷ NiFeP (277 mV),⁵⁵ Ni/Ni₃C (350 mV),⁵⁶ Ni₂P/NiCo₂O₄ (250 mV),⁵⁷ Ni₂P/NPCM NCs (255 mV),⁵⁸ Ni₅P₄ NSs (290 mV),⁵⁹ CNT@NiCoP/C (297 mV),⁶⁰ Co₂P/Ni₂P@NF (310 mV),⁶¹ Fe₂P/Ni₂P HS/NF (185 mV),⁶² Fe-CoNiP (280 mV),⁶³ NiFeP@CNT (254 mV),⁶⁴ NiFeP@GNS (211 mV),⁶⁵ NFP@NG (295 mV),⁶⁶ NiP₂@FeP@CNT (261 mV),⁶⁷ FeP/Ni₂P@CNT (240 mV),⁶⁸ and NiMn-P (190 mV).⁶⁹ To explore the OER kinetics, the Tafel slope of IrO₂, PBI-OP, and Ni₃P@Ni/CNP electrocatalysts was calculated, as shown in Fig. 5c. Not surprisingly, compared with IrO₂ (91 mV dec⁻¹), PBI-OP (112 mV dec⁻¹), Ni₃P@Ni/CNP-L (68 mV dec⁻¹),

and Ni₃P@Ni/CNP-H (64 mV dec⁻¹), Ni₃P@Ni/CNP-M has a smaller Tafel slope of only 52 mV dec⁻¹, indicating that Ni₃P@Ni/CNP-M could greatly accelerate the rate-determining step to acquire the more desirable OER kinetics. Moreover, the electrochemical double-layer capacitance (C_{dl}), representing the electrochemical surface area (ECSA), could be obtained by using CVs with different scan rates in the non-Faraday region and recording the j ($j = j_a - j_c$) curves at different scan rates at 1.26 V (vs. RHE) (Fig. S15[†]). From Fig. 5d, it was noteworthy that the linear slope (equivalent to twice the C_{dl}) of Ni₃P@Ni/CNP-M was calculated to be as high as 8.9 mF cm⁻², much greater than those of PBI-OP (0.08 mF cm⁻²), Ni₃P@Ni/CNP-L (2.2 mF cm⁻²), and Ni₃P@Ni/CNP-H (4.8 mF cm⁻²), verifying that the effective Ni/Ni₃P heterojunction construction could greatly enlarge the exposure of electrochemically active sites, thus promoting the OER electrocatalytic activity.^{70,71} Taking into consideration the electrocatalytic durability of the above-mentioned samples, the

Ni₃P@Ni/CNP-M delivered the most stable performance with almost no attenuation in the current density during the consecutive 48 h operation (Fig. 5e), further identifying a favorable electrocatalytic stability owing to the strong interaction of the Ni₃P@Ni heterojunction nanosheets and the CNP substrate of Ni₃P@Ni/CNP-M, which has been authenticated by XPS analysis. In addition, as can be seen from the inset of Fig. 5e, the trends of the LSV curves of Ni₃P@Ni/CNP-M after the 48 h stability test are basically the same, and the overpotential change required for the same current density is negligible, which further proves that Ni₃P@Ni/CNP-M has excellent operational stability for OER during long-term electrochemical processes. More impressively, we characterized the Ni₃P@Ni/CNP-M samples after stability testing by ICP-OES, XRD, TEM, and XPS. Table S5[†] indicates the content of each element of Ni₃P@Ni/CNP-M before and after the stability test, and it can be seen that the composition of Ni₃P@Ni/CNP-M did not change significantly after the test, showing good stability. From the XRD spectra shown in Fig. S16,[†] it can be seen that the Ni₃P@Ni/CNP-M electrocatalysts showed no obvious crystal structure changes before and after the test. In addition, from the TEM images shown in Fig. S17,[†] it can be seen that the micro-morphology of Ni₃P@Ni/CNP samples after the stability test was still highly consistent with that before the test. Moreover, from the analysis of the XPS spectra of Ni₃P@Ni/CNP-M after the stability test (Fig. S18[†]), it was found that there was no significant change in the C, N, O, Ni, and P elements, and the above results verified the excellent stability of the Ni₃P@Ni/CNP-M material.

To gain a thorough insight into the OER electrocatalytic kinetics, electrochemical impedance spectroscopy (EIS) was employed for the above-mentioned electrocatalysts in 1 M KOH electrolyte. As shown in Fig. 6a, the EIS Nyquist curves of all the samples displayed similar curves with a semi-circular curve in the high-frequency region, whose diameter represented the charge-transfer resistance and the equivalent resistance of the intermediate at the electrode/electrolyte interface. It could be detected that when compared with PBI-OP, Ni₃P@Ni/CNP-L, and Ni₃P@Ni/CNP-H, Ni₃P@Ni/CNP-M delivered the least relaxation time of semicircle, indicating its lowest resistance to electron transfer, which could be attributed to the synergistic effect of Ni and Ni₃P brought about by their formation of heterojunction interfaces, thus devoting to OER kinetics.^{42,54,55,72} Moreover, these impedance spectra were well-fitted and analyzed using ZView software and the EIS Spectrum Analyzer program and found to fit well with the $R_s(R_{ct}CPE)$ equivalent circuit (Fig. 6b). Thereinto, R_s represented the solution resistance, CPE represented the constant phase element, and R_{ct} represented the reactive charge transfer resistance at the electrode/electrolyte interface. The results elaborated that the data obtained by the simulation were basically consistent with the experimental data, and the corresponding EIS fitting parameters are exhibited in Table S6.[†] In the fitted data, R_{ct} was the largest in the overall impedance, indicating that the charge transfer resistance was the main factor determining the OER kinetics of Ni₃P@Ni/CNP electrocatalysts. More importantly, the R_{ct} value of Ni₃P@Ni/CNP-M was measured to be 5.367 $\Omega\text{ cm}^2$, much lower than those of Ni₃P@Ni/CNP-L (10.920 $\Omega\text{ cm}^2$) and Ni₃P@Ni/CNP-H (9.544 $\Omega\text{ cm}^2$),




Fig. 6 (a) EIS Nyquist plots. (b) Simulated equivalent circuit diagram and fitted Nyquist plots of PBI-OP, Ni₃P@Ni/CNP-L, Ni₃P@Ni/CNP-M, and Ni₃P@Ni/CNP-H. (c) CV curves of Ni₃P@Ni/CNP-M in 1 M KOH before and after the addition of 1 M CH₃OH. (d) Schematic display of the accelerated OER kinetics of Ni₃P@Ni/CNP samples by turning the adsorption strength of *OH intermediates.

manifesting its favorable charge transfer capability during the OER process. Noticeably, numerous research studies have demonstrated that the OER performances of electrocatalysts are mainly determined by the adsorption strength of $^*\text{OH}$ intermediates over the electrocatalysts.^{55,56} In response to this, the corresponding CV curves of OER were extensively examined in KOH electrolyte before and after adding 1 M CH_3OH , and the results are depicted in Fig. 6c and S19.† After the addition of CH_3OH , the current density of PBI-OP showed a small increase, while the current density of the $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP}$ electrocatalyst showed a significant increase, with that of $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP-M}$ being the most obvious. This was attributed to the weak adsorption strength of PBI-OP on $^*\text{OH}$ intermediates and the poor coverage of $^*\text{OH}$ intermediates on the surface, which limited the occurrence of the oxidation reaction (MOR) between CH_3OH and $^*\text{OH}$ intermediates,⁴⁰ whereas $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP-M}$ provided a large number of sites for the coverage of $^*\text{OH}$ intermediates, which allowed the MOR to occur rapidly. Besides, the results also demonstrated the high surface coverage of $^*\text{OH}$ intermediates and strong adsorption strength over the $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP-M}$ heterojunction interface, which was crucial to accelerate the oxidation deprotonation reaction process from $^*\text{OH}$ to $^*\text{O}$ intermediates (Fig. 6d), thus speeding up the overall OER kinetics.⁷³

To further unveil the feasibility of the heterojunction construction and electrocatalysis process of $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP}$ and IrO_2 , their relevant nano-structural properties and electrocatalytic OER kinetics were extendedly investigated by DFT calculations. More concretely, the $\text{Ni}_3\text{P}@/\text{Ni}$ structure supported by the CNP substrate was constructed as a heterojunction with

Ni_3P (202) and Ni (111). The stable structure of $\text{Ni}_3\text{P}@/\text{Ni}$ heterojunction after geometry optimizations by DFT calculation is exhibited in Fig. S20.† Whereas for the IrO_2 , the triple-layer (110) crystal plane of IrO_2 served to acquire the optimized IrO_2 structure, as illustrated in Fig. S21.† For the electrocatalytic process, a four-step OER mechanism was proposed for IrO_2 , including $^*\text{OH}$, $^*\text{O}$, and $^*\text{OOH}$ intermediates. However, what is completely different is that a five-step OER mechanism^{74,75} occurred over the $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP}$, including $^*\text{OH}$, $^*\text{O}$, $^*\text{O} + ^*\text{OH}$, $^*\text{O} + ^*\text{O}$ intermediates (Fig. 7a). This was mainly because the formation of a heterojunction over $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP}$ could effectively strengthen the synergistic effect of electrocatalytic active sites and ameliorate the adsorption strength of intermediate species, enabling a change in the OER intermediate steps as compared with IrO_2 . Furthermore, the charge density distribution of the $\text{Ni}_3\text{P}@/\text{Ni}$ heterojunction is described in Fig. 7b. It is noticeable that superfluous electrons were gathered at the $\text{Ni}_3\text{P}@/\text{Ni}$ heterojunction interface, which could make the rearrangement of electron configuration at the interface and adjust the adsorption/desorption energy of intermediates, thus reducing the overall energy barrier of OER.⁷⁶ From the calculated free energy diagram of the OER process (Fig. 7c), it was noteworthy that for $\text{Ni}_3\text{P}@/\text{Ni}$, the coupling process step from $^*\text{O}$ intermediates to the O_2 product ($^*\text{O} + ^*\text{O} \rightarrow \text{O}_2$) required the largest energy barrier to overcome and could be perceived as the rate-determining step with an energy potential barrier of 1.5217 eV. Whereas for IrO_2 , the rate-determining step was the protonation step of $^*\text{OOH}$ to O_2 ($^*\text{OOH} \rightarrow \text{O}_2$) with an energy barrier of 1.5479 eV. The calculations disclosed that $\text{Ni}_3\text{P}@/\text{Ni}/$



Fig. 7 (a) OER mechanism of $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP}$ in alkaline medium. (b) Schematic diagram of the interface charge. (c) Gibbs free energy plots of the OER steps on $\text{Ni}_3\text{P}@/\text{Ni}/\text{CNP}$ and IrO_2 at $U = 0$ V.

CNP had a lower OER activation energy than IrO₂, thereby identifying the above experimental phenomenon that the OER activity of Ni₃P@Ni/CNP is better than IrO₂, as expected.

4. Conclusions

In conclusion, Ni₃P@Ni/CNP heterojunction electrocatalysts were successfully synthesized by a wet-impregnation process of the Ni/PBI-OP precursor and subsequent phosphating/carbonization treatment. To this end, this exceptional microstructure could provide rich Ni₃P@Ni heterojunction interfacial sites and strong interaction with CNP microspheres, which not only optimized and rearranged the electron configuration to elevate the intrinsic activity of electrochemically active sites but also boosted the structural stability and facilitated the interfacial electron transfer. Besides, there were affluent crystal defects that could be detected over the Ni₃P@Ni/CNP samples, which could initiate the conductivity band to upgrade the electronic conductivity for the enhancement of OER kinetics. Furthermore, XPS illustrated that a large amount of pyridinic N species survived over the Ni₃P@Ni/CNP samples, which could accelerate the O₂ release and reduce the OER overpotential. Noticeably, DFT calculation also demonstrated that Ni₃P@Ni/CNP presented a lower OER activation energy than IrO₂, thereby further approving the OER kinetics. Among these samples, Ni₃P@Ni/CNP-M perfectly inherited the advantages of a larger specific surface area, more exposed electrocatalytic active sites, higher conductivity, and a satisfactory heterojunction structure, thus accelerating the OER performance. Thus, Ni₃P@Ni/CNP-M only needs a low overpotential of 239 mV in 1 M KOH electrolyte to reach the current density of 10 mA cm⁻², and the low Tafel slope of 52 mV dec⁻¹ is much lower than that of commercial supplies such as IrO₂, showing excellent OER catalytic performance. Eventually, Ni₃P@Ni/CNP-M presented excellent stability when tested continuously for 48 h at a current density of 10 mA cm⁻².

Conflicts of interest

The authors declared that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgements

This research was financially supported by the National Natural Science Foundation of China (No. U1904171), the Science and Technology Foundation of Henan Province (No. 222102240032), the Young Backbone Teachers Training Program Foundation of Henan University of Technology, and the Innovative Funds Plan of Henan University of Technology (No. 2021ZKCJ08).

References

- 1 A. Buttler and H. Spliethoff, *Renewable Sustainable Energy Rev.*, 2018, **82**, 2440–2454.
- 2 J. Chi and H. Yu, *Chin. J. Catal.*, 2018, **39**, 390–394.

- 3 H. Sun, Z. Yan, F. Liu, W. Xu, F. Cheng and J. Chen, *Adv. Mater.*, 2020, **32**, 1806326.
- 4 Y. Xu and B. Zhang, *ChemElectroChem*, 2019, **6**, 3214–3226.
- 5 V. Charles, A. O. Anumah, K. A. Adegoke, M. O. Adesina, I. P. Ebuka, N. A. Gaya, S. Ogwuche and M. O. Yakubu, *Sustainable Mater. Technol.*, 2021, **28**, e00252.
- 6 S. Chen, H. Huang, P. Jiang, K. Yang, J. Diao, S. Gong, S. Liu, M. Huang, H. Wang and Q. Chen, *ACS Catal.*, 2020, **10**, 1152–1160.
- 7 A. Zagalskaya and V. Alexandrov, *ACS Catal.*, 2020, **10**, 3650–3657.
- 8 A. Dutta and N. Pradhan, *J. Phys. Chem. Lett.*, 2017, **8**, 144–152.
- 9 H. Li, P. Wen, D. S. Itanze, M. W. Kim, S. Adhikari, C. Lu, L. Jiang, Y. Qiu and S. M. Geyer, *Adv. Mater.*, 2019, **31**, 1900813.
- 10 R. Wang, X.-Y. Dong, J. Du, J.-Y. Zhao and S.-Q. Zang, *Adv. Mater.*, 2018, **30**, 1703711.
- 11 J. Yang, F. Zhang, X. Wang, D. He, G. Wu, Q. Yang, X. Hong, Y. Wu and Y. Li, *Angew. Chem., Int. Ed.*, 2016, **55**, 12854–12858.
- 12 D. Gao, J. Zhang, T. Wang, W. Xiao, K. Tao, D. Xue and J. Ding, *J. Mater. Chem. A*, 2016, **4**, 17363–17369.
- 13 X. Shen, W. Tan, Z. Wei, X. Wang, H. Zhou, J. Lv, M. Zhao, M. Zhang, J. Yang, G. He and L. Yang, *J. Mater. Sci.: Mater. Electron.*, 2021, **32**, 22974–22983.
- 14 F. Zhang, S. Xi, G. Lin, X. Hu, X. W. Lou and K. Xie, *Adv. Mater.*, 2019, **31**, 1806552.
- 15 Q. Gao, W. Zhang, Z. Shi, L. Yang and Y. Tang, *Adv. Mater.*, 2019, **31**, 1802880.
- 16 Q. Hu, X. Liu, B. Zhu, L. Fan, X. Chai, Q. Zhang, J. Liu, C. He and Z. Lin, *Nano Energy*, 2018, **50**, 212–219.
- 17 S.-J. Guan, P. Zhang, S.-J. Ji, Y. Cao and N.-T. Suen, *Inorg. Chem.*, 2022, **61**, 12772–12780.
- 18 L. Jin, H. Xia, Z. Huang, C. Lv, J. Wang, M. G. Humphrey and C. Zhang, *J. Mater. Chem. A*, 2016, **4**, 10925–10932.
- 19 S. P. Keerthana, B. J. Rani, G. Ravi, R. Yuvakkumar, S. I. Hong, D. Velauthapillai, B. Saravanakumar, M. Thambidurai and C. Dang, *Int. J. Hydrogen Energy*, 2020, **45**, 18859–18866.
- 20 M. B. Stevens, C. D. M. Trang, L. J. Enman, J. Deng and S. W. Boettcher, *J. Am. Chem. Soc.*, 2017, **139**, 11361–11364.
- 21 A. Ray, S. Sultana, L. Paramanik and K. M. Parida, *J. Mater. Chem. A*, 2020, **8**, 19196–19245.
- 22 X. Li, J. Zhou, C. Liu, L. Xu, C. Lu, J. Yang, H. Pang and W. Hou, *Appl. Catal., B*, 2021, **298**, 120578.
- 23 B. Lu, Y. Wang, W. Li, S. Zhou, H. Gao, Q. Zou, J. Li and J. Zang, *ACS Appl. Nano Mater.*, 2021, **4**, 7443–7453.
- 24 F. Wang, J. Chen, X. Qi, H. Yang, H. Jiang, Y. Deng and T. Liang, *Appl. Surf. Sci.*, 2019, **481**, 1403–1411.
- 25 Y. Tan, Q. Li, Q. Che, X. Chen, X. Xu and Y. Chen, *Electrochim. Acta*, 2019, **324**, 134897.
- 26 J. Liu, Y. Wang, Y. Liao, C. Wu, Y. Yan, H. Xie and Y. Chen, *ACS Appl. Mater. Interfaces*, 2021, **13**, 26948–26959.
- 27 S. Li, Y. Zhang, Y. Yuan, F. Chang, K. Zhu, G. Li, Z. Bai and L. Yang, *Int. J. Hydrogen Energy*, 2023, **48**, 3355–3363.

- 28 Z. Li, M. Hu, P. Wang, J. Liu, J. Yao and C. Li, *Coord. Chem. Rev.*, 2021, **439**, 213953.
- 29 X. Chen, Y. Chen, Z. Shen, C. Song, P. Ji, N. Wang, D. Su, Y. Wang, G. Wang and L. Cui, *Appl. Surf. Sci.*, 2020, **529**, 147173.
- 30 Y. Zhuang, J. G. Seong, W. H. Lee, Y. S. Do, M. J. Lee, G. Wang, M. D. Guiver and Y. M. Lee, *Macromolecules*, 2015, **48**, 5286–5299.
- 31 Q. Wu, G. Xiao and D. Yan, *e-Polym.*, 2008, 073.
- 32 G. Wang, G. Xiao and D. Yan, *J. Mater. Sci.*, 2011, **369**, 388–396.
- 33 G. Wang, Y. Yao, G. Xiao and D. Yan, *J. Membr. Sci.*, 2013, **425–426**, 200–207.
- 34 G. Wang, S. Yang, Y. Ding, M. Lu, B. Hua, J. Kang, W. Tang, H. Wei, L. Zhu and X. Cao, *Chem. Commun.*, 2022, **58**, 12333–12336.
- 35 T. Chen, B. Yang, S. Li, K. Wang, X. Jiang, Y. Zhang and G. He, *Ind. Eng. Chem. Res.*, 2011, **50**, 11043–11048.
- 36 C. Du, M. Shang, J. Mao and W. Song, *J. Mater. Chem. A*, 2017, **5**, 15940–15949.
- 37 J. Wojewoda-Budka, A. Wierzbicka-Miernik, L. Litynska-Dobrzynska, M. J. Szczerba, G. Mordarski, M. Mosialek, Z. Huber and P. Zieba, *Electrochim. Acta*, 2016, **209**, 183–191.
- 38 D. A. L. Almeida, A. B. Couto and N. G. Ferreira, *J. Alloys Compd.*, 2019, **788**, 453–460.
- 39 M. Zhang, Q. Dai, H. Zheng, M. Chen and L. Dai, *Adv. Mater.*, 2018, **30**, 1703711.
- 40 G. Wang, S. Yang, M. Lu, B. Hua, Z. Zhang, J. Kang, W. Tang, H. Wei, L. Cui and X. Chen, *Electrochim. Acta*, 2023, **443**, 141939.
- 41 J. Yu, G. Cheng and W. Luo, *J. Mater. Chem. A*, 2017, **5**, 11229–11235.
- 42 M. Yan, Z. Zhao, P. Cui, K. Mao, C. Chen, X. Wang, Q. Wu, H. Yang, L. Yang and Z. Hu, *Nano Res.*, 2021, **14**, 4220–4226.
- 43 G. Shi, C. Yu, Z. Fan, J. Li and M. Yuan, *ACS Appl. Mater. Interfaces*, 2019, **11**, 2662–2669.
- 44 D. Li, Z.-F. Zhang, Z.-Y. Yang, W.-Y. Wu, M.-H. Zhang, T.-R. Yang, Q.-S. Zhang and J.-Y. Xie, *J. Alloys Compd.*, 2022, **921**, 166204.
- 45 Q. Dong, M. Li, M. Sun, F. Si, Q. Gao, X. Cai, Y. Xu, T. Yuan, S. Zhang, F. Peng, Y. Fang and S. Yang, *Small Methods*, 2021, **5**, 2100878.
- 46 G. Li, J. Wang, J. Yu, H. Liu, Q. Cao, J. Du, L. Zhao, J. Jia, H. Liu and W. Zhou, *Appl. Catal., B*, 2020, **261**, 118147.
- 47 X. Chen, Y. Chen, X. Luo, H. Guo, N. Wang, D. Su, C. Zhang, T. Liu, G. Wang and L. Cui, *Appl. Surf. Sci.*, 2020, **526**, 146626.
- 48 Y. Du, G. Pan, L. Wang and Y. Song, *Appl. Surf. Sci.*, 2019, **469**, 61–67.
- 49 M. Li, L. Zhang, Q. Xu, J. Niu and Z. Xia, *J. Catal.*, 2014, **314**, 66–72.
- 50 X. Li, L. Ni, J. Zhou, L. Xu, C. Lu, G. Yang, W. Ding and W. Hou, *Nanoscale*, 2020, **12**, 13987–13995.
- 51 P. Ding, H. Song, J. Chang and S. Lu, *Nano Res.*, 2022, **15**, 7063–7070.
- 52 J. Y. Xiang, J. P. Tu, X. L. Wang, X. H. Huang, Y. F. Yuan, X. H. Xia and Z. Y. Zeng, *J. Power Sources*, 2008, **185**, 519–525.
- 53 X.-D. Wang, Y. Cao, Y. Teng, H.-Y. Chen, Y.-F. Xu and D.-B. Kuang, *ACS Appl. Mater. Interfaces*, 2017, **9**, 32812–32819.
- 54 B. You, N. Jiang, M. Sheng, M. W. Bhushan and Y. Sun, *ACS Catal.*, 2016, **6**, 714–721.
- 55 C. G. Read, J. F. Callejas, C. F. Holder and R. E. Schaak, *ACS Appl. Mater. Interfaces*, 2016, **8**, 12798–12803.
- 56 Q. Qin, J. Hao and W. Zheng, *ACS Appl. Mater. Interfaces*, 2018, **10**, 17827–17834.
- 57 L. Wang, C. Gu, X. Ge, J. Zhang, H. Zhu and J. Tu, *Adv. Mater. Interfaces*, 2017, **4**, 1700481.
- 58 L. Yan, H. Jiang, Y. Wang, L. Li, X. Gu, P. Dai, D. Liu, S.-F. Tang, G. Zhao, X. Zhao and K. M. Thomas, *Electrochim. Acta*, 2019, **297**, 755–766.
- 59 M. Ledendecker, S. K. Calderon, C. Papp, H.-P. Steinrueck, M. Antonietti and M. Shalom, *Angew. Chem., Int. Ed.*, 2015, **54**, 12361–12365.
- 60 Y. Zhao, G. Fan, L. Yang, Y. Lin and F. Li, *Nanoscale*, 2018, **10**, 13555–13564.
- 61 H. Zhao, J. Liang and Y. Zhao, *J. Alloys Compd.*, 2022, **907**, 164479.
- 62 X. Wang, B. Wang, Y. Chen, M. Wang, Q. Wu, K. Srinivas, B. Yu, X. Zhang, F. Ma and W. Zhang, *J. Mater. Sci. Technol.*, 2022, **105**, 266–273.
- 63 M. Ramadoss, Y. Chen, X. Chen, Z. Su, M. Karpuraranjith, D. Yang, M. A. Pandit and K. Muralidharan, *J. Phys. Chem. C*, 2021, **125**, 20972–20979.
- 64 Y. Liu, B. Wang, K. Srinivas, M. Wang, Z. Chen, Z. Su, D. Liu, Y. Li, S. Wang and Y. Chen, *Int. J. Hydrogen Energy*, 2022, **47**, 12903–12913.
- 65 D. Yang, Z. Su, Y. Chen, Y. Lu, B. Yu, K. Srinivas, B. Wang and W. Zhang, *J. Mater. Chem. A*, 2020, **8**, 22222–22229.
- 66 H. Wang, X. Wang, B. Zheng, D. Yang, W. Zhang and Y. Chen, *Electrochim. Acta*, 2019, **318**, 449–459.
- 67 Y. Liu, B. Wang, Y. Lu, Z. Su, Y. Li, Q. Wu, D. Yang, Y. Chen and S. Wang, *J. Mater. Sci.*, 2021, **56**, 16000–16009.
- 68 Z. Su, Y. Lu, K. Srinivas, B. Wang, W. Zhang, Y. Chen and D. Yang, *J. Alloys Compd.*, 2021, **883**, 160926.
- 69 D. Yang, Z. Su, Y. Chen, K. Srinivas, J. Gao, W. Zhang, Z. Wang and H. Lin, *Small*, 2020, **17**, 2006881.
- 70 L. S. Bezerra and G. Maia, *J. Mater. Chem. A*, 2020, **8**, 17691–17705.
- 71 Q. Mou, Z. Xu, G. Wang, E. Li, J. Liu, P. Zhao, X. Liu, H. Li and G. Cheng, *Inorg. Chem. Front.*, 2021, **8**, 2889–2899.
- 72 Y. Wang, S. Tao, H. Lin, G. Wang, K. Zhao, R. Cai, K. Tao, C. Zhang, M. Sun, J. Hu, B. Huang and S. Yang, *Nano Energy*, 2021, **81**, 105606.
- 73 Q. Hu, Z. Wang, X. Huang, Y. Qin, H. Yang, X. Ren, Q. Zhang, J. Liu, M. Shao and C. He, *Appl. Catal., B*, 2021, **286**, 119920.
- 74 C. Hu, L. Zhang and J. Gong, *Energy Environ. Sci.*, 2019, **12**, 2620–2645.
- 75 M. Najibah, E. Tsoy, H. Khalid, Y. Chen, Q. Li, C. Bae, J. Hnat, M. Plevová, K. Bouzek and J. H. Jang, *J. Membr. Sci.*, 2021, **640**, 119832.
- 76 H. Liu, J. Gao, X. Xu, Q. Jia, L. Yang, S. Wang and D. Cao, *Chem. Eng. J.*, 2022, **448**, 137706.