

Chemical Science

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



Journal Name

ARTICLE

Solid State Lithiation-Delithiation of Sulphur in Sub-Nano Confinement: A New Concept for Designing Lithium-Sulphur Batteries

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

Chengyin Fu,^a Bryan M. Wong,^{ab} Krassimir N. Bozhilov^{bc} and Juchen Guo^{*ab}

We investigate the detailed effects and mechanisms of sub-nano confinement on lithium-sulfur (Li-S) electrochemical reactions in both ether-based and carbonate-based electrolytes. Our results demonstrate a clear correlation between the size of sulfur confinement and the resulting Li-S electrochemical mechanisms. In particular, when sulfur is confined within sub-nano pores, we observe identical lithium-sulfur electrochemical behavior, which is distinctly different from conventional Li-S reactions, in both ether and carbonate electrolytes. Taken together, our results highlight the critical importance of sub-nano confinement effects on controlling solid-state reactions in Li-S electrochemical systems.

Introduction

Rechargeable lithium-sulphur (Li-S) batteries continue to be one of the most promising technologies for electrochemical energy storage. In order to dramatically improve the performance of these Li-S systems, we require a detailed understanding of the interactions between lithium and sulphur in these complex, heterogeneous electrochemical environments. Due to the high electrical resistivity of sulfur,¹ it is essential to incorporate sulphur into conductive hosts, of which the majority are carbonaceous materials. The rationale for using carbonaceous hosts, particularly porous carbon materials, is rooted from the well-known polysulfide shuttle reaction induced by the dissolution of lithium polysulfides (Li₂S_n) into electrolytes. To date, it is widely accepted that only ether-based electrolytes are feasible for Li-S batteries. The two most common ones are tetra(ethylene glycol) dimethyl ether (TEGDME) and a mixture of 1,3-dioxolane (DOL) and 1,2-dimethoxyethane (DME). These solvents can efficiently solubilize lithium polysulfides, which is necessary to achieve an in-depth lithiation of sulphur. However, at the same time the polysulfide dissolution also causes problematic characteristics, so-called "shuttle reactions." Our measurements show that the solubility of Li₂S₈ in TEGDME at room temperature is very high as 0.18 ± 0.005 M (equivalent to 1.44 M of sulphur); i.e. approximately 22 mL of TEGDME electrolyte can completely

dissolve Li₂S₈ generated from 1 g of S₈. As a result, most of the Li-S batteries are essentially batteries with "liquid phase" cathodes – upon lithiation, the initial product (Li₂S₈) immediately dissolves with high local concentration at the cathode-electrolyte interface. Products from further lithiation have distinctly lower solubility so that precipitation/deposition of Li₂S_n (n < 8) on the cathode sequentially occurs. Therefore, the complex Li-S electrochemical processes at the cathode involve generation, disappearance, and migration of multiple electroactive species both in the solution and on the electrode. As clear evidence, lithium polysulfide generation and re-distribution during the first discharge was recently observed via *in situ* techniques including Raman spectroscopy,² transmission X-ray microscopy,³ and X-ray fluorescence microscopy.⁴

Certainly, the complex Li-S electrochemical processes in these systems can be further tailored to achieve enhanced battery performance. One effective strategy, pioneered by Nazar and coworkers,⁵ is to employ porous structures as sulphur hosts and polysulfides reservoirs. Many porous cathode structures including amorphous porous carbons,⁶⁻¹⁰ core-shell structures,¹⁰⁻¹³ carbon nanotube networks,¹⁴⁻¹⁶ and porous structures composed of graphene/graphene oxide¹⁷⁻²² have been investigated. Another viable strategy is the "catholyte" concept.²³⁻²⁷ Instead of sequestering lithium polysulfides in the cathode, catholyte Li-S cells use electrolytes with a high concentration of dissolved lithium polysulfides, and excellent battery performance was achieved by optimizing the concentration and composite of the catholytes. The third strategy is to chemically modify the cathode hosts to render strong adsorption to the lithium polysulfides species. Heteroatoms in the carbon matrix, including nitrogen and oxygen, have been proven effective.²⁸⁻³¹

In spite of these impressive improvements, a fundamental question of both scientific and technological importance

^a Department of Chemical and Environmental Engineering, University of California Riverside, Riverside, CA 92521, USA. E-mail: jguo@engr.ucr.edu.

^b Materials Science and Engineering Program, University of California Riverside, Riverside, CA 92521, USA.

^c Central Facility for Advanced Microscopy and Microanalysis, University of California, Riverside, CA 92521, United States.

Electronic Supplementary Information (ESI) available: Detailed experimental procedures and additional electrochemical, spectroscopic, and computational data. See DOI: 10.1039/x0xx00000x

remains: is it possible to restrict the electroactive sulphur-containing species in the solid state during the Li-S electrochemical reaction? If possible, this hypothesized solid-state Li-S electrochemical reaction would have transformative implications for altering the electrochemical processes and performance of Li-S batteries.

Results and Discussion

To answer this question, we investigate two factors that play decisive roles in Li-S electrochemical processes: the size of the sulphur confinement (i.e. pore size in the carbon hosts) and the type of electrolyte solvents. To precisely capture the subtle changes in Li-S electrochemical behaviour due to the different sulphur confinement size, a series of porous carbon hosts with narrow ranges of pore sizes is selected: resorcinol-formaldehyde derived porous carbon fibres with four distinctly different pore sizes, 0.4-1.0 nm, 0.4-2.0 nm, 0.4-2.5 nm, and 0.4-3.0 nm (denoted as CF10, CF20, CF25, and CF30), respectively, were purchased from Kuraray Chemical Co., Ltd. The scanning electron microscope (SEM) images of these carbon fibres are shown in Figure S1 in ESI. **Figure 1a** shows the Type-I nitrogen adsorption-desorption isotherms of these four carbon fibers, and **Figure 1b** shows their pore size

distributions calculated based on a non-local density functional theory (NLDFT) model. The detailed structural properties are listed in Table S1 in ESI.

In addition to the different pore sizes, two different electrolyte solvent systems are selected for this study: The first one is TEGDME, which is a typical solvent for conventional Li-S batteries as aforementioned. The other solvent is a mixture of ethylene carbonate and diethyl carbonate (EC/DEC) with a 1:1 volume ratio, which is a typical solvent for Li-ion batteries and is well-known for their failure in conventional Li-S batteries. Commercial grade EC/DEC electrolyte with 1 M lithium hexafluorophosphate (LiPF_6) salt was purchased from Sigma-Aldrich. Since LiPF_6 does not dissociate well in etheral solvents, lithium bis(trifluoromethane sulfonyl)imide (LiTFSI), which has a higher dissociation constant,³² was used in TEGDME electrolyte with a concentration of 1 M. The previous study by Abruña and co-workers suggests that the type of the lithium salt (LiPF_6 vs. LiTFSI) does not affect lithium-sulphur electrochemical reactions.³³ Therefore, the major difference between these two electrolytes is their solubility of lithium polysulfides, particularly for the high order structures. As shown in Table S2 in ESI, TEGDME is a superior solvent for lithium polysulfides comparing to EC/DEC.

To demonstrate the effects of sulphur confinement on Li-S




Figure 1. (a) Type-I nitrogen adsorption-desorption isotherms and (b) pore size distributions (cumulative pore volume as inset) of the four different carbon fibers.




Figure 2. (a) TGA curves and (b) XRD patterns of CF10- S_{pore} , CF10- S_{60} and CF10- S_{90} .

electrochemical reactions, we first investigated three CF10 (the smallest pore size among all four carbon fibers) samples with different sulphur contents. Among these samples, CF10-S₆₀ and CF10-S₉₀ have 60 wt.% and 90 wt.% of sulphur, respectively, by infusing the designated amount of sulphur through heating the mixture of CF10 and sulphur at 155 °C in argon for 10 hours.

CF10-S_{pore} was obtained by further heating CF10-S₆₀ at 200 °C in flowing argon for 6 hours to remove the sulphur deposited on the surface. Thermogravimetric analysis (TGA) was performed in argon from room temperature to 600 °C with a heating ramp of 5 °C min⁻¹, and a 2-hour isothermal step was imposed at 200 °C. As shown in **Figure 2a**, the TGA plots clearly show that both CF10-S₆₀ and CF10-S₉₀ have two weight loss stages: the first weight loss starts with the isothermal step at 200 °C and completes prior to the end of the isothermal step. The second weight loss stage starts at 270 °C and completes at 400 °C. The first weight loss was due to the sublimation of the sulphur deposited on the surface of CF10 (denoted as superficial sulphur), and the second weight loss arises from the sublimation of the sulphur confined in the sub-nano pores of CF10 (denoted as confined sulphur).⁶ In stark contrast, CF10-S_{pore} only demonstrates the second weight loss stage, indicating that the sulphur in CF10-S_{pore} is exclusively confined in the sub-nano pores, and the confined sulphur content in CF10-S_{pore} is 30 wt.%, which is consistent with the

percentage of confined sulphur in both CF10-S₆₀ and CF10-S₉₀. The X-ray diffraction (XRD) pattern of CF10-S_{pore} in **Figure 2b** indicates that the sulphur confined in the sub-nano pores is amorphous, and the superficial sulphur in CF10-S₆₀ and CF10-S₉₀ has an orthorhombic crystal structure.

As demonstrated in **Figures 3a** and **b**, the drastically different cyclic voltammetry (CV) and galvanostatic charge-discharge (GCD) characteristics of CF10-S₉₀, CF10-S₆₀, and CF10-S_{pore} show a clear correlation to the sulphur distribution (superficial vs. confined) in the TEGDME electrolyte. The CV scan of CF10-S₉₀ demonstrates typical liquid-phase Li-S electrochemical behaviour with two cathodic peaks at 2.40 V and 1.95 V and one anodic peak at 2.5 V (with a shoulder at 2.7 V), which is consistent with the GCD curve of CF10-S₉₀ with a lithiation capacity of 750 mA h g⁻¹. When the content of superficial sulphur is reduced in CF10-S₆₀, its CV scan is rather interesting: in addition to the two aforementioned conventional cathodic peaks representing the liquid-phase lithiation of sulphur, it also shows a broad cathodic peak below 1.8 V. Accordingly, the anodic scan demonstrates a broad peak at 2.1 V in addition to the typical anodic peaks at 2.5 V. The GCD curve of CF10-S₆₀ is consistent: it shows the typical sulphur discharge plateaus at 2.45 V and 2.0 V and a pronounced new discharge slope at 1.5 V with a total lithiation capacity of 900 mA h g⁻¹. The transition of CV and GCD behaviours becomes more clear when the sulphur content is




Figure 3. The first CV scans at 0.1 mV s⁻¹ and the first GCD curves at 160 mA g⁻¹ of CF10-S_{pore}, CF10-S₆₀, and CF10-S₉₀ in TEGDME electrolyte (a) and (b) respectively, and in EC/DEC electrolyte (c) and (d), respectively.

further reduced in CF10-S_{pore}: With sulphur exclusively confined in the sub-nano pores, the conventional Li-S CV peaks completely disappear. Instead, the CV scan of CF10-S_{pore} only shows a single pair of redox peaks centred at 1.4 V and 2.1 V. Accordingly, the GCD curve of CF10-S_{pore} shows a single lithiation slope starting from 1.6 V and a single delithiation slope starting from 1.8 V with a lithiation capacity of 1650 mA h g⁻¹.

As shown in **Figure 3c** and **d**, the electrochemical characteristics of CF10-S₉₀, CF10-S₆₀, and CF10-S_{pore} in EC/DEC electrolyte also show a strong correlation to the sulphur distribution in CF10. The CV scan of CF10-S₉₀ in EC/DEC only shows a small cathodic peak centred at 2.1 V and no reversible anodic peak is shown. This observation indicates that the lithiation process of CF10-S₉₀ in EC/DEC electrolyte is not only terminated at a very early stage, but is also irreversible. Consistently, the GCD curve of CF10-S₉₀ in EC/DEC shows only a very short discharge plateau at 2.3 V and no charge capacity at all, which is consistent with the known behaviour of Li-S electrochemical reaction in carbonate electrolytes.^{33,34} The first cathodic scan of CF10-S₆₀ in EC/DEC also shows a small peak at 2.2 V with an additional small peak below 1.8 V, which corresponds to a broad anodic peak at 2.1 V. The GCD curve of CF10-S₆₀ in EC/DEC consistently shows a small discharge slope from 2.3 V with a modest capacity of 300 mA h g⁻¹ that is partially reversible. This observation suggests that CF10-S₆₀ still has a very low electrochemical activity in EC/DEC electrolyte, although improved from CF10-S₉₀. When the superficial sulphur is completely removed, however, the electrochemical behaviour of CF10-S_{pore} is strikingly different: Its CV scan in EC/DEC shows a single pair of redox peaks at 1.4 V and 2.1 V, which is identical to the CV scan of CF10-S_{pore} in the TEGDME electrolyte. The GCD curve of CF10-S_{pore} in EC/DEC electrolyte shows a single lithiation slope starting from 1.7 V and a single delithiation slope starting from 1.8 V with a lithiation capacity of 1700 mA h g⁻¹, which is also nearly identical with that in the TEGDME electrolyte. The sequential CV scans and GCD cycles of all three samples in both electrolytes are all consistent as shown in Figure S2 in ESI.

It is clear that the electrochemical behaviour of these three samples are determined by the surrounding environment of the sulphur, i.e. confined sulphur vs. superficial sulphur. When superficial sulphur is present, only TEGDME (an ether) is a viable electrolyte solvent for enabling conventional liquid-phase Li-S electrochemical processes. However, when the sulphur is exclusively confined in the sub-nano pores, both TEGDME and EC/DEC (carbonates) can facilitate identical Li-S electrochemical reactions. These anomalous electrochemical behaviours of sulphur were scarcely investigated in some previous studies using microporous carbons as sulphur hosts, and a few mechanisms have been proposed.³⁴⁻⁴¹ One generally accepted hypothesis ascribes these anomalous behaviours to

the lithiation and delithiation of small sulphur allotropes such as S₄ or S₂ in the sub-nano pores.³⁶⁻⁴⁰ Another hypothesis attributes these anomalous behaviours to the lithiation and delithiation of sulfurized carbon.⁴¹ With the assumption of the existence of small sulphur allotropes (S₂₋₄) in the sub-nano pores, Li and co-workers proposed a solid-state Li-S reaction mechanism induced by the prevention of solvent penetration due to the pore size limitation.⁴⁰

We agree with Li and co-workers on the mechanism of solid-state Li-S reactions in sub-nano confinement, although the form of sulphur in sub-nano confinement calls for further studies. (ESI) When sulphur is exclusively confined in very small pores, the electrochemical lithiation and delithiation of sulphur can only occur when Li ions enter the pores. Previous studies of porous carbon capacitors demonstrated that sub-nano pores in carbon might not be accessible to cations in non-aqueous electrolytes due to the larger solvation shell.^{42,43} For instance, the size of the Li ion solvation shell in propylene carbonate was estimated as 1.59 nm.⁴⁴ As a result, Li ions can only enter the pores by either desolvation or solvation shell distortion, and there may be none or very few solvent molecules inside the sub-nano pores where the Li-S electrochemical reaction occurs. Meanwhile, the extremely small sulphur grains in sub-nano confinement and the intimate contact with carbon can ensure the in-depth lithiation in solid state. In an analogous experiment, Gogotsi and co-workers discovered an anomalously high capacitance in supercapacitor electrodes made of microporous carbon, and they hypothesized that it was due to ions entering the sub-nano pores via desolvation.⁴⁵⁻⁴⁷ We posit that a similar phenomenon occurs during the lithiation-delithiation of sulphur in very small confinement within liquid electrolytes. This hypothesized mechanism explains why both TEGDME and EC/DEC are viable electrolyte solvents for CF10-S_{pore} with identical characteristics: the solid-state Li-S electrochemical reaction no longer involves the dissolution of polysulfides or prohibited by severe polysulfide/electrolyte incompatibility.³³ It is worth noting that recent studies on all-solid-state Li-S batteries with ceramic electrolytes^{48,49} demonstrated very similar electrochemical behaviours of sub-nano confined sulphur in liquid electrolyte, which also supports our hypothesized solid-state reaction mechanism.

The cycle stability of CF10-S_{pore}, CF10-S₆₀, and CF10-S₉₀ in TEGDME and EC/DEC electrolytes are shown in Figure S3 in ESI. The cycle stability of CF10-S_{pore} indicates a slight advantage of EC/DEC electrolyte over TEGDME electrolyte in terms of long-term cycle stability, which was also reported in a previous study.³⁷ This observation can be attributed to the fact that the microporous structure of CF10 is not ideal; therefore, lithium polysulfides could be gradually generated and dissolved in the TEGDME electrolyte.

For further evidence of the solid-state lithiation-delithiation mechanism of sub-nano confined sulphur, we performed the following experiments: CF10-S_{pore} and CF10-S₉₀ electrodes containing an equal mass of sulphur (~10 mg) were lithiated in 5 mL TEGDME electrolyte, respectively, in two home-made PTFE cylindrical cells with 80 mA g⁻¹ current density to ensure in-depth lithiation. After the lithiation, the TEGDME electrolytes in these two cells were immediately extracted for UV-Vis spectroscopy analysis. The inset in **Figure 4a** shows the photographs of the TEGDME electrolytes used in the CF10-S_{pore} lithiation (vial #1) and CF10-S₉₀ lithiation (vial #2). It can be clearly seen that the electrolyte used for CF10-S_{pore} has no visible colour change; however, the electrolyte used for CF10-S₉₀ becomes dark red, which indicates the presence of lithium polysulfides. To facilitate UV-Vis spectra measurements, the TEGDME electrolyte for CF10-S₉₀ was diluted 5 times, and the colour changed from burgundy to ultramarine green (vial #3), which indicates the presence of S₃⁻ free radical.⁵⁰ **Figure 4a** shows the UV-Vis spectra of the TEGDME electrolyte for CF10-S_{pore} and the diluted TEGDME electrolyte for CF10-S₉₀; lithium polysulfide species including S₆²⁻ anion and S₃⁻ free radical were detected in the diluted TEGDME electrolyte for CF10-S₉₀.⁵¹ In contrast, no polysulfide species were detected in the TEGDME electrolyte for CF10-S_{pore}. This observation clearly demonstrates that no lithium polysulfides are dissolved into the electrolyte when sulphur is confined in sub-nano pores and, therefore, the lithiation

occurs in the solid state.

To analyse the composition of the final products from the lithiation of CF10-S_{pore} and CF10-S₉₀ in the TEGDME electrolyte, we further performed XPS analyses on these lithiated electrodes, of which the S 2p spectra are shown in **Figure 4b** and **c**, respectively. Sulphur at any valence state always has split peaks in XPS separated by 1.18 eV arising from S 2p_{3/2} (higher binding energy) and S 2p_{1/2} (lower binding energy) spin-orbit splitting. In our analysis, we index the sulphur species by the higher binding energy of the S 2p_{3/2} peak. The two split-peaks at 167.6 eV (purple) and 170.2 eV (crimson) in both CF10-S_{pore} and CF10-S₉₀ can be attributed to the sulphonyl residue from the LiTFSI salt and the sulphur oxide species from sulphur infusion and electrolyte decomposition.⁵²⁻⁵⁴ The three split-peaks in the range from 167 eV to 159.5 eV represent three sulphur species resulting from the lithiation. The first observation is that both CF10-S_{pore} and CF10-S₉₀ have same lithiated species at 164.0 eV (orange), ~162.0 eV (green), and ~161.0 eV (blue), which can be respectively assigned as un-lithiated sulphur, lithium persulphide (Li₂S₂), and lithium sulphide (Li₂S).⁵⁵ It is not surprising that no other lithium polysulfide species was observed in the lithiated CF10-S_{pore} according to our proposed solid-state lithiation mechanism not involving polysulfides. It is also not surprising to see the same products in the lithiated CF10-S₉₀: previous investigations on the Li-S phase diagram clearly demonstrated that elemental sulphur and Li₂S are the only stable phases in solid state at




Figure 4. (a) UV-Vis spectra of the TEGDME electrolyte used in CF10-S_{pore} lithiation and the diluted TEGDME electrolyte used in CF10-S₉₀ lithiation, inset is photograph of the TEGDME electrolytes used in CF10-S_{pore} and CF10-S₉₀ lithiation; XPS spectra of S 2p in (b) lithiated CF10-S_{pore} and (c) lithiated CF10-S₉₀; (d) predicted binding energies of sulfur in Li₂S₂ and Li₂S from DFT calculation.

room temperature.^{56,57} Lithium polysulfides spontaneously disproportionate to sulphur and Li_2S upon drying. Meanwhile, both experimental and theoretical studies indicate Li_2S_2 is a metastable phase, which could exist in the solid state at room temperature.⁵⁸⁻⁶⁰ Despite these similarities, the percentage of each sulphur species in the lithiated $\text{CF10-S}_{\text{pore}}$ and lithiated CF10-S_{90} are distinctly different as indicated by the peak area (Table S3 in ESI). Only 2.6% of the lithiated sulphur in $\text{CF10-S}_{\text{pore}}$ remains as elemental sulphur, and the content of S^{2-} and S_2^{2-} anions are 67.8% and 29.6%, respectively. On the contrary, 22.8% of the lithiated sulphur in CF10-S_{90} still remains as elemental sulphur, and the content of S^{2-} and S_2^{2-} anions are 49.5% and 27.7%, respectively. The much lower sulphur content in the lithiated $\text{CF10-S}_{\text{pore}}$ clearly indicates superior sulphur utilization in the solid-state lithiation mechanism, which is also consistent with the demonstrated higher sulphur-based capacity of $\text{CF10-S}_{\text{pore}}$ in Figure 3b.

electron microscopy (TEM) images and the elemental mapping of the cross sections $\text{CF10-S}_{\text{pore}}$, $\text{CF20-S}_{\text{pore}}$, $\text{CF25-S}_{\text{pore}}$, and $\text{CF30-S}_{\text{pore}}$ (Figure S5 in ESI) clearly show that sulfur is uniformly dispersed in all of the carbon fiber samples. The XRD patterns (Figure S6 in ESI) indicate that the sulfur in all four confinements is amorphous.

As we anticipated, the electrochemical characteristics of sulphur indeed show a clear correlation to the confinement size. **Figures 5a and b**, respectively, show the first CV scans and the first GCD cycles of $\text{CF10-S}_{\text{pore}}$, $\text{CF20-S}_{\text{pore}}$, $\text{CF25-S}_{\text{pore}}$, and $\text{CF30-S}_{\text{pore}}$ in the TEGDME electrolyte. As aforementioned, the CV of $\text{CF10-S}_{\text{pore}}$ shows a single pair of redox peaks. The CV of $\text{CF20-S}_{\text{pore}}$ shows both the redox peaks representing the liquid phase Li-S electrochemical reactions (cathodic peaks at 2.5 V, 2.2 V, 2.0 V and anodic peaks at 2.4 V and 2.6 V) and the low-potential redox peaks representing the solid-state Li-S reaction. In the CV of $\text{CF25-S}_{\text{pore}}$, the peak currents of the low-




Figure 5. The first CV scans at 0.1 mV s^{-1} and GCD curves at 160 mA g^{-1} of $\text{CF10-S}_{\text{pore}}$, $\text{CF20-S}_{\text{pore}}$, $\text{CF25-S}_{\text{pore}}$, and $\text{CF30-S}_{\text{pore}}$ in TEGDME electrolyte (a) and (b) respectively, and in EC/DEC electrolyte (c) and (d), respectively.

Based on these results, we find that the size of the sulphur confinement has a profound effect on Li-S electrochemical processes; i.e. there is a critical size regime in order for the proposed solid-state Li-S electrochemical reaction to occur. To investigate these effects, another three carbon fibers with different ranges of pore size (CF20, CF25, and CF30) were investigated as sulfur hosts. Samples with sulfur exclusively confined in the pores, namely $\text{CF20-S}_{\text{pore}}$, $\text{CF25-S}_{\text{pore}}$, and $\text{CF30-S}_{\text{pore}}$, were prepared using the same method for $\text{CF10-S}_{\text{pore}}$ preparation (TGA in Figure S4 in ESI). The transmission

potential redox pair are further reduced, whereas the peaks representing liquid phase Li-S reactions become more dominating. For $\text{CF30-S}_{\text{pore}}$, its CV demonstrates the characteristics of conventional liquid phase Li-S electrochemical reactions without the low-potential redox peaks. All the CV scans are consistent with their corresponding GCD curves shown in Figure 5b. Based on the evolution of the characteristics of Li-S electrochemical reactions as a function of the pore size, we posit that the critical size of sulphur confinement for solid-state Li-S electrochemical reaction is

about 1.0 nm, i.e. sub-nanometre confinement. **Figures 5c** and **d** are the first CV scans and the first GCD cycles of CF10-S_{pore}, CF20-S_{pore}, CF25-S_{pore}, and CF30-S_{pore} in the EC/DEC electrolyte. All of the CV scans and the corresponding GCD curves demonstrate consistent characteristics with a single pair of redox peaks and single lithiation-delithiation slopes. However, compared to CF10-S_{pore}, the CV redox pairs of CF20-S_{pore}, CF25-S_{pore}, and CF30-S_{pore}, which have larger pore sizes, demonstrate higher peak separation indicating inferior charge transfer kinetics. Also as shown in Figure 5d, the lithiation and delithiation capacity drastically decreases with increasing pore size. The decreased capacity can be attributed to the fact that sub-nano confined sulphur population decreases as the pore size range increases from 0.4-1.0 nm to 0.4-3.0 nm. The second CV scans and GCD cycles show consistent characteristics (Figure S7 in ESI). The cycle stability results in both EC/DEC electrolyte and TEGDME are shown in Figure S8 in ESI.

We further studied the equilibrium potential of the solid-state Li-S reaction under sub-nano confinement (CF10-S_{pore}) using galvanostatic intermittent titration techniques (GITT) as shown in **Figure 6a** and **b**. The GITT results of CF20-S_{pore} and CF25-S_{pore} in both TEGDME and EC/DEC electrolytes are shown in Figure S9 in ESI. Comparing the GITT results of CF10-S_{pore} in the EC/DEC electrolyte with that in the TEGDME electrolyte, it is clear that the single lithiation plateau is an inherently thermodynamic characteristic of the solid-state Li-S

electrochemical reaction in the sub-nano confinement regardless electrolyte. The equilibrium solid-state lithiation potential is 1.8 V vs. Li/Li⁺ in both electrolytes. However, the lithiation overpotential in TEGDME is 280 mV, which is much higher than that in EC/DEC (150 mV). Since the electrodes are identical, the different overpotentials must be due to the electrolytes. One possibility is the different solvation size or solvation energy of Li ions in TEGDME vs. EC/DEC: A previous study by Henderson and co-workers suggested the Li-ion solvation structure in TEGDME consisting of two six-coordinate Li cations coordinated by two TEGDME molecules.⁶¹ Such a double-helix dimer structure can impose energy barriers to the desolvation of TEGDME resulting in a higher overpotential. The solid-state Li diffusivity in sulphur is calculated from the GITT data as shown in **Figure 6c** and **d** as a function of lithiation potential. The average diffusivity is calculated as 1.16×10^{-15} cm²/s as measured in EC/DEC and 1.26×10^{-15} cm²/s as measured in TEGDME in the plateau region, which are in excellent agreement with each other. The Li diffusivity increases when the voltage is decreased below 1.7 V, which can be attributed to the enrichment of Li in the lithiated sulphur. The diffusivity of Li in the liquid-phase Li-S reaction was also estimated from the high-voltage plateau region from CF25-S_{pore} in TEGDME (Figure S10d in ESI). The diffusivity of Li in the liquid-phase is in the order of 10^{-13} cm²/s, which is two orders of magnitude higher than that in the solid-state. For delithiation, the equilibrium behaviours of CF10-S_{pore} in both




Figure 6. GITT curves of CF10-S_{pore} in (a) EC/DEC electrolyte and (b) TEGDME electrolyte; diffusivity of Li vs. potential calculated from the GITT data in (c) EC/DEC electrolyte and (d) TEGDME electrolyte.

TEGDME and EC/DEC electrolytes are identical, i.e. the same equilibrium potential and overpotential. This observation is consistent with the solid-state Li-S reaction mechanism since the delithiation process does not rely on Li ion desolvation so that the type of solvent does not affect the delithiation. A persistent behaviour of the solid-state Li-S electrochemical reaction is the low delithiation capacity in the first cycle (previously shown in Figures 3 and 5), which is also demonstrated as an inherent property of the sulphur in sub-nano confinements by GITT. Although the exact mechanism is still under investigation, we propose the following explanations: (1) the imposed potential ($< 3V$ vs. Li/Li^+) is insufficient to delithiate Li_2S within the solid-state environment; (2) degradation of the electrical connection induced by the sulfur volume change.

Conclusions

In conclusion, we elucidate a mechanism of solid-state Li-S electrochemical reaction in liquid electrolytes enabled by sub-nano confinement of sulphur. Our results demonstrate unambiguous transition of electrochemical behaviours from superficial sulphur to sub-nano confined sulphur, and from sub-nano confined sulphur to sulphur in relatively larger confinements. We clearly demonstrate that the lithiation and delithiation of sulphur in sub-nano confinement is thermodynamically different from conventional liquid phase Li-S reactions. As a result, both ether-based electrolyte and carbonate-based electrolytes are viable for Li-S electrochemical reactions in sub-nano confinement environments since the solid-state mechanism does not involve or require lithium polysulfide dissolution or polysulfide/electrolyte compatibility. Therefore, any Li-ion electrolyte satisfying the electrochemical stability and conductivity requirements should work with the sub-nano confined sulphur cathode. Compared to conventional liquid phase Li-S electrochemical reactions, this solid-state mechanism has the benefit of simplicity, which can provide a new paradigm for future Li-S battery materials design and synthesis. Meanwhile, the large irreversible capacity in the first cycle presents an inherent challenge to both sub-nano confined sulphur environments and the resulting low sulphur content, which are areas currently under investigation in our group.

Acknowledgements

The authors thank the financial support from the University of California, Riverside. We acknowledge the National Science Foundation for the use of supercomputing resources through the Extreme Science and Engineering Discovery Environment (XSEDE), Project No. TG-CHE150028. We are also deeply grateful to Drs. Karen Gaskell and Yunhua Xu at the University of Maryland for the XPS experiments.

Notes and references

- 1 Lange's Handbook of Chemistry; Dean, J. A., Ed.; McGraw-Hill: New York, 1985.
- 2 M. Hagen, P. Schiffels, M. Hammer, S. Dorfler, J. Tubke, M.J. Hoffmann, H. Althues and S. Kaskel, *J. Electrochem. Soc.* **2013**, *160*, A1205.
- 3 C. Lin, W. Chen, Y. Song, C. Wang, L. Tsai, N. Wu, *J. Power Sources* **2014**, *263*, 98.
- 4 X. Yu, H. Pan, Y. Zhou, P. Northrup, J. Xiao, S. Bak, M. Liu, K. Nam, D. Qu, J. Liu, T. Wu and X. Yang, *Adv. Energy Mater.* **2015**, *5*, 1500072.
- 5 X. Ji, K. Lee and L.F. Nazar, *Nature Mater.* **2009**, *8*, 500.
- 6 Liang, C.; Dudney, N.J.; Howe J.Y. *Chem. Mater.* **2009**, *21*, 4724-4730.
- 7 Yao, H.; Zheng, G.; Li, W.; McDowell, M. T.; She, Z.; Liu, N.; Lu, Z.; Cui, Y. *Nano Lett.* **2013**, *13*, 3385-3390.
- 8 Weng, W.; Pol, V. G.; Amine, K. *Adv. Mater.* **2013**, *25*, 1608-1615.
- 9 Lee, J. T.; Zhao, Y.; Thieme, S.; Kim, H.; Soschatz, M.; Borchardt, L.; Magasinski, A.; Cho, W. I.; Kaskel, S.; Yushin, G. *Adv. Mater.* **2013**, *25*, 4573-5479.
- 10 Jayaprakash, N.; Shen, J.; Moganty, S.S.; Corona, A.; Archer, L.A. *Angew. Chem. Int. Ed.* **2011**, *50*, 5904-5908.
- 11 Zheng, G.; Yang, Y.; Cha, J.J.; Hong, S.S.; Cui, Y. *Nano Lett.* **2011**, *11*, 4462-4467.
- 12 Seh, Z.; Li, W.; Cha, J. J.; Zheng, G.; Yang, Y.; McDowell, T., Hsu, P.; Cui, Y. *Nat. Commun.* **2013**, *4*, Article number: 1331.
- 13 Liang, Z.; Zheng, G.; Li, W.; She, Z.; Yao, H.; Yan, K.; Kong, D.; Cui, Y. *ACS Nano* **2014**, *8*, 5249-5256.
- 14 Zheng, W.; Liu, Y. W.; Hu, X. G.; Zhang, C. F. *Electrochim. Acta* **2006**, *51*, 1330-1335.
- 15 Zhou, G.; Wang, D.; Li, F.; Hou, P.; Yin, L.; Liu, C.; Lu, G.; Gentle, I.R.; Cheng, H. *Energy Environ. Sci.* **2012**, *5*, 8901-8906.
- 16 Zhao, Y.; Wu, W.; Li, J.; Xu, Z.; Guan, L. *Adv. Mater.* **2014**, *26*, 5113-5118.
- 17 Ji, L.; Rao, M.; Zheng, H.; Zhang, L.; Li, Y.; Duan, W.; Guo, J.; Cairns, E.J.; Zhang, Y. *J. Am. Chem. Soc.* **2011**, *133*, 18522-18525.
- 18 Wang, H.; Yang, Y.; Liang, Y.; Robinson, J.T.; Li, Y.; Jackson, A.; Cui, Y.; Dai, H. *Nano Lett.* **2011**, *11*, 2644-2647.
- 19 Zhou, W.; Chen, H.; Yu, Y.; Wang, D.; Cui, Z.; DiSalvo, F. J.; Abruña, H. D. *ACS Nano* **2013**, *7*, 8801-8808.
- 20 Chen, R.; Zhao, T.; Lu, J.; Wu, F.; Li, L.; Chen, J.; Tan, G.; Ye, Y.; Amine, K. *Nano Lett.* **2013**, *13*, 4642-4649.
- 21 Song, M.; Zhang, Y.; Cairns, E.J. *Nano Lett.* **2013**, *13*, 5891-5899.
- 22 Zheng, S.; Wen, Y.; Zhu, Y.; Han, Z.; Wang, J.; Yang, J.; Wang, C. *Adv. Energy Mater.* **2014**, *4*, Article number: 1400482.
- 23 Yang, Y.; Zheng, G.; Cui, Y. *Energy Environ. Sci.* **2013**, *6*, 1552-1558.
- 24 Yao, H.; Zheng, G.; Hsu, P.; Kong, D.; Cha, J. J.; Li, W.; She, Z.; McDowell, M. T.; Yan, K.; Liang, Z.; Narasimhan, V. K.; Cui, Y. *Nat. Commun.* **2014**, *5*, Article number: 3943.
- 25 Su, Y.; Manthiram, A. *Nat. Commun.* **2012**, *3*, Article number: 1166.
- 26 Han, X.; Xu, Y.; Chen, Y.; Chen, Y.; Weadock, N.; Wan, J.; Zhu, H.; Liu, Y.; Li, H.; Rubloff, G.; Wang, C.; Hu, L. *Nano Energy* **2013**, *2*, 1197-1206.
- 27 Chung, S.; Manthiram, A. *Adv. Funct. Mater.* **2014**, *24*, 5299-5306.
- 28 Zheng, G.; Zhang, Q.; Cha, J.J.; Yang, Y.; Li, W.; Seh, Z.W.; Cui, Y. *Nano Lett.* **2013**, *13*, 1265-1270.
- 29 Ma, L.; Zhuang, H.; Lu, Y.; Moganty, S.S.; Hennig, R.G.; Archer, L.A. *Adv. Energy Mater.* **2014**, *4*, Article number: 1400390.

- 30 Zheng, T.; Tian, J.; Wu, D.; Gu, M.; Xu, W.; Wang, C.; Gao, F.; Engelhard, M.H.; Zhang, J.; Liu, J.; Xiao, J. *Nano Lett.* **2014**, *14*, 2345-2352.
- 31 Song, J.; Xu, T.; Gordin, M.L.; Zhu, P.; Lv, D.; Jiang, Y.; Chen, Y.; Duan, Y.; Wang, D. *Adv. Funct. Mater.* **2014**, *24*, 1243-1250.
- 32 Xu, K. *Chem. Rev.* **2004**, *104*, 4303-4417.
- 33 Gao, J.; Lowe, M.A.; Kiya, Y.; Abruña, H.D. *J. Phys. Chem. C* **2011**, *115*, 25132-25137.
- 34 Lai, C.; Gao, X. P.; Zhang, B.; Yan, T. Y.; Zhou, Z. *J. Phys. Chem. C* **2009**, *113*, 4712-4716.
- 35 Zhang, B.; Qin, X.; Li, G.R.; Gao, X.P. *Energy Environ. Sci.* **2010**, *3*, 1531-1537.
- 36 Guo, J.; Xu, Y.; Wang, C. *Nano Lett.* **2011**, *11*, 4288-4294.
- 37 Xin, S.; Gu, L.; Zhao, N.; Yin, Y.; Zhou, L.; Guo, Y.; Wan, L. *J. Am. Chem. Soc.* **2012**, *134*, 18510-18513.
- 38 Wu, H.; Wei, S.; Zhang, L.; Xu, R.; Hng, H.; Lou, X. *Chem. Eur. J.* **2013**, *19*, 10804-10808.
- 39 Xu, Y.; Wen, Y.; Zhu, Y.; Gaskell, K.; Cychosz, K.A.; Eichhorn, B.; Xu, K.; Wang, C. *Adv. Funct. Mater.* **2015**, *27*, 4312-4320.
- 40 Li, Z.; Yuan, L.; Yi, Z.; Sun, Y.; Liu, Y.; Liu, Y.; Jiang, Y.; Shen, Y.; Xin, Y.; Zhang, Z.; Huang, Y. *Adv. Energy Mater.* **2014**, *4*, Article number: 1301473.
- 41 Zhang, S. *Frontiers in Energy Research* **2013**, *1*, Article 10.
- 42 Conway, B. E., *Double-layer capacitors and related devices* S. Wolsky, N. Marincic Eds. Proceedings Fourth International Symposium. Florida Educational Seminars, Boca Raton, FL, 1994.
- 43 Frackowiak, E.; Beguin, F. *Carbon* **2001**, *39*, 937-950.
- 44 Xu, K.; von Wald Cresce, A. *J. Mater. Res.* **2012**, *27*, 2327-2341.
- 45 Chmiola, J.; Yushin, G.; Gogotsi, Y.; Portet, C.; Simon, P.; Taberna, P. L. *Science* **2006**, *313*, 1760-1763.
- 46 Chmiola, J.; Largeot, C.; Taberna, P. L.; Simon, P.; Gogotsi, Y. *Angew. Chem. Int. Ed.* **2008**, *47*, 3392-3395.
- 47 Largeot, C.; Portet, C.; Chmiola, J.; Taberna, P.-L.; Gogotsi, Y.; Simon, P. *J. Am. Chem. Soc.* **2008**, *130*, 2730-2731.
- 48 Nagao, M.; Imade, Y.; Narisawa, H.; Kobayashi, T.; Watanabe, R.; Yokoi, T.; Tatsumi, T.; Kanno, R. *J. Power Sources* **2013**, *222*, 237-242.
- 49 Nagata, H.; Chikusa, Y. *J. Power Sources* **2014**, *264*, 206-210.
- 50 Clark, R.J.H.; Cobbold, D.G. *Inorganic Chemistry* **1978**, *17*, 3169-3174.
- 51 Barchasz, C.; Molton, F.; Duboc, C.; Leprêtre, J.-C.; Patoux, S.; Alloin, F. *Anal. Chem.* **2012**, *84*, 3973-3980.
- 52 Fu, Y.; Zu, C.; Manthiram, A. *J. Am. Chem. Soc.* **2013**, *135*, 18044-18047.
- 53 Su, Y.-S.; Fu, Y.; Cochell, T.; Manthiram, A. *Nat. Commun.* **2013**, *4*, Article number: 2985.
- 54 Tao, X.; Wang, J.; Ying, Z.; Cai, Q.; Zheng, G.; Gan, Y.; Huang, H.; Xia, Y.; Liang, C.; Zhang, W.; Cui, Y. *Nano Lett.* **2014**, *14*, 5288-5294.
- 55 Yang, C.; Yin, Y.; Guo, Y.; Wan, L. *J. Am. Chem. Soc.* **2015**, *137*, 2215-2218.
- 56 Sharma, R.A. *J. Electrochem. Soc.: Electrochemical Science and Technology* **1972**, *119*, 1439-1443.
- 57 Cunningham, P.T.; Johnson, S.A.; Cairns, E.J. *J. Electrochem. Soc.: Electrochemical Science and Technology* **1972**, *119*, 1448-1450.
- 58 Kao, J. *J. Mol. Struct.* **1979**, *56*, 147-152.
- 59 Liu, Z.; Hubble, D.; Balbuena, B.P.; Mukherjee, P.P. *Phys. Chem. Chem. Phys.* **2015**, *17*, 9032-9039.
- 60 Yang, G.; Shi, S.; Yang, J.; Ma, Y. *J. Mater. Chem. A* **2015**, *3*, 8865-8869.
- 61 W.A. Henderson, N.R. Brooks and V.G. Young, Jr. *Chem. Mater.* **2003**, *15*, 4685.