Chemical Science

EDGE ARTICLE

Cite this: Chem. Sci., 2015, 6, 1825

Received 6th October 2014 Accepted 10th January 2015

DOI: 10.1039/c4sc03062a

www.rsc.org/chemicalscience

Introduction

Hypoxia has been found to be closely related to various diseases, such as solid tumors,¹ brain abnormalities² and retinal diseases.³ Especially, hypoxia is a feature of tumor tissues, and the median oxygen (O_2) concentration in some solid tumors is around 4% and may even decrease to 0% locally.⁴ The real-time monitoring of O_2 concentration in living cells and tissue can not only lead to accurate diagnosis of cancer, but can also be used to evaluate therapeutic effects. Thus far, enormous efforts have been focused on the development of hypoxia sensing. Hypoxia can be selectively detected by utilizing immunostaining,⁵

Fluorescent/phosphorescent dual-emissive conjugated polymer dots for hypoxia bioimaging†

Qiang Zhao, *a Xiaobo Zhou, a Tianye Cao, ^c Kenneth Yin Zhang, a Lijuan Yang, a Shujuan Liu,^a Hua Liang,^a Huiran Yang,^a Fuyou Li^{*c} and Wei Huang^{*ab}

A kind of fluorescent/phosphorescent dual-emissive conjugated polyelectrolyte has been prepared by introducing phosphorescent platinum(II) porphyrin (O₂-sensitive) into a fluorene-based conjugated polyelectrolyte (O₂-insensitive), which can form ultrasmall conjugated polymer dots (FP-Pdots) in the phosphate buffer solution (PBS) via self-assembly caused by their amphiphilic structures with hydrophobic backbones and hydrophilic side chains. These FP-Pdots can exhibit an excellent ratiometric luminescence response to $O₂$ content with high reliability and full reversibility for measuring oxygen levels, and the excellent intracellular ratiometric $O₂$ sensing properties of the FP-Pdots nanoprobe have also been confirmed by the evident change in the $I_{\text{red}}/I_{\text{blue}}$ ratio values in living cells cultured at different $O₂$ concentrations. To confirm the reliability of the $O₂$ sensing measurements of the FP-Pdots nanoprobe, O_2 quenching experiments based on lifetime measurements of phosphorescence from Pt(II) porphyrin moieties have also been carried out. Utilizing the sensitivity of the long phosphorescence lifetime from Pt(II) porphyrins to oxygen, the FP-Pdots have been successfully applied in time-resolved luminescence imaging of intracellular $O₂$ levels, including photoluminescence lifetime imaging and timegated luminescence imaging, which will evidently improve the sensing sensitivity and reliability. Finally, in vivo oxygen sensing experiments were successfully performed by luminescence imaging of tumor hypoxia in nude mice. EDGE ARTICLE

Close this Comparison in the Comparison of the

magnetic resonance imaging,⁶ positron emission tomography imaging,⁷ and optical imaging techniques.⁸⁻¹⁰ Among them, non-invasive optical imaging offers a powerful approach to map oxygen in living cells and tissues with high sensitivity and spatial resolution. Many fluorescence probes for optical imaging that employ organic dyes containing a nitro group, quinone group, or azo group as the hypoxia-sensing moiety have been developed.¹⁰ Most of these probes, however, usually show an irreversible fluorescence change upon bioreduction reaction under hypoxia, which limits their applications in real-time fluorescence monitoring of oxygen concentration.

Phosphorescent probes based on transition-metal complexes can be used for fully reversible real-time monitoring of $O₂$ levels in vitro with high-resolution by utilizing the energy transfer between the triplet excited state of the metal complex and the triplet ground state of O_2 .^{8,11} Thus, phosphorescent metal complexes with a long-lived triplet excited state, such as plati $num(n),¹²$ palladium $(n),¹³$ ruthenium $(n),¹⁴$ and iridium $(m)¹⁵$ complexes, have been regarded as a kind of fascinating hypoxia probe. The phosphorescence intensities of these complexes are reversibly dependent on the change in $O₂$ concentration. However, most of these reported probes are based on the variation in single phosphorescent emission ("ON–OFF" or "OFF– ON" type). The single intensity-based reporting signal is easily influenced by the external environment, such as the probe's

YAL SOCIETY
CHEMISTRY

a Key Laboratory for Organic Electronics and Information Displays & Institute of Advanced Materials (IAM), Jiangsu National Synergistic Innovation Center for Advanced Materials (SICAM), Nanjing University of Posts & Telecommunications, 9 Wenyuan Road, Nanjing 210023, China. E-mail: iamqzhao@njupt.edu.cn; wei-huang@njtech.edu.cn; Fax: +86-25-85866396

b Key Laboratory of Flexible Electronics (KLOFE) & Institute of Advanced Materials (IAM), Jiangsu National Synergistic Innovation Center for Advanced Materials (SICAM), Nanjing Tech University (NanjingTech), 30 South Puzhu Road, Nanjing 211816, China

c Department of Chemistry & State Key Laboratory of Molecular Engineering of Polymers & Institute of Biomedicine Science, Fudan University, Shanghai 200433, China. E-mail: fyli@fudan.edu.cn; Fax: +86-21-55664621

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/c4sc03062a

concentration, temperature, or pH value. The standardization and use of accurate readout of O_2 concentration are also difficult. Therefore, an advisable choice is to develop ratiometric O_2 probes that can allow for accurate measurement of $O₂$ concentration through the ratio change of the emission intensities at two different wavelengths.

For the design of ratiometric O_2 probes, herein, we hope to demonstrate an effective way to construct a Förster resonance energy transfer (FRET) system with an $O₂$ -insensitive fluorophore as the energy donor and an $O₂$ -sensitive phosphorescent metal complex as the acceptor (Fig. 1). The occurrence of FRET can significantly improve the sensitivity of sensing by promoting the population of the oxygen-sensitive triplet excited state of the acceptor. We introduced phosphorescent plati $num(\text{II})$ porphyrin (O₂-sensitive) into a fluorene-based conjugated polyelectrolyte $(O_2$ -insensitive). Fluorescent/ phosphorescent dual-emissive polymer dots (FP-Pdots, see Fig. 1A) were successfully prepared as excellent O_2 probes. The as-prepared FP-Pdots enabled ratiometric measurements of hypoxia in living cells with the advantages of eliminating photobleaching and excitation power fluctuation by using the O_2 insensitive fluorescence from polyfluorene moieties as a reference and O_2 -sensitive phosphorescence from Pt(π) porphyrins as the sensing signal.¹⁶ Taking advantage of the long excitedstate lifetime of phosphorescent $Pt(II)$ porphyrins, time-resolved luminescence imaging of $O₂$ levels in living cells, including photoluminescence lifetime imaging microscopy (PLIM) and time-gated luminescence imaging (TGLI), was realized. These Chemical Science

concernantion, rempeatance, or pH value. The sandardization recharges content

and an of decomposition and the concernation are deal office incorrected to concernantic common

content concernes are descr

techniques can eliminate external influences and autofluorescence interferences from biological samples.^{17,18} Furthermore, we applied the FP-Pdots probe to nude mice for the luminescence imaging of tumor hypoxia. These experiments have shown that FP-Pdots are an excellent class of luminescent probes for practical application in determining $O₂$ concentrations in living samples.

Results and discussion

Design, synthesis and properties of the FP-Pdots

We chose conjugated polymer as the oxygen-insensitive energy donor to construct FRET-based ratiometric O_2 probes (Fig. 1) because of their high light absorptivity, extraordinary fluorescence brightness, excellent photostability, and good water-dispersibility.19,20 The synthetic route and chemical structures of the conjugated polyfluorene electrolyte are shown in Scheme 1. The Pt (n) complex-polymer precursor P1 was prepared via a Suzuki polycondensation reaction, and its structure was characterized via 1 H NMR and 13 C NMR. The number-average molecular weight of the polymer was determined to be 25 400 with a polydispersity index of 2.49, measured via gel permeation chromatography (GPC) in THF by using the calibration curve of polystyrene standards. The target $Pt(_{II})$ complex-polymer P2 was obtained by the quarternization of the precursor P1 (Scheme 1). The initial feed ratio of $Pt(II)$ porphyrins to the total monomers was 10 mol%. The actual $Pt(II)$ porphyrin content in the copolymer, which was estimated via ¹H NMR, was about

Fig. 1 (A) The chemical structure of fluorescent/phosphorescent conjugated polyelectrolyte P2, and a schematic illustration of the selfassembly behavior of P2 into the polymer dots (FP-Pdots); (B) oxygen sensing mechanism of conjugated polyelectrolyte and schematic illustrations of the energy level of the moieties in FP-Pdots.

Scheme 1 Synthetic route of the target conjugated Pt(II) complexpolyelectrolyte P2 and the intermediate P1.

7 mol%. This value is lower than that of the feed ratio probably because of the reaction activity or steric hindrance.

The morphology of P2 in the phosphate buffer solution (PBS) was investigated via transmission electron microscopy (TEM)

Fig. 2 (A) A TEM image of FP-Pdots in aqueous solution; (B) normalized absorption and emission spectra of FP-Pdots (12 μ g mL $^{-1}$) in aqueous solution; (C) emission spectra of FP-Pdots (12 μ g mL $^{-1}$) in $H₂O$ under the different $O₂$ concentrations; inset: the emission photos of FP-Pdots in the presence and absence of O₂; $\lambda_{ex} = 375$ nm. (D) Plot of R_1^0/R_1 as a function of O_2 concentration; (E) phosphorescence decays of FP-Pdots in aqueous solution saturated with N_2 or air, monitored at 656 nm from the Pt(II) porphyrin moiety; $\lambda_{ex} = 405$ nm. (F) Plot of τ_0/τ as a function of O₂ concentration ($\lambda_{ex} = 405$ nm).

and dynamic light scattering (DLS), as shown in Fig. 2A and S1.† Each of the FP-Pdots have a diameter of approximately 5 nm and they were formed via self-assembly caused by their amphiphilic structures with hydrophobic backbones and hydrophilic side chains. Thus, the as-prepared FP-Pdots were well dispersed in PBS. In addition, the zeta-potential of P2 was measured to be 54.00 mV, which further demonstrated the good dispersibility and stability of the FP-Pdots in PBS.

A particular degree of spectral overlap between the emission spectrum of $Pt(II)$ -free polyfluorene **P3** (see Scheme S1[†]) and the absorption spectrum of $Pt(_{II})$ porphyrin ensures the efficient energy transfer from polyfluorene segments as host to $Pt(II)$ porphyrin moieties as guest (Fig. S4†). The photophysical properties of P2, specifically of the FP-Pdots, are shown in Fig. 2B. The UV-vis absorption spectrum of the FP-Pdots is dominated by a strong featureless transition centered at 395 nm, which consists of a mixture of Soret bands of $Pt(II)$ porphyrin²¹ and the π - π ^{*} transition of fluorene units. An additional two weak and broad absorptions, which peaked at 510 and 540 nm, respectively, were also found. These results correspond to $Q(1,0)$ and $Q(0,0)$ of the Pt(π) porphyrin moieties. 21 FP-Pdots excited at 375 nm exhibit strong blue fluorescence, attributed to the π - π ^{*} emission of the fluorene moieties, as well as relatively weak red phosphorescence of the $Pt(II)$ porphyrin moieties (Fig. 2B). In addition, the FP-Pdots of P2 also show more efficient FRET than the blend of $Pt(II)$ porphyrin (1) and Pt (n) -free polyelectrolyte P3 according to the PL spectra (Fig. S5†). Although the mixture of 1 and P3 showed the same molar ratio of $Pt(n)$ porphyrin and fluorene to P2, the emission from the $Pt(II)$ porphyrin was weaker than that in P2. The Förster radius is calculated to be 4.7 nm,^{15a} demonstrating the effectiveness of covalent incorporation of $Pt(\pi)$ porphyrin into P2. It also indicated that the dose of $Pt(II)$ porphyrin was reduced when FRET was present. Therefore, the nanoprobe will be less toxic to cells and animals. Furthermore, due to the high molar absorption coefficient and quantum yield of polyfluorene, the FRET from polyfluorene to $Pt(II)$ porphyrin will be of benefit for better O_2 -sensitivity than for non-FRET systems. Edge Article

2013. Downloaded on 12 2015. Downloaded on 12 2015. Downloaded on 12 2015. Downloaded on 12 2022

2014. This article is license on 18 2015. The common article is cliented to contain a cliented to contain a c

Luminescence response to $O₂$ content

The PL spectra of the FP-Pdots at various O_2 concentrations in water at room temperature are shown in Fig. 2C. Under an atmosphere of 21% O_2 , the FP-Pdots showed strong emission centered at 425 nm with a shoulder peak at 450 nm attributed to polyfluorene moieties as well as weak emission at 656 nm with a shoulder peak at 721 nm from $Pt(II)$ porphyrins. The solution exhibited very bright blue emission under UV excitation (Fig. 2C, inset). With decreasing O_2 content, the blue fluorescence intensities showed little change, but the red phosphorescence intensities grew progressively. This result is in agreement with the O_2 sensitivity of the Pt(II) porphyrin complexes. The red phosphorescence became dominant under an atmosphere of 0% O_2 . Thus, the color of the emission changed from very bright blue to red under UV excitation (Fig. 2C, inset).

The ratiometric oxygen sensing of the FP-Pdots was analyzed quantitatively based on the data of phosphorescence intensities shown in Fig. 2C, according to the Stern-Volmer equation:²²

$$
\frac{R_I^0}{R_I} = 1 + K_{SV} pO_2 \tag{1}
$$

where $K_{\rm sv}$ is the Stern–Volmer constant, pO_2 is the oxygen partial pressure, $R_I^0 = (I_{656}{}^0/I_{422}{}^0)$ and $R_I = (I_{656}/I_{422})$ represent the ratios of the phosphorescence (656 nm) intensity of $Pt(II)$ porphyrin to the fluorescence (422 nm) intensity of the polyfluorene moieties in the absence and presence of O_2 , respectively.

A good linearity of R_I^0/R_I as a function of O_2 concentration was observed (Fig. 2D and S6†), according to eqn (1). The $K_{\rm sv}$ value is 1.67×10^{-2} mmHg⁻¹. At the same time, no change in the fluorescence intensities of the FP-Pdots monitored at 425 nm from the polyfluorene moiety was observed at various $O₂$ concentrations (Fig. 2C), which means that the ratio of the phosphorescence intensity at 656 nm to the fluorescence intensity at 422 nm for the FP-Pdots is dependent on O_2 concentration. Therefore, the FP-Pdots can be used as a ratiometric phosphorescent probe with high reliability for measuring oxygen levels. The limit of detection of the FP-Pdots was determined to be 0.5 mmHg.

Lifetime response to $O₂$

To confirm the reliability of the O_2 sensing measurements of the FP-Pdots nanoprobe, we performed similar $O₂$ quenching experiments based on lifetime measurements of phosphorescence from $Pt(II)$ porphyrin moieties, according to eqn (2) :

$$
\frac{\tau_0}{\tau} = 1 + K_{SV} p \mathcal{O}_2 \tag{2}
$$

where K_{sv} is the Stern–Volmer constant, pO_2 is the oxygen partial pressure, and τ_0 and τ are the phosphorescence lifetimes in the absence and presence of O_2 , respectively.

The lifetime (τ) monitored at 656 nm decreased evidently with increasing O_2 concentration, as shown in Fig. 2E. For example, the phosphorescence lifetimes of the FP-Pdots in N_2 and air were 33.7 and 9.9 µs, respectively. As illustrated in Fig. 2F, a good linear relationship between τ_0/τ and pO_2 was observed. The constant $K_{\rm sv}$ based on the excited state lifetime was 1.57×10^{-2} mmHg⁻¹, which is very close to that $(1.54 \times$ 10^{-2} mmHg⁻¹) obtained from luminescence intensity measurements. However, the fluorescence lifetime of the FP-Pdots monitored at 425 nm from the polyfluorene moiety remains constant at various O_2 concentrations (Fig. S7 \dagger). Therefore, the FP-Pdots can be used as a lifetime-based phosphorescent probe with high reliability for measuring oxygen levels.

Ratiometric imaging of intracellular $O₂$ levels

We then used the FP-Pdots as a ratiometric luminescence nanoprobe to investigate intracellular $O₂$ levels. The cells were cultured for 24 h at 37 °C at 21% and 2.5% O_2 concentrations. The excitation wavelength was 405 nm. As shown in Fig. 3, the

Fig. 3 Confocal luminescence imaging and ratiometric luminescence imaging (λ_{ex} = 405 nm) of HepG2 cells incubated with the FP-Pdots (10 μ g mL⁻¹) at 21% or 2.5% O₂ concentrations. In luminescence imaging, the emission channels at wavelengths of 420–460 nm and 630–680 nm were collected. In ratiometric imaging, the ratio of emission intensity at 630–680 nm to that at 420–460 nm was chosen as the detected signal.

emission intensities collected at wavelengths from 420 nm to 460 nm (I_{blue}) , which correspond to the reference fluorescence of polyfluorene moieties, are almost the same at 21% and 2.5% $O₂$ concentrations. By contrast, the emission images taken in the wavelength range of 630 nm to 680 nm (I_{red}) , which corresponds to the phosphorescence of $Pt(n)$ porphyrin complexes, show a much brighter image at a condition of 2.5% O_2 than at 21% O_2 . The excellent intracellular ratiometric O_2 sensing properties of the FP-Pdots nanoprobe can also be confirmed by the evident change in the $I_{\text{red}}/I_{\text{blue}}$ ratio values in living cells cultured at different $O₂$ concentrations, as shown in ratio images in Fig. 3.

Time-resolved luminescence imaging of intracellular $O₂$ levels

Considering the response of long phosphorescence lifetime from $Pt(\pi)$ porphyrins to oxygen, we have applied our FP-Pdots in time-resolved luminescence imaging of intracellular $O₂$

Fig. 4 Photoluminescence lifetime images ($\lambda_{ex} = 405$ nm) of HepG2 cells incubated with 10 μ g mL⁻¹ FP-Pdots at 37 °C for 2 h at 21% and 2.5% $O₂$ concentrations, respectively. The magnification of the objective lens is $40\times$. The luminescence signals were collected in the range of 420–680 nm.

levels. First, the PLIM of intracellular $O₂$ level was performed using the FP-Pdots as a lifetime-based nanoprobe, as shown in Fig. 4. The average emission lifetime τ was about 17 ns at 21% $O₂$ concentration and increased to about 95 ns when the $O₂$ concentration was lowered to 2.5%. The interference from short-lived autofluorescence was eliminated because of the relatively long average lifetime of FP-Pdots. This result demonstrated that the FP-Pdots probe exhibits an evident difference in emission lifetime at different $O₂$ concentrations and it can be applied as an excellent PLIM probe for sensing intracellular $O₂$ levels.

To further demonstrate the ability of anti-interference when the FP-Pdots were applied for O_2 sensing in living cells, we performed TGLI measurements, and the luminescence intensity images at different time ranges were collected (Fig. 5). When the signal was collected at a time range of 0 ns to 2000 ns, the images of FP-Pdot-treated HepG2 cells exhibited a high signal intensity at 21% and 2.5% O_2 concentrations because of the presence of reference fluorescence from polyfluorene moieties. Once a particular time delay was exerted, such as in the image collected at a time range of 250 ns to 2000 ns, the signal intensity of the FP-Pdot-treated HepG2 cells at 21% O₂ concentration could not be observed. By contrast, the signal intensity collected at a time range of 250 ns to 2000 ns at 2.5% O2 concentration was still high enough to be observed, although the decrease in the luminescence intensity of the FP-Pdottreated HepG2 cells is reasonable. When the time delay was increased to 500 ns, the TGLI image of the FP-Pdot-treated HepG2 cells can still be measured. This phenomenon is attributed to the long phosphorescence lifetime of the FP-Pdots. The difference in the emission intensity at $O₂$ concentrations of 21% and 2.5% became increasingly more evident, which indicated that $O₂$ sensing can be made more sensitive by collecting the signal at a long time range via the TGLI technique. As far as we know, this study is the first to use Pdots-based TGLI for intracellular oxygen detection. Edge Article

Unport of the PLAN of interactional components and interactional components are a lifetime-Satellite is considered to $\frac{1}{2}$ and $\frac{1}{2}$ are a lifetimal baseline and interactional components are a lifet

Luminescence imaging of tumor hypoxia in nude mice

To further confirm the potential of the probe for practical application, we applied the FP-Pdots probe for luminescence

Fig. 5 Time-gated luminescence intensity images ($\lambda_{ex} = 405$ nm) of HepG2 cells incubated with the FP-Pdots (10 μ g mL⁻¹) at 37 °C for 2 h at 21% or 2.5% $O₂$ conditions with different time delays. The magnification of the objective lens is $40\times$. The luminescence signals were collected in the range of 420-680 nm

Fig. 6 (A) Luminescence imaging in vivo of a tumor-bearing mouse (ROI 1) and the control nude mouse (ROI 2) after injection of the FP-Pdots. (B) The change in luminescence intensity of the marked regions (ROI 1, ROI 2 and ROI 3) following different times after injection of the FP-Pdots into the nude mice. A xenon lamp was used as the excitation source, collocating with a bandpass filter (410 \pm 15 nm).

imaging of tumor hypoxia in nude mice. In vivo and ex vivo luminescence imaging were performed using a modified Kodak in vivo imaging system. The luminescence signals were collected at 660 ± 13 nm. The mice were intratumorally injected with the FP-Pdots solution (10 μ L, 2 mg mL⁻¹) without being deoxygenized. For the purpose of comparison, the mice were subcutaneously injected with the FP-Pdots probe under the same conditions. As shown in Fig. 6A, a very intense signal from the area of the tumor (ROI 1) was detected. When compared to the area of the subcutaneous injection (ROI 2), an obviously high signal-to-noise ratio in the emission intensity within the tumor area can be observed. To intuitively estimate the change in luminescence intensity, imaging dynamic curves were plotted, as shown in Fig. 6B. The luminescence intensity of the FP-Pdots located in tumor ROI 1 increased abruptly following 3 seconds of injection into the tumor and subsequently increased. The intensity was up to 3.3 times greater than that at 660 ± 13 nm of the FP-Pdots (ROI 3) compared with the phosphorescence intensity at ROI 2. Therefore, the FP-Pdots exhibited excellent oxygen-sensitivity and can be applied as tumor hypoxia probes in vivo.

Lastly, the cytotoxicity of the FP-Pdots nanoprobe toward HepG2 cells was determined via an MTT 3-(4,5-dimethylthiazol-2-yl)-2,5-diphenyltetrazolium bromide assay. The plot of cellular viabilities (%) vs. incubation concentrations (0–50 μ g mL $^{-1}$) of the probe in PBS buffer at 37 \degree C for 24 h is illustrated in Fig. S8.† The viabilities of the HepG2 cells still retained a value higher than 70% even after incubation with a high concentration $(50$ μ g mL⁻¹) of the nanoprobe. Under the living cell imaging experimental conditions (10 μ g mL⁻¹ concentration, 2 h incubation time), the FP-Pdots nanoprobe showed negligible cytotoxicity toward HepG2 cells with cell viabilities of more than 95%. These data demonstrated that the use of the FP-Pdots as a hypoxia probe shows excellent biocompatibility.

Conclusions

In conclusion, we have presented a hypoxia nanoprobe based on fluorescent/phosphorescent dual-emissive FP-Pdots, which was prepared from conjugated polyelectrolyte by using poly fluorenes as an O_2 -insensitive fluorophore and Pt(π) porphyrins

as an O_2 -sensitive phosphor. The FP-Pdots nanoprobe was demonstrated to be a kind of excellent ratiometric O_2 nanoprobe with full reversibility and low toxicity toward living cells. Importantly, the FP-Pdots can perform excellently in PLIM and TGLI techniques, which will evidently improve the sensing sensitivity and reliability. In addition, the FP-Pdots nanoprobe was applied to tumor-bearing mice for luminescence imaging of tumor hypoxia. These initial studies showed that the fluorescent/phosphorescent dual-emissive FP-Pdots are a promising kind of hypoxia nanoprobe, which will be helpful in designing a ratiometric and time-resolved luminescent probe for monitoring tumor hypoxia. Chemical Science

As an O_penwidto Burear Commons Article is limited on 12 2015. Despite the simulation of a suitable interaction (a paper). 123. ESS (b) Letti, Y. Chon, Y. P. 2014, Y. P. 2014, Y. P. 2014, Y. P. 2014, Y.

Acknowledgements

We thank the National Basic Research Program of China (2012CB933301), National Natural Science Foundation of China (51473078, 21171098 and 21174064), Program for New Century Excellent Talents in University (NCET-12-0740), and Priority Academic Program Development of Jiangsu Higher Education Institutions for financial support.

Notes and references

- 1 (a) G. L. Semenza, Science, 2007, 318, 62; (b) P. Carmeliet, Y. Dor, J. M. Herbert, D. Fukumura, K. Brusselmans, M. Dewerchin, M. Neeman, F. Bono, R. Abramovitch, P. Maxwell, C. J. Koch, P. Ratcliffe, L. Moons, R. K. Jain, D. Collen and E. Keshet, Nature, 1998, 394, 485.
- 2 (a) D. J. Heeger and D. Ress, Nat. Rev. Neurosci., 2002, 3, 142; (b) C. Iadecola, Nat. Rev. Neurosci., 2004, 5, 347.
- 3 R. N. Frank, N. Engl. J. Med., 2004, 350, 48.
- 4 P. Vaupel, K. Schlenger, C. Knoop and M. Hçckel, Cancer Res., 1991, 51, 3316.
- 5 (a) S. Kizaka-Kondoh, M. Inoue, H. Harada and M. Hiraoka, Cancer Sci., 2003, 94, 1021; (b) A. L. Harris, Nat. Rev. Cancer, 2002, 2, 38; (c) E. K. Rofstad, H. Rasmussen, K. Galappathi, B. Mathiesen, K. Nilsen and B. A. Graff, Cancer Res., 2002, 62, 1847.
- 6 (a) J. Pacheco-Torres, P. Lopeź-Larrubia, P. Ballesteros and S. Cerdán, *NMR Biomed.*, 2011, 24, 1; (b) S. Iwaki, K. Hanaoka, W. Piao, T. Komatsu, T. Ueno, T. Terai and T. Nagano, Bioorg. Med. Chem. Lett., 2012, 22, 2798.
- 7 (a) D. J. Yang, S. Wallace, A. Cherif, C. Li, M. B. Gretzer, E. E. Kim and D. A. Podoloff, Radiology, 1995, 194, 795; (b) J. L. J. Dearlin, J. S. Lewis, G. E. D. Mullen, M. J. Welch and P. J. J. Blower, Biol. Inorg. Chem., 2002, 7, 249.
- 8 (a) D. B. Papkovsky and R. I. Dmitriev, Chem. Soc. Rev., 2013, 42, 8700; (b) X.-D. Wang and O. S. Wolfbeis, Chem. Soc. Rev., 2014, 43, 3666.
- 9 (a) S. Zhang, M. Hosaka, T. Yoshihara, K. Negishi, Y. Iida, S. Tobita and T. Takeuchi, Cancer Res., 2010, 70, 4490; (b) S. Sakadžić, E. Roussakis, M. A. Yaseen, E. T. Mandeville, V. J. Srinivasan, K. Arai, S. Ruvinskaya, A. Devor, E. H. Lo, S. A. Vinogradov and D. A. Boas, Nat. Methods, 2010, 7, 755.
- 10 (a) K. Kiyose, K. Hanaoka, D. Oushiki, T. Nakamura, M. Kajimura, M. Suematsu, H. Nishimatsu, T. Yamane,

T. Terai, Y. Hirata and T. Nagano, J. Am. Chem. Soc., 2010, 132, 15846; (b) L. Cui, Y. Zhong, W. P. Zhu, Y. F. Xu, Q. S. Du, X. Wang, X. H. Qian and Y. Xiao, Org. Lett., 2011, 13, 928; (c) J. N. Liu, Y. Liu, W. B. Bu, J. W. Bu, Y. Sun, J. L. Du and J. L. Shi, J. Am. Chem. Soc., 2014, 136, 9701.

- 11 (a) Q. Zhao, F. Y. Li and C. H. Huang, Chem. Soc. Rev., 2010, 39, 3007; (b) Q. Zhao, C. H. Huang and F. Y. Li, Chem. Soc. Rev., 2011, 40, 2508; (c) Y. M. You and W. W. Nam, Chem. Soc. Rev., 2012, 41, 7061.
- 12 (a) R. P. Briñas, T. Troxler, R. M. Hochstrasser and S. A. Vinogradov, J. Am. Chem. Soc., 2005, 127, 11851; (b) X. D. Wang, X. Chen, Z. X. Xie and X. R. Wang, Angew. Chem., Int. Ed., 2008, 47, 7450; (c) X. Wang, J. A. Stolwijk, T. Lang, M. Sperber, R. J. Meier, J. Wegener and O. S. Wolfbeis, *J. Am. Chem. Soc.*, 2012, 134, 17011.
- 13 S. M. Borisov, R. Saf, R. Fischer and I. Klimant, Inorg. Chem., 2013, 52, 1206.
- 14 K. A. McGee, D. J. Veltkamp, B. J. Marquardt and K. R. Mann, J. Am. Chem. Soc., 2007, 129, 15092.
- 15 (a) T. Yoshihara, Y. Yamaguchi, M. Hosaka, T. Takeuchi and S. Tobita, Angew. Chem., Int. Ed., 2012, 51, 4148; (b) D.-L. Ma, H.-Z. He, K.-H. Leung, D. S.-H. Chan and C.-H. Leung, Angew. Chem., Int. Ed., 2013, 52, 7666; (c) D.-L. Ma, H.-Z. He, H.-J. Zhong, S. Lin, D. S.-H. Chan, L. Wang, S. M.-Y. Lee, C.-H. Leung and C.-Y. Wong, ACS Appl. Mater. Interfaces, 2014, 6, 14008; (d) K. K.-W. Lo, A. W.-T. Choi and W. H. T. Law, Dalton Trans., 2012, 41, 6021; (e) K. K.-W. Lo, K. Y. Zhang, S.-K. Leung and M.-C. Tang, Angew. Chem., Int. Ed., 2008, 47, 2213.
- 16 I. Sanchez-Barragan, J. M. Costa-Fernandez, M. Valledor, J. C. Campo and A. Sanz-Medel, Trends Anal. Chem., 2006, 25, 958.
- 17 (a) S. W. Botchway, M. Charnley, J. W. Haycock, A. W. Parker, D. L. Rochester, J. A. Weinstein and J. A. G. Williams, Proc. Natl. Acad. Sci. U. S. A., 2008, 105, 16071; (b) Y. You, S. Lee, T. Kim, K. Ohkubo, W. S. Chae, S. Fukuzumi, G. J. Jhon, W. Nam and S. J. Lippard, *J. Am. Chem. Soc.*, 2011, 133, 18328; (c) H. Shi, H. Sun, H. Yang, S. Liu, G. Jenkins, W. Feng, F. Li, Q. Zhao, B. Liu and W. Huang, Adv. Funct. Mater., 2013, 23, 3268; (d) C. Shi, H. Sun, X. Tang, W. Lv, H. Yan, Q. Zhao, J. Wang and W. Huang, Angew. Chem., Int. Ed., 2013, 52, 13434; (e) K. Y. Zhang, J. Zhang, Y. Liu, S. Liu, P. Zhang, Q. Zhao, Y. Tang and W. Huang, Chem. Sci., 2015, 6, 301.
- 18 (a) A. V. Kondrashina, R. I. Dmitriev, S. M. Borisov, I. Klimant, I. O'Brien, Y. M. Nolan, A. V. Zhdanov and D. B. Papkovsky, Adv. Funct. Mater., 2012, 22, 4931; (b) A. Grichine, A. Haefele, S. Pascal, A. Duperray, R. Michel, C. Andraud and O. Maury, Chem. Sci., 2014, 5, 3475; (c) E. Baggaley, S. W. Botchway, J. W. Haycock, H. Morris, I. V. Sazanovich, J. A. G. Williams and J. A. Weinstein, Chem. Sci., 2014, 5, 879.
- 19 (a) C. Zhu, L. Liu, Q. Yang, F. Lv and S. Wang, Chem. Rev., 2012, 112, 4687; (b) H. N. Kim, Z. Guo, W. Zhu, J. Yoon and H. Tian, Chem. Soc. Rev., 2011, 40, 79.
- 20 (a) C. Wu and D. T. Chiu, Angew. Chem., Int. Ed., 2013, 52, 3086; (b) L. Xiong, A. J. Shuhendler and J. Rao, Nat.

Commun., 2012, 3, 1193; (c) W. Sun, J. Yu, R. Deng, Y. Rong, B. Fujimoto, C. Wu, H. Zhang and D. T. Chiu, Angew. Chem., Int. Ed., 2013, 52, 11294; (d) E. Ahmed, S. W. Morton, P. T. Hammond and T. M. Swager, Adv. Mater., 2013, 25, 4504; (e) T. Adachi, L. Tong, J. Kuwabara, T. Kanbara, A. Saeki, S. Seki and Y. Yamamoto, J. Am. Chem. Soc., 2013, 135, 870; (f) C. Wu, B. Bull, K. Christensen and J. McNeill, Angew. Chem., Int. Ed., 2009, 48, 2741; (g) K. Pu and B. Liu, Adv. Funct. Mater., 2011, 21, 3408; (h) K. Li, D. Ding, D. Huo, K. Pu, N. N. P. Thao, Y. Hu, Z. Li and B. Liu, Adv. Copen Access Article Contents Articles Articles Articles. Published on 12 2015. Download Distribution 2.0024. This article is licensed on D. The Licensed under a Creative Commons Articles. 2017, (1) X. This year, Articles

Funct. Mater., 2012, 22, 3107; (i) X. Liu, Y. Tang, L. Wang, J. Zhang, S. Song, C. Fan and S. Wang, Adv. Mater., 2007, 19, 1471; (j) H. Xu, H. Wu, F. Huang, S. Song, W. Li, Y. Cao and C. Fan, Nucleic Acids Res., 2005, 33, e83.

- 21 S. M. Borisov, A. S. Vasylevska, C. Krause and O. S. Wolfbeis, Adv. Funct. Mater., 2006, 16, 1536.
- 22 (a) B. Valeur, Molecular Fluorescence, WILEY-VCH, Weinheim, 2002; (b) N. J. Turro, V. Ramamurthy and J. C. Scaiano, Modern Molecular Photochemistry of Organic Molecules, University Science Books, Sausalito, CA, 2010.