



**[Ru]-Catalyzed Olefin Metathesis and Ethenolysis for the
Synthesis and Recycling of Bio-Based Polycarbonates and
Polycyanurates**

Journal:	<i>Polymer Chemistry</i>
Manuscript ID	PY-ART-08-2024-000940.R1
Article Type:	Paper
Date Submitted by the Author:	26-Oct-2024
Complete List of Authors:	Pinson, Dana; Naval Air Warfare Center Weapons Division, Research Department, Chemistry Division Eckstrom, Francesca; Naval Air Warfare Center Weapons Division, Research Department, Chemistry Division; Colorado State University, Department of Chemistry Ostrom, Gregory; Naval Air Warfare Center Weapons Division, Research Department, Chemistry Division McClain, K.; Naval Air Warfare Center Weapons Division, Research Department, Chemistry Div. Baldwin, Lawrence; Naval Air Warfare Center Weapons Division, Research Department, Chemistry Division Harvey, Benjamin; Naval Air Warfare Center Weapons Division, Research Department, Chemistry Division

[Ru]-Catalyzed Olefin Metathesis and Ethenolysis for the Synthesis and Recycling of Bio-Based Polycarbonates and Polycyanurates

Dana M. Pinson, Francesca D. Eckstrom, Gregory S. Ostrom, Randall K. McClain, Lawrence C. Baldwin, and Benjamin G. Harvey*

US NAVY, NAWCWD, Research Department, Chemistry Division, China Lake, California 93555

*Corresponding author (email: benjamin.g.harvey.civ@us.navy.mil)

Abstract:

Eugenol, an abundant, naturally occurring phenolic compound, was converted into a thermoplastic polycarbonate by olefin metathesis followed by interfacial polymerization with triphosgene. This resulted in polymers with M_n ranging from 5300 – 12700 g mol⁻¹ and an average glass transition temperature (T_g) of 82 °C. The polycarbonates were depolymerized via ethenolysis reactions under modest ethylene pressures (150 – 240 psi) in the presence of [Ru]-metathesis catalysts to yield a discrete monomer [bis(4-allyl-2-methoxyphenol) carbonate, compound **2**]. **2** was then polymerized with a second generation Grubbs catalyst (M204) to produce a recycled polymer with M_n = 7500 g mol⁻¹ and a T_g of 114 °C. The 32 °C increase in T_g was due to the isomerization of the allyl group to internal positions, which then allowed for the formation of stilbene and 3-carbon unsaturated linkages between aromatic groups. To expand the ethenolysis recycling approach to cross-linked networks, eugenol was converted into a cyanate ester (**3**), which was then thermally cyclotrimerized to generate 2,4,6-tris(4-allyl-2-methoxyphenoxy)-1,3,5-triazine (**4**), a monomer with a triazine core and three pendent aromatic rings with methoxy and allyl substituents. **4** was cross-linked via olefin metathesis (M204 catalyst) to generate a network with M_n = 8600 g mol⁻¹ and a T_g of 180 °C. Similar to the polycarbonate, the polycyanurate was efficiently depolymerized in the presence of ethylene to regenerate **4**. Compound **4** was then polymerized and depolymerized two additional times, demonstrating full circularity for the triazine monomer/network. The recycled networks exhibited similar T_g s (167–184 °C) and thermal stability compared to the virgin polymer. Overall, this work demonstrates that both thermoplastic and cross-linked networks can be readily prepared from eugenol and catalytically recycled under standard ethenolysis conditions. Unlike many conventional approaches, the recycled polymers described in this work exhibited no significant degradation in thermomechanical properties. This type of approach supports a circular bioeconomy and may help to reduce plastic waste and the accumulation of micro/nanoplastic particles in the environment.

Introduction:

Replacing petroleum-based polymers with bio-based, recyclable, and upcycled polymer materials has been proposed as an important step in the development of a sustainable circular economy.[1-3] In addition to sustainability, the use of bio-based phenols may help address toxicity issues related to bisphenol A (BPA).[4, 5] Polymers containing bisphenols or phenolic moieties are ubiquitous in modern society and include polycarbonates, polysulfones, polycyanurates and epoxy resins.[6] Polycarbonates account for a large portion of the polymer industry due to their outstanding thermal, mechanical, and optical properties that enable widespread use in packaging, medical devices, and agriculture.[7] Petroleum-based bisphenol A (BPA) is the most commonly used building block in these polymers, with 4.5 million tons manufactured

in 2021.[8, 9] Unfortunately, BPA is a pervasive contaminant in both the environment and human body. In the latter, it acts as an endocrine disruptor, coordinating to estrogen receptors in place of the hormone estradiol and poses health risks to the reproductive, developmental, and cardiovascular systems.[10] Adding to the problem, BPA does not follow standard toxicologic paradigms, namely, lower levels of BPA exposure may cause more severe effects than high exposure levels.[11] Despite longstanding knowledge of the complex toxicology and adverse health consequences of BPA, its use has persisted around the globe in consumer and industrial products due to the lack of economical alternatives.[12]

Microplastic accumulation is another key driver for the development of BPA alternatives.[13] Microplastics are potential contributors to oxidative stress, metabolic disorders, immune response, and neurotoxicity as well as reproductive and developmental toxicity. These negative health impacts have created a critical need for the study of polymers based on lower toxicity bisphenols. Bio-based alternatives could offer a solution to both BPA toxicity and dependence on unsustainable petrochemicals. Eugenol is an important biorenewable phenolic compound that can be obtained by extraction from plants, such as clove buds, from the valorization of lignin, or through fermentation of sugar substrates.[14, 15] Currently, approximately 2000 tons of eugenol are produced from clove oil extraction annually.[16] In addition to being widely available, eugenol is approved as a food additive, possesses anti-bacterial and antioxidant activities, and has a chemical structure that is ideal for use as a bio-based commodity monomer.[17] Eugenol is a phenol with a methoxy group ortho to the hydroxyl group and a three-carbon pendent allyl chain in the position para to the hydroxyl group. This unique functionality provides a synthetic handle for either polymerization or the installation of additional chemical groups. Furthermore, the methoxy group as well as the allylic tail impart unique thermomechanical properties to derivative polymers. Most of the research to date on eugenol-based polymers has focused on developing materials with comparable performance to those prepared from BPA. For example, researchers have prepared a cyanate ester monomer from a eugenol-based bisphenol synthesized by the ruthenium-catalyzed homometathesis of eugenol followed by hydrogenation of the olefin. [18] In related work, polycarbonates were synthesized from the same eugenol-based bisphenol and triphosgene with molecular weights up to $14,600 \text{ g mol}^{-1}$ and

polydispersity indexes (D) below 2. Despite these success stories, it would be of significant interest to move beyond the mere utilization of bio-based eugenol polymers to developing methods that leverage the alkene functionality in eugenol for efficient and low-energy recycling protocols.

Olefin metathesis is a powerful and adaptable synthetic tool that generates new carbon-carbon bonds in the presence of transition metal centered carbene complexes. Ethenolysis is a catalytic chemical transformation belonging to the class of olefin metathesis reactions involving ethylene as one of the reactants.[19] This versatile technique can be leveraged to cleave internal olefins in polymers in the presence of ethylene to generate compounds with terminal olefins. Acyclic diene metathesis (ADMET) is a step growth polymerization technique where an unconjugated diene polymerizes in the presence of Schrock or Grubbs-type catalysts, typically at temperatures between 40 – 80 °C.[19] With the development of metathesis catalysts exhibiting increased activity and functional group tolerance, combined with the mild nature of the polymerization conditions, ADMET has become an important synthetic tool for the creation of engineering plastics as well as specialty polymers.[20,21] In a particularly compelling approach, polymers with internal olefins can be depolymerized via ethenolysis and then repolymerized via ADMET[22] resulting in an infinite recycling loop. Several studies have explored the depolymerization of unsaturated polymers such as polybutadiene and polyisoprene via ethenolysis.[23-25] However, the recycling of bio-based engineering thermoplastics (e.g. polycarbonates) via ethenolysis has not been explored in detail. Furthermore, additional work is needed to explore the viability of ethenolysis as a depolymerization strategy for cross-linked thermoset networks, which are typically insoluble in common organic solvents, leading to mass transfer issues and reduced reactivity.

In this work, by leveraging the internal alkene in a eugenol-based repeat unit, we demonstrate the ability to depolymerize a high-performance aromatic polycarbonate in the presence of ethylene to generate a monomeric species. This monomer is then repolymerized and upcycled via ADMET chemistry. This methodology is extended to a multi-functional triazine monomer that forms a cross-linked network upon

polymerization. The robustness and versatility of the ethenolysis/metathesis cycle suggests that it has broad applications for polymer recycling in support of a circular plastic economy.[26]

Experimental

General. Unless otherwise noted, all reagents were purchased and used as received from the manufacturer without further purification. Eugenol, triphosgene, triethylamine (TEA), dichloromethane (DCM), hexanes, tetrahydrofuran (THF), ethyl acetate, Grubbs M102 and M204 catalysts, benzoquinone, and deuterated chloroform (CDCl_3) were purchased from Sigma-Aldrich. Methanol, diethyl ether, cyanogen bromide and ethyl vinyl ether were purchased from Fisher Chemicals. Sodium hydroxide (NaOH) was purchased from PolarChem and M720 catalyst was purchased from Ambeed. Ethylene gas (purity 99.95%) was purchased from Linde. All NMR chemical shifts are reported in ppm downfield from tetramethylsilane and are referenced relative to the NMR solvent according to the literature values: ^1H NMR (CDCl_3 = 7.26 ppm, DMSO-d_6 = 2.50 ppm); ^{13}C NMR (CDCl_3 = 77.16 ppm, DMSO-d_6 = 39.52 ppm). Fourier transform infrared (FTIR) spectroscopy was performed using a Thermo Scientific Nicolet 6700 FTIR spectrometer equipped with a liquid nitrogen cooled MCTA detector. Experiments were performed using an attenuated total reflectance (ATR) smart accessory with a germanium window. Each FTIR spectrum reported is the average of 32 scans with 4 cm^{-1} resolution. Background subtraction of the clean germanium crystal and baseline corrections were used to decrease noise from the system. Gel permeation chromatography (GPC) to determine the molecular weight of the samples was performed on a Viscotec TriSEC Model 302 GPC with a refractive index (RI) detector. Differential scanning calorimetry (DSC) analysis was conducted on a DSC Q200 TA instrument under N_2 at 50 mL/min. Approximately 5 mg of sample were tested under a heating scan from 40 to 200 °C with a heating rate of 10 °C/min. Thermogravimetric analysis (TGA) was performed on a TGA Q5000 TA instrument under N_2 flow from 24 to 800 °C with a heating rate of 10 °C/min. The decomposition temperature is reported as the temperature at which 5% mass loss occurs ($T_{d\ 5\%}$).

Synthesis of *(E)*-4,4'-(*But-2-ene-1,4-diyl*)bis(2-methoxyphenol) (compound 1). The eugenol bisphenol was synthesized as described in previous work.[17] Eugenol (25.88 g, 158 mmol) was combined with

Grubbs M102 catalyst (0.532 g, 0.4 mol%) under a nitrogen atmosphere to form a thick purple solution. The evolution of bubbles attributed to ethylene gas was immediately observed. After 8 h under nitrogen, the flask was placed under reduced pressure and allowed to react for an additional 24 h with stirring to yield a thick resinous mass. Anhydrous DCM was then added and the resulting solution was allowed to react for an additional 48 h. The solvent was evaporated under reduced pressure and the resulting solid dissolved in an aqueous NaOH solution (1 L, 1.25 M), which was then filtered through a Celite pad to remove a dark black precipitate. After filtration, the solution was acidified with concentrated HCl, which resulted in the precipitation of a pale gray solid. The solid was collected by filtration, redissolved in DCM, washed with brine (6 x 200 mL), and the organic layer dried over MgSO₄. The solvent was then removed in vacuo to yield 20.09 g of product (78% yield). Single crystals suitable for X-ray crystallography were grown by slow evaporation of a methanol solution. ¹H NMR (DMSO-d₆, 400 MHz) δ : 8.70 (s, 1H, OH), 6.72 (s, 1H, Ar-H), 6.66 (s, 1H, Ar-H), 6.56 (s, 1H, Ar-H), 5.59 (bs, 2H, c(sp²)-H), 3.71 (s, 3H, OCH₃) 3.21 (d, J = 7.8 Hz, 2H, CH₂). ¹³C NMR (CDCl₃, 400 MHz) δ : 146.46, 143.87, 132.73, 130.60, 121.06, 114.27, 111.15, 55.87, 38.60.

Polycarbonate synthesis. Compound **1** was converted into a polycarbonate based on a literature method.[26, 27] In a general procedure, recrystallized bisphenol (0.901 g, 3.0 mmol) was dissolved in a 1.25 M NaOH solution (25 mL) and allowed to stir for a minimum of one h. TEA (0.05 mL, 0.3 mmol) was added to the solution and then triphosgene (0.37 g, 1.25 mmol) dissolved in dichloromethane (10 mL) was added dropwise to yield a biphasic reaction mixture. The mixture was stirred for 10 min at ambient temperature and then diluted with 100 mL of DCM. The heterogeneous mixture was transferred to a separatory funnel, and the organic layer was washed with distilled H₂O (6 x 100 mL). The organic phase was then concentrated and added dropwise to stirring MeOH (800 mL) to precipitate the polycarbonate. The precipitate was isolated by filtration, redissolved in minimal DCM, reprecipitated in MeOH, and recollected by filtration. The resulting solid was dried in a vacuum oven (60 °C, ~50 torr) for 18 h to yield 0.4316 g of the polycarbonate as a white powder (48% yield). Two different batches of polycarbonate were prepared, one with a low molecular weight (PC1_{low}, M_n = 5300), and one with a higher molecular weight

(PC1_{high}, $M_n = 12700$). ^1H NMR (DMSO- d_6 , 400 MHz) δ : 7.2 (d, $J = 8.3$ Hz, Ar-H), 7.0 (bs, Ar-H), 6.8 (d, $J = 8.57$ Hz, Ar-H), 5.7 (bs, C(sp²)-H), 3.8 (bs, OCH₃), 3.3 (bs, CH₂).

General polycarbonate depolymerization conditions. The polycarbonate, 5-10 mol % of either M204 or M720, DCM (5 mg polymer/mL) and 10 mol % benzoquinone were charged to a Parr reactor under a nitrogen atmosphere. Ethylene gas (99.95% purity) was then charged to the reactor to a pressure of either 150 or 240 psi at either 25 or 70 °C for either 24 or 72 hours. Upon completion of the reaction, pressure was released from the reactor and the contents were transferred to a round bottom flask. An excess of ethyl vinyl ether was added, and the mixture was allowed to stir for one h to quench the reaction. An excess of imidazole was then introduced and the mixture was stirred for one hour followed by the addition of activated charcoal and an additional hour of stirring. The reaction mixture was then filtered through silica gel and the solvent was removed under reduced pressure. The resulting solid was then dried overnight under reduced pressure at 60 °C. In cases where complete depolymerization was obtained, the product of the reaction was *bis(4-allyl-2-methoxyphenyl) carbonate (compound 2)*: ^1H NMR (CDCl₃, 400 MHz) δ : 7.2 (d, 2H, $J = 8.0$ Hz, Ar-H), 6.8 (d, 4H, $J = 16.0$ Hz, Ar-H), 5.97 (septet 2H, $J = 6.6$ C(sp²)-H), 5.13 (m, 4H, 17.0 Hz), 3.88 (s, 6H, OCH₃), 3.39 (d, 4H, $J = 6.7$ Hz). ^{13}C NMR (DMSO- d_6 , 400 MHz) δ : 151.00, 150.33, 139.60, 137.77, 137.35, 122.00, 120.34, 116.18, 113.27, 55.92. Single crystals suitable for X-ray crystallography were grown from slow evaporation of a concentrated ethyl acetate solution.

Polycarbonate synthesis via ADMET polymerization of *bis(4-allyl-2-methoxyphenyl)carbonate*. 2 (0.1075 g, 0.30 mmol), 1,4 benzoquinone (10 mol %), M204 (10 mol %) and DCM (500 mg/mL) were charged to a flask under an inert atmosphere and allowed to react for 18 h. Then, 2 mL of ethyl vinyl ether were introduced into the flask and allowed to stir for 1 hour to quench the reaction. The reaction mixture was precipitated in hexanes (50 mL) and the solid precipitate was collected by vacuum filtration. The precipitate was then redissolved in minimal THF, precipitated in cold methanol and collected via vacuum filtration. The solid was dried in a vacuum oven (60 °C, ~50 torr) for 18 h to yield 0.0916 g of white powder (85.2%). $M_n =$ ^1H NMR (CDCl₃, 400 MHz) δ : 6.80 – 7.15 (m, Ar-H), 5.08 – 6.45 (m, C(sp²)-H), 3.89 (bs, OCH₃), 3.35 (m, CH₂)


4-Allyl-1-cyano-2-methoxybenzene (Compound 3). Eugenol (5.00 g, 30.5 mmol) was combined with cyanogen bromide (4.83 g, 1.5 equivalents, 45.6 mmol), placed under a nitrogen atmosphere and cooled to -78 °C. TEA (1.05 equivalents, 32.0 mmol) was diluted 1:1 with diethyl ether and placed in an addition funnel under nitrogen. The TEA solution was added dropwise to the stirring reaction mixture over 30 minutes. The reaction was allowed to proceed for 3 h at -78 °C and then allowed to warm to 0 °C. A large amount of white solids were produced. Once the reaction mixture reached 0 °C, the mixture was filtered through Celite to remove the white solids, diluted with additional ether, washed with brine (6 x 100 mL) and 2M HCl (1 x 100 mL), dried over MgSO₄, concentrated under reduced pressure, and dried in a vacuum oven (60 °C, ~50 torr) for 18 h to yield 4.201 g of a clear, yellow liquid (79.6%). ¹H NMR (CDCl₃, 400 MHz) δ: 7.21 (d, 1H, *J* = 7.2 Hz, Ar-H), 6.81 (s, 1H, Ar-H), 6.72 (d, 1H, *J* = 6.7 Hz, Ar-H), 5.88 (septet, 1H, *J* = 5.9 Hz, C(sp²)-H), 5.08 (m, 2H *J* = 5.1 Hz, C(sp²)-H), 3.84 (s, OCH₃), 3.34 (d, *J* = 6.8 Hz, 2H, CH₂). ¹³C NMR (DMSO-d₆, 400 MHz) δ: 148.02, 140.79, 138.92, 136.97, 120.64, 117.34, 116.36, 114.14, 109.53, 56.25.

2,4,6-tris(4-allyl-2-methoxyphenoxy)-1,3,5-triazine (Compound 4). Compound **3** (4.201 g, 24.25 mmol) was placed in a flask under a nitrogen atmosphere and heated to 150 °C for two h. The temperature was then increased to 210 °C and held at that temperature for 18 h. The resulting brown solid was dissolved in a mixture of 90:10 hexanes:ethyl acetate and then filtered. The filtrate was concentrated under reduced pressure and the resulting solid was dried in a vacuum oven (60 °C, ~50 torr) for 18 h to yield 1.554 g of the product as a white powder (37.0%). Single crystals suitable for X-ray crystallography were grown by slow evaporation of a concentrated solution of **4** in a mixture of 99:1 heptane:ethyl acetate. ¹H NMR (CDCl₃, 400 MHz) δ: 6.98 (d, 3H, *J* = 7.0 Hz Ar-H), 6.70 (m, 6H, *J* = 6.7 Hz, Ar-H), 5.95 (septet, 3H, *J* = 6.0 Hz C(sp²)-H), 5.12 (m, 6H, C(sp²)-H), 3.71(s, 9H, OCH₃), 3.35 (d, 6H, *J* = 3.4 Hz, CH₂). ¹³C NMR (CDCl₃, 400 MHz) δ: 173.72, 150.88, 139.07, 138.85, 137.13, 122.13, 120.53, 137.13, 122.13, 120.53, 116.16, 112.89, 55.78, 40.15.

General Synthesis of Polycyanurates. **4** (0.708 g, 1.25 mmol) was combined with M204 (0.053 g, 5.0 mol %) and DCM (50 mL) in a flask under a nitrogen atmosphere. The solution was stirred for 14 h at ambient

temperature. Then, 5 mL of ethyl vinyl ether were introduced into the flask and the solution was stirred for 1 h to quench the reaction. The reaction mixture was precipitated in hexanes (500 mL) and the solid precipitate was collected by vacuum filtration. The precipitate was redissolved in minimal THF, precipitated in cold methanol and collected via vacuum filtration. The solid was then dried in a vacuum oven (60 °C, ~50 torr) for 18 h to yield 0.4675 g of the polymer as a beige powder (66.1%). Reactions conducted for 24 h at ambient temperature resulted in the formation of insoluble cross-linked networks.

General Ethenolysis Conditions for Polycyanurates. In an inert atmosphere, the polycyanurate, 10 mol % of either M204 or M720, DCM (5 mg polymer/mL) and 10 mol % benzoquinone were charged to a Parr reactor. Ethylene gas (99.95% purity) was then added to the reactor and the pressure was equilibrated to 240 psi. The reaction was allowed to proceed at 25 °C for 24 h. The pressure was then released from the reactor and the contents were transferred to a round bottom flask. An excess of ethyl vinyl ether was introduced into the flask and the reaction mixture allowed to stir for 1 h to quench the reaction. An excess of imidazole was then added followed by activated charcoal. The reaction mixture was stirred for an additional hour and then filtered through silica gel. The filtrate was concentrated under reduced pressure and the resulting solid was dried in a vacuum oven (60 °C, ~50 torr) for 18 h. In cases where complete depolymerization was obtained, the product of the reaction was 2,4,6-*tris*(4-allyl-2-methoxyphenoxy)-1,3,5-triazine (*compound 4*). The NMR spectra for this product were identical to those obtained for the starting monomer.



Scheme 1. (a) Bisphenol synthesis, polymerization, ethenolysis, and repolymerization of eugenol-based polycarbonates. (b) Cyanation, thermal trimerization, network synthesis, ethenolysis, and subsequent rounds of repolymerization and ethenolysis.

Results and Discussion

3.1 Synthesis and Characterization of Bio-based Polymers

The homometathesis of eugenol was performed following previously reported methods to yield 4,4'-(2-butene-1,4-diyl)bis[2-methoxyphenol] (**1**).^[11-13] (**Scheme 1**). A polycarbonate was then synthesized from **1** and triphosgene under biphasic conditions.^[27,28] Triphosgene was selected as a safer reagent compared to phosgene while interfacial polymerization allowed us to mimic conditions commonly used in the industrial production of polycarbonates. There are literature reports describing polymerization of similar monomers with diphenyl carbonate, but this approach results in low molecular weight oligomers ranging from 3,000 – 4,000 g mol⁻¹.^[29] More importantly, the diphenyl carbonate route is plagued by a side reaction that creates ether linkages. This changes the connectivity of the repeat units in the polymer,

which impacts the ability of the polymer to depolymerize to monomer via ethenolysis.[20, 30 - 31] The yield of the polycarbonate ranged between 48 – 52 % (**Table 1**). Despite the solubility of the bisphenol in the NaOH solution, a heterogenous mixture was obtained even after many hours of rigorous stirring. Future research might focus on the use of pyridine or other amines in place of aqueous NaOH to improve yields.[30] Extending the reaction time from 10 to 15 min did not impact yield, but increased the molecular weight more than two-fold, from 5,300 g mol⁻¹ to 13,000 g mol⁻¹ (**Figure 1b**).

The polycarbonate was characterized by ¹H NMR as well as ATR FTIR spectroscopy (**Figures 1a and S5**). ¹H NMR spectroscopy was used to verify successful polymerization. The ¹H NMR spectrum of the polymer did not contain the peak at 8.70 ppm attributed to the -OH of the bisphenol. In addition, all of the peaks were shifted slightly downfield. For example, the methoxy peak in the monomer was seen at 3.71 ppm while the methoxy peak for the polymer occurred at 3.79 ppm.




Figure 1. (a) ¹H NMR spectrum of PC1_{high} in DMSO-d₆. (b) GPC data for PC1_{low} and PC1_{high}. (c) DSC traces for PC1_{low} and PC1_{high}. Heating cycles ran from 40 °C – 200 °C at 10 °C/min

The FTIR spectrum of the polycarbonate (**Figure S5**) exhibited an intense peak at 1780 cm^{-1} attributed to C=O stretching of the carbonyl group while a peak at 1236 cm^{-1} was consistent with C-O-C stretching. A broad peak observed from $1442 - 1477\text{ cm}^{-1}$ was attributed to both a $\text{C}_{\text{sp}^2}\text{-H}$ bending vibration and C=C stretching. Other C=C stretching peaks attributed to aromatic ring carbons appeared at 1510 and 1006 cm^{-1} . [32-33]

The molecular weights of the polycarbonates were measured by gel permeation chromatography (GPC) and found to be dependent on reaction time (**Table 1**). The number-average molecular weight (M_n) for the polycarbonates in the current work are higher than those reported by Trita et. al. for a similar polycarbonate synthesized by ester exchange with diphenyl carbonate. [31] The molecular weight ranges achieved with triphosgene allow for a better comparison to commercially available BPA-based polycarbonates such as Lexan™ (typical $M_n = 30,000 - 50,000\text{ g mol}^{-1}$). [34]

In addition to the thermoplastic polycarbonate, a trifunctional monomer was synthesized from eugenol by cyanation followed by thermal cyclotrimerization (Scheme 1). First, eugenol was reacted with cyanogen bromide in the presence of base to yield 4-allyl-1-cyano-2-methoxybenzene (**3**). Successful synthesis of **3** was confirmed by ^1H NMR (Figure 2a) and FTIR spectroscopy (Figure 3). In the ^1H NMR spectrum, peaks ranging from $7.20\text{--}6.74\text{ ppm}$ were attributed to the aromatic protons. A septet and multiplet attributed to the alkene protons were observed at 5.88 ppm and 5.06 ppm , respectively. A singlet attributed to the methoxy protons occurred at 3.84 ppm and a doublet for the methylene protons was present at 3.35 ppm (**Figure 2a**). Thermal trimerization of **3** resulted in the formation of 2,4,6-tris(4-allyl-2-

Table 1. Synthetic, GPC, and DSC results for eugenol-based polycarbonates (PC1_{low} , PC1_{high}) and a cross-linked polycyanurate (CEN1)

Polymer	Reaction Time (min)	Yield (%)	M_n , GPC (g mol^{-1})	$\bar{D}$	T_g^a ($^{\circ}\text{C}$)
PC1_{low}	10	48	5,300	1.65	82
PC1_{high}	15	52	12,700	2.36	82
CEN1	840	66	8,600	1.75	180

^a T_g measured by DSC

methoxyphenoxy-1,3,5-triazine (Compound **4**), a monomer with three pendent alkenes. Successful creation of the triazine ring was confirmed by both ^1H and ^{13}C NMR spectroscopy (**Figure 2b and c**). In the ^1H NMR spectrum, the aromatic protons were shifted downfield upon successful triazine formation. The peak attributed to the terminal alkene protons shifted slightly downfield (**Figure 2b**) while the peak for the alkene shifted from 3.84 ppm to 3.71 ppm. In the ^{13}C NMR spectrum, a peak attributed to the carbons of the triazine ring can be seen at 173.8 ppm (**Figure 2c**). FTIR spectroscopy provided further evidence of the successful synthesis of **3** and complete conversion of the cyanate ester group during the thermal cyclotrimerization reaction (**Figure 3a and b**). In the FTIR spectrum for **3**, a prominent peak at 2257 cm^{-1} was observed, confirming successful installation of the cyanate group on eugenol.[36] Upon thermal cyclotrimerization, this peak was no longer visible, indicating complete cyclotrimerization to generate **4** (**Figure 3b**). In the




Figure 2. (a) ^1H NMR spectrum of 4-allyl-1-cyano-2-methoxybenzene (compound **3**) in CDCl_3 . (b) ^1H NMR spectrum of 2,4,6-tris(4-allyl-2-methoxyphenoxy)-1,3,5-triazine (compound **4**) in CDCl_3 generated via thermal cyclotrimerization of **3**. (c) ^{13}C NMR of compound **4** in CDCl_3 .

FTIR spectra for both **3** and **4**, peaks for the aromatic C=C groups were observed at 1500, 1270 and 1190 cm^{-1} while a peak for the C-O stretching vibration appeared at 1030 cm^{-1} .^[35] Upon thermal trimerization, peaks for the triazine moiety were seen at 1610 cm^{-1} (C=N) as well as 1565 and 1506 cm^{-1} (C=C).^[32-33] Finally, single crystals of **4** were grown from a mixture of heptane/ethyl acetate, and the structure of **4** was confirmed using X-ray crystallography (**Figure 3c**).

Compound **4** was polymerized via olefin metathesis using the M204 catalyst to yield a cross-linked material (CEN1). The polymerization was conducted at ambient temperature and the reaction time was carefully controlled (14 h) to ensure the arrested polycyanurate network was of low enough molecular weight to be fully soluble in organic solvents. This enabled straightforward GPC and NMR characterization, as well as ethenolysis of the network. When the reaction time was extended to 24 h, a




Figure 3. (a) ATR-FTIR spectrum of **3** before and after thermal cyclotrimerization. (b) Expanded view of the -OCN region in the FTIR spectrum. (c) X-ray crystal structure of compound **4**. Ortep drawings with thermal ellipsoids at the 50% probability level are included in the supporting information.

solid insoluble material precipitated out of solution, which suggested the formation of a highly cross-linked network. ^1H NMR spectroscopy of the soluble arrested network showed significant peak broadening when compared to the monomer spectrum, which was indicative of successful polymerization (**Figure 4a**). The degree of polymerization was evaluated by GPC and CEN1 was found to have an M_n (based on polystyrene standards) of $8,600\text{ g mol}^{-1}$ (**Figure 4b** and **Table 1**).

Both the thermoplastic polycarbonates and CEN1 were analyzed by TGA and DSC to characterize thermal stability and measure glass transition temperatures (T_g), melting points (T_m) and crystallization temperatures (T_c). The eugenol-based polycarbonates exhibited similar T_g s ($82\text{ }^\circ\text{C}$) irrespective of molecular weight (**Figure 1c** and **Table 1**). This value is higher than previously reported values of $52 - 71\text{ }^\circ\text{C}$ for a saturated eugenol-based polycarbonate [27,35] likely due to the presence of the alkene bridge located between the aromatic rings in the current work. However, the T_g s measured for PC1_{low} and PC1_{high} were much lower than commercially available LexanTM, which is based on BPA and has a $T_g = 146\text{ }^\circ\text{C}$. [38]




Figure 4. (a) ^1H NMR spectrum of CEN1 in CDCl_3 . (b) GPC of CEN1.

Despite this shortcoming, the T_g of the eugenol polycarbonate was still well above room temperature, which should make it suitable for a number of commercial applications.[33, 36] The moderate T_g of PC1_{low} and PC1_{high} was attributed to the 4-carbon bridges between the aromatic rings, which allow for greater flexibility compared to the isopropylidene linkage in LexanTM. Interestingly, no T_m or T_c was observed for PC1_{low} or PC1_{high} via DSC. Examination of the material in a standard melting temperature apparatus revealed a T_m between 160 – 173 °C. CEN1 was found to have a T_g of 180 °C (**Table 1**), which is close to the reported T_g of a saturated polycyanurate network derived from eugenol (186 °C).[18] The similarity in these values despite the modest molecular weight in the current case suggests that a fully cross-linked network derived from the unsaturated eugenol-based monomer would have a higher T_g compared to the network obtained from the saturated version. The T_g for CEN1 is much lower, approximately 100 °C, compared to the T_g of a polycyanurate network derived from bisphenol A dicyanate.[39, 40] As discussed above for the polycarbonates, this difference is likely due to the more flexible 4-carbon linker between aromatic rings. As expected, no T_m or T_c was observed for CEN1 due to the amorphous branched structure.

3.2 Catalytic Recycling via Ethenolysis and Olefin Metathesis

After characterizing the polymers, we first explored the depolymerization of the polycarbonates via ethenolysis (**Figure 5a**). A key step in closed loop recycling is the ability to convert used polymers back to monomers followed by repolymerization. Initial ethenolysis conditions were chosen based on previous work with methyl oleate. [41] Catalytic depolymerization to monomer or low molecular weight oligomers is desirable for recycling as it prevents damage to the polymer chains that can occur during mechanical recycling. In addition, this approach creates α,ω -diene monomers that can be used in the synthesis of other polymers.[42, 43] The impact of reaction conditions as well as the molecular weight of the starting polymer were explored to optimize ethenolysis conditions for obtaining monomeric product. The products of ethenolysis were purified and characterized by ¹H NMR and GPC. For the depolymerized products derived from PC1_{low} and PC1_{high}, the terminal alkene peaks of the product were clearly visible at 5.95 and 5.09 ppm (**Figure 5b**). Integration was performed and normalized to the terminal alkene resonance at 5.95 ppm. The




Figure 5. (a) Ethenolysis scheme for depolymerization of polycarbonates. (b) ¹H NMR spectrum of depolymerized PC1_{low} in CDCl₃. (c) GPC chromatogram of ethenolysis products derived from PC1_{low}. (d) Magnified view of the GPC chromatogram of depolymerized PC1_{low}.

peak at 5.68 ppm was attributed to the internal alkene along the backbone of the oligomers. Based on the ¹H NMR integration, it was determined that the ethenolysis reaction yielded oligomers with an average length of approximately 6 repeat units. Complimentary to the ¹H NMR analysis, GPC analysis revealed 5 peaks attributable to different oligomers (**Figure 5c and d**). The average M_n for all of the experiments ranged from 1700 – 2600 g mol⁻¹, which is consistent with the molecular weight determined by ¹H NMR spectroscopy. It should be noted that the molecular weights determined by ¹H NMR are quantitative whereas the molecular weights determined by GPC are estimates as they are based on elution time related to polystyrene standards. In addition, the GPC method has less fidelity compared to NMR analysis, particularly for low molecular weight species.

The ethenolysis of the eugenol-based polycarbonate was repeated several times while varying the starting molecular weight, catalyst type, time, temperature, pressure, and use of a radical inhibitor (**Table 2**). In every case, the product of ethenolysis was an oligomeric distribution with an M_n of $\sim 1,500$ g mol⁻¹ (as determined by ¹H NMR spectroscopy). Although it is unclear exactly why the initial depolymerization step is limited to the formation of oligomers, one possible explanation is that the catalyst is deactivated due to irreversible binding of the oligomeric product as the reaction proceeds. Alternatively, there may be some impurity in the reaction mixture that poisons the catalyst prior to complete depolymerization. In an attempt to drive the reaction to completion, the depolymerization products of several ethenolysis trials were combined and subjected to further ethenolysis with fresh catalyst. This resulted in complete depolymerization to bis(4-allyl-2-methoxyphenyl) carbonate (compound **2**) as confirmed by ¹H NMR spectroscopy (**Figure 6a**). The GPC chromatogram of the depolymerization product exhibited one narrow peak providing further evidence for complete conversion to the monomer (**Figure S4**). Finally, large single

Table 2. Ethenolysis results for eugenol-based polycarbonates and a polycyanurate under varying conditions

Polymer	Starting M_n (g mol ⁻¹)	M_n After Ethenolysis (g mol ⁻¹)	Yield (%)	Catalyst Type and loading	Time (hours)	Temperature (°C)	Benzo-quinone (mol%)
PC1 _{low}	5,300	1700	62	5 mol % M204	24	25	None
PC1 _{low}	5,300	2500	67	10 mol % M720	24	70	10
PC1 _{low}	5,300	2600	64	10 mol % M204	72	25	10
PC1 _{high}	12,700	2000	59	10 mol % M204	24	25	10
5-mer PC	1600 – 2600 ^a	294.35 ^b	64	10 mol % M204	24	25	10
CEN1a	8600	1000	58	10 mol % M204	24	25	10
CEN1b	1000	600	71	10 mol % M204	24	25	10

^astarting material is a combination of products of the 4 previous reactions

^bpure monomer obtained from the ethenolysis reaction




Figure 6. (a) ^1H NMR spectrum of the ethenolysis product generated from oligomers of the eugenol-based polycarbonates CDCl_3 . (b) Photograph showing crystalline monomer obtained via ethenolysis. (c) X-ray crystal structure of the monomer. Ortep drawings with thermal ellipsoids at the 50% probability level are included in the supporting information.

crystals of **2** were grown from ethyl acetate (**Figure 6b**) and an X-ray crystal structure was obtained (**Figure 6c**). Although two rounds of ethenolysis were required, this work demonstrated that a high molecule weight bio-derived polycarbonate could be selectively depolymerized to a monomeric species via [Ru]-catalyzed ethenolysis.

Having found great success in depolymerizing a thermoplastic material to a monomeric building block, the ethenolysis of CEN1 was attempted (**Table 2**). The ^1H NMR spectrum of the depolymerized network and X-ray crystal structure of the monomeric species (**4**) are shown in **Figures 7a** and **7b**, respectively. Unlike the polycarbonate example, it was not possible to estimate the molecular weight of the depolymerized product via NMR spectroscopy. The internal alkene peak appearing at 5.64 ppm was not present in the spectrum, suggesting complete depolymerization. However we did observe some broadening of the peaks which suggested some polymeric impurity. GPC analysis revealed primarily monomer with a




Figure 7. (a) ^1H NMR spectrum of the CEN1a ethenolysis product in CDCl_3 . (b) Chemical structure of the ethenolysis product. (c) GPC chromatogram of the ethenolysis product.

shoulder due to the presence of oligomers (**Figure 7c**). However, based on the NMR data it did not appear that the shoulder was due to oligomers with unsaturated alkenes in the backbone.

Although the triazine monomer could be easily purified from the product mixture after one ethenolysis cycle, we typically conducted a second round of ethenolysis to ensure product composition across multiple experiments for subsequent polymerization reactions (**Figure 8**). The triazine product obtained after two rounds of ethenolysis was analyzed via ^1H NMR spectroscopy and found to be consistent with an authentic sample of **4** (**Figure 8a**). Similarly, GPC analysis of the product revealed one narrow peak attributable to the monomer (**Figure 8b**). The successful depolymerization of the polycyanurate is significant as it shows that a cross-linked structure does not prevent depolymerization via ethenolysis and may open the door to depolymerization of thermoset networks.




Figure 8. (a) ¹H NMR spectrum of fully depolymerized polycyanurate (CEN1b) in CDCl₃. (b) GPC chromatogram of CEN1b

The monomeric ethenolysis products from both the polycarbonate and triazine network were repolymerized via olefin metathesis in dichloromethane at ambient temperature in the presence of 10% M204 to generate PC2 and CEN2 from **2** and **4**, respectively (**Table 3**). During the repolymerization of **2**, a partial isomerization of the primary olefin to the internal position was observed by NMR spectroscopy (**Figure 9a**). The ¹H NMR spectrum showed a new stilbene linkage at 6.45 and 6.32 ppm derived from the metathesis reaction of two internal alkenes. In addition, we observed a second set of alkene hydrogens at 5.97 ppm attributable to the product obtained by a metathesis reaction between an internal and primary alkene (**Figure 9b**).^[44] Finally, we observed the conventional linkage from the parent polymer at 5.68 ppm

Table 3. Synthetic and characterization results for a eugenol-based polycarbonate and polycyanurate repolymerized from ethenolysis products

Polymer	Time (min)	Yield (%)	M_n GPC (g mol ⁻¹)	$\bar{D}$	T_g (°C)
PC2	1080	59	7,500	1.49	114
CEN2	840	70	8,600	1.73	173




Figure 9. (a) ^1H NMR spectrum of the repolymerized polycarbonate in CDCl_3 . (b) Zoomed-in region of ^1H NMR spectrum showing alkene isomerization. (c) GPC chromatogram of the repolymerized polycarbonate. (d) DSC thermogram of the repolymerized polycarbonate.

(Figure 9b). Careful integration of these regions allowed us to quantify the relative amount of each type of linkage in the polycarbonate. 61% of the linkages were between two allyl groups, 10% were asymmetric (between an internal alkene and a primary alkene), and 29% of the linkages were of the stilbene type. An attempt was made to prevent isomerization of the allyl group to an internal position by the addition of 1,4-benzoquinone, however, we saw no difference in the product distribution, despite a contrary result in the

literature.[45] GPC analysis was performed on the recycled polymer, and M_n was found to be 7,500 g mol⁻¹ (**Figure 9c**). This is substantially lower than the initial M_n of 12,700 g mol⁻¹ for PC1_{high}, however, direct molecular weight comparisons are not warranted because the original polycarbonate was polymerized via step-growth interfacial polymerization, whereas the recycled polymer was polymerized via ADMET.

Further evidence of alkene isomerization prior to polymerization was provided by DSC analysis of the recycled material. The T_g of the repolymerized polycarbonate was found to be 114 °C, an increase of 32 °C compared to the virgin polycarbonate (**Figure 9d**). Mechanically recycled polymers typically exhibit lower T_g s due in part due to dangling chain ends created during the recycling process.[1, 43] Similarly, harsh chemical depolymerization mechanisms can generate “dirty mixtures” which negatively impact the properties of the repolymerized material. In the current case, the substantial increase in T_g was attributed to the partial isomerization of the allyl group, which resulted in the formation of more rigid linking groups, particularly stilbenes. Despite the structural differences, it is remarkable that the recycled polymer product has an improved T_g compared to the initial material. It is likely that subsequent cycles of de- and repolymerization would result in additional isomerization of the alkene, leading to further increases in T_g . [44]

3.3 Circularity of Catalytic Recycling

The repolymerized polycarbonate was not subjected to further ethenolysis cycles due to the isomerization of the allyl group under the established conditions. The isomerization process would generate a different polycarbonate product over time, resulting in changing material properties. Additionally, the solubility of the material would be expected to diminish as the stilbenic linkages increase. While the polycarbonate can be efficiently recycled, the isomerization process would make it hard to evaluate if the catalytic recycling process detrimentally affected the material properties for this particular system. In contrast, we did not observe any isomerization during repolymerization of **4**. After the initial depolymerization and repolymerization cycle, two additional cycles of catalytic recycling were successfully performed. In each cycle, the network was fully depolymerized to **4** (two steps, a and b) and subsequently repolymerized to generate a polycyanurate (**Tables 4 and 5**). For clarity, polymers are identified by their polymerization

round number. For example, CEN1 represents the first round of polymerization while CEN2 is the network repolymerized from the first round of ethenolysis products, CEN3 is the network repolymerized from the second depolymerization step, and so on.

Table 4. Ethenolysis results for repolymerized polycyanurates^a

Polymer Identity	Starting M_n (g mol ⁻¹)	M_n After Ethenolysis (g mol ⁻¹)	Yield (%)	Catalyst Type ^b	Time (hours)
CEN2a	8600	1800	67	M204	24
CEN2b	1800	700	68	M204	24
CEN3a	7500	1900	72	M204	24
CEN3b	1900	600	85	M204	24
CEN4a	8000	1500	59	M204	48
CEN4b	1540	600	83	M204	24

^a240 PSI, 25 °C, 10 mol % benzoquinone

^b10 mol %; pure monomer required 2 consecutive ethenolysis reactions.

Table 5. Olefin metathesis polymerization results for polycyanurates repolymerized from ethenolysis products.

Polymer	Reaction Time (minutes)	% yield	M_n , GPC (g mol ⁻¹)	$\bar{D}$	T_g , °C
CEN2	840	68	8600	1.73	173
CEN3	840	90	7500	4.21	167
CEN4	840	82	8000	1.33	184

After each polymerization, the thermomechanical properties of the reconstituted networks were evaluated. Neither the T_g nor the molecular weight were significantly different in the repolymerized samples (Table 5 and Figure 10). For CEN3, the 2nd repolymerization of the polycyanurate, $\bar{D}$ was extremely high. Careful examination of the GPC trace revealed a small amount of high molecular weight material combined with a peak attributed to unpolymerized monomer present in this sample. The effects of residual monomer greatly impacted T_g , which was 13 °C lower than the virgin polymer. However, in the next cycle the T_g recovered to 184 °C, an increase in 4 °C over the virgin polymer. Overall, these results show full circularity for the eugenol-based polycyanurate network, opening the door for this novel recycling method to be applied to insoluble thermoset networks, a long-standing challenge within the polymer industry.




Figure 10. (a) ^1H NMR of CEN4 and (b) DSC and (c) TGA thermogram of CEN1 – CEN4.

Conclusions

A thermoplastic polycarbonate and a cross-linked polycyanurate with alkenes incorporated in the backbone were synthesized from the biobased phenol eugenol and fully characterized. The resulting materials were then depolymerized via a two-step [Ru]-catalyzed ethenolysis process to generate monomers with pendent allyl groups. These monomers were subsequently repolymerized via olefin metathesis to obtain high molecular weight linear and cross-linked polymers. The depolymerization products were purified without rigorous effort and found to be suitable for repolymerization. For the depolymerization products of the linear polycarbonate, isomerization of the allyl group during ADMET polymerization was observed, preventing direct comparison of the thermo-mechanical properties of the recycled polycarbonate with the initial polycarbonate. Future work may explore alternative catalysts or lower catalyst loading as a possible route to prevent isomerization of the allyl group. Interestingly, the isomerization during repolymerization resulted in a dramatic increase in T_g (32°C), which essentially providing a route to upcycle the polycarbonate. In contrast, most polymers recycled via either mechanical routes or treatment with harsh chemicals at elevated temperature result in materials with decreased T_g s and poorer mechanical properties.

In parallel with the polycarbonate work we demonstrated efficient depolymerization/repolymerization protocols for a polycyanurate. No isomerization was observed during the repolymerization of this monomer, enabling full circularity. Three cycles of depolymerization and repolymerization were performed and no significant decrease in thermo-mechanical properties was observed. Future work in our laboratory will focus on recycling the ethenolysis catalyst, using more environmentally friendly solvents, and attempting the ethenolysis of insoluble thermoset networks. Overall, this work demonstrates the potential of sustainable and fully recyclable eugenol-based polymers for commercial applications. This approach can be readily extended to other alkene containing thermoplastics and cross-linked networks, offering a versatile recycling strategy to support the creation of a circular economy.

Acknowledgements

The authors would like to thank the National Research Council for administering the postdoctoral fellowship for DMP and the Office of Naval Research for supporting FDE through the Naval Research Enterprise Internship Program (NREIP).

References

1. Payne, J.; M.D. Jones. The Chemical Recycling of Polyesters for a Circular Plastics Economy: Challenges and Emerging Opportunities. *ChemSusChem*. **2021**, *14*(19), 4041-4070, <https://doi.org/10.1002/cssc.202100400>
2. Schirmeister, C.G.; Mülhaupt, R. Closing the Carbon Loop in the Circular Plastics Economy. *Macromolecular Rapid Communications*. **2022**, *43*(13), 220-247, <https://doi.org/10.1002/marc.202200247>
3. Bening, C.R.; Pruess, J.T.; Blum, N.U. Towards a circular plastics economy: Interacting barriers and contested solutions for flexible packaging recycling. *Journal of Cleaner Production*. **2021**, *302*, 126966, <https://doi.org/10.1016/j.jclepro.2021.126966>
4. Tarafdar, A.; Siroh, R.; Balakumaran, P.A.; Reshmy, R.; Madhavan, A.; Sindhu, R.; Binod, P.; Kumar, Y.; Kumar, D.; Sim, S.J. The hazardous threat of Bisphenol A: Toxicity, detection and remediation. *Journal of Hazardous Materials*. **2022**, *423*, 127097, <https://doi.org/10.1016/j.jhazmat.2021.127097>
5. Trullemans, L.; Koelwijn, S.F.; Scodeller, I.; Hendrickx, T. Puyvelde, P.V.; Sels, B.F.; A guide towards safe, functional and renewable BPA alternatives by rational molecular design: structure–property and structure–toxicity relationships. *Polymer Chemistry*. **2021**, *12*(41), 5870-5901, <https://doi.org/10.1039/D1PY00909E>
6. Wu, X.; Li, J.; Yao, L.; Xu, Z. Auto-sorting commonly recovered plastics from waste household appliances and electronics using near-infrared spectroscopy. *Journal of Cleaner Production*. **2020**, *246*(10), 118732, <https://doi.org/10.1016/j.jclepro.2019.118732>
7. Thomas, S.; Visakh, P.M. Handbook of Engineering and Specialty Thermoplastics, Volume 3: Polyethers and Polyesters. 3 ed, S.T.a.V. P.M. 2011: John Wiley & Sons. ISBN: 978-0-470-63926-9
8. Warner, G.; Flaws, J.A. Bisphenol A and Phthalates: How Environmental Chemicals Are Reshaping Toxicology. *Toxicological Sciences*. **2018**, *166*(2), 246-249, <https://doi.org/10.1093/toxsci/kfy232>
9. Kumar, M.; Sarma, D.K.; Shubham, S.; Kumawat, M.; Verma, V.; Prakash, A.; Tiwari, R. Environmental Endocrine-Disrupting Chemical Exposure: Role in Non-Communicable Diseases. *Front Public Health*. **2020**, *8*, 553850, doi: 10.3389/fpubh.2020.553850.
10. Vandenberg, L.N.; Colborn, T.; Hayes, T.B.; Heindel, J.J.; Jacobs, D.R.; Lee, D.H.; Shioda, T.; Soto, A.M. Saal, S.F.; Welshons, W.V.; Zoeller, R.T.; Myers, J.P. Hormones and endocrine-disrupting chemicals: low-dose effects and nonmonotonic dose responses. *Endocr Rev*. **2012**, *33*(3), 378-455, <https://doi.org/10.1210/er.2011-1050>
11. Melzer, D.; Osborne, N.J.; Henley, W.E.; Cipelli, R.; Young, A.; Money, C.; McCormack, P.; Luben, R.; Khaw, K.; Wareham, N.; Galloway, T.S. Urinary bisphenol A concentration and risk of future coronary artery disease in apparently healthy men and women. *Circulation*. **2012**, *125*(12), 1482-90, <https://doi.org/10.1161/circulationaha.111.069153>
12. Pelch, K.; Wignall, J.A.; Goldstone, A.E.; Ross, P.K.; Blain, R.B.; Shapiro, A.J.; Holmgren, S.D.; Hsieh, J.; Svoboda, D.; Auerback, S.S.; Parham, F.M.; Masten, S.A.; Walker, V.; Rooney, A.; Thayer, K.A. A scoping review of the health and toxicological activity of bisphenol A (BPA) structural analogues and functional alternatives. *Toxicology*. **2019**, *424*, 152235, <https://doi.org/10.1016/j.tox.2019.06.006>
13. Li, Y.; Tao, L.; Wang, Q.; Wang, F.; Li, G.; Song, M. Potential Health Impact of Microplastics: A Review of Environmental Distribution, Human Exposure, and Toxic Effects. *Environment & Health*. **2023**, *1*(4), 249-257, <https://doi.org/10.1021/envhealth.3c00052>
14. Fache, M.; Darroman, E.; Besse, V.; Auvergne, R.; Caillol, S.; Boutevin, B. Vanillin, a promising biobased building-block for monomer synthesis. *Green Chemistry*. **2014**, *16*(4), 1987-1998, <https://doi.org/10.1039/C3GC42613K>

15. Hanko, E.K.R.; Valdehuesa, K.N.G.; Verhagen, K.J.A.; Chromy, J.; Stoney, R.A.; Chua, J.; Yan, C.; Roubos, J.A.; Schmitz, J.; Breitling, R. Carboxylic acid reductase-dependent biosynthesis of eugenol and related allylphenols. *Microb Cell Fact.* **2023**, *22*(238), <https://doi.org/10.1186/s12934-023-02246-4>
16. Hüsni, K.; Başer, C.; Demirci, F. Chemistry of Essential Oils. *Flavours and Fragrances*. **2007**, 43 - 86, https://doi.org/10.1007/978-3-540-49339-6_4
17. Prakash, P.; Gupta, N. Therapeutic uses of *Ocimum sanctum* Linn (Tulsi) with a note on eugenol and its pharmacological actions: a short review. *Indian J Physiol Pharmacol.* **2005**, *49*(2), 125-31, doi: 10.3390/molecules28031193.
18. Harvey, B.G.; Sahagun, C.M.; Guenther, A.J.; Groshens, T.J.; Cambrea, L.R.; Reams, J.T.; Mabry, J.M. A High-Performance Renewable Thermosetting Resin Derived from Eugenol. *ChemSusChem*. 2014, *7*(7), 1964-1969, <https://doi.org/10.1002/cssc.201400019>
19. Odian, G. Step Polymerization. *Principles of Polymerization*. 2004, 39-197, DOI:10.1002/047147875X
20. Pribyl, J.; Wagener, K.B.; Rojas, G. ADMET polymers: synthesis, structure elucidation, and function. *Materials Chemistry Frontiers*. **2021**, *5*(1), 14-43, <https://doi.org/10.1039/D0QM00273A>
21. Kajetanowicz, A.; Grela, K. Nitro and Other Electron Withdrawing Group Activated Ruthenium Catalysts for Olefin Metathesis Reactions. *Angewandte Chemie International Edition*. **2021**, *60*(25), 13738-13756, <https://doi.org/10.1002/anie.202008150>
22. Foster, J.C.; Zheng, J.; Arifuzzaman, M.; Rahman, M.; Damron, J.; Guan, C.; Popovs, I.; Galan, N.; Demchuk, Z.; Saito, T. Closed-loop recycling of semi-aromatic polyesters upcycled from poly(ethylene terephthalate). *Cell Reports Physical Science*. **2023**, *4*(12), 101734, <https://doi.org/10.1016/j.xcrp.2023.101734>
23. Wagener, K.B.; Marmo, J.C. Acyclic diene metathesis (ADMET) depolymerization: The synthesis of 1,4-polybutadiene telechelics. *Macromolecular Rapid Communications*. **1995**, *16*(8), 557-561, <https://doi.org/10.1002/marc.1995.030160804>
24. Sedransk, K.L.; Kaminski, C.F.; Hutchings, L.R.; Moggridge, G.D. The metathetic degradation of polyisoprene and polybutadiene in block copolymers using Grubbs second generation catalyst. *Polymer Degradation and Stability*. **2011**, *96*(6), 1074-1080, <https://doi.org/10.1016/j.polymdegradstab.2011.03.007>
25. Wagener, K.B.; Boncella, J.M.; Nel, J.G. Acyclic diene metathesis (ADMET) polymerization. *Macromolecules*. **1991**, *24*(10), 2649-2657, <https://doi.org/10.1016/j.polymdegradstab.2011.03.007>
26. Utekar, S.; K, S.V.; More, N.; Rao, A. Comprehensive study of recycling of thermosetting polymer composites – Driving force, challenges and methods. *Composites Part B: Engineering*. **2021**, 207, 108596, <https://doi.org/10.1016/j.compositesb.2020.108596>
27. Garrison, M.D.; Storch, P.J.; Eck, W.S.; Adams, V.H.; Fedick, P.W.; Harvey, B.G. BPA-free high-performance sustainable polycarbonates derived from non-estrogenic bio-based phenols. *Green Chemistry*. **2021**, *23*(20), 8016-8029, <https://doi.org/10.1039/D1GC01500A>
28. Chen, Q.; Huang, W.; Chen, P.; Peng, C.; Xie, H.; Zhao, Z.K.; Sohail, M.; Bao, M. Synthesis of Lignin-Derived Bisphenols Catalyzed by Lignosulfonic Acid in Water for Polycarbonate Synthesis. *ChemCatChem*, **2015**, *7*(7), 1083-1089, <https://doi.org/10.1002/cctc.201500010>
29. Trita, A.S.; Over, L.C.; Pollini, J.; Riegsinger, S.; Meier, M.A.R.; Gooben, L.J. Synthesis of potential bisphenol A substitutes by isomerising metathesis of renewable raw materials. *Green Chemistry*. **2017**, *19*(13), 3051-3060, <https://doi.org/10.1039/C7GC00553A>
30. Kim, W.B.; Joshi, U.A.; Lee, J.S. Making Polycarbonates without Employing Phosgene: An Overview on Catalytic Chemistry of Intermediate and Precursor Syntheses for Polycarbonate. *Industrial & Engineering Chemistry Research*. **2004**, *43*(9), 1897-1914, <https://doi.org/10.1039/C7GC00553A>

31. Harvey, B.G.; Guenther, A.J.; Koontz, T.A.; Storch, P.J. Reams, J.T.; Groshens, T.J. Sustainable hydrophobic thermosetting resins and polycarbonates from turpentine. *Green Chemistry*. **2016**, *18*(8), 2416-2423, <https://doi.org/10.1039/C5GC02893K>
32. B.C. Smith, Infrared Spectral Interpretation, A Systematic Approach. *CRC Press*, **1999**, 119 - 221, DOI: 10.5860/choice.36-5697
33. Socrates, G. Infrared and Raman Characteristic Group Frequencies: Tables and Charts. *The University of West London, Middlesex, U.K. J. Wiley and Sons: Chichester*. **2001**, 3, ISBN 0-471-85298-8
34. Kyriacos, D., Chapter 17 - Polycarbonates. *Brydson's Plastics Materials*. **2017**, 8, 457-485, <https://doi.org/10.1016/C2009-0-30435-3>
35. Yang, Z.; Chai, Y.; Yao, X.; Ji, H. Mechanism for efficient separation of eugenol and eugenol acetate with β -cyclodextrin as a selective solvent. *Supramolecular Chemistry*. **2019**, *31*(12), 767-775, <https://doi.org/10.1080/10610278.2019.1702663>
36. Abuzeid, H.R.; El-Mahdy, A.F.M.; Ahmed, M.M.M.; Kuo, S. Triazine-functionalized covalent benzoxazine framework for direct synthesis of N-doped microporous carbon. *Polymer Chemistry*. **2019**, *10*(44), 6010-6020, DOI: 10.1039/c9py01231a
37. Harvey, B.G.; Guenther, A.J.; Yandek, G.R.; Cambrea, L.R.; Meylemans, H.A.; Baldwin, L.C.; Reams, J.T. Synthesis and characterization of a renewable cyanate ester/polycarbonate network derived from eugenol. *Polymer*. **2014**, *55*(20), 5073-5079, <https://doi.org/10.1016/j.polymer.2014.08.034>
38. DeRudder, J.L., Handbook of Polycarbonate Science and Technology. *CRC Press*. **2000**, 1, 101-144, <https://doi.org/10.1201/9781482273694>
39. Kessler, R. Cyante Ester Resins. *Wiley Encyclopedia of Composites*. **2012**, 1, <https://doi.org/10.1002/9781118097298.weoc062>
40. Shimp, A. Chemistry and Technology of Cyanate Ester Resins. *Chapman and Hall*. **1994**, 1, <https://doi.org/10.1007/978-94-011-1326-7>
41. Spekrijse, J.; Sanders, J.P.; Bitter, J.H.; Scott, E.L. The Future of Ethenolysis in Biobased Chemistry. *ChemSusChem*. **2017**, *10*(3), 470-482, doi: 10.1002/cssc.201601256
42. La Mantia, F.P., Polymer Mechanical Recycling: Downcycling or Upcycling?. *Progress in Rubber, Plastics and Recycling Technology*. **2004**, *20*(1), 11-24, <https://doi.org/10.1177/147776060402000102>
43. Jin, H.; Gonzalez-Guitierrez, J.; Oblak, P.; Zupancic, B.; Emri, I. The effect of extensive mechanical recycling on the properties of low density polyethylene. *Polymer Degradation and Stability*. **2012**, *97*(11), 2262-2272, <https://doi.org/10.1016/j.polymdegradstab.2012.07.039>
44. Günther, S.; Lamprecht, P.; Luinstra, G.A. ADMET-Polymerization of Dienes based on Sustainable Chemicals. *Macromolecular Symposia*. **2010**, *293*(1), 15-19, <https://doi.org/10.1016/j.polymdegradstab.2012.07.039>
45. Huang, M.; Bai, D.; Chen, Q.; Zhao, C.; Ren, T.; Huang, C.; North, M.; Zie, H. Facile preparation of polycarbonates from bio-based eugenol and 2-methoxy-4-vinylphenol. *Polymer Chemistry*. **2020**, *11*(32), 5133-5139, <https://doi.org/10.1039/D0PY00291G>

Data Availability Statement

The data supporting this article are included in the supplementary information. Crystallographic data for compounds 1, 2, and 4 have been deposited in the Cambridge Structural Database (CCDC deposition numbers 2360344, 2360346, and 2360345, respectively).