



Cite this: RSC Adv., 2016, 6, 57446

Surface and interface design in cocatalysts for photocatalytic water splitting and CO₂ reduction

 Song Bai,^{*ab} Wenjie Yin,^a Lili Wang,^b Zhengquan Li^a and Yujie Xiong^{*b}

Recent advances in photocatalysis highlight the important role of cocatalysts in improving the solar-to-chemical conversion efficiency for various reactions, such as water splitting and CO₂ reduction reactions. Given that cocatalysts play two important roles, in charge trapping and surface reactions, the rational material design of cocatalysts would be an effective route in pursuing their maximum contribution to the performance of photocatalysts. In this review, we aim to outline the recent progress of surface and interface design in cocatalysts for photocatalytic water splitting and CO₂ reduction. We first introduce the surface design of cocatalysts, which enables the enhancement of specific water splitting or CO₂ reduction reactions through surface parameter (e.g., the composition, facets and phases) adjustments. We then present key parameters for designing the interface between photocatalyst and cocatalyst, which offer a set of versatile options for tuning the charge transfer to the cocatalyst. Taken together, the surface and interface of cocatalysts may have synergetic effects on the photocatalytic performance, which are discussed to provide guidance for simultaneously tailoring surface and interface parameters. Finally, we summarize the challenges and opportunities for the surface and interface design of cocatalysts for the efficient production of solar fuels.

 Received 23rd April 2016
 Accepted 2nd June 2016

 DOI: 10.1039/c6ra10539d
www.rsc.org/advances

^aKey Laboratory of the Ministry of Education for Advanced Catalysis Materials, College of Chemistry and Life Sciences, Institute of Physical and Chemistry, Zhejiang Normal University, Jinhua, Zhejiang 321004, China. E-mail: songbai@zjnu.edu.cn


^bHefei National Laboratory for Physical Sciences at the Microscale, iChEM (Collaborative Innovation Center of Chemistry for Energy Materials), School of Chemistry and Materials Science, University of Science and Technology of China, Hefei, Anhui 230026, China. E-mail: yjxiong@ustc.edu.cn; Fax: +86-551-63606657



Song Bai received his B.S. and M.S. degrees from Jiangsu University in 2009 and 2012, respectively. In 2015, he obtained his Ph.D. degree with Professor Yujie Xiong from the University of Science and Technology of China (USTC), and started as an assistant professor in Zhejiang Normal University. His research interests focus on the design and synthesis of novel hybrid nanomaterials for photocatalysis.

1. Introduction

Since the discovery of photocatalytic water splitting on TiO₂ electrodes by Fujishima and Honda in 1972, significant efforts have been made to develop highly efficient photocatalysts for various photocatalytic reactions, such as water splitting and CO₂ reduction, providing a promising route to alleviate steadily worsening environmental issues and an energy crisis.^{1–5} Among various photocatalyst designs, the combination of



Yujie Xiong received his B.S. in chemical physics in 2000 and his Ph.D. in inorganic chemistry in 2004 (with Professor Yi Xie), both from the University of Science and Technology of China (USTC). After four years training with Professors Younan Xia and John A. Rogers, he joined the NSF-NNIN at the Washington University in St. Louis as the Principal Scientist and Lab Manager. Starting from 2011, he is a Professor of Chemistry at the USTC. He has published 120 papers with over 10 000 citations (H-index 48). His research interests include the synthesis, fabrication and assembly of inorganic materials for energy and environmental applications.

a semiconductor with a cocatalyst to form a hybrid structure is a widely used approach to promote the performance of photocatalysts in the production of solar fuels.^{6,7} In such photocatalytic hybrid structures, cocatalysts themselves are not the light-harvesting components for generating photoinduced charge carriers. Instead, a cocatalyst mainly plays two positive roles in steering the charge kinetics in photocatalysis: (i) trapping charge carriers to promote electron–hole separation by forming an interface with the semiconductor; and (ii) serving as a highly active reaction site to supply the trapped charges for redox reactions on their surface.^{8,9} Both the improved charge separation and surface catalytic reactions contribute to the enhancement of photocatalytic activity and selectivity. In addition, the use of cocatalysts as alternative reaction sites may suppress the photocorrosion of semiconductors resulting from charge carrier accumulation and thus increase the stability of photocatalysts.¹⁰

The two key roles of cocatalysts highlight the importance of designing their surface and interface to maximize the improvement in photocatalyst performance.^{11,12} On one hand, the surface of a cocatalyst is the location for redox reactions, which greatly determines the adsorption and activation abilities for reactant molecules and thus the activity and selectivity for photocatalytic reactions.^{13,14} For this reason, the design of a cocatalyst surface depends on the type of chemical reaction occurring on the surface – water splitting or CO₂ reduction. On the other hand, the interface between a cocatalyst and semiconductor is the location where the charge carriers are transferred and separated, holding the key to preventing adverse electron–hole recombination in the semiconductor.¹⁵

In a realistic photocatalytic system, the situation is rather complicated so as to entangle surface reactions and interfacial charge transfer, further emphasizing the significance of cocatalyst surface and interface design.¹¹ Inefficient interfacial charge transfer would only bring a limited number of charge carriers to the surface of a co-catalyst, thereby restricting the efficacy of surface reactions. Inversely, slow surface reactions may lead to the accumulation of charges on the side of the cocatalyst, which in turn reduces the potential difference and prevents further interfacial charge transfer. In brief, only when the surface and interface are simultaneously well designed to promote surface catalytic reactions and interfacial charge transfer can the maximization of cocatalyst efficacy be realized. From another point of view, the surface and interface design of cocatalysts also represents a more straightforward strategy for improving photocatalysis in comparison with the surface modification of bare semiconductors. In the case of bare semiconductors, the semiconductor acts as both the light-harvesting center and surface reaction site. As such, tailoring the surface of the semiconductor would affect the light absorption of the photocatalyst in addition to tuning surface reactions,¹⁶ which makes it challenging to assess the contribution of surface design to photocatalytic performance.

Recently, the rational design of cocatalyst surfaces and interfaces has been widely implemented to promote the performance of photocatalytic nanomaterials. Certainly this research is greatly facilitated by the development of advanced

synthetic approaches which realize design through precisely controlling surface and interface parameters of cocatalysts at the nanoscale.^{17,18} In this review, we focus on the design of cocatalyst surfaces and interfaces toward photocatalytic water splitting and CO₂ reduction. We will first outline the forms of combination of cocatalysts with photocatalysts, as well as their basic architectural structures. Then we will discuss the surface design of cocatalysts in detail, according to the relationship between key surface parameters and photocatalysis. In the next section, the design of cocatalyst–photocatalyst interfaces will be elucidated based on a set of critical interfacial parameters. Subsequently, we will further highlight the simultaneous control of surfaces and interfaces associated with cocatalysts for enhanced photocatalytic performance. Finally, the remaining challenges and future prospects for surface and interface design in cocatalysts for photocatalytic applications will be provided.

2. Architectural structures of cocatalysts in photocatalysis

According to the trapped charge carriers that in turn determine the type of surface reaction, cocatalysts can be classified as having two functions: reduction cocatalysts trapping electrons for reduction half reactions, and oxidation cocatalysts trapping holes for oxidation half reactions. In general, noble metals (e.g., Pt, Pd, Rh and Au),^{19–22} non-noble transition metals (e.g., Cu, Co and Ni),^{23–25} metal sulfides (e.g., MoS₂, NiS and WS₂),^{26–28} metal oxides (e.g., NiO and CuO),^{29,30} phosphides (e.g., Co₂P, NiP and MoP),^{31–33} and carbon materials (e.g., graphene and carbon nanotubes)^{34,35} can serve as reduction cocatalysts for the hydrogen evolution reaction. In parallel, noble metals (e.g., Pt, Pd and Ag),^{14,36,37} metal oxides (e.g., CuO, NiO and RuO₂),^{38–40} and cobaltates (e.g., ZnCo₂O₄ and MnCo₂O₄)^{41,42} have been reported as reduction cocatalysts for CO₂ reduction. As for oxidation cocatalysts, transitional metal oxides (e.g., IrO_x, MnO_x, RuO_x and CoO_x),^{43–47} and phosphates (e.g., CoP)^{48–50} have been widely used for water oxidation.

Cocatalysts can be integrated into photocatalysis in many different forms. In a hybrid photocatalyst, reduction or oxidation cocatalysts can be loaded alone on a light-harvesting semiconductor, in which the photogenerated electrons in the conduction band (CB) or holes in the valence band (VB) of the semiconductor are transferred to the cocatalyst for a reduction or oxidation reaction (Fig. 1a and b).^{14,48} In other cases, reduction and oxidation cocatalysts can be co-loaded on the same light-harvesting semiconductor for reduction and oxidation reactions (Fig. 1c).^{51,52} It is worth pointing out that the semiconductor for loading cocatalysts is not necessarily photoexcited. Alternatively, plasmonic metals or photosensitizers are integrated with a semiconductor so that the photoexcited metals or sensitizers can inject hot electrons or holes into the CB or VB of the semiconductor, respectively. As such, the injected electrons or holes are further transferred to the reduction or oxidation cocatalyst for surface reactions (Fig. 1d).^{53–55} Certainly in rare circumstances, cocatalysts may directly interface with plasmonic metals or photosensitizers to




Fig. 1 Schematic diagram illustrating the integration of photocatalysts with cocatalysts in various configurations: (a) semiconductor–reduction cocatalyst structure; (b) semiconductor–oxidation cocatalyst structure; (c) reduction cocatalyst–semiconductor–oxidation cocatalyst structure; (d) plasmonic metal/sensitizer–semiconductor–cocatalyst structure; and (e) plasmonic metal/sensitizer–cocatalyst structure.

form hybrid photocatalysts in the absence of a semiconductor (Fig. 1e).^{56–59} The hot charge carriers generated in the plasmonic metal or photosensitizer are directly injected to the cocatalyst for redox reactions without the bridge of a semiconductor.

As the viewpoint is further narrowed down to a single reduction or oxidation cocatalyst, the integration of a cocatalyst with a semiconductor can still involve a variety of basic architectural structures, particularly in the case of reduction cocatalysts. This situation involves many different surface and interface structures in the cocatalyst design. To simplify the case, here we mainly take reduction cocatalysts as examples. When the cocatalyst is a mono-component structure (namely, a semiconductor–cocatalyst I structure), the cocatalyst surface and semiconductor–cocatalyst interface are quite simple (Fig. 2a).^{14,26,37,60–62} As the reduction cocatalyst has two or more components involved, the models for integrating the components become more diversified. In one case, two reduction cocatalysts (namely, cocatalyst I and cocatalyst II) in mutual contact are loaded on the same semiconductor. In this so-called “semiconductor–cocatalyst I/II structure”, two semiconductor–cocatalyst interfaces (*i.e.*, the interfaces of semiconductor–cocatalyst I and semiconductor–cocatalyst II) as well as a cocatalyst I–cocatalyst II interface are simultaneously formed for electron transfer, and meanwhile, the surfaces of the two cocatalysts are both exposed for reduction reactions (Fig. 2b).^{63,64} In another case, a quasi-core–shell structure is formed between cocatalyst I and cocatalyst II, fabricated by selectively coating the semiconductor-supported cocatalyst I core with a shell of cocatalyst II (*i.e.*, a semiconductor–cocatalyst

I@II core–shell structure) (Fig. 2c).^{21,65–67} In this structure, the interfaces of semiconductor–cocatalyst I and cocatalyst I–cocatalyst II are formed for tandem electron transfer, leaving only the cocatalyst II surface exposed for reduction reactions. Similarly, the semiconductor–cocatalyst I–II structure, in which cocatalyst II is selectively loaded on cocatalyst I to form a supported structure (Fig. 2d),^{68,69} has both the interfaces of semiconductor–cocatalyst I and cocatalyst I–cocatalyst II designed for electron transfer. In this case, however, both the surfaces of cocatalyst I and cocatalyst II are exposed for reduction reactions.

Certainly it is not necessary to have the cocatalyst in direct contact with the semiconductor. Alternatively, a conductive component (*e.g.*, graphene or carbon quantum dots) can also serve as a charge bridge between the cocatalyst and semiconductor to form a semiconductor–conductor–cocatalyst structure (Fig. 2e).^{70–72} As the conductor surface barely possesses catalytic activity, a tandem electron transfer through the interfaces of semiconductor–conductive layer and conductive layer–cocatalyst will designate the cocatalyst surface as the reduction reaction site. In the literature, there have been reported more complicated architectural structures for cocatalysts (*e.g.*, ternary cocatalysts), and they still derive from one of the aforementioned structures or the combination of multiple structures.⁷³ From the discussion above, it can be recognized that the mutual interfaces of the cocatalyst–cocatalyst or cocatalyst–conductor are also of great importance to the charge transfer in photocatalysis when multiple components are involved in the cocatalyst design.




Fig. 2 Schematic diagram illustrating the architectural structures of cocatalysts for photocatalysis, as well as the functions of their surfaces and interfaces for photocatalytic reactions: (a) semiconductor–cocatalyst I structure; (b) semiconductor–cocatalyst I/II structure; (c) semiconductor–cocatalyst I@II core–shell structure; (d) semiconductor–cocatalyst I-II structure; and (e) semiconductor–conductor–cocatalyst structure. Here a reduction cocatalyst is used as an example.

3. Surface design of cocatalysts in photocatalysis

The analysis above clearly reveals that the cocatalyst surface is the location where activation reactions take place during the photocatalytic process. For this reason, surface design holds promise for tuning photocatalytic reactions through tailoring some surface parameters of cocatalysts. Firstly, surface parameters can be designed not only to realize high adsorption and activation ability for specific reactant molecules, but also to prevent side or back reactions. This would enhance the activity in the main photocatalytic reaction as well as improve the selectivity between competing reactions. Secondly, surface parameters are critical for the accumulation of electrons or holes on the reactive surface for reduction or oxidation reactions, respectively. Thirdly, the chemical stability of photocatalysts during the catalytic process can be improved by modifying the surface parameters. In this section, the surface design of cocatalysts for photocatalytic H_2 evolution and CO_2 reduction is discussed according to some important surface parameters such as surface composition, facets, phases and defects.

3.1 Surface composition

The surface composition greatly determines the atomic or ionic arrangements on a cocatalyst surface and thus the adsorption

and activation behavior of reactants. To date, the surface design of cocatalysts through composition optimization has been widely used to enhance the performance of photocatalysts for various reactions. As the adsorption and activation behaviors are the keys to this performance tuning, the selection of cocatalyst compositions certainly depends on the type of reaction – water splitting or CO_2 reduction. For instance, metallic Pt is the most widely used reduction cocatalyst in water splitting mainly due to its low activation energy for H_2 evolution.⁶ However, the back reaction of hydrogen oxidation may also be catalyzed by the metallic Pt cocatalyst, thus limiting the solar energy conversion efficiency. To solve this problem, Li *et al.* loaded Pt in an oxidized state (PtO) on anatase TiO_2 nanosheets (Fig. 3a), using a similar chemical reduction method to metallic Pt, except for the addition of a poly(methacrylic acid) ligand.⁷⁴ Fig. 3b summarizes the photocatalytic performance of the two samples in pure water splitting, with the pre-injection of stoichiometric H_2 and O_2 into the closed test system. The TiO_2 –Pt photocatalyst exhibited a remarkable decrease in H_2 and O_2 amounts with extended periods of light irradiation, mainly resulting from the undesirable hydrogen oxidation reaction (HOR) on the Pt cocatalyst. In sharp contrast, the TiO_2 –PtO offered the capability for stoichiometric H_2 and O_2 to evolve steadily as the reaction proceeded. The cocatalyst PtO not only acts as efficient H_2 evolution sites, but also exhibits the remarkable ability of suppressing the HOR as it can hardly activate and dissociate H_2 molecules (Fig. 3c).

In photocatalytic water splitting, another effective strategy for suppressing the back reaction of hydrogen oxidation on noble metals is to develop core–shell cocatalysts. In a typical case, to prevent the HOR on a metal cocatalyst, Cr_2O_3 was selectively coated on the noble metal (*e.g.*, Rh) to form an $M@Cr_2O_3$ core–shell cocatalyst. The Cr_2O_3 surface provided alternative H_2 evolution sites and prevented the back reaction, while the metal facilitated electron migration toward the Cr_2O_3 surface (Fig. 3d and e).²¹ In a further study, a selective permeation mechanism was proposed for the core–shell cocatalyst, in which the Cr_2O_3 layer (*i.e.*, microporous $CrO_{(1.5-m)}(OH)_{2m} \cdot xH_2O$ in aqueous solution) does not interfere with proton reduction at the Cr_2O_3 –Pt interface and the diffusion of H_2 , but suppresses the permeation of oxygen atoms and molecules (Fig. 3f).⁷⁵ Later on, metal@ Cr_2O_3 core–shell cocatalysts have been widely used in photocatalysis and further extended to metal oxide@ Cr_2O_3 core–shell cocatalysts.^{67,76–78} With a similar mechanism, the $Ni@NiO$ core–shell structure is another important cocatalyst with the capability of inhibiting the back reaction in water splitting.^{18,79–81} In the structure, the NiO shell allows the diffusion of protons to reach Ni sites for reduction reactions as well as the diffusion and escape of the produced H_2 , but it can act as a valid barrier for O diffusion.

As a matter of fact, Cr_2O_3 has been extensively employed as a second cocatalyst component in UV-excitible photocatalysis with wide-bandgap semiconductors. Recently, novel surface modification methods have offered alternative materials to replace the Cr_2O_3 shell to achieve overall water splitting.^{82–84} A layer of amorphous transition-metal oxynitride or oxyhydroxide covered the entire surface of the semiconductor and cocatalyst,




Fig. 3 (a) STEM image of a TiO_2 – PtO photocatalyst, (b) time-resolved profiles of the HOR with pre-injected H_2 and O_2 on TiO_2 – Pt and TiO_2 – PtO photocatalysts under light irradiation, (c) schematic diagram illustrating the surface reactions on Pt and PtO cocatalysts during water splitting (adapted with permission from ref. 74, Copyright 2013 Nature Publishing Group); (d) TEM image of $(\text{Ga}_{1-x}\text{Zn}_x)(\text{N}_{1-x}\text{O}_x)$ -supported $\text{Rh@Cr}_2\text{O}_3$ core–shell cocatalyst; (e) schematic diagram illustrating the surface reactions on Rh and $\text{Rh@Cr}_2\text{O}_3$ core–shell cocatalysts during water splitting; (f) mechanism of $\text{Rh@Cr}_2\text{O}_3$ core–shell cocatalysts for water splitting (adapted with permission from ref. 21 and 75, Copyright 2006 Wiley–VCH and 2009 American Chemical Society); (g) HRTEM image of Ta_2O_5 -coated SrTiO_3 : Sc – Rh_2O_3 photocatalyst; (h) time course of gas evolution during the photoirradiation of pure water with SrTiO_3 : Sc – Rh_2O_3 and SrTiO_3 : Sc – Rh_2O_3 / Ta_2O_5 as the photocatalyst; (i) schematic diagram illustrating the reaction mechanism for overall water splitting on SrTiO_3 : Sc – Rh_2O_3 and SrTiO_3 : Sc – Rh_2O_3 / Ta_2O_5 core–shell photocatalysts (adapted with permission from ref. 84, Copyright 2015 American Chemical Society).

and functioned as a molecular sieve to selectively filter reactant and product molecules. For instance, to prevent the backward oxygen reduction reaction (ORR) reaction on the surface of a SrTiO_3 -supported Rh_2O_3 cocatalyst, oxyhydroxide layers of Ta^{5+} (referred to as Ta_2O_5 for simplicity) were formed to fully cover the photocatalyst to form SrTiO_3 : Sc – Rh_2O_3 / Ta_2O_5 core–shell structures (Fig. 3g).⁸⁴ In the absence of a Ta_2O_5 coating, the photocatalytic H_2 and O_2 evolution on SrTiO_3 : Sc – Rh_2O_3 was largely limited by the rapid backward reaction (Fig. 3h). In comparison, SrTiO_3 : Sc – Rh_2O_3 / Ta_2O_5 behaved very differently. Upon irradiation, a considerable amount of O_2 evolved during the initial 3–4 h due to contaminants from the catalyst synthesis. After evacuating the reaction system, H_2 and O_2 were produced at constant rates and at the stoichiometric ratio of water splitting. It was demonstrated that the ORR back reaction was successfully prevented by the Ta_2O_5 coating. In this design, the amorphous Ta_2O_5 layer allows H^+ ions and H_2O molecules to reach the surface of Rh_2O_3 and SrTiO_3 for H_2 and O_2

evolution, respectively. Although the produced O_2 can be released from the coating layer through penetration, O_2 permeation in the opposite direction is unlikely to occur as the partial O_2 pressure in the outer phase is lower than in the coating layer. Such one-way permeation of O_2 effectively prevents the back reaction without compromising the forward reaction (Fig. 3i).

In addition to water splitting, the surface composition also plays an important role in the photocatalytic reduction of CO_2 with H_2O . For instance, a $\text{Pt@Cu}_2\text{O}$ core–shell cocatalyst was designed to enhance photocatalytic selectivity in the reduction of CO_2 to CO and CH_4 .¹³ Given the high ability of the Pt cocatalyst for H_2O activation, H_2 would be the major product when a TiO_2 – Pt hybrid structure is used as a photocatalyst, reducing the selectivity of CO_2 conversion. To improve the selectivity, Cu_2O , a material with high CO_2 activation ability, was selectively coated on the Pt to modify the surface composition (Fig. 4a). As shown in Fig. 4b, the Cu_2O coating significantly suppressed the

formation of H_2 and promoted the production of CH_4 and CO , remarkably increasing the selectivity for CO_2 reduction. In this structure, the Pt core transferred the photogenerated electrons from TiO_2 to the Cu_2O shell, and the Cu_2O shell served as the reaction sites for producing CH_4 and CO (Fig. 4c).

In addition to surface coating or decoration, surface composition control can also be achieved through incorporating new atoms into a cocatalyst surface. Metal cocatalysts can be tailored by forming alloys with different metal atoms.^{85,86} For instance, H_2 evolution using TiO_2 nanosheets with a Pt cocatalyst could be enhanced by incorporating Pd into the Pt lattice to form a PdPt alloy cocatalyst with both cases of $\text{Pt}/\text{Pd}\{100\}$ and $\{111\}$ surface facets at various typical Pd/Pt ratios (Fig. 4d-f).⁸⁶ In this system, the difference in the work functions of Pd and Pt induced electron accumulation at Pt sites. The increase in

electron density in turn enhanced the H_2O adsorption and activation on the Pt sites for H_2 production (Fig. 4g). In another case, an $\text{Au}@\text{(AuPd alloy)}$ core-shell cocatalyst has been developed for efficient H_2 production with $\text{CdSe}@\text{CdS}$ as the photoactive charge generation unit (Fig. 4h).⁸⁷ The $\text{CdSe}@\text{CdS}$ rods with $\text{Au}@\text{alloy}$ core-shell tips exhibited a significant enhancement in photocatalytic activity in comparison with Pd, Au and $\text{Au}@\text{Pd}$ core-shell tips, benefiting from both the alteration in electronic structure by the Au core and the atomic rearrangement of the Pd surface (Fig. 4i). In the AuPd alloy, Pd reaction sites are separated with Au, which reduces the H adsorption strength to release H_2 as well as eliminating the so-called self-poisoning effect. Furthermore, the Au on the surface enhances the photocatalytic stability by suppressing cation exchange reactions between Cd and Pd (Fig. 4j and k).




Fig. 4 (a) HRTEM image of a TiO_2 -supported $\text{Pt}@\text{Cu}_2\text{O}$ core–shell cocatalyst, (b) the dependence of photocatalytic behavior on Cu content in $\text{TiO}_2\text{-Pt}@\text{Cu}_2\text{O}$ photocatalysts for the reduction of CO_2 with H_2O , (c) a schematic illustration of the selective coating of a Pt cocatalyst with Cu_2O to enhance photocatalytic CO_2 reduction selectivity (adapted with permission from ref. 13, Copyright 2013 Wiley-VCH); (d and e) TEM images of TiO_2 -supported PdPt alloy (d) nanocube and (e) nanotetrahedron cocatalysts, (f) hydrogen production rates using TiO_2 -supported Pd and Pt and PdPt alloy (with different Pd/Pt ratios) nanocube cocatalysts, (g) schematic illustration of photocatalytic H_2 evolution on TiO_2 -supported PdPt alloy cocatalysts (adapted with permission from ref. 86, Copyright 2016 Wiley-VCH); (h) TEM image and EDS elemental mapping of $\text{CdSe}@\text{CdS}$ rods with $\text{Au}@\text{PdAu}$ alloy core–shell cocatalysts on their tips, (i) schematic illustration and relative hydrogen production rates of $\text{CdSe}@\text{CdS}$ seeded rods with Pd, $\text{Au}@\text{Pd}$, and $\text{Au}@\text{(Au/Pd alloy)}$ tips serving as reduction cocatalysts relative to their Au-tip counterpart, and (j and k) TEM images of $\text{CdSe}@\text{CdS}$ with (j) $\text{Au}@\text{Pd}$ and (k) $\text{Au}@\text{(Au/Pd alloy)}$ tips after photocatalysis (adapted with permission from ref. 87, Copyright 2015 American Chemical Society).

3.2 Surface facets

With the same surface composition, tailoring the facets exposed on a cocatalyst surface can also lead to a variation in atomic arrangements. Similarly, this would maneuver the adsorption and activation of reactive molecules, and tune the photocatalytic activity and selectivity. During the process of photocatalytic conversion of CO_2 and H_2O into carbon fuels, water splitting often competes with CO_2 reduction by consuming photoexcited electrons. In a typical case, the selectivity between CO_2 reduction and water splitting can be tuned through adjusting the exposed facets of Pd reduction cocatalysts supported on $\text{g-C}_3\text{N}_4$ nanosheets.¹⁴ In this example, Pd nanocubes enclosed with $\{100\}$ facets and Pd nanotetrahedrons with $\{111\}$ facets were grown *in situ* on C_3N_4 nanosheets to form $\text{C}_3\text{N}_4\text{-Pd}\{100\}$ and $\text{C}_3\text{N}_4\text{-Pd}\{111\}$ photocatalysts, respectively (Fig. 5a and b). With the same Pd loading (*ca.* 6 wt%), $\text{C}_3\text{N}_4\text{-Pd}\{100\}$ preferred to reduce H_2O to H_2 , while $\text{C}_3\text{N}_4\text{-Pd}\{111\}$ mainly supported CO_2 reduction to carbon products (*i.e.*, CO , CH_4 and $\text{C}_2\text{H}_5\text{OH}$). As a result, the selectivity for CO_2 reduction turned out to be 20.7% for Pd $\{100\}$ *versus* 78.1% for Pd $\{111\}$ (Fig. 5c). Behind the observations, theoretical simulations revealed that the Pd $\{111\}$ facets offered higher CO_2 adsorption energy and a lower CO_2 activation barrier, while the Pd $\{100\}$ facets possessed much higher H_2O adsorption energy. Despite comparable electron transfer efficiencies, the electrons trapped on various facets of the Pd cocatalyst would be mainly utilized for different reduction reactions (Fig. 5d). Besides Pd, the

exposed facets of Pt cocatalysts have also been reported to play an important role in determining the photocatalytic performance for H_2 production.^{88,89}

3.3 Surface phase

When we design the surface of a cocatalyst, the surface phase is another important parameter that has to be taken into account. For instance, it turned out that different photocatalytic H_2 production rates could be achieved when metallic (1T, octahedral phase) and semiconducting (2H, trigonal prismatic phase) MoS_2 were used as reduction cocatalysts with light-harvesting TiO_2 .⁹⁰ In this case, comparable TiO_2 nanocrystals were loaded on the MoS_2 nanosheets in 1T and 2H phases to form $\text{TiO}_2\text{-MoS}_2$ (1T) and $\text{TiO}_2\text{-MoS}_2$ (2H) hybrid structures (Fig. 6a). As shown in Fig. 6b, $\text{TiO}_2\text{-MoS}_2$ (1T) exhibited a dramatically higher photocatalytic H_2 production rate in comparison to $\text{TiO}_2\text{-MoS}_2$ (2H). The advantages of the 1T phase in cocatalysts originated from two aspects: (i) the active sites for H_2 evolution were only located at the edges of the 2H MoS_2 nanosheets, while the 1T MoS_2 nanosheets had abundant active sites at both the edges and basal planes; and (ii) the 1T MoS_2 nanosheets offered significantly higher mobility for electron transfer in comparison with the 2H MoS_2 nanosheets. As such, the higher diffusion rate and shorter diffusion distance ensure more photogenerated electrons from TiO_2 arrive at the reaction sites of the 1T MoS_2 cocatalyst and participate in photocatalytic reactions (Fig. 6c). Owing to these advantages, transition metal oxides and




Fig. 5 (a and b) TEM and HRTEM images of (a) $\text{C}_3\text{N}_4\text{-Pd}$ nanocubes with exposed Pd $\{100\}$ facets and (b) $\text{C}_3\text{N}_4\text{-Pd}$ nanotetrahedrons with Pd $\{111\}$ facets; (c) production rates of H_2 and carbon products using $\text{C}_3\text{N}_4\text{-Pd}$ photocatalysts with *ca.* 6 wt% Pd loading; and (d) schematic illustration of $\text{C}_3\text{N}_4\text{-Pd}\{100\}$ and $\text{C}_3\text{N}_4\text{-Pd}\{111\}$ samples in photocatalytic CO_2 reduction in the presence of H_2O (adapted with permission from ref. 14, Copyright 2014 Royal Society of Chemistry).




Fig. 6 (a) TEM image of TiO₂-MoS₂(1T) photocatalyst; (b) photocatalytic hydrogen production rates of TiO₂-MoS₂; (c) schematic diagram illustrating charge-transfer behavior and H₂ evolution active sites on TiO₂-MoS₂(1T) and TiO₂-MoS₂(2H) (adapted with permission from ref. 90, Copyright 2015 Springer); and (d) time course of H₂ evolution over CdS, CdS-MoS₂ (defect-free) and CdS-MoS₂ (defect-rich) (adapted with permission from ref. 91, Copyright 2015 Royal Society of Chemistry).

phosphides (e.g., MoO₂ and MoP) with surface metallic phases have also been developed as highly efficient noble-metal-free cocatalysts for photocatalytic hydrogen production from water.^{32,60}

3.4 Surface defects

In terms of surface photocatalytic reactions, the adsorption and activation of reactants often take place at surface defects or vacancies where dangling bonds are prone to capture both charge carriers and reactants. Thus the activity and selectivity in photocatalysis can be improved by controlling the number of surface defects or altering the type of surface defects. For instance, CdS nanocrystals were anchored on defect-free and defect-rich MoS₂ ultrathin nanoplates, respectively, to act as H₂ evolution cocatalysts.⁹¹ The CdS-MoS₂ (defect-rich) structure exhibited dramatically higher H₂ evolution activity compared to CdS-MoS₂ (defect-free), mainly owing to the role of defects as reactive sites (Fig. 6d). It should be noted that here we do not bother to consider the side effects of surface defects on charge recombination, as only electrons or holes are trapped on the surface of cocatalysts.

4. Interface design of cocatalysts for photocatalysis

Differently from surface design, interface design is mainly performed *via* parameter adjustments and optimization of the contact interfaces between cocatalysts and other components. The interface has to be tightly controlled simply because it is the location through which the photogenerated charge carriers are transferred. As a matter of fact, interface design enables an

improvement in photocatalytic performance from several different angles. Firstly, interface parameters can be designed to realize highly efficient charge transfer. The efficiency of charge transfer determines the number of charge carriers for redox reactions at the cocatalyst surface. Secondly, spatial charge separation can be enabled through interface control to prevent detrimental electron-hole recombinations in the semiconductor. Thirdly, the interface quality actually represents the bonding between the cocatalyst and other components, so the stability of the photocatalyst is largely relevant to the interface. In this section, we will discuss interface design according to key interface parameters, including interfacial composition, location and facets.

4.1 Interfacial composition

Similarly to surface composition, the composition of the interface, where the cocatalyst contacts with the adjacent component, is a key parameter for affecting the efficiency of charge transfer across the interface. For instance, the similar composition of the two sides of an interface would favor their intimate contact and strong coupling for highly efficient charge transfer. In typical cases, transition metal sulfides (e.g., MoS₂, WS₂ and NiS) were often used as H₂ evolution cocatalysts for CdS-based photocatalysts,^{26–28,91} because their analogous compositions (*i.e.*, containing S²⁻ anions) favored the formation of a covalent junction with a low defect density at the interface to facilitate electron transfer.

Recently, interfacial composition adjustment on the cocatalyst has been reported to improve the performance of photocatalysts. For instance, the interface between a CoO_x oxidation co-catalyst and a Ta₃N₅ semiconductor has been tailored toward

improved water oxidation.¹⁵ As intimate contact could hardly be made between the hydrophobic Ta_3N_5 and hydrophilic CoO_x for efficient interfacial charge transfer, a magnesia nanolayer was used to turn the Ta_3N_5 surface from hydrophobic to hydrophilic through *in situ* or *ex situ* surface coating prior to CoO_x deposition, forming $\text{Ta}_3\text{N}_5\text{-(in)MgO/CoO}_x$ and $\text{Ta}_3\text{N}_5\text{-(ex)MgO/CoO}_x$, respectively (Fig. 7a). The magnesia coating not only improved the interfacial contact between CoO_x and Ta_3N_5 , but also reduced the defect density of Ta_3N_5 through a passivation effect (Fig. 7b). As a result, $\text{Ta}_3\text{N}_5\text{-(in)MgO/CoO}_x$ and $\text{Ta}_3\text{N}_5\text{-(ex)MgO/CoO}_x$ exhibit substantially higher oxygen evolution rates than $\text{Ta}_3\text{N}_5\text{-CoO}_x$ (Fig. 7c). The transient absorption spectra revealed that the MgO layer effectively suppressed the recombination of photoinduced carriers and prolonged their lifetimes (Fig. 7d).

4.2 Interfacial location

The location for forming the interface is critical to the efficiency of interfacial charge transfer, especially when electrons and holes are accumulated on different components in a heterostructure. To ensure high charge-transfer efficiency, reduction or oxidation cocatalysts should be deposited on locations where electrons or holes are accumulated, respectively. For instance, Park *et al.* reported that the configuration of loading Pt cocatalysts onto CdS/TiO_2 hybrid catalysts greatly determined the overall H_2 production efficiency.⁹² The Pt cocatalyst could be deposited on the surface of either CdS (*i.e.*, $\text{TiO}_2/\text{CdS-Pt}$) or TiO_2 (*i.e.*, $\text{CdS/TiO}_2\text{-Pt}$) or on both surfaces, to form different interface configurations (Fig. 8a). Under visible light, the $\text{CdS/TiO}_2\text{-Pt}$ structures exhibited remarkably higher H_2 production rates in comparison with $(\text{CdS/TiO}_2)\text{-Pt}$ and $\text{TiO}_2/\text{CdS-Pt}$ (Fig. 8b and c), as the decoration of Pt cocatalyst on the TiO_2 side enabled successive electron transfer along $\text{CdS} \rightarrow \text{TiO}_2 \rightarrow \text{Pt}$ and maximized the electron transfer efficiency. In a different way, the multi-directional electron transfer throughout $(\text{CdS/TiO}_2)\text{-Pt}$ and $\text{TiO}_2/\text{CdS-Pt}$ inevitably lowered the efficiency (Fig. 8a).

When dual cocatalysts are involved in a photocatalytic system for reduction and oxidation reactions, the relative locations of the cocatalysts can also affect the photocatalytic performance. The spatial separation of a reduction cocatalyst from an oxidation one can not only reduce charge recombination owing to the different transfer directions of electrons and holes, but also prevent the back reaction between products given their long-distance separation. As just mentioned, the key to this system is to deposit the corresponding cocatalysts at appropriate locations on the semiconductor where electrons or holes are accumulated. Mubeen *et al.* designed and fabricated an autonomous plasmonic solar water splitter based on Au nanorod arrays. In the system, the TiO_2 at the tips of the Au nanorods was decorated with Pt nanoparticles, as a H_2 evolution cocatalyst, while Co-OEC material, as an O_2 evolution cocatalyst, was deposited on the lower portion of the nanorods (Fig. 8d and e).⁹³ The different interfacial locations of the Pt and Co-OEC cocatalysts along the Au nanorods effectively lowered the possibility of recombining plasmonic hot electrons with the remaining positive charges (*i.e.*, hot holes) on the nanorods.

Apparently nanorods provide an anisotropic platform for separating electrons from holes, designating the locations for reduction and oxidation cocatalysts. However, the anisotropy of semiconductor nanostructures is not indispensable for cocatalyst separation. For example, Wang *et al.* reported a $\text{SiO}_2/\text{Ta}_3\text{N}_5$ core-shell photocatalyst with reduction cocatalyst Pt nanoparticles loaded on a Ta_3N_5 inner shell surface, and with an oxidation cocatalyst, IrO_2 or CoO_x , on the outer shell surface (*i.e.*, $\text{Pt(in)-Ta}_3\text{N}_5\text{-MO}_x\text{(out)}$, $\text{M} = \text{Ir}$ or Co) (Fig. 8f).⁹⁴ The separated locations of the cocatalysts facilitated the migration of photoexcited electrons and holes toward the inner and outer surfaces, respectively. This design not only reduced charge recombination, but also prevented the back reaction between the newly produced H_2 and O_2 to form H_2O . As a result, $\text{Pt(in)-Ta}_3\text{N}_5\text{-IrO}_x\text{(out)}$ exhibited higher H_2 evolution rates than a $\text{SiO}_2/\text{Ta}_3\text{N}_5$ core-shell photocatalyst.




Fig. 7 (a) Schematic diagram illustrating hydrophilic interface modification for improving the interfacial contact between Ta_3N_5 and CoO_x for enhanced water oxidation; (b) TEM image of $\text{Ta}_3\text{N}_5\text{-(in)MgO/CoO}_x$; (c) rates of oxygen evolution on the Ta_3N_5 -based photocatalysts; and (d) the decay in transient absorption for the representative Ta_3N_5 -based photocatalysts: (a) $\text{Ta}_3\text{N}_5\text{-(in)MgO/CoO}_x$, (b) $\text{Ta}_3\text{N}_5\text{-(ex)MgO/CoO}_x$, (c) $\text{Ta}_3\text{N}_5\text{-CoO}_x$ and (d) Ta_3N_5 (adapted with permission from ref. 15, Copyright 2015 Wiley-VCH).




Fig. 8 (a) Illustrative diagrams for the charge kinetics in hybrid photocatalysts: (a) CdS/TiO₂, (b) (CdS/TiO₂)-Pt, (c) TiO₂/CdS-Pt, and (d) CdS/TiO₂-Pt; (b) hydrogen production using (CdS/TiO₂)-Pt and CdS/TiO₂-Pt under visible light; (c) hydrogen production using sgTiO₂/CdS-Pt and CdS/sgTiO₂-Pt under visible light (adapted with permission from ref. 92, Copyright 2008 Royal Society of Chemistry); (d) schematic diagram of a cross-section of an individual photosynthetic unit, and (e) corresponding TEM images of Pt and Co-OEC cocatalysts in the unit (adapted with permission from ref. 93, Copyright 2013 Nature Publishing Group); (f) schematic illustration of the use of two separated cocatalysts on a core-shell Ta₃N₅ photocatalyst as effective charge collectors for water splitting; (g and h) time course of (g) H₂ and (h) O₂ evolution on core-shell Ta₃N₅ photocatalysts with and without spatially separated cocatalysts (adapted with permission from ref. 94, Copyright 2013 Wiley-VCH); (i) and (j) the difference in photocatalytic performance between Pd-TiO₂-IrO_x and TiO₂-Pd/IrO_x in (i) H₂ production and (j) CO/H₂ production; and (k) schematic description of the proposed mechanisms of the photocatalytic reactions on TiO₂ with dual cocatalysts: (case I) spatially separated and (case II) with intimate contact (adapted with permission from ref. 95, Copyright 2014 Royal Society of Chemistry).

Ta₃N₅ core-shell structure with both Pt and IrO_x on the outer surface (Pt(out)-Ta₃N₅-IrO_x(out)) (Fig. 8g). Similarly, the separated loading of the Pt and CoO_x cocatalysts on the inner and outer surfaces of SiO₂/Ta₃N₅, respectively, could also improve the O₂ evolution rate (Fig. 8h).

Recently, new insight into the interfacial locations of cocatalysts has been proposed by Ma *et al.*⁹⁵ They found that intimate contact between the reduction (Pd) and oxidation (IrO_x) cocatalysts on TiO₂ (*i.e.*, TiO₂-Pd/IrO_x) could surprisingly lead to a significant enhancement in the photocatalytic activity for H₂ production *via* methanol reforming compared with separated Pd and IrO_x cocatalysts on TiO₂ (*i.e.*, Pd-TiO₂-IrO_x). As shown in Fig. 8i, with Pd-TiO₂-IrO_x with separated cocatalysts the H₂ production can be increased by 32% with respect to TiO₂ with

a single Pd cocatalyst deposited with the same photodeposition method (*i.e.*, TiO₂-Pd(PD)). In comparison, the TiO₂-Pd/IrO_x achieved an 81% enhancement in H₂ production in reference to TiO₂-Pd(IM) prepared with the same impregnation method. In addition, the Pd-IrO_x/TiO₂ design also achieved improved performance toward the CO/H₂ ratio (Fig. 8j). They proposed that the electrons and holes could be readily separated at the interface between IrO_x and Pd in this special case. Moreover, the photogenerated charges in the surface skin region would have a shorter transportation length to the surface where the reduction and oxidation cocatalysts were closely located. On the other hand, differently from water splitting, the backward reaction with the methanol reforming products (CO₂ + H₂) could hardly take place when the cocatalysts were in intimate

contact. A similar design has also been reported for other cocatalysts. For instance, the NiO_x cocatalyst has been widely used for water splitting, and most recently, it was found that this material was actually composed of Ni and NiO which could play the role of H_2 and O_2 evolution cocatalyst, respectively.^{96,97}

4.3 Interfacial facets

The efficiency of charge transfer is also dependent on the facets of components used in forming the interface. First of all, the interfacial facets, which are characterized with atomic arrangements, determine the bonding situation and lattice consistency between components as well as the coupling of their electronic structures. Secondly, the energy bands of material surfaces have a strong correlation with their surface facets, resulting in a certain alignment on the interface between the electronic band structures. Taken together, the charge transfer process at the interface largely relies on the component facets. Intuitively, the interfacial structures can be tailored either through adjusting the facet of the cocatalyst or by controlling the facet of the semiconductor for the deposition of the cocatalyst.

For instance, Pt nanoparticles with different exposed facets were loaded on graphene (rGO) nanosheets to form rGO–Pt{100} and rGO–Pt{111} cocatalysts, respectively.⁵⁸ With Eosin Y (EY) as a photosensitizer and rGO as a conductive component, the photoinduced electrons were transferred to the Pt cocatalyst

through the rGO–Pt interface for H_2 evolution. Enabled through different Pt facets at the interface, the H_2 evolution activity using rGO–Pt{100} was substantially higher than that with rGO–Pt{111} (Fig. 9a). With the same tunable facets, however, bare Pt{111} as a cocatalyst exhibited a higher H_2 evolution activity than bare Pt{100}, manifesting the higher catalytic activity of Pt{111}. The performance of Pt{100} can be boosted *via* integration with rGO, because it has stronger interactions with rGO than Pt{111} enabling faster interfacial charge transfer (Fig. 9b).

In addition to the interfacial coupling, facet control also allows the tuning of the interfacial band alignments. For instance, the EY-sensitized TiO_2 –Pt samples with different exposed Pt facets including {100}, {100/111} and {111} were employed as photocatalysts toward H_2 evolution.⁹⁸ EY– TiO_2 –Pt{111} presented the highest H_2 generation rate among the EY– TiO_2 –Pt samples (Fig. 9c), owing to its unique energy band alignment. The Fermi level of Pt{111} is lower than that of Pt{100}, so as to enlarge the difference between the Fermi level and the conduction band minimum (CBM) of TiO_2 . As a result, Pt{111} should be capable of trapping electrons from the CB of TiO_2 more effectively (Fig. 9d).

It is worth noting that the variation in cocatalyst facets not only alters the interfacial structure, but also designates different exposed facets for surface reactions. This feature makes it difficult to analyze the contribution of interfacial facet design to facet-dependent photocatalytic performance. To exclude the




Fig. 9 (a) H_2 evolution from EY-photosensitized systems catalyzed using RGO, Pt{100}, Pt{111}, RGO–Pt{100}, and RGO–Pt{111} as cocatalysts; (b) the proposed photocatalytic mechanism for hydrogen evolution over RGO–Pt{100} and RGO–Pt{111} cocatalysts under visible-light irradiation (adapted with permission from ref. 58, Copyright 2015 American Chemical Society); (c) photocatalytic H_2 evolution rates from a TEOA aqueous solution on EY– TiO_2 –Pt{100}, EY– TiO_2 –Pt{100/111}, and EY– TiO_2 –Pt{111} under visible-light irradiation; and (d) schematic diagram of the different energy levels in the Pt{100} (dotted curve) and Pt{111} facets (solid curve) (adapted with permission from ref. 98, Copyright 2013 American Chemical Society).

effect from surface facets, a more straightforward method has been developed to tune interfacial facets, in which cocatalysts are selectively deposited on the different facets of a semiconductor. When semiconductor crystals are enclosed with more than one type of facet, the varied energy band structures of the surface facets may lead to spatial charge separation, so as to accumulate electrons and holes on different facets.⁸ In this case, the selective deposition of a reduction cocatalyst on the facet which has accumulated electrons and/or an oxidation cocatalyst on the one with holes can readily realize highly efficient interfacial charge transfer. This further promotes spatial charge separation between the facets.

For instance, Li *et al.* reported the selective photodeposition of metals (*e.g.*, Pt) as reduction cocatalysts on the {010} facets of BiVO₄ crystals, and metal oxides (*e.g.*, MnO_x) as oxidation cocatalysts on the {110} facets, respectively (Fig. 10a).^{99,100} This selective photodeposition is indeed enabled by spatial charge separation accumulating photogenerated electrons and holes on the {010} and {110} facets, respectively (Fig. 10b). In the photocatalytic water oxidation reaction, the Pt-{010}BiVO₄{110}-MnO_x structure exhibited remarkably higher activity in comparison with bare BiVO₄ as well as BiVO₄{010}-Pt and BiVO₄{110}-MnO_x with a single cocatalyst, manifesting the synergistic function of dual-cocatalysts (Fig. 10c). Furthermore, this study demonstrates well that interfacial facets are critical in the efficacy of cocatalysts, as a random distribution of Pt and MnO_x on BiVO₄ cannot offer comparable efficiency for photocatalysis.


Nowadays, many photocatalysts have been reported through photodepositing suitable reduction (*e.g.*, Au) and/or oxidation (*e.g.*, Co₃O₄ and MnO_x) cocatalysts on electron- and/or hole-accumulating facets, respectively.^{101,102} In addition to the spatial charge separation between different facets, photo-generated electrons and holes may also diffuse in opposite directions through spontaneous polarization, driven by an built-in dipole field in semiconductor crystals with polar facets or by a ferroelectric field in ferroelectric oxide semiconductors. This mechanism can accumulate electrons and holes at the two ends of the facets perpendicular to the field direction.⁸ This case calls for the necessity of selectively depositing an appropriate cocatalyst on a specific location of a facet. For instance, the asymmetric selective photodeposition of Pt and MnO_x cocatalysts on the positively and negatively charged {001} facets of PbTiO₃, a ferroelectric oxide semiconductor, has been demonstrated by Zhen *et al.*¹⁰³ The resulting product showed greatly improved photocatalytic activity over those with random deposition.

When a semiconductor nanocrystal is enclosed with different facets, the traveling length of charge carriers toward the facets may depend on the nanocrystal geometry. In this case, the selective deposition of cocatalysts on the facet with a short charge transfer length may reduce electron-hole recombination and enhance the photocatalytic performance. For instance, Pt and PtO as reduction cocatalysts were dispersed on TiO₂ nanosheets and octahedra dominated with {001} and {101} facets, respectively (namely, TiO₂/001 and TiO₂/101).¹⁰⁴ The synthesis indicated that the metallic Pt cocatalyst was more

favorably deposited on the {101} facet, while the PtO could be stabilized on both the {001} and {101} facets (Fig. 10d-g). For photocatalytic H₂ evolution, TiO₂/101-Pt exhibited higher activity than TiO₂/001-Pt, and the activity of TiO₂/001-PtO exceeded that of TiO₂/101-PtO (Fig. 10h). This performance difference may originate from the reduction of charge recombination from short traveling lengths. The average electron migration length (*i.e.*, the distance from the center of the photocatalyst to the co-catalyst) was measured to be 2 nm in TiO₂/001-PtO, 25 nm in TiO₂/001-Pt, and 12 nm in both TiO₂/101-PtO and TiO₂/101-Pt. As a result, the TiO₂/101-Pt and TiO₂/001-PtO greatly shortened the migration path of photogenerated electrons as compared to TiO₂/001-Pt and TiO₂/101-PtO (Fig. 10i), reducing the probability of charge recombination.

As the energy band structure of the semiconductor surface depends on the facets, face control would also alter interfacial band alignments, altering the charge transfer efficiency at the interface. In a typical example, for Cu₂WS₄ (CWS) decahedra, the CBM and valance band maximum (VBM) of the {101} facets are 80 meV and 60 meV higher than those of the {001} facets, respectively, thus resulting in spatial charge separation between the facets.^{105,106} Using a photodeposition method, a Pt cocatalyst was preferentially formed on the {001} facets owing to the accumulation of photogenerated electrons; the photo-free chemical deposition resulted in Pt nucleation at both the {001} and {101} facets (Fig. 10j and k).¹⁰⁵ As illustrated in Fig. 10l, the spatial charge separation in CWS{001}-Pt drove the photogenerated electrons to move toward the Pt cocatalyst for H⁺ reduction, while the holes transferred toward the uncovered {101} facets to oxidize the Na₂S/Na₂SO₃ sacrificial reagent. In comparison, CWS{001}/{101}-Pt contained one additional CWS {101}-Pt interface (Fig. 10m). As the {101} facet was rich with holes, it is not expected to be an ideal facet for loading Pt cocatalysts. In the practical photocatalytic measurements, however, CWS{001}/{101}-Pt exhibited notably higher H₂ evolution activity than CWS{001}-Pt (Fig. 10n), and this activity was further promoted by increasing the {101}/{001} ratio from CWS-S to CWS-L. This indicates that the catalytic activity of Pt cocatalysts on the {101} facet should be higher than on the {001} facet (Fig. 10n). As revealed from energy band analysis, the elevated CB level of the CWS{101} facet in comparison with the {001} facet offered a larger potential difference, so that the excited electrons would more easily jump from the CWS{101} facets to the Pt cocatalysts. This feature enabled faster interfacial electron transfer toward improved photocatalysis (Fig. 10m).

Similarly to cocatalysts, altering the facets of semiconductors also brings about variations in interfacial coupling with the cocatalyst, which will influence the charge transfer efficiency across the interface. For instance, a Ni@NiO core-shell cocatalyst could be selectively loaded on the {002} and {101} facets of K₂La₂Ti₃O₁₀ photocatalysts for water splitting.¹⁰⁷ The interfacial electronic structures between Ni{111} and the different facets of K₂La₂Ti₃O₁₀ were investigated using two-dimensional surface model density functional theory (DFT) calculations (Fig. 10o). As indicated from the electron density contour maps for K₂La₂Ti₃O₁₀ CBM (Fig. 10p), the Ni3d + Ti3d hybrid orbitals



spread from the interface region to the Ni bulk region in the $\text{K}_2\text{La}_2\text{Ti}_3\text{O}_{10}\{101\}$ –Ni{111} interface, whereas the $\text{K}_2\text{La}_2\text{Ti}_3\text{O}_{10}\{002\}$ –Ni{111} interface localizes electron density within $\text{K}_2\text{La}_2\text{Ti}_3\text{O}_{10}$. This suggests that electron transfer at the $\text{K}_2\text{La}_2\text{Ti}_3\text{O}_{10}\{101\}$ –Ni{111} interface can work more smoothly.

5. Simultaneous control over the cocatalyst surface and interface for photocatalysis

In Sections 3. and 4., surface and interface design in cocatalysts have been discussed, respectively. As briefly mentioned above, interfacial charge transfer and surface activation reactions have substantial interplay and thus are entangled together, which highlights the necessity of simultaneously controlling surface and interface parameters. If achieved, this design will allow the improvement of both charge trapping and surface activation in a single system, which would be a promising approach for high-

performance photocatalysts. Certainly the parameters to be controlled in the co-design of surface and interface are quite similar to those mentioned in Sections 3. and 4. However, given the entangled relationships between surface and interface parameters, we have to more systematically consider their interplay as well as find out new approaches. For instance, it was reported that, in comparison with Pt{100}, Pt{111} cannot only trap electrons from TiO_2 more effectively, but also provide more reaction sites for water reduction.⁹⁸ In practical application, however, the corresponding design has not shown its strong advantages, as a high-quality interface may not be formed based on the selected cocatalyst surface. For this reason, it is imperative to develop new methods, theories and mechanisms to circumvent undesired situations.

Recently, Su *et al.* realized the co-design of surface and interface by optimizing the electronic properties of metal cocatalysts through compositional and structural fine-tuning.¹⁰⁸ In a semiconductor (TiO_2)–metal cocatalyst system, the interfacial charge transfer from the metal to the electron acceptor (A)




Fig. 11 (a) Schematic diagram of energy levels in a semiconductor (TiO_2)–metal cocatalyst system under UV irradiation: E_F and E'_F represent the Fermi level of the system before and after irradiation; the trap states of excited electrons and holes are indicated as e_t and h_t ; k_{red} and k_{rev} denote the reduction rate, and the reversed trapping rate, respectively; (b–d) representative HAADF-STEM images of (b) a Au_1Pd_1 random alloy particle, (c) a $\text{Au}_{\text{shell}}\text{–Pd}_{\text{core}}$ particle, and (d) a $\text{Pd}_{\text{shell}}\text{–Au}_{\text{core}}$ particle; (e) rate constants k_{red} and k_{rev} as a function of Pd concentration under constant irradiation; (f) photocatalytic H_2 production from a 25 vol% ethanol solution using random alloys and core–shell Au–Pd cocatalysts supported on TiO_2 ; (g) electronic density of states (DOS) profiles of 147-atom icosahedral clusters of Au, Pd, $\text{Au}_8\text{Pd}_{\text{c}}$, and $\text{Pd}_{\text{s}}\text{Au}_{\text{c}}$; the total valence DOS (gray) is complemented by contributions from the d-orbitals in both the core (red) and outer shell (blue) region; the E_F of the metal clusters, and the CBM and VBM of TiO_2 are indicated with black, red and green dashed lines, respectively; (h) charge localization from the view of the {100} surface of 147-atom icosahedral clusters of Au, Pd, $\text{Au}_8\text{Pd}_{\text{c}}$, and $\text{Pd}_{\text{s}}\text{Au}_{\text{c}}$; the blue and red colors represent atoms with electron accumulation and depletion, respectively (adapted with permission from ref. 108, Copyright 2014 American Chemical Society).

is a very slow process as compared to from TiO_2 to the metal. For this reason, the electrons accumulated in the metal may get trapped *via* reverse transportation to the trap states (e_t) of the semiconductor (Fig. 11a). Thus a fast reduction reaction (high k_{red}) on the surface and a slow reverse transfer process (low k_{rev}) for the trapped photogenerated electrons at the interface are both required for optimal performance. Au nanoparticles that were deposited on TiO_2 could offer a large k_{red} and k_{rev} , whereas Pd on TiO_2 showed the opposite. To optimize both the k_{red} and k_{rev} , Au- and Pd-based nanoparticles in a range of specific random alloy and core–shell configurations, such as Au_1Pd_1 random alloy (Fig. 11b), $\text{Au}_{\text{shell}}\text{–Pd}_{\text{core}}$ (Au_sPd_c , Fig. 11c) and $\text{Pd}_{\text{shell}}\text{–Au}_{\text{core}}$ (Pd_sAu_c , Fig. 11d) nanoparticles, were formed and supported on TiO_2 as cocatalysts. By probing the kinetics under constant irradiation, it was revealed that an increase in Pd content in the alloy nanoparticles resulted in a ~33–50% reduction in k_{red} as well as an exponential decrease in k_{rev} (Fig. 11e). Conversely, Pd_sAu_c maintained a relatively high k_{red} but a very low k_{rev} relative to Au_sPd_c . As a result, the $\text{TiO}_2\text{–Pd}_s\text{Au}_c$ exhibited higher H_2 evolution rates in comparison with the $\text{TiO}_2\text{–AuPd}$ alloy and $\text{TiO}_2\text{–Au}_s\text{Pd}_c$ (Fig. 11f).

Fig. 11g shows the electronic density of states (DOS) profiles of 147-atom icosahedral clusters of Au, Pd, Au_sPd_c , and Pd_sAu_c , respectively. It depicts that Pd clusters possess more unoccupied states just above the Fermi level (E_F) than Au, favorable for electron trapping. In the case of the core–shell structure, the number of unoccupied surface states just above E_F increases with the Pd concentration on the surface. Compared to <8% for Au_sPd_c , Pd_sAu_c shows that >60% of all states just above E_F are

surface-localized d-orbitals, which are highly beneficial for extending the lifetime of the photoexcited states transferred from the CB of TiO_2 . Furthermore, charge localization on the surface of the icosahedral clusters shows that net electron accumulation predominantly occurs throughout the shell, whereas for Pd_sAu_c , a net accumulation of charge takes place primarily on the vertex sites (Fig. 11h). On the other hand, charge depletion is prominent for the core regions of all the cocatalysts except Pd_sAu_c owing to the electronegative and capacitive properties of the Au core. It was proposed that the reduced surface accumulation of electrons in Pd_sAu_c facilitated the storage and release of photoexcited electrons toward surface catalysis.

In another case, we achieved the co-design of a cocatalyst surface and interface by employing a different mechanism – interfacial charge polarization. To implement the mechanism, atomically controlled $\text{Pd}@\text{Pt}$ core–shell cocatalysts were fabricated on TiO_2 nanosheets.⁶⁵ Specifically, we used Pd nanocubes supported on TiO_2 nanosheets ($\text{TiO}_2\text{–Pd}$) as precursors, and Pt shells with a controllable thickness could be selectively coated on the Pd cubes to form $\text{TiO}_2\text{–Pd}@\text{Pt}$ photocatalysts. As shown in Fig. 12a and b, $\text{TiO}_2\text{–Pd}@\text{Pt}$ photocatalysts with three ($\text{TiO}_2\text{–Pd}@\text{Pt}_{3L}$) and ten ($\text{TiO}_2\text{–Pd}@\text{Pt}_{10L}$) Pt atomic layers on average were synthesized by altering the $\text{TiO}_2\text{–Pd}/\text{Pt}$ precursor ratios. As such, the surface of the cocatalysts changed from $\text{Pd}\{100\}$ to Pt {100} with higher H_2 evolution activity. Furthermore, the Pt nanocubes with the same Pt{100} exposed were also loaded on TiO_2 nanosheets to provide a reference sample ($\text{TiO}_2\text{–Pt}$). From the photocurrent *versus* time ($I\text{–}t$) curves in Fig. 12c, the




Fig. 12 (a and b) TEM images and atomic-resolution HAADF-STEM images of (a) $\text{Pd}@\text{Pt}_{3L}$ and (b) $\text{Pd}@\text{Pt}_{10L}$ quasi-core–shell cocatalysts supported on TiO_2 nanosheets; (c and d) $I\text{–}t$ curves (c) and photocatalytic H_2 evolution (d) for $\text{TiO}_2\text{–Pd}@\text{Pt}_{3L}$ and $\text{TiO}_2\text{–Pd}@\text{Pt}_{10L}$ in comparison with bare TiO_2 nanosheets, $\text{TiO}_2\text{–Pd}$, and $\text{TiO}_2\text{–Pt}$ hybrid structures under UV light irradiation; (e) differential charge density determined using first-principles simulations for Pt{100} shells on Pd{100} substrates in the presence of one additional electron: the olive and cyan colors represent an increase and decrease in electron density, respectively (adapted with permission from ref. 65, Copyright 2015 Wiley–VCH).

photocurrents turn out to be in the order of $\text{TiO}_2\text{-Pd} < \text{TiO}_2\text{-Pt} < \text{TiO}_2\text{-Pd@Pt}_{10\text{L}} < \text{TiO}_2\text{-Pd@Pt}_{3\text{L}}$, suggesting more efficient electron-hole separation by the Pd@Pt cocatalyst. The same order was also recognized for hydrogen production rates, but the improvement in hydrogen production from the cocatalyst design appears to be more significant than the photocurrent (Fig. 12d).

The enhancement of photocatalytic performance with the Pd@Pt cocatalyst resulted from charge polarization at the Pd-Pt interface. Owing to the different work functions of Pd and Pt, electron migration across the interface from Pd to Pt will equilibrate their electron Fermi distributions. When TiO_2 was photoexcited, interfacial charge transfer would occur from TiO_2 to Pd driven by a $\text{TiO}_2\text{-Pd}$ Schottky junction. Meanwhile, the interfacial polarization would serve as a new driving force for the migration of photogenerated electrons from the Pd to Pt surface, improving the charge separation in the entire system. Furthermore, the interfacial polarization also led to the accumulation of electrons on the Pt surface. Both the electron accumulation and lattice strain at the Pd-Pt interface facilitated H_2O adsorption. As a result, the charge polarization does not only improve the charge separation, but it also enhances the H_2O adsorption. It should be noted that the interfacial polarization effect decays with an increase in Pt shell thickness (Fig. 12e). For this reason, the shell thickness has to be kept within a few atomic layers. This delicate design enables a boosting of the photocatalytic performance and a reduction in the amount of expensive Pt used.

6. Summary and outlook

The surface and interface design of cocatalysts would be a promising route to fabricate high-performance photocatalysts through maximizing the efficacy of cocatalysts. In this review, we have highlighted the emerging horizons of cocatalyst design based on surface and interface adjustment. On one hand, surface parameters such as the composition, facets, phases and defects have been tailored to enhance catalytic reactions on cocatalyst surfaces. On the other hand, interface parameters including interfacial composition, location and facets have been optimized to improve the charge transfer across the interface of cocatalysts with semiconductors. With novel methods, theories, and mechanisms (e.g., the interfacial polarization effect) implemented in cocatalyst design, surface and interface control has enabled the enhancement of surface reactions and interfacial charge transfer simultaneously. This set of designs not only deepens our understanding of fundamental aspects, but also provides technical approaches to significantly enhance the activity and selectivity in water splitting and CO_2 reduction.

Although great achievement and remarkable progress have been made in the surface and interface design of cocatalysts, there is a long way to go toward the practical use of photocatalysis in industry and our lives. Firstly, most of the previous reports on cocatalyst design were to tailor only one surface or interface parameter. It remains a grand challenge to design cocatalysts taking more parameters into account. The

bottlenecks include the interplaying effects of the parameters and the limited synthetic methods for realizing complicated designs. Secondly, some experimental results achieved in the designs still remain elusive. In many cases, existing observations seem contradictory between different reports. For instance, it has been reported that spatially separating reduction and oxidation cocatalysts and having them in intimate contact can both enhance charge separation,^{94,95} and that surface reactions on reduction cocatalysts can be facilitated by both reducing electron density or accumulating electrons on the surface.^{65,108} Thirdly, advanced characterization techniques are lacking to monitor the processes of surface reactions and interfacial charge transfer at high spatial and temporal resolution. Dynamic evolution at electron and molecular levels will provide important information for establishing the relationship between surface/interface parameters and catalytic performance. The above bottlenecks call for research at the intersection of precisely controlled synthesis, theoretical simulations and advanced spectroscopic characterization.⁸ Multidisciplinary collaborations at the intersection of these will offer the research community the capabilities to tailor cocatalyst structures with atomic precision and to understand the underlying mechanisms at the electron and molecular level. As soon as these existing bottlenecks are overcome, the more rational and systematic design of cocatalyst surfaces and interfaces would serve as a strong driving force toward the fabrication of highly efficient photocatalysts for solar fuel production.

Acknowledgements

This work was financially supported by the 973 Program (No. 2014CB848900), NSFC (No. 21471141, U1532135), the Recruitment Program of Global Experts, the CAS Hundred Talent Program, Hefei Science Center CAS (No. 2015HSC-UP009, 2015HSC-UP020), Fundamental Research Funds for the Central Universities (No. WK2060190025, WK2310000035), Zhejiang Provincial Natural Science Foundation (No. LQ16B010001), and the Open Research Fund of Top Key Discipline of Chemistry in Zhejiang Provincial Colleges and Key Laboratory of the Ministry of Education for Advanced Catalysis Materials (Zhejiang Normal University) (ZJHX201507).

Notes and references

- 1 A. Fujishima and K. Honda, *Nature*, 1972, **238**, 37.
- 2 A. L. Linsebigler, G. Lu and J. T. Yates Jr, *Chem. Rev.*, 1995, **95**, 735.
- 3 X. Chen, S. Chen, L. Guo and S. S. Mao, *Chem. Rev.*, 2010, **110**, 6503.
- 4 T. Hisatomi, J. Kubota and K. Domen, *Chem. Soc. Rev.*, 2014, **43**, 7520.
- 5 S. N. Habisreutinger, L. Schmidt-Mende and J. K. Stolarczyk, *Angew. Chem., Int. Ed.*, 2013, **52**, 7372.
- 6 J. Yang, D. Wang, H. Han and C. Li, *Acc. Chem. Res.*, 2013, **46**, 1900.
- 7 J. Ran, J. Zhang, J. Yu, M. Jaroniec and S. Z. Qiao, *Chem. Soc. Rev.*, 2014, **43**, 7787.

8 S. Bai, J. Jiang, Q. Zhang and Y. Xiong, *Chem. Soc. Rev.*, 2015, **44**, 2893.

9 Y. Ma, X. Wang, Y. Jia, X. Chen, H. Han and C. Li, *Chem. Rev.*, 2014, **114**, 9987.

10 L. Wang, F. Dionigi, N. T. Nguyen, R. Kirchgeorg, M. Gliech, S. Grigorescu, P. Strasser and P. Schmuki, *Chem. Mater.*, 2015, **27**, 2360.

11 S. Bai and Y. Xiong, *Chem. Commun.*, 2015, **51**, 10261.

12 S. Bai, W. Jiang, Z. Li and Y. Xiong, *ChemNanoMat*, 2015, **1**, 223.

13 Q. Zhai, S. Xie, W. Fan, Q. Zhang, Y. Wang, W. Deng and Y. Wang, *Angew. Chem., Int. Ed.*, 2013, **52**, 5776.

14 S. Bai, X. Wang, C. Hu, M. Xie, J. Jiang and Y. Xiong, *Chem. Commun.*, 2014, **50**, 6094.

15 S. Chen, S. Shen, G. Liu, Y. Qi, F. Zhang and C. Li, *Angew. Chem., Int. Ed.*, 2015, **54**, 3047.

16 M. Guan, C. Xiao, J. Zhang, S. Fan, R. An, Q. Cheng, J. Xie, M. Zhou, B. Ye and Y. Xie, *J. Am. Chem. Soc.*, 2013, **135**, 10411.

17 R. Long, S. Zhou, B. J. Wiley and Y. Xiong, *Chem. Soc. Rev.*, 2014, **43**, 6288.

18 A. Kudo and Y. Miseki, *Chem. Soc. Rev.*, 2009, **38**, 253.

19 M. Yoshida, A. Yamakata, K. Takanabe, J. Kubota, M. Osawa and K. Domen, *J. Am. Chem. Soc.*, 2009, **131**, 13218.

20 F. N. Sayed, O. D. Jayakumar, R. Sasikala, R. M. Kadam, S. R. Bharadwaj, L. Kienle, U. Schurmann, S. Kaps, R. Adelung, J. P. Mittal and A. K. Tyagi, *J. Phys. Chem. C*, 2012, **116**, 12462.

21 K. Maeda, K. Teramura, D. Lu, N. Saito, Y. Inoue and K. Domen, *Angew. Chem., Int. Ed.*, 2006, **45**, 7806.

22 C. G. Silva, R. Juarez, T. Marino, R. Molinari and H. Garcia, *J. Am. Chem. Soc.*, 2011, **133**, 595.

23 P. D. Tran, L. Xi, S. K. Batabyal, L. H. Wong, J. Barber and J. S. C. Loo, *Phys. Chem. Chem. Phys.*, 2012, **14**, 11596.

24 W. J. Foo, C. Zhang and G. W. Ho, *Nanoscale*, 2013, **5**, 759.

25 T. Simon, N. Bouchonville, M. J. Berr, A. Vaneski, A. Adrovic, D. Volbers, R. Wyrwich, M. Doblinger, A. S. Susha, A. L. Rogach, F. Jackel, J. K. Stolarczyk and J. Feldmann, *Nat. Mater.*, 2014, **13**, 1013.

26 X. Zong, H. Yan, G. Wu, G. Ma, F. Wen, L. Wang and C. Li, *J. Am. Chem. Soc.*, 2008, **130**, 7176.

27 J. Yuan, J. Wen, Y. Zhong, X. Li, Y. Fang, S. Zhang and W. Liu, *J. Mater. Chem. A*, 2015, **3**, 18244.

28 X. Zong, J. Han, G. Ma, H. Yan, G. Wu and C. Li, *J. Phys. Chem. C*, 2011, **115**, 12202.

29 Z. H. Shah, J. Wang, Y. Ge, C. Wang, W. Mao, S. Zhang and R. Lu, *J. Mater. Chem. A*, 2015, **3**, 3568.

30 C. C. Hu and H. S. Teng, *J. Catal.*, 2010, **272**, 1.

31 S. Cao, Y. Chen, C. C. Hou, X. J. Lv and W. F. Fu, *J. Mater. Chem. A*, 2015, **3**, 6096.

32 Q. Yue, Y. Wan, Z. Sun, X. J. Wu, Y. Yuan and P. Du, *J. Mater. Chem. A*, 2015, **3**, 16941.

33 Z. Sun, H. Zheng, J. Li and P. Du, *Energy Environ. Sci.*, 2015, **8**, 2668.

34 G. Xie, K. Zhang, B. Guo, Q. Liu, L. Fang and J. R. Gong, *Adv. Mater.*, 2013, **25**, 3820.

35 A. Ye, W. Fan, Q. Zhang, W. Deng and Y. Wang, *Catal. Sci. Technol.*, 2012, **2**, 969.

36 J. Yu, K. Wang, W. Xiao and B. Cheng, *Phys. Chem. Chem. Phys.*, 2014, **16**, 11492.

37 K. Iizuka, T. Wato, Y. Miseki, K. Saito and A. Kudo, *J. Am. Chem. Soc.*, 2011, **133**, 20863.

38 I. H. Tseng, J. C. S. Wu and H. Y. Chou, *J. Catal.*, 2004, **221**, 432.

39 P. W. Pan and Y. W. Chen, *Catal. Commun.*, 2007, **8**, 1546.

40 S. C. Yan, S. X. Ouyang, J. Gao, M. Yang, J. Y. Feng, X. X. Fan, L. J. Wan, Z. S. Li, J. H. Ye, Y. Zhou and Z. G. Zou, *Angew. Chem., Int. Ed.*, 2010, **49**, 6400.

41 S. Wang, Z. Ding and X. Wang, *Chem. Commun.*, 2015, **51**, 1517.

42 S. Wang, Y. Hou and X. Wang, *ACS Appl. Mater. Interfaces*, 2015, **7**, 4327.

43 L. Liu, Z. Ji, W. Zou, X. Gu, Y. Deng, F. Gao, C. Tang and L. Dong, *ACS Catal.*, 2013, **3**, 2052.

44 R. Asai, H. Nemoto, Q. Jia, K. Saito, A. Iwase and A. Kudo, *Chem. Commun.*, 2014, **50**, 2543.

45 F. Zhang, A. Yamakata, K. Maeda, Y. Moriya, T. Takata, J. Kubota, K. Teshima, S. Oishi and K. Domen, *J. Am. Chem. Soc.*, 2012, **134**, 8348.

46 B. Ma, J. Yang, H. Han, J. Wang, X. Zhang and C. Li, *J. Phys. Chem. C*, 2010, **114**, 12818.

47 R. Abe, M. Higashi and K. Domen, *J. Am. Chem. Soc.*, 2010, **132**, 11828.

48 E. M. P. Steinmiller and K. S. Choi, *Proc. Natl. Acad. Sci. U. S. A.*, 2009, **106**, 20633.

49 D. Wang, R. Li, J. Zhu, J. Shi, J. Han, X. Zong and C. Li, *J. Phys. Chem. C*, 2012, **116**, 5082.

50 G. Ai, R. Mo, H. Li and J. Zhong, *Nanoscale*, 2015, **7**, 6722.

51 K. Maeda, A. K. Xiong, T. Yoshinaga, T. Ikeda, N. Sakamoto, T. Hisatomi, M. Takashima, D. L. Lu, M. Kanehara, T. Setoyama, T. Teranishi and K. Domen, *Angew. Chem., Int. Ed.*, 2010, **49**, 4096.

52 S. S. K. Ma, K. Maeda, R. Abe and K. Domen, *Energy Environ. Sci.*, 2012, **5**, 8390.

53 A. Tanaka, S. Sakaguchi, K. Hashimoto and H. Kominami, *ACS Catal.*, 2013, **3**, 79.

54 A. Tanaka, K. Nakanishi, R. Hamada, K. Hashimoto and H. Kominami, *ACS Catal.*, 2013, **3**, 1886.

55 W. Jiang, S. Bai, L. Wang, X. Wang, L. Yang, Y. Li, D. Liu, X. Wang, Z. Li, J. Jiang and Y. Xiong, *Small*, 2016, **12**, 1640.

56 Z. Zheng, T. Tachikawa and T. Majima, *J. Am. Chem. Soc.*, 2014, **136**, 6870.

57 W. Zhang, Y. Li, X. Zeng and S. Peng, *Sci. Rep.*, 2015, **5**, 10589.

58 Z. Li, Q. Wang, C. Kong, Y. Wu, Y. Li and G. Lu, *J. Phys. Chem. C*, 2015, **119**, 13561.

59 C. Kong, S. Min and G. Lu, *Chem. Commun.*, 2014, **50**, 9281.

60 H. Du, X. Xie, Q. Zhu, L. Lin, Y. F. Jiang, Z. K. Yang, X. Zhou and A. W. Xu, *Nanoscale*, 2015, **7**, 5752.

61 Y. P. Xie, G. Liu, G. Q. Lu and H. M. Cheng, *Nanoscale*, 2012, **4**, 1267.

62 K. Maeda, M. Higashi, D. Lu, R. Abe and K. Domen, *J. Am. Chem. Soc.*, 2010, **132**, 5858.

63 S. Xie, Y. Wang, Q. Zhang, W. Deng and Y. Wang, *ACS Catal.*, 2014, **4**, 3644.

64 S. Xie, Y. Wang, Q. Zhang, W. Fan, W. Deng and Y. Wang, *Chem. Commun.*, 2013, **49**, 2451.

65 S. Bai, L. Yang, C. Wang, Y. Lin, J. Lu, J. Jiang and Y. Xiong, *Angew. Chem., Int. Ed.*, 2015, **54**, 14810.

66 C. W. Tsai, H. M. Chen, R. S. Liu, K. Asakura and T. S. Chan, *J. Phys. Chem. C*, 2011, **115**, 10180.

67 K. Maeda, N. Sakamoto, T. Ikeda, H. Ohtsuka, A. Xiong, D. Lu, M. Kanehara, T. Teranishi and K. Domen, *Chem.-Eur. J.*, 2010, **16**, 7750.

68 Z. Wang, G. Liu, C. Ding, Z. Chen, F. Zhang, J. Shi and C. Li, *J. Phys. Chem. C*, 2015, **119**, 19607.

69 D. Jiang, L. Chen, J. Xie and M. Chen, *Dalton Trans.*, 2014, **43**, 4878.

70 Q. Xiang, J. Yu and M. Jaroniec, *J. Am. Chem. Soc.*, 2012, **134**, 6575.

71 K. Chang, Z. Mei, T. Wang, Q. Kang, S. Ouyang and J. Ye, *ACS Nano*, 2014, **8**, 7078.

72 Q. Li, C. Cui, H. Meng and J. Yu, *Chem.-Asian J.*, 2014, **9**, 1766.

73 G. W. Busser, B. Mei, P. Weide, P. C. K. Vesborg, K. Stuhrenberg, M. Bauer, X. Huang, M. G. Willinger, I. Chorkendorff, R. Schlogl and M. Muhler, *ACS Catal.*, 2015, **5**, 5530.

74 Y. H. Li, J. Xing, Z. J. Chen, Z. Li, F. Tian, L. R. Zheng, H. F. Wang, P. Hu, H. J. Zhao and H. G. Yang, *Nat. Commun.*, 2013, **4**, 2500.

75 M. Yoshida, K. Takanabe, K. Maeda, A. Ishikawa, J. Kubota, Y. Sakata, Y. Ikezawa and K. Domen, *J. Phys. Chem. C*, 2009, **113**, 10151.

76 D. Wang, A. Pierre, M. G. Kibria, K. Cui, X. Han, K. H. Bevan, H. Guo, S. Paradis, A. R. Hakima and Z. Mi, *Nano Lett.*, 2011, **11**, 2353.

77 M. G. Kibria, S. Zhao, F. A. Chowdhury, Q. Wang, H. P. T. Nguyen, M. L. Trudeau, H. Guo and Z. Mi, *Nat. Commun.*, 2014, **5**, 3825.

78 K. Maeda and K. Domen, *J. Phys. Chem. Lett.*, 2010, **1**, 2655.

79 G. Zhang, G. Li and X. Wang, *ChemCatChem*, 2015, **7**, 2864.

80 L. Zhang, Q. Liu, T. Aoki and P. A. Crozier, *J. Phys. Chem. C*, 2015, **119**, 7207.

81 Q. Liu, L. Zhang and P. A. Crozier, *Appl. Catal., B*, 2015, **172**, 58.

82 T. Takata, C. Pan and K. Domen, *ChemElectroChem*, 2016, **3**, 31.

83 C. Pan, T. Takata, M. Nakabayashi, T. Matsumoto, N. Shibata, Y. Ikuhara and K. Domen, *Angew. Chem., Int. Ed.*, 2015, **54**, 2955.

84 T. Takata, C. Pan, M. Nakabayashi, N. Shibata and K. Domen, *J. Am. Chem. Soc.*, 2015, **137**, 9627.

85 C. Kong, S. Min and G. Lu, *Chem. Commun.*, 2014, **50**, 9281.

86 S. Bai, M. Xie, Q. Kong, W. Jiang, R. Qiao, Z. Li, J. Jiang and Y. Xiong, *Part. Part. Syst. Charact.*, DOI: 1002/ppsc.201500239.

87 E. Aronovitch, P. Kalisman, S. Mangel, L. Houben, L. Amirav and M. Bar-Sadan, *J. Phys. Chem. Lett.*, 2015, **6**, 3760.

88 M. Luo, W. Yao, C. Huang, Q. Wu and Q. Xu, *J. Mater. Chem. A*, 2015, **3**, 13884.

89 G. Kovacs, S. Fodor, A. Vulpoi, K. Schrantz, A. Dombi, K. Hernadi, V. Danciu, Z. Pap and L. Baia, *J. Catal.*, 2015, **325**, 156.

90 S. Bai, L. Wang, X. Chen, J. Du and Y. Xiong, *Nano Res.*, 2015, **8**, 175.

91 J. Xiong, Y. Liu, D. Wang, S. Liang, W. Wu and L. Wu, *J. Mater. Chem. A*, 2015, **3**, 12631.

92 H. Park, W. Choi and M. R. Hoffmann, *J. Mater. Chem.*, 2008, **18**, 2379.

93 S. Mubeen, J. Lee, N. Singh, S. Kramer, G. D. Stucky and M. Moskovits, *Nat. Nanotechnol.*, 2013, **8**, 247.

94 D. Wang, T. Hisatomi, T. Takata, C. Pan, M. Katayama, J. Kubota and K. Domen, *Angew. Chem., Int. Ed.*, 2013, **52**, 11252.

95 Y. Ma, R. Chong, F. Zhang, Q. Xu, S. Shen, H. Han and C. Li, *Phys. Chem. Chem. Phys.*, 2014, **16**, 17734.

96 T. K. Townsend, N. D. Browning and F. E. Osterloh, *Energy Environ. Sci.*, 2012, **5**, 9543.

97 Q. Zhang, Z. Li, S. Wang, R. Li, X. Zhang, Z. Liang, H. Han, S. Liao and C. Li, *ACS Catal.*, 2016, **6**, 2182.

98 E. Cui and G. Lu, *J. Phys. Chem. C*, 2013, **117**, 26415.

99 R. Li, F. Zhang, D. Wang, J. Yang, M. Li, J. Zhu, X. Zhou, H. Han and C. Li, *Nat. Commun.*, 2013, **4**, 1432.

100 R. Li, H. Han, F. Zhang, D. Wang and C. Li, *Energy Environ. Sci.*, 2014, **7**, 1369.

101 R. Li, X. Tao, R. Chen, F. Fan and C. Li, *Chem.-Eur. J.*, 2015, **21**, 14337.

102 L. Zhang, W. Wang, S. Sun, D. Jiang and E. Gao, *Appl. Catal., B*, 2015, **162**, 470.

103 C. Zhen, J. C. Yu, G. Liu and H. M. Cheng, *Chem. Commun.*, 2014, **50**, 10416.

104 Y. H. Li, C. Peng, S. Yang, H. F. Wang and H. G. Yang, *J. Catal.*, 2015, **330**, 120.

105 B. Wang, M. Liu, Z. H. Zhou and L. Guo, *Adv. Sci.*, 2015, **2**, 1500153.

106 N. Li, M. Liu, Z. Zhou, J. Zhou, Y. Sun and L. Guo, *Nanoscale*, 2014, **6**, 9695.

107 Y. Shimodaira, A. Kudo and H. Kobayashi, *Chem. Lett.*, 2007, **36**, 170.

108 R. Su, R. Tiruvalam, A. J. Logsdail, Q. He, C. A. Downing, M. T. Jensen, N. Dimitratos, L. Kesavan, P. P. Wells, R. Bechstein, H. H. Jensen, S. Wendt, C. R. A. Catlow, C. J. Kiely, G. J. Hutchings and F. Besenbacher, *ACS Nano*, 2014, **8**, 3490.