

Cite this: *Chem. Sci.*, 2021, 12, 7125

All publication charges for this article have been paid for by the Royal Society of Chemistry

Highly efficient ammonia synthesis at low temperature over a Ru–Co catalyst with dual atomically dispersed active centers†

Xuanbei Peng,^{‡a} Han-Xuan Liu,^{‡b} Yangyu Zhang,^{‡a} Zheng-Qing Huang,^b Linlin Yang,^a Yafei Jiang,^c Xiuyun Wang,^{*a} Lirong Zheng,^d Chunran Chang,^{id b} Chak-tong Au,^a Lilong Jiang,^{id *a} and Jun Li^{ce}

The desire for a carbon-free society and the continuously increasing demand for clean energy make it valuable to exploit green ammonia (NH₃) synthesis that proceeds via the electrolysis driven Haber–Bosch (eHB) process. The key for successful operation is to develop advanced catalysts that can operate under mild conditions with efficacy. The main bottleneck of NH₃ synthesis under mild conditions is the known scaling relation in which the feasibility of N₂ dissociative adsorption of a catalyst is inversely related to that of the desorption of surface N-containing intermediate species, which leads to the dilemma that NH₃ synthesis could not be catalyzed effectively under mild conditions. The present work offers a new strategy via introducing atomically dispersed Ru onto a single Co atom coordinated with pyrrolic N, which forms RuCo dual single-atom active sites. In this system the d-band centers of Ru and Co were both regulated to decouple the scaling relation. Detailed experimental and theoretical investigations demonstrate that the d-bands of Ru and Co both become narrow, and there is a significant overlapping of t_{2g} and e_g orbitals as well as the formation of a nearly uniform Co 3d ligand field, making the electronic structure of the Co atom resemble that of a “free-atom”. The “free-Co-atom” acts as a bridge to facilitate electron transfer from pyrrolic N to surface Ru single atoms, which enables the Ru atom to donate electrons to the antibonding π* orbitals of N₂, thus resulting in promoted N₂ adsorption and activation. Meanwhile, H₂ adsorbs dissociatively on the Co center to form a hydride, which can transfer to the Ru site to cause the hydrogenation of the activated N₂ to generate N₂H_x (x = 1–4) intermediates. The narrow d-band centers of this RuCo catalyst facilitate desorption of surface *NH₃ intermediates even at 50 °C. The cooperativity of the RuCo system decouples the sites for the activation of N₂ from those for the desorption of *NH₃ and *N₂H_x intermediates, giving rise to a favorable pathway for efficient NH₃ synthesis under mild conditions.

Received 16th January 2021
Accepted 7th April 2021

DOI: 10.1039/d1sc00304f

rsc.li/chemical-science

Introduction

The N₂-to-NH₃ conversion is one of the most important reactions for human society. NH₃ is not only used for the production of fertilizers and important chemicals, but also considered as a future fuel alternative and hydrogen storage vector.^{1–7} The

potential utilization of NH₃ in the coming chemical industry revolution is highly promising.⁸ Unfortunately, the industrial synthesis of NH₃ via the Haber–Bosch (HB) process using iron-based catalysts requires stringent reaction conditions (400–600 °C, 20–40 MPa),^{9–12} and consumes 1–2% of the global energy and produces ~1.5 tons of carbon dioxide per ton of NH₃.^{10–12} Traditionally, the H₂ supply for the HB process is mainly from coal or natural gas through the water-gas shift (WGS) or methane reforming reaction,¹³ and these processes account for the energy requirement and carbon dioxide production. Therefore, it is imperative to develop new HB technology that is both environmentally friendly and energy saving. Recently, with the green generation of electricity using renewable sources (such as hydro, wind, solar and tidal), it becomes economically acceptable to use the H₂ produced by water electrolysis, and NH₃ can be synthesized from renewable H₂ and N₂ via the electrolysis driven Haber–Bosch (eHB) process.

^aNational Engineering Research Center of Chemical Fertilizer Catalyst, Fuzhou University, Fuzhou, Fujian, 350002, China. E-mail: xywang2017@fzu.edu.cn; jllfzu@sina.cn; jll@fzu.edu.cn

^bShaanxi Key Laboratory of Energy Chemical Process Intensification, School of Chemical Engineering and Technology, Xi'an Jiaotong University, Xi'an 710049, China

^cDepartment of Chemistry, Southern University of Science and Technology, Shenzhen, China

^dInstitute of High Energy Physics, Chinese Academy of Sciences, Beijing, China

^eDepartment of Chemistry, Tsinghua University, Beijing, China

† Electronic supplementary information (ESI) available: Experimental details of reference samples, Tables S1–S6, and Fig. S1–S38. See DOI: 10.1039/d1sc00304f

‡ These authors contributed equally.



Nowadays, the subsequent NH_3 re-conversion to H_2 and the handling as well as shipping infrastructure including regulations for transportation are already in place.⁶ The above process follows a protocol of “renewable power supply \rightarrow electrolytic H_2 production \rightarrow NH_3 synthesis \rightarrow NH_3 storage \rightarrow H_2 energy”, in which efficient utilization of renewable energy for green production of NH_3 could be realized to achieve a “zero-loss” seasonal energy storage cycle that is carbon-free.^{3,13–15} However, the present bottleneck is that NH_3 cannot be synthesized under mild conditions. Currently, huge plants are required, and for a plant with an annual capacity of 200 000 tons, the investment is at the scale of US\$ 1000–2000 per ton of ammonia.⁷ The aim is to match the pressure of the NH_3 synthetic system with that of the electrolysis system employed for H_2 production (<5 MPa, mostly lying in the range of 1.0–3.2 MPa) so as to avoid expensive pressure ramping.¹⁵ Therefore, advanced catalysts that are adoptable to an efficient eHB process are urgently needed, which can activate N_2 for NH_3 synthesis at lower pressure.

The major obstacle of NH_3 synthesis under mild conditions is the scaling relation.^{15–18} In order to achieve NH_3 synthesis under mild conditions, great efforts have been devoted to seek catalytic materials that can either lower N_2 activation barriers^{19–21} or circumvent the scaling relationship.^{5,6,22–27} Previous advanced surface-science and theoretical investigations disclose that d-block transition metals (TMs), such as Re, Mo, Ru, Co and Rh, obey the scaling relationship because their surface d-bands are broad in bulk metals.^{18,28–31} The d-band center of such metals results in strong binding of N-containing intermediates, which require high temperature to desorb. Upon regulating the surface d-band centers of TMs, it is possible to simultaneously tune the binding energy of N_2 adsorption and that of surface N-containing intermediates. By so doing, the scaling relation for TMs can be decoupled. Indeed, the surface d-band of a metal-based catalyst can be effectively tuned through the strategy of single-atom catalysts (SACs)^{32–34} or single-cluster catalysts (SCCs),^{23,35} leading to d-band adsorption modes different from those of pure metals and conventional alloy compositions.^{36,37} The unusual electronic behavior of SACs and SCCs could also change the adsorption properties and bonding abilities of each metal atom,^{30,38} resulting in significant deviations from the scaling relationship.^{36,39,40} Among the SCCs, dual single-atom catalysts (DSACs) offer the simplest active sites for catalytic reactions.

For the well-known active Ru and Co metals in NH_3 synthesis, the Co d-band is narrower than that of Ru because of the quantum primogenic effect,⁴¹ resulting in the N_2 dissociative adsorption energy of Co being much lower than that of Ru. Despite the fact that the state-of-the-art Ru metal catalysts are efficient for NH_3 synthesis, the loading and high cost limit the large-scale use of the noble metal. It is hence advantageous to achieve efficient utilization of Ru by having a small amount of Ru atomically dispersed on atomistic Co to generate a RuCo DSAC. It is expected that the surface d-bands of the two metal atoms could be regulated through the formation of a DSAC, resulting in unique electronic and/or geometric features different from those of monometallic Ru and Co metals.^{42–44} As there is so far no experimental demonstration on the use of

DSACs for NH_3 synthesis, we are interested in exploring whether the RuCo DSAC is capable of decoupling the scaling relationship and which mechanism this DSAC system might adopt. Especially, the following issues deserve investigation: (1) the existing form of dual active centers, (2) the state of the surface d-band, (3) the pathway of N_2 activation and dissociation, and (4) how to decouple the scaling relation.

Herein, we report the preparation of a RuCo DSAC by introducing a Ru atom on a surface layer of Co–N–C material with Co atoms coordinated by a pyrrolic N of g- C_3N_4 . It is found that with Ru atomically anchored on the surface of single-site Co, there is significant overlapping of Co t_{2g} and e_g orbitals, resulting in an electronic structure resembling that of a “free” Co atom. Our experimental and theoretical studies demonstrate that the cooperativity of Ru and Co dual single-atom active centers could decouple the scaling relationship by separating N_2 adsorption and activation (on the Ru sites) from H_2 dissociative adsorption as well as N-containing intermediate species (mainly $^*\text{N}_2\text{H}_4$ and $^*\text{NH}_3$) desorption (on the Co sites). By so doing, the scaling relation over RuCo DSAC in NH_3 synthesis can be decoupled, and the developed RuCo DSAC could efficiently promote NH_3 synthesis at 200 °C, giving an NH_3 synthesis rate of up to 1.24 $\text{mmol}_{\text{NH}_3} \text{g}_{\text{cat}}^{-1} \text{h}^{-1}$. We believe the acquired understanding can help to accomplish rational design of transition-metal-based DSACs for the decoupling of the scaling relation to achieve high catalytic efficiency under mild conditions as well as to develop advanced catalysts to achieve pressure matching between the electrolysis and catalytic systems in eHB technology.

Results

Confirmation of Ru and Co atomic dispersion

To highlight the effect of the DSAC active centers, monometallic Ru/N–C and Co/N–C (denoted hereinafter as Co SAC) were also prepared for comparison purposes. Representative scanning electron microscopy (SEM) images demonstrate that the morphology of RuCo DSAC (Fig. 1a) is similar to that of Ru/N–C (Fig. S1a†) and Co SAC (Fig. S1b†), showing spherical structures of different sizes. The low magnification SEM-mapping of RuCo DSAC (Fig. 1b) reveals a homogeneous distribution of Ru and Co throughout the support material. And the amount of Ru and Co was 0.92 wt% and 2.24 wt%, respectively, according to the inductively coupled plasma atomic emission spectroscopy (ICP-AES) results (Table S1†). Structural information on RuCo DSAC was obtained based on X-ray diffraction (XRD) analysis. The characteristic peak at 26.4° (Fig. S2†) can be ascribed to the g- C_3N_4 phase. With the insertion of Ru and/or Co atoms into g- C_3N_4 , this peak decreases in intensity, revealing a distorted g- C_3N_4 crystal structure. No obvious diffraction peaks ascribable to Ru and/or Co species can be discerned. Also, the transmission electron microscopy (TEM, Fig. S3a–d†) images of RuCo DSAC show no obvious Ru or Co nanoparticles (NPs). These reveal that the Ru and/or Co species of Co SAC and RuCo DSAC are highly dispersed either as tiny clusters or as single atoms. This conclusion is further determined from spherical






Fig. 1 The morphology of the synthesized catalysts. (a) SEM image of RuCo DSAC, (b) SEM-mapping of N–K, C–K, Co–K and Ru–L over RuCo DSAC, (c–h) AC-STEM images: (c and d) Ru/N–C, (e and f) Co SAC and (g and h) RuCo DSAC samples.

aberration-corrected high-angle annular dark-field scanning transmission electron microscopy (AC-STEM) characterization.

According to the AC-STEM results, there is distribution of Ru single atoms as well as small clusters on Ru/N–C (Fig. 1c and d, and S4a–d†); the latter is a result of Ru aggregation as indicated by the individual bright dots of different intensity levels. Moreover, the AC-STEM images (Fig. 1e and f, and S5a–d†) taken at different regions of Co SAC show the predominant presence of Co single atoms (Fig. 1e and f, and S5a–d, related descriptions are provided in the ESI†). Interestingly, RuCo DSAC exhibits many individual bright dots (Fig. 1g and h). The dots over RuCo DSAC are repeatedly found at different magnifications (Fig. S6a–c†). Most of these dots show no obvious difference (Fig. 1g and h), and the results show that Ru and Co are uniformly dispersed. The result agrees with the fact that there is formation of dual single-atom Ru and Co as confirmed by extended X-ray absorption fine structure (EXAFS) measurements over RuCo DSAC. The conclusion is in accordance with the fact that there is a Ru–Ru bond attributable to Ru clusters as revealed by EXAFS measurements over Ru/N–C (Fig. S7†).

The EXAFS Ru K-edge (Fig. 2a) and Co K-edge (Fig. 2b and S8†) spectra show no obvious Ru–Ru or Co–Co interaction over RuCo DSAC and Co SAC (Fig. S9†), providing direct evidence for the presence of individually isolated Ru and/or Co atoms in the samples. Assignment of signals from 1 to 4 Å in RuCo DSAC is further confirmed by detailed WT-EXAFS wavelet transform plots (Fig. S10†). A WT intensity maximum near 4.5 \AA^{-1} can be assigned to the Co–N contribution. Moreover, the EXAFS fitting curves (Fig. S11a–d†) show that Ru (Fig. S11b†) and Co (Fig. S11d†) atoms over RuCo DSAC are coordinated with nitrogen atoms, and the coordination numbers (CN) of Ru–N and Co–N over RuCo DSAC are 2.9 ± 0.5 and 2.9 ± 0.9 (Table S2†), respectively, while the CN for Co–Ru is around 2.1.




Fig. 2 Physical characterization. (a) Ru K-edge EXAFS spectra of RuCo DSAC and reference samples, (b) Co K-edge EXAFS spectra over RuCo DSAC, (c) normalized Ru K-edge XANES spectra and (d) normalized Co K-edge XANES spectra over RuCo DSAC and reference samples.

We then performed XPS and XANES measurements to investigate the chemical state of Ru and Co species. XPS study results show that the surface Ru content in the case of RuCo DSAC is close to the total Ru content (total Ru content is determined by ICP-AES measurements). Notably, there is no detection of the Ru 3p signal after deep etching by Ar⁺ (Table S3†). These results indicate that Ru mainly disperses on the surface of DSAC. Moreover, the energy absorption edge of Ru K-edge XANES over RuCo DSAC (Fig. 2c) is higher than that of Ru foil but lower than that of RuO₂, suggesting an oxidation state of Ruⁿ⁺ ($0 < n < 4$) rather than Ru⁴⁺ or Ru⁰.⁴⁵ Similarly, the Co K-edge XANES spectra (Fig. 2d) show that the absorption edge position of RuCo DSAC locates between that of Co foil and CoO bulk, suggesting that the single Co atom carries positive charge, which is in accord with the XPS Co 2p study (Fig. S12a†). The XPS binding energy (BE) of the Co 2p_{3/2} peak (Fig. S12a†) over RuCo DSAC is higher than that of Co²⁺ (779.2 eV), and lower than that of Co³⁺ (781.0 eV),⁴⁶ suggesting that the surface Co atom has a hetero-valence state of Co²⁺ and Co³⁺. Additionally, the absorption edge of Ru K-edge over RuCo DSAC (Fig. S13†) is lower than that of Ru/N–C, while the BE of the XPS Co 2p_{3/2} peak for RuCo DSAC is higher than that for Co SAC (Fig. S12a†), indicating that there is electron transfer from Co to Ru *via* the Ru–Co bond,⁴⁷ plausibly due to the higher electronegativity of the Ru atom.⁴⁸ Meanwhile, the XPS Co 2p peaks of the RuCo DSAC sample significantly shift to lower BE values (-1.58 ± 0.7 eV, Fig. S12b†) when it is subject to Ar⁺ etching at different depths. These observations further suggest electron redistribution *via* electron transfer from Co to the surface Ru atom.

“Free-Co-atom” and electron transfer

Additional evidence of electron transfer between Co and Ru can be obtained by electron paramagnetic resonance (EPR) and NEXAFS analyses. According to the EPR spectra of Fig. 3a, the *g* value (3.0) of RuCo DSAC can be ascribed to an unpaired






Fig. 3 Evidence of charge transfer. (a) EPR spectra, (b) and (c) NEXAFS results: (b) Co L-edge and (c) N K-edge. (d–f) Electronic function location (EFL) for Ru and Co atoms on (d) graphitic N, (e) pyridinic N and (f) pyrrolic N species. (g and h) Charge density differences over (g) RuCo DSAC and (h) RuCo DSAC@N₂. (i) Charge variation during N₂ adsorption on RuCo DSAC and Co SAC samples.

electron in the $3d_{x^2-y^2}$ orbital of Co^{II} and Ru^{III}.⁴⁹ In comparison with Co SAC, the value shift in g value and the shape broaden asymmetrically for RuCo DSAC, indicative of a dipolar broadening due to electron–electron interaction between atomically dispersed Ru and Co, and the phenomenon supports the idea of charge transfer,⁵⁰ in agreement with the observation of Co K-edge NEXAFS results (Fig. 3b). It is to be noted that there is no EPR signal of Ru/N–C because of no obvious electron transfers between the Ru and N atoms. The Co L-edge NEXAFS over RuCo DSAC and Co SAC can be fitted into L2 and L3 sub-bands (Fig. 3b), matching well with the transition from $2p_{1/2}$ and $2p_{3/2}$ levels to the vacant d band,^{51,52} respectively. Compared with Co SAC, the absorption Co L-edge of RuCo DSAC shifts towards lower excitation energy by 0.6 eV. Meanwhile, the Co L-edge intensity of RuCo DSAC is lower than that of Co SAC (Fig. 3b), implying that the former has higher occupancy of Co 3d electrons. It is to be noted that the extent of electron transfer is dependent on the nature of surface unoccupied Co 3d charge, which could be semi-quantitatively calculated on the basis of the Co L-edge NEXAFS spectra (Fig. S14†), using the calculation method of Mattheiss and Dietz (see the ESI†).⁵³ The relative number of unoccupied Co 3d charge (Kh_T) in RuCo DSAC (14.7) is higher than that of Co SAC (11.2). The much higher unpaired Co 3d charge of RuCo DSAC indicates the higher feasibility of d electron donation from Co to the unoccupied Ru 3d t_{2g} (feature L2) and e_g (feature L3) states in the RuCo DSAC case.³⁶

Owing to the fact that the total electron yield (TEY) is highly surface sensitive, we collected the N K-edge NEXAFS spectra of RuCo DSAC, Co SAC and Ru/N–C to gain insight into the direction of electron transfer (Fig. 3c). Over RuCo DSAC in the range of 397–402 eV, the characteristic π^* peaks at 397.5 (peak a), 398.6 (peak b) and 401.2 (peak c) eV can be assigned to pyridinic, pyrrolic and graphitic nitrogen species, respectively.^{54,55} The presence of the π^* peak is attributed to N

coordination that involves electron transfer from N to the coordinated metal atom. Based on DFT calculation results including the electron localization function (ELF) (Fig. 3d–f), charge density differences (Fig. 3g and h), and Bader charges (Fig. 3i), it can be confirmed that there is charge transfer from the N atom of g-C₃N₄ to the Co atom, with loss of negative charge in the former while gain of negative charge in the latter. Then, the Co atom enriched with an electron acts as a bridge to facilitate the transfer of electrons from Co 3d orbitals to the Ru atom.

The extent of electron transfer from Co to Ru is dependent on the nature of the N species involved in the interaction. The chunk in ELF mapping (Fig. 3d–f) demonstrates the electron interaction between Co and Ru, and that the involvement of pyrrolic N species is the strongest (a greener chunk represents weaker electron interaction). The transferred electron density from the nitrogen species to Co and then to Ru follows the order pyrrolic N \gg graphitic N > pyridinic N species (Table S4†). Taking together the N K-edge NEXAFS results (Fig. 3c), because of the absence of the a peak over Ru/N–C, it is deduced that Ru does not coordinate with pyrrolic N. In a previous study of ours, it was confirmed that single cobalt atoms can anchor and get stabilized on pyrrolic N species.⁵⁶ Then, Co acts as a bridge to facilitate electron transfer from g-C₃N₄ through pyrrolic N and Co to the surface Ru atom. Consequently, there is a decrease of N₂ adsorption energy, and the N₂ molecule adsorbed on Ru shows a negative charge of $-0.39 e^-$ (Fig. 3i). As a site for N₂ adsorption, the electron-enriched Ru atom readily donates electrons to the antibonding π^* orbitals of adsorbed N₂, promoting N₂ activation *via* the weakening of the N≡N triple bond.

The electron release and/or donation behaviors of RuCo could influence the nature of N₂ adsorption and activation, while the binding and desorption energies of N-containing intermediates are closely related with the d-band centers. Therefore, we investigated the d-band center of the RuCo DSAC surface by ultraviolet photoemission spectroscopy (UPS) and projected density of states (PDOS) calculation. The UPS spectrum (Fig. 4a) shows that RuCo DSAC has a d-band width narrower than that of bulk Co and Ru foil.⁵⁷ Also, the d-band width of RuCo DSAC is obviously narrower than that of traditional RuCo alloy, as revealed in Fig. S15 (for more details see the ESI†). These results strongly suggest that the d bands of Co and Ru in RuCo DSAC are narrow, which is further implied by the results of PDOS calculation (Fig. 4b–e). For RuCo DSAC, the PDOS of Co over RuCo DSAC (Fig. 4c) significantly shifts towards the Fermi level in comparison with that of bulk Co (Fig. 4b), and the corresponding d-band center of Co shifts from -1.30 eV for bulk Co to -1.65 eV for RuCo DSAC (Table S5†). Also, the shift of the d-band center of Co is obviously more than that of Ru. In comparison with bulk Co (Fig. 4g), the PDOS (Fig. 4h) of RuCo DSAC shows that the e_g and t_{2g} states of Co in RuCo DSAC are almost degenerate, suggesting almost overlapping t_{2g} and e_g PDOS, and there is a nearly uniform coordination field for the Co 3d states. These results imply that the electronic structure of the Co 3d state in RuCo DSAC resembles that of a “free-Co atom”.³⁹ It is expected that such unique






Fig. 4 UPS and PDOS results. (a) UPS spectrum. Calculated s, p, and d-bands over (b) Co bulk, (c) Co in RuCo DSAC, (d) Ru bulk and (e) Ru in RuCo DSAC. (f) Spin density of RuCo DSAC. (g and h) t_{2g} and e_g for (g) Co bulk, (h) Co over RuCo DSAC and (i) Ru over RuCo DSAC.

electronic structure could promote desorption of N-containing intermediates, and thus have a beneficial influence on low-temperature NH_3 synthesis.

NH_3 synthesis performance

The catalytic performances of the C_3N_4 support and as-synthesized samples for NH_3 synthesis were evaluated in a 25% N_2 -75% H_2 feed at a WHSV of 60 000 $\text{mL g}^{-1} \text{h}^{-1}$ as a function of reaction temperature. Obviously, there is only insignificant NH_3 production over the C_3N_4 support within the test temperature range, which is less than 0.04 $\text{mmol}_{\text{NH}_3} \text{g}_{\text{cat}}^{-1} \text{h}^{-1}$ even at 400 °C. Meanwhile, the NH_3 synthesis rates over the

three samples in the range of 200–400 °C differ significantly (Fig. 5a). The addition of Ru to Co SAC significantly enhances the NH_3 synthesis rate (Fig. 5a), and the rate of RuCo DSAC is much higher than that of the monometallic Ru and Co catalysts. For example, the NH_3 synthesis rate over RuCo DSAC at 200 °C is 1.24 $\text{mmol}_{\text{NH}_3} \text{g}_{\text{cat}}^{-1} \text{h}^{-1}$, which is 8.2-fold that of monometallic Co SAC (0.15 $\text{mmol}_{\text{NH}_3} \text{g}_{\text{cat}}^{-1} \text{h}^{-1}$). However, there is hardly any activity over Ru/N-C below 350 °C. Also, the RuCo DSAC outperforms the Cs-promoted Ru/C catalyst, which is one of the most active NH_3 synthesis catalysts, by 13.6 times at 200 °C (Table S6†). At 400 °C, the NH_3 synthesis rate over RuCo DSAC is 11.20 $\text{mmol}_{\text{NH}_3} \text{g}_{\text{cat}}^{-1} \text{h}^{-1}$, which is 2.6-fold and 7.5-fold that of monometallic Co SAC (4.20 $\text{mmol}_{\text{NH}_3} \text{g}_{\text{cat}}^{-1} \text{h}^{-1}$) and monometallic Ru/N-C (1.49 $\text{mmol}_{\text{NH}_3} \text{g}_{\text{cat}}^{-1} \text{h}^{-1}$) catalysts, respectively. It is noteworthy that the outlet CH_4 concentration over RuCo DSAC is negligibly low (Fig. S16†) upon the NH_3 synthesis at 400 °C for 25 h under 1 MPa, suggesting that under the adopted conditions the RuCo DSAC is highly stable. Moreover, because the Brunauer–Emmett–Teller (BET) surface areas of Ru/N-C (88 $\text{m}^2 \text{g}^{-1}$) and RuCo DSAC (189 $\text{m}^2 \text{g}^{-1}$) as determined by N_2 adsorption measurements at 77 K (Fig. S17†) are significantly different (Table S1†), we obtained the surface-area-normalized NH_3 synthesis rates and made a comparison (Fig. S18†). An NH_3 synthesis rate of $6.36 \times 10^{-6} \text{ mmol m}^{-2} \text{ s}^{-1}$ was acquired at 350 °C on RuCo DSAC, while that over monometallic Ru/N-C is negligible. To find out whether the N species of the Ru–Co catalyst could be involved in NH_3 synthesis, we exposed the Ru–Co catalyst to 75% H_2/Ar at 400 °C and 1 MPa, and the cumulative amount of NH_3 as a function of time is provided in Fig. S19.† It can be seen that the NH_3 synthesis rate first increases to peak at 60 min, and then decreases sharply with time prolonging under a 75% H_2/Ar atmosphere. The NH_3 synthesis rate is lower than 0.1 $\text{mmol}_{\text{NH}_3} \text{g}_{\text{cat}}^{-1} \text{h}^{-1}$ after 250 min. To further confirm that the NH_3 produced mainly




Fig. 5 Catalytic performances. (a and b) NH_3 synthesis performances: (a) NH_3 synthesis rate at different temperatures and 1 MPa, and (b) NH_3 synthesis rate of selected Ru and/or Co catalysts for NH_3 synthesis at 400 °C and 1 MPa. (c) Time course of NH_3 synthesis rate over the RuCo DSAC sample at 350 °C and 1 MPa. (d) Arrhenius plots. (e and f) Reaction orders: (e) N_2 reaction order and (f) H_2 reaction order at 400 °C and 1 MPa.



originates from the catalytic synthesis of N_2 gas rather than the nitrogen source of N-doped carbon support, the NH_3 synthesis rate of RuCo DSAC has also been measured at 400 °C and 1 MPa using the feed gas of 75% H_2 -25% $15N_2$, instead of 25% N_2 -75% H_2 . Our studies show that the NH_3 synthesis rate in the presence of 75% H_2 -25% $15N_2$ ($10.59 \text{ mmol}_{NH_3} \text{ g}_{cat}^{-1} \text{ h}^{-1}$) is slightly lower than that of 75% H_2 -25% N_2 ($11.20 \text{ mmol}_{NH_3} \text{ g}_{cat}^{-1} \text{ h}^{-1}$) at 400 °C and 1 MPa (Fig. S20†), showing that the NH_3 produced mainly originates from the catalytic synthesis of N_2 - H_2 mixed gases. The H_2 -TPD-MS experiment was also carried out (Fig. S21†). The signal of $m/z = 17$ is very close to the baseline, showing that the production of ammonia can be ignored. However, a very weak signal of $m/z = 32$ can be discerned, indicating that there are only tiny amounts of dynamic N in the catalyst that can be reacted with hydrogen.

In addition, the NH_3 synthesis rate over RuCo DSAC at 400 °C exhibits an approximately linear increase from 11.20 to 20.39 $\text{mmol}_{NH_3} \text{ g}_{cat}^{-1} \text{ h}^{-1}$ when the pressure is raised from 1.0 to 5.0 MPa (Fig. S22†). The catalytic performance of RuCo DSAC at such pressure range should permit convenient eHB operation on a large scale. To further reveal the unique intrinsic catalytic activity, we calculated the turnover frequency (TOF). It is well known that Ru and Co entities are both active for NH_3 synthesis, and therefore it is difficult to differentiate the catalytic contribution of the two. Herein, TOF_M was calculated (more details are provided in the Experimental section) to express catalytic activity on a per-M-active-site basis. Interestingly, TOF_{Ru} and TOF_{Co} over RuCo DSAC reach 0.016 s^{-1} and $6.7 \times 10^{-3} \text{ s}^{-1}$ (Fig. S23†), respectively, at 400 °C, which is 10.7-fold that of monometallic Ru/N-C and 5.8-fold that of Co SAC. Therefore, it is reasonable to attribute the effective formation of NH_3 under mild conditions to strong synergism between the dual atomically dispersed Ru and Co active centers.

Previous studies have shown that the addition of a proper promoter to Ru or Co-based catalysts could promote NH_3 synthesis.^{58,59} In the present work, we studied the effect of adding Ba into the best-performing RuCo DSAC (5 wt% against RuCo DSAC) on the NH_3 production rate. As displayed in Fig. 5a, the results reveal that the NH_3 synthesis rate of Ba/RuCo DSAC is (1.8–3)-fold that of the non-promoted one, depending on the reaction temperature. Surprisingly, when the temperature is 400 °C, the NH_3 synthesis rate over Ba/RuCo DSAC is $23.90 \text{ mmol}_{NH_3} \text{ g}_{cat}^{-1} \text{ h}^{-1}$. Moreover, we compared the NH_3 synthesis rates of Ba/RuCo DSAC (Table S6†) and RuCo DSAC (Fig. 5b) with those of selected Ru- and Co-based catalysts, and they are superior to those of the conventional Ru- and Co-based catalysts.

The long-term stability test of RuCo DSAC was conducted at 350 °C for 100 h, and its NH_3 synthesis rate remains almost constant after a slight decrease at the initial stage (Fig. 5c). The used RuCo DSAC was subject to TEM, HR-TEM, AC-STEM and XRD analyses. The TEM (Fig. S24a and b†) and HR-TEM images (Fig. S24c and d†) of the used RuCo DSAC show no Ru or Co NPs, and the AC-STEM images (Fig. S25a and b†) of the used RuCo DSAC still show a large number of individual bright dots, revealing the retention of the Ru and Co atomic dispersion even after a stability test of 100 h. The XRD patterns (Fig. S26†) of the

used Ba/RuCo DSAC and RuCo DSAC samples indicate the absence of Ru or Co phases. One characteristic peak that is related to the g- C_3N_4 phase can still be observed after the NH_3 synthesis reaction, suggesting high thermal stability of g- C_3N_4 . Meanwhile, the H_2 -TPR (Fig. S27†) profile of the C_3N_4 support shows no reduction peak below 550 °C. Also, the H_2 -TPR profile of RuCo DSAC exhibits no reduction peaks below 500 °C. In addition, the Ar-TPD-MS analysis of the as-synthesized fresh catalysts does not show any desorption or decomposition peak below 600 °C (Fig. S28†). These results undoubtedly confirm that the C_3N_4 support and RuCo DSAC are stable under the reaction for NH_3 synthesis. Evidently, the RuCo DSAC is not only active but also stable under the adopted mild conditions for NH_3 synthesis.

Kinetic studies

The kinetic parameters of NH_3 synthesis such as activation energies and reaction orders over the as-synthesized catalysts are depicted in Fig. 5d–f. The apparent activation energy (E_a) of NH_3 synthesis over the as-synthesized catalysts was derived from the Arrhenius plots depicted in Fig. 5d. The E_a is determined to be 58 kJ mol^{-1} for RuCo DSAC, which is lower than that of Ru/N-C (79 kJ mol^{-1}) or Co SAC (65 kJ mol^{-1}). The E_a value of RuCo DSAC is similar to that of previously reported Ru-loaded electrides (50 – 60 kJ mol^{-1})^{11,26,60} and hydrides (49 – 60 kJ mol^{-1}).^{6,25} Moreover, experiments to determine the reaction orders of N_2 and H_2 over the as-prepared catalysts were performed. For traditional Ru-based catalysts in NH_3 synthesis, the N_2 reaction order is between 0.8 and 1.0 while that of H_2 is negative in value. The former suggests that N_2 dissociation is the rate-limiting step, while the latter indicates the poisoning effect of H_2 on Ru.^{61,62} It was observed that the reaction orders of N_2 (Fig. 5e), H_2 (Fig. 5f) and NH_3 (Fig. S29†) over RuCo DSAC are 0.37, 0.61 and -1.07 , respectively. The results of the positive H_2 reaction order indicate that the effect of H_2 poisoning on the Ru sites is circumvented over RuCo DSAC. The reaction orders for the RuCo DSAC are different from those for Ru/N-C and Co SAC, consistent with the presence of the dual single-atom active centers that may create the cooperativity that favors N_2 adsorption/activation and H_2 dissociative adsorption occurring separately on different sites. In this regard, we performed surface-science characterization and theoretical modeling to acquire insights into the roles of the dual single-atom active centers at the atomic level for NH_3 synthesis.

Discussion

A suite of elaborate characterization and DFT calculations were employed to explore the adsorption and activation behavior of N_2 and H_2 . In H_2 -TPD (Fig. S30a†) and N_2 -TPD (Fig. S30b†) studies, the desorption temperatures of H_2 and N_2 over RuCo DSAC and monometallic Ru/N-C as well as Co SAC are slightly different, but they are all below 200 °C, suggesting that the adsorption and activation of H_2 and N_2 are not difficult on these catalysts. For Ru/N-C and Co SAC, there is detection of mass signals of $m/z = 32$ (Fig. S31a†) and $m/z = 17$ (Fig. S31b†),



respectively, corresponding to the desorption of *N_2H_4 and *NH_3 species accumulated on the catalyst surface during NH_3 synthesis, and desorption of these species can still be observed even at 700 °C. It is to be noted that the signal intensity of $m/z = 32$ and $m/z = 17$ over the used RuCo DSAC is much lower, the former getting close to the baseline at *ca.* 200 °C, while the latter can be ignored even at 50 °C. This observation is in good agreement with the UV-vis DRS experiment (for more details see the ESI†) and DFT calculation reported below, displaying that the energies needed for *N_2H_4 and *NH_3 desorption over RuCo DSAC are only 0.2 eV and 0.1 eV, respectively. These results strongly suggest facile desorption of surface *N_2H_4 and *NH_3 intermediates from RuCo DSAC. Moreover, an *in situ* DRIFTS deuterium labeling investigation was performed to determine the reactivity of intermediate species for NH_3 synthesis. For the fresh C_3N_4 sample, there is detection of bands at 1637, 1406, 1316, and 1236 cm^{-1} which are characteristic of the CN heterocycle.⁶³ After C_3N_4 was exposed to a mixture of 25% N_2 –75% D_2 or 25% N_2 –75% H_2 at 400 °C for 30 min, there is no detection of any additional IR peaks in comparison with fresh C_3N_4 (Fig. S32†). The observation is in accord with the fact that C_3N_4 shows almost no catalytic activity. After Ru/N–C and Co SAC were exposed to a mixture of 25% N_2 –75% D_2 at 400 °C, there is detection of bands at 2394 cm^{-1} that are related to the $\nu_5(B_u)N_2D_2$ transition or N–D torsion modes within the ND_2 or N_2D_4 fragments,^{64–68} and the band intensity significantly increases with prolonged exposure from 1 to 30 min, further indicating the accumulation of *N_2D_x species on the surface of Ru/N–C (Fig. S31c†) and Co SAC (Fig. S31d†). These results indicate that the surface Ru or Co active sites are partially covered by the intermediate species, which can only desorb at high temperature (>400 °C). Interestingly, such a troublesome scenario is virtually eliminated in the case of RuCo DSAC (Fig. S33†). Specifically, the band at 2394 cm^{-1} is attributed to the $\nu_5(B_u)N_2D_2$ transition or N–D torsion modes within the ND_2 or N_2D_4 fragments. Two bands located at 2574 cm^{-1} and 1545 cm^{-1} can also be discerned, which can be attributed to *trans*-HNND and NN stretching in N_2D_x species, respectively.⁶⁶ The formation of *trans*-HNND may be a result of NND interaction with the surface H left behind in the pretreatment of the catalyst in 10% H_2/Ar at 400 °C for 2 h. These results further confirm the existence of N_2D_x species. The UV-vis DRS spectra (Fig. S34†) show that the main intermediate species of RuCo DSAC in NH_3 synthesis is N_2H_4 , and the peak intensity of the N_2H_4 compound decreases with the increase of reaction temperature.

From these observations and analyses, it follows that *N_2H_4 is likely the main intermediates under the reaction conditions, and the presence of *N_2H_4 also suggests that the activation of N_2 is more facile *via* hydrogenation to NNH than *via* direct dissociation of $N\equiv N$ triple bonds. Moreover, the accumulation of species such as *N_2H_4 and *NH_3 on Ru/N–C and Co SAC will block the sites for further activation of N_2 and H_2 , thus hindering NH_3 formation at low temperature over both samples. For RuCo DSAC, the immediate implications of the involvement of the dual single-atom active sites with narrow d-band centers are the interruption of the scaling correlation

between the adsorption/activation of N_2 and desorption of surface N-containing species, and hence the superior low-temperature NH_3 synthesis performance upon the decoupling of scaling correlation.

To illustrate the role of dual single-atom active centers and to deduce the possible reaction pathway over RuCo DSAC, DFT calculations were performed and the calculation results are shown in Fig. 6a–e and S35–S39.† From these results, the Ru atom is the dominant site for N_2 adsorption, due to the higher adsorption energy (–0.56 eV, Fig. S36a†) on Ru than on the Co atom (–0.43 eV, Fig. S36c†). Notably, the adsorption of a N_2 molecule on a single Ru atom tends to adopt the side-on coordination (Fig. S36a and c†), due to symmetry matching between the π^* orbitals of N_2 and 3d orbitals of Ru. Then, the adsorbed N_2 on the Ru site is more facile to be hydrogenated than direct N_2 dissociation. The energy for directly breaking the $N\equiv N$ bond under the active state on the Ru atom is still up to 2.53 eV, indicating difficult direct dissociation. In general, the cleavage of $N\equiv N$ triple bond needs at least two adjacent Ru atoms.^{69,70} The absence of Ru–Ru ensembles as revealed in EXAFS and AC-STEM analyses over RuCo DSAC implies that the direct dissociation of N_2 is unlikely, which is also consistent with the determination of *N_2H_4 desorption in Ar-TPD measurements (Fig. S31a†). Then, the N_2 molecule on the Ru site needs to be activated before the occurrence of hydrogenation (Fig. 6a). The Co site as a bridge accelerates the electron transfer from g- C_3N_4 to the Ru site, which promotes the donation of 3d electrons from the Ru atom to the π^* orbitals of N_2 and weakening of $N\equiv N$ bonds as mentioned earlier.⁶⁹

On the other hand, the dissociative adsorption of H_2 over the Co active center of RuCo DSAC is efficient (Fig. S37a–d†), where H_2 adsorption is thermodynamically exothermic throughout the entire reaction pathway. Also, the Co atom plays an important role in gathering and activating H_2 for N_2 hydrogenation at the Ru atom. The above analysis indicates that the adsorption and dissociation of N_2 and that of H_2 occur at different active sites. The significant advantage of RuCo DSAC is that the competitive adsorption of N_2 and H_2 can be effectively avoided, as reflected by the positive reaction order of H_2 (Fig. 5f). Comparing the charge density differences (Fig. 6c–e) of N_2 and H_2 co-adsorption on RuCo DSAC (Fig. 6c) and Co or Ru SAC (Fig. 6d and e) sites, electron filling of π^* orbitals decreases with the drop of electron density on N_2 , clearly showing that the existence of H_2 poses a negative effect on N_2 activation, and it is more obvious in the latter (charge of N_2 shift more than 0.7 e^-). H_2 -TPD results (Fig. S30a†) show that the amount of H_2 desorption from RuCo DSAC (1.40 mmol g^{-1}) is much higher than the Co coverage, therefore it is reasonable to deduce that there is a spillover of H atoms from the Co atom to Ru active centers.

What follows is the attack of activated N_2 on Ru by spillover H atoms to generate N_2H_x species. Note that when the N–N bond becomes weak enough the cleavage of the N–N bond and the generation of *NH_2 species may take place. Fig. 6a displays the energy profiles of the full pathway for NH_3 production (from state i to xxi), and the pathways of N–N bond dissociation (states iii, iv, ix, and xi) and hydrogenation (from state ii to xiii) for






Fig. 6 DFT calculations of NH_3 synthesis on the RuCo DSAC. (a) Reaction pathway on the RuCo DSAC. (b–e) Charge density differences over nitrogen adsorbed on (b and c) Ru–Co DSAC, (d) Ru SAC and (e) Co SAC sites with the adsorption of H_2 . The red area shows an increase of electron density while the blue area indicates a decrease. (f) NH_3 generation on different adsorption sites of RuCo DSAC. (g) Schematic of the NH_3 synthesis reaction pathway over RuCo DSAC.

comparison. The first hydrogenation step for the generation of *N_2H (from state ii to iii) needs to overcome an energy barrier of 1.56 eV, much lower than that of direct N_2 breakage (2.53 eV). Upon the formation of *N_2H , the N=N bonds are further

weakened as indicated by the charge density differences shown in Fig. 6b. Both the hydrogenation of *N_2H species and the cleavage of the N–N bond of *N_2H_x species are much easier than the direct dissociation of N_2 , demonstrating the unique



function of H atoms for N₂ activation (Fig. 6a). Notably, the entire pathway of N₂ hydrogenation is in the presence of excessive adsorbed H atoms, and the Ru site with spillover H atoms can keep the adsorption of N₂ activated throughout as illustrated in Fig. 6a.

Subsequently, the *N₂H species is further hydrogenated to *N₂H₂, *N₂H₃ and *N₂H₄ intermediates with energy barriers in the range of 0.11–1.20 eV. With the stepwise hydrogenation of *N₂H_x species, the energy barrier for breaking the N–N bond keeps falling (2.53 eV for *N₂, 2.08 eV for *N₂H, 2.06 eV for *N₂H₂, 0.94 eV for *N₂H₃ and 0.83 eV for *N₂H₄), showing that N₂ hydrogenation is an effective way to sharply weaken the N–N bond. Finally, the indirect cleavage of the *H₂N–NH₂ bond takes place together with the formation of two *NH₂ species. It is noteworthy that the activation energy for *N₂H₃ dissociation is also lower than that for *N₂H₃ hydrogenation, thus the cleavage of the N–N bond of *N₂H₃ is also possible for the generation of the *NH₂ intermediate. Then, the transfer of the *NH₂ species from the Ru atom to the Co atom is favorable because of the crowding at the Ru site. With active H atoms available on the Co site, further hydrogenation of *NH₂ to *NH₃ on the Co site is ready to occur. Compared to the Ru site, the Co site is more favorable for NH₃ desorption, releasing the first NH₃ molecule to the gas phase. It is remarkable that the reaction energies for the generation of the second NH₃ on the Co sites and Ru sites are similar (–1.32 eV and –1.34 eV, Fig. 6f), while the desorption energy of *NH₃ on the Co atom (0.10 eV) is much lower than that on the Ru atom (0.66 eV), indicating that NH₃ desorption from the Co sites is more preferred in comparison to that from the Ru site.

Overall, two significant findings have been acquired in the present study. First, with the Ru and Co dual single-atom active site, a new route for NH₃ synthesis is made possible (Fig. 6g), which is essentially different from those of previously reported monometallic Co or Ru catalysts as well as traditional alloy clusters.^{71,72} According to the results of experimental and theoretical investigations, electron release and/or donation between Ru and Co atoms could promote N₂ adsorption and activation as well as hydrogenation, while the narrow d-band centers of Ru and Co allow desorption of surface intermediate species such as *N₂H₄ and *NH₃ at low temperature. Therefore, the superior performance of RuCo DSAC in NH₃ synthesis under mild conditions is attributed to the cooperativity of dual single-atom Ru and Co centers. Second, NH₃ synthesis over RuCo DSAC proceeds *via* the associative pathway, similar to that occurring in the cases of metal single atoms,^{24,57} clusters,^{23,36} Li-promoted Ru catalysts and Co₃Mo₃N.^{73,74} Over the RuCo DSAC in N₂ activation to NH₃, the step with the highest kinetic barrier is the hydrogenation of N₂ to generate *N₂H on the Ru site, which is the rate-determining step. After considering the entropy contribution, the entropy contribution in the RDS step is only 0.007 eV. Notably, it was experimentally observed that *N₂H₄ is the major detected species, which can be ascribed to the fact that the stepwise hydrogenation of *N₂H to *N₂H₂, *N₂H₃ and *N₂H₄ has much lower energy barriers than that of the “*N₂ + H → *N₂H” or “*N₂H₄ → *2NH₂” process. The net outcome is

a steady state of *N₂H₄ presence and hence easy detection of N₂H₄.

Conclusions

To summarize, we have successfully synthesized a RuCo DSAC, in which there is integration of Ru atoms onto an atomically dispersed cobalt surface in the form of RuCo dual single-atom sites on g-C₃N₄. We found that the RuCo DSAC structure could effectively facilitate electron transfer from pyrrolic N to the surface Ru atom, which acts as an efficient site for N₂ adsorption and activation as well as hydrogenation. The RuCo DSAC with narrow d-band centers favors desorption of surface intermediate species such as *N₂H₄ and *NH₃ at low temperature. The cooperativity of Ru and Co centers decouples the scaling relation by providing separated sites discretely for N₂ activation and *N₂H/*NH₃ desorption, respectively. The NH₃ synthesis rate over the RuCo DSAC is about 2.6–8.2-fold that of monometallic Co at 200–400 °C and 6.2–7.5-fold that of Ru at 350–400 °C. It is anticipated that the cooperative roles of Ru and Co disclosed in the present study shed light on the design of dual single-atom active sites that could enable energy-efficient NH₃ synthesis under mild conditions.

Experimental section

Chemicals and materials

Melamine and ruthenium nitrosyl nitrate solution were purchased from Shanghai Aladdin Biochemical Technology Co., Ltd. Cobalt phthalocyanine (CoPc) and cyanuric acid were from Shanghai Macklin Biochemical Co., Ltd. Dimethyl sulfoxide (DMSO) and ethanol were from Sinopharm Chemical Reagent Co., Ltd. High purity argon (99.9999%) and nitrogen (99.9999%) gases were supplied by Linde Industrial Gases. The N₂–H₂, H₂–Ar and CO–He mixed gases of designated proportions were also from Linde Industrial Gases. D₂ (99.999%) was purchased from Cambridge Isotope Laboratories, Inc.

Catalyst preparation

Preparation of RuCo DSAC. Typically, 0.35 mL of ruthenium nitrosyl nitrate solution, 0.201 g of CoPc and 0.50 g of melamine were mixed and dissolved in 40 mL of DMSO under ultrasonic treatment for 10 min to obtain a blue solution. Meanwhile, 0.51 g of cyanuric acid was dissolved in 10 mL of DMSO under ultrasonic treatment for 10 min to give a transparent solution. Then, the transparent solution was slowly added into the blue solution and the resulting mixture was stirred at room temperature for 10 min. After filtration and washing with 150 mL deionized water and 100 mL ethanol, the solid precursor was obtained. Finally, the obtained precursor was dried at 60 °C for 12 h, followed by thermal polymerization at 600 °C under an Ar atmosphere for 8 h in a tube furnace at a ramp rate of 1 °C min^{–1}.

The synthetic procedure of Ru/N–C and Co/N–C SAC was similar to that of RuCo DSAC, except for the absence of CoPc and ruthenium nitrosyl nitrate solution, respectively.



For the Ba-promoted RuCo DSAC, 5 wt% Ba(NO₃)₂ was added to the RuCo DSAC *via* an incipient wetness impregnation (IWI) method.

NH₃ synthesis performance

Before the evaluation of catalytic performance for NH₃ synthesis, the samples (0.15 g, diluted with quartz powder in a 1 : 8 volumetric ratio) were reduced in a flow of 25% N₂-75% H₂ at 400 °C for 4 h. Under the conditions for NH₃ synthesis in a 25% N₂-75% H₂ mixture at a WHSV of 60 000 mL g⁻¹ h⁻¹ and a given pressure, the outlet NH₃ concentrations were measured using a known amount of diluted H₂SO₄ solution (1 mol L⁻¹) and analyzed by ion chromatography (Thermo Scientific, DIONEX, ICS-600). Finally, the NH₃ synthesis rates were acquired based on the outlet NH₃ concentrations. Turnover frequency (TOF_M, M = Co or Ru) was acquired by dividing the NH₃ synthesis rate by the total number of Co or Ru atoms.

Experiments for methanation determination

For the determination of the possibility of methanation, 0.2 g of RuCo DSAC was exposed to a flow of 25% N₂-75% H₂ at 400 °C at a WHSV of 60 000 mL g⁻¹ h⁻¹ under a pressure of 1 MPa. The outlet CH₄ concentration was detected using an online GC-mass spectrometer (GCMS-QP2010 SE).

Measurement of N₂ and H₂ reaction orders

The sample (0.25 g) was first exposed to a mixture of 10% H₂/Ar at 350 °C for 4 h before the introduction of N₂ or H₂. All measurements were conducted at 350 °C at a designated pressure, and the outlet NH₃ was measured using a known amount of diluted H₂SO₄ solution (0.02 mol L⁻¹) and analyzed by ion chromatography (Thermo Scientific, DIONEX, ICS-600). Finally, the NH₃ synthesis rates based on the outlet NH₃ concentrations were calculated. The constituent gases in volume fraction of the reactant feed (N₂, H₂, Ar) were as follows in volume fraction (12.5%, 37.5%, 50%), (35%, 37.5%, 27.5%), (45%, 37.5%, 17.5%) and (55%, 37.5%, 7.5%) for the N₂ reaction order and (25%, 62.5%, 12.5%), (25%, 50%, 25%), (25%, 25%, 50%) and (25%, 12.5%, 62.5%) for the H₂ reaction order.

Materials characterization

Powder X-ray diffraction (XRD) was performed (at 40 kV and 40 mA) on a Panalytical X'Pert Pro diffractometer using Cu-K α radiation ($\lambda = 0.1789$ nm). The Brunauer-Emmett-Teller (BET) surface area and Barrett-Joyner-Halenda (BJH) pore size distribution were measured by N₂ adsorption-desorption on a Micromeritics ASAP 2020 instrument at -196 °C after the sample was degassed at 120 °C for 2 h in a vacuum. Inductively coupled plasma atomic emission spectroscopy (ICP-AES) analysis was conducted using an Ultima 2 spectrometer. Scanning electron microscopy (SEM) was performed on a Hitachi Model S-4800 microscope operated at 5 kV. Transmission electron microscopy (TEM) and high-resolution transmission electron microscopy (HR-TEM) were conducted on a JEM-2010 microscope.

Aberration-corrected high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM) was conducted on a JEOL JEM-ARM 200 F instrument equipped with a CEOS probe corrector, with a guaranteed resolution of 0.08 nm.

Ultraviolet photoelectron spectroscopy (UPS)

UPS measurements were conducted using a helium resonance lamp which provided He I ($h\nu = 21.2$ eV) and He II ($h\nu = 40.8$ eV) photons (1 eV = 0.16 aJ).

H₂ temperature-programmed reduction (H₂-TPR)

A H₂-TPR experiment was performed on an AutoChem II 2920 equipped with a thermal conductivity detector (TCD), in which samples were first pretreated under Ar flow (30 mL min⁻¹) at 400 °C for 0.5 h. After cooling to room temperature, the temperature was increased from RT to 800 °C at 5 °C min⁻¹ in a gas flow of 10 vol% H₂/Ar (30 mL min⁻¹).

H₂ temperature-programmed desorption (H₂-TPD-MS) experiment

First, the fresh RuCo DSAC was pretreated with H₂ at 400 °C for 2 h and then cooled to room temperature, and then temperature-programmed desorption was performed. In this process, the signals of $m/z = 32$ and 17 were collected using the mass spectrometer.

NEXAFS measurements

The N K-edge and Co L-edge near-edge X-ray absorption fine structure spectroscopy (NEXAFS) measurements were performed at the BL12B beamline of the Beijing Synchrotron Radiation Facility. The bending magnet was connected to the beamline, which is equipped with three gratings covering photon energies from 100 to 1000 eV with an energy resolution of *ca.* 0.2 eV. The NEXAFS signal was detected at room temperature using the surface-sensitive total electron yield (TEY) mode by recording the sample drain current. The resolving power of the grating was typically $E/\Delta E = 1000$, and the photon flux was 1×10^{-10} photons per second.

XANES and EXAFS measurements

X-ray absorption near-edge structure (XANES) and extended X-ray absorption fine structure (EXAFS) analyses were conducted at the 1W2B beamline of the Beijing Synchrotron Radiation Facility. Before the test, the sample was firstly treated with 25% N₂-75% H₂ at 400 °C for 2 h. The Co and Ru K-edge spectra of the samples and reference samples in transmission mode were measured at room temperature. A Si(111) double-crystal monochromator was used to abate the harmonic content of the monochromatic beam.

XPS measurements and Ar⁺ etching

X-ray photoelectron spectroscopy (XPS) measurements were performed on an ESCALAB 250Xi photoelectron spectrometer (Thermo Fisher Scientific) equipped with a monochromatic Al-



$K\alpha$ source ($K_{\alpha} = 1486.6$ eV) and a charge neutralizer. The XPS binding energy was calibrated against the C 1s peak at 284.6 eV of adventitious carbon. Prior to *in situ* measurements, XPS spectra of the fresh sample were acquired. Argon ion etching was carried out with the MAGCIS dual mode ion source, which can be operated as a monatomic argon ion source, and the monatomic mode at an energy of 1000 eV was selected.

In situ DRIFTS deuterium labeling experiments

An *in situ* DRIFTS D_2 -isotopic labeling experiment was performed using a Nicolet Nexus FT-IR spectrometer. The sample was first reduced in a 10% H_2/Ar mixture at 400 °C for 4 h. After collecting the background spectrum, the catalyst was exposed to a 25% N_2 -75% D_2 mixture at 400 °C for different periods.

Temperature-programmed Ar desorption

An Ar-TPD-MS experiment was conducted by mass spectrometry using an Autochem 2920 instrument. After the activity test of NH_3 synthesis, 50 mg of the used catalyst was flushed with Ar before being heated to 700 °C at a rate of 10 °C min^{-1} . The $m/z = 32$ (N_2H_4) and 17 (NH_3) signals during desorption were recorded.

UV-vis absorption spectra

A UV-vis DRS experiment was performed using a PerkinElmer Lambda 750s UV-visible spectrometer. We installed a flask trap containing sulfuric acid solution and *para*-(dimethylamino) benzaldehyde at the exit of the reactor during the NH_3 synthesis reaction. The collected solution was then used for the UV-vis measurements.

Electron-paramagnetic resonance (EPR) measurements

EPR measurements were carried out on an E500 spectrometer (Bruker-BioSpin) with a 100 kHz magnetic field in the X band at RT.

Computational method

First-principles calculations based on spin-polarized density functional theory (DFT) were performed using the Vienna *Ab initio* Simulation Package (VASP)⁷⁵ and the projected augmented wave (PAW) method.⁷⁶ The generalized gradient approximation with the Perdew–Burke–Ernzerhof (PBE) exchange–correlation functional was employed.⁷⁷ The kinetic energy cutoff in plane-wave expansion was set as 400 eV with $2 \times 2 \times 1$ Monkhorst–Pack grids involved in the Brillouin zone integration.⁷⁸ The convergence thresholds of the energy change and the maximum force for the structural optimizations were set as 10^{-5} eV and 0.02 eV \AA^{-1} , respectively. The energies of species were corrected with zero-point energies and the thermodynamic data of gas-phase molecules were obtained from NIST (<http://cccbdb.nist.gov/>). The catalyst models were constructed on C_3N_4 with loaded metal atoms, adopting a vacuum space thickness of 15 Å. Four different structures were built and optimized as depicted in the ESI.† The energy of $Co@C_3N_4$ and $Ru@C_3N_4$ SACs was set as the reference and the most stable

structure with the lowest energy was used for further calculations.

Conflicts of interest

The authors declare no competing financial interest.

Acknowledgements

The work was supported by the National Natural Science Foundation of China (NSFC grant no. 21825801 to L. J., 21972019 to X. W. and 91645203 to J. L.). The support of the Guangdong Provincial Key Laboratory of Catalysis (No. 2020B121201002) is also acknowledged. The calculations were performed using the supercomputers at Southern University of Science and Technology (SUSTech).

Notes and references

- 1 S. L. Foster, S. I. P. Bakovic, R. D. Duda, S. Maheshwari, R. D. Milton, S. D. Minter, M. J. Janik, J. N. Renner and L. F. Greenlee, *Nat. Catal.*, 2018, **1**, 490–500.
- 2 R. Schlögl, *Angew. Chem., Int. Ed.*, 2003, **42**, 2004–2008.
- 3 M. Kitano, Y. Inoue, M. Sasase, K. Kishida, Y. Kobayashi, K. Nishiyama, T. Tada, S. Kawamura, T. Yokoyama, M. Hara and H. Hosono, *Angew. Chem., Int. Ed.*, 2018, **57**, 2648–2652.
- 4 J. Zhang, X. Tian, M. Liu, H. Guo, J. Zhou, Q. Fang, Z. Liu, Q. Wu and J. Lou, *J. Am. Chem. Soc.*, 2019, **141**, 19269–19275.
- 5 F. Chang, Y. Guan, X. Chang, J. Guo, P. Wang, W. Gao, G. Wu, J. Zheng, X. Li and P. Chen, *J. Am. Chem. Soc.*, 2018, **140**, 14799–14806.
- 6 Y. Kobayashi, Y. Tang, T. Kageyama, H. Yamashita, N. Masuda, S. Hosokawa and H. Kageyama, *J. Am. Chem. Soc.*, 2017, **139**, 18240–18246.
- 7 A. Valera-Medina, H. Xiao, M. Owen-Jones, W. I. F. David and P. J. Bowen, *Prog. Energy Combust. Sci.*, 2018, **69**, 63–102.
- 8 T. M. Gür, *Energy Environ. Sci.*, 2018, **11**, 2696–2767.
- 9 S. Zhou, X. Yang, X. Xu, S. X. Dou, Y. Du and J. Zhao, *J. Am. Chem. Soc.*, 2020, **142**, 308–317.
- 10 J. Qian, Q. An, A. Fortunelli, R. J. Nielsen and W. A. Goddard III, *J. Am. Chem. Soc.*, 2018, **140**, 6288–6297.
- 11 M. Kitano, Y. Inoue, Y. Yamazaki, F. Hayashi, S. Kanbara, S. Matsuishi, T. Yokoyama, S. W. Kim, M. Hara and H. Hosono, *Nat. Chem.*, 2012, **4**, 934–940.
- 12 Q. An, M. McDonald, A. Fortunelli and W. A. Goddard III, *J. Am. Chem. Soc.*, 2020, **142**, 8223–8232.
- 13 C. Smith, A. K. Hill and L. Torrente-Murciano, *Energy Environ. Sci.*, 2020, **13**, 331–344.
- 14 W. Gao, J. Guo, P. Wang, Q. Wang, F. Chang, Q. Pei, W. Zhang, L. Liu and P. Chen, *Nat. Energy*, 2018, **12**, 1067–1075.
- 15 J. Zheng, F. Liao, S. Wu, G. Jones, T. Y. Chen, J. Fellowes, T. Sudmeier, I. J. McPherson, I. Wilkinson and S. C. E. Tsang, *Angew. Chem., Int. Ed.*, 2019, **58**, 17335–17341.
- 16 M. M. Rodriguez, E. Bill, W. W. Brennessel and P. L. Holland, *Science*, 2011, **334**, 780–783.



- 17 Z. J. Zhao, S. Liu, S. Zha, D. Cheng, F. Studt, G. Henkelman and J. Gong, *Nat. Rev. Mater.*, 2019, **4**, 792–804.
- 18 J. K. Nørskov, T. Bligaard, J. Rossmeisl and C. H. Christensen, *Nat. Chem.*, 2009, **1**, 37–46.
- 19 Y. Lu, J. Li, T. Tada, Y. Toda, S. Ueda, T. Yokoyama, M. Kitano and H. Hosono, *J. Am. Chem. Soc.*, 2016, **138**, 3970–3973.
- 20 J. Kammert, J. Moon, Y. Cheng, L. Daemen, S. Irle, V. Fung, J. Liu, K. Page, X. Ma, V. Phaneuf, J. Tong, A. J. Ramirez-Cuesta and Z. Wu, *J. Am. Chem. Soc.*, 2020, **142**, 7655–7667.
- 21 S. Laassiri, C. D. Zeinalipour-Yazdi, C. R. A. Catlow and J. S. J. Hargreaves, *Appl. Catal., B*, 2018, **223**, 60–66.
- 22 P. Wang, H. Xie, J. Guo, Z. Zhao, X. Kong, W. Gao, F. Chang, T. He, G. Wu, M. Chen, L. Jiang and P. Chen, *Angew. Chem., Int. Ed.*, 2017, **56**, 8716–8720.
- 23 J. Liu, X. Ma, Y. Li, Y. Wang, H. Xiao and J. Li, *Nat. Commun.*, 2018, **9**, 1610.
- 24 J. Qiu, J. Hu, J. Lan, L. Wang, G. Fu, R. Xiao, B. Ge and J. Jiang, *Chem. Mater.*, 2019, **31**, 9413–9421.
- 25 P. Wang, F. Chang, W. Gao, J. Guo, G. Wu, T. He and P. Chen, *Nat. Chem.*, 2017, **9**, 64–70.
- 26 M. Kitano, S. Kanbara, Y. Inoue, N. Kuganathan, P. V. Sushko, T. Yokoyama, M. Hara and H. Hosono, *Nat. Commun.*, 2015, **6**, 6731.
- 27 S. Wu, Y. Peng, T. Chen, J. Mo, A. Large, I. Mcpherson, H. Chou, I. Wilkinson, F. Venturini, D. Grinter, P. F. Escorihuela, G. Held and S. C. E. Tsang, *ACS Catal.*, 2020, **10**, 5614–5622.
- 28 S. Wu, Y. Peng, T. Chen, J. Mo, A. Large, I. Mcpherson, H. Chou, I. Wilkinson, F. Venturini, D. Grinter, P. F. Escorihuela, G. Held and S. C. E. Tsang, *Chem. Phys. Lett.*, 2014, **598**, 108–112.
- 29 F. Abild-Pedersen, J. Greeley, F. Studt, J. Rossmeisl, T. R. Munter, P. G. Moses, E. Skulason, T. Bligaard and J. K. Nørskov, *Phys. Rev. Lett.*, 2007, **99**, 16105.
- 30 M. T. Greiner, T. E. Jones, S. Beeg, L. Zwiener, M. Scherzer, F. Girgsdies, S. Piccinin, M. Armbruster, A. Knop-Gericke and R. Schlogl, *Nat. Chem.*, 2018, **10**, 1008–1015.
- 31 F. Studt, F. Abild-Pedersen, T. Bligaard, R. Z. Sorensen, C. H. Christensen and J. K. Nørskov, *Science*, 2008, **320**, 1320–1322.
- 32 B. Qiao, A. Wang, X. Yang, L. F. Allard, Z. Jiang, Y. Cui, J. Liu, J. Li and T. Zhang, *Nat. Chem.*, 2011, **3**, 634.
- 33 X.-F. Yang, A. Wang, B. Qiao, J. Li, J. Liu and T. Zhang, *Acc. Chem. Res.*, 2013, **46**, 1740–1748.
- 34 A. Wang, J. Li and T. Zhang, *Nat. Rev. Chem.*, 2018, **2**, 65–81.
- 35 X. Ma, J. Liu, H. Xiao and J. Li, *J. Am. Chem. Soc.*, 2018, **140**, 46–49.
- 36 H. Thirumalai and J. R. Kitchin, *Top. Catal.*, 2018, **61**, 462–474.
- 37 M. T. Darby, M. Stamatakis, A. Michaelides and E. C. H. Sykes, *J. Phys. Chem. Lett.*, 2018, **9**, 5636–5646.
- 38 J. Liu, Y. Tang, Y. Wang, T. Zhang and J. Li, *Natl. Sci. Rev.*, 2018, **5**, 638–641.
- 39 G. Giannakakis, M. Flytzani-Stephanopoulos and E. C. H. Sykes, *Acc. Chem. Res.*, 2019, **52**, 237–247.
- 40 G. Sun, Z. Zhao, R. Mu, S. Zha, L. Li, S. Chen, K. Zang, J. Luo, Z. Li, S. C. Purdy, A. J. Kropf, J. T. Miller, L. Zeng and J. Gong, *Nat. Commun.*, 2018, **9**, 4454.
- 41 Y. Tang, S. Zhao, B. Long, J.-C. Liu and J. Li, *J. Phys. Chem. C*, 2016, **120**, 17514–17526.
- 42 L. Wang, W. Zhang, S. Wang, Z. Gao, Z. Luo, X. Wang, R. Zeng, A. Li, H. Li, M. Wang, X. Zheng, J. Zhu, W. Zhang, C. Ma, R. Si and J. Zeng, *Nat. Commun.*, 2016, **7**, 14036.
- 43 X. Zhang, G. Cui, H. Feng, L. Chen, H. Wang, B. Wang, X. Zhang, L. Zheng, S. Hong and M. Wei, *Nat. Commun.*, 2019, **10**, 5812.
- 44 L. Zhang, J. M. T. A. Fischer, Y. Jia, X. Yan, W. Xu, X. Wang, J. Chen, D. Yang, H. Liu, L. Zhuang, M. Hanke, D. Searles, K. Huang, S. Feng, C. Brown and X. Yao, *J. Am. Chem. Soc.*, 2018, **140**, 10757–10763.
- 45 J. Ge, D. He, W. Chen, H. Ju, H. Zhang, T. Chao, X. Wang, R. You, Y. Lin, Y. Wang, J. Zhu, H. Li, B. Xiao, W. Huang, Y. Wu, X. Hong and Y. Li, *J. Am. Chem. Soc.*, 2016, **138**, 13850–13853.
- 46 J. Wang, W. Liu, G. Luo, Z. Li, C. Zhao, H. Zhang, M. Zhu, Q. Xu, X. Wang, C. Zhao, Y. Qu, Z. Yang, T. Yao, Y. Li, Y. Lin, Y. Wu and Y. Li, *Energy Environ. Sci.*, 2018, **11**, 3375–3379.
- 47 P. Li, M. Wang, X. Duan, L. Zheng, X. Cheng, Y. Zhang, Y. Kuang, Y. Li, Q. Ma, Z. Feng, W. Liu and X. Sun, *Nat. Commun.*, 2019, **10**, 1711.
- 48 Y. Pan, R. Lin, Y. Chen, S. Liu, W. Zhu, X. Cao, W. Chen, K. Wu, W. Cheong, Y. Wang, L. Zheng, J. Luo, Y. Lin, Y. Liu, C. Liu, J. Li, Q. Lu, X. Chen, D. Wang, Q. Peng, C. Chen and Y. Li, *J. Am. Chem. Soc.*, 2018, **140**, 4218–4221.
- 49 Bo. Hu, A. B. Getsoian, N. M. Schweitzer, U. Das, H. Kim, J. Niklas, O. Poluektov, L. A. Curtiss, P. C. Stair, J. T. Miller and A. S. Hock, *J. Catal.*, 2015, **322**, 24–37.
- 50 S. Nong, W. Dong, J. Yin, B. Dong, Y. Lu, X. Yuan, X. Wang, K. Bu, M. Chen, S. Jiang, L.-M. Liu, M. Sui and F. Huang, *J. Am. Chem. Soc.*, 2018, **140**, 5719–5727.
- 51 J. Wang, W. Liu, G. Luo, Z. Li, C. Zhao, H. Zhang, M. Zhu, Q. Xu, X. Wang, C. Zhao, Y. Qu, Z. Yang, T. Yao, Y. Li, Y. Lin, Y. Wu and Y. Li, *Energy Environ. Sci.*, 2018, **11**, 3375–3379.
- 52 J. Zhou, X. Zhou, R. Li, X. Sun, Z. Ding, J. Cutler and T. K. Sham, *Chem. Phys. Lett.*, 2009, **474**, 320–324.
- 53 L. Mattheiss and R. Dietz, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1980, **22**, 1663–1676.
- 54 Y. Liang, H. Wang, J. Zhou, Y. Li, J. Wang, T. Regier and H. Dai, *J. Am. Chem. Soc.*, 2012, **134**, 3517–3523.
- 55 D. N. Kelly, C. P. Schwartz, J. S. Uejio, A. M. Duffin, A. H. England and R. J. Saykally, *J. Chem. Phys.*, 2010, **133**, 101103.
- 56 X. Wang, X. Peng, W. Chen, G. Liu, A. Zheng, L. Zheng, J. Ni, C. T. Au and L. Jiang, *Nat. Commun.*, 2020, **11**, 653.
- 57 M. Xiao, L. Gao, Y. Wang, X. Wang, J. Zhu, Z. Jin, C. Liu, H. Chen, G. Li, J. Ge, Q. He, Z. Wu, Z. Chen and W. Xing, *J. Am. Chem. Soc.*, 2019, **141**, 19800–19806.
- 58 W. Raróg-Pilecka, E. Miskiewicz, L. Kepinski, Z. Kaszukur, K. Kielar and Z. Kowalczyk, *J. Catal.*, 2007, **249**, 24–33.



- 59 Z. You, K. Inazu, K. Aika and T. Baba, *J. Catal.*, 2007, **251**, 321–331.
- 60 M. Hattori, T. Mori, T. Arai, Y. Inoue, M. Sasase, T. Tada, M. Kitano, T. Yokoyama, M. Hara and H. Hosono, *ACS Catal.*, 2018, **8**, 10977–10984.
- 61 K.-I. Aika, *Catal. Today*, 2017, **286**, 14–20.
- 62 F. Rosowski, A. Hornung, O. Hinrichsen, D. Herein, M. Muhler and G. Ertl, *Appl. Catal., A*, 1997, **151**, 443–460.
- 63 L. Lu, X. Xu, K. An, Y. Wang and F. Shi, *ACS Sustainable Chem. Eng.*, 2018, **6**, 11869–11876.
- 64 M. Carlotti, J. W. C. Johns and A. Trombetti, *Can. J. Phys.*, 1974, **52**, 340–344.
- 65 F. Hegelund, H. Bürger and O. Polanz, *J. Mol. Spectrosc.*, 1996, **179**, 142–149.
- 66 J. Demaison, F. Hegelund and H. Bürger, *J. Mol. Struct.*, 1997, **413–414**, 447–456.
- 67 K. Rosengren and G. C. Pimentel, *J. Chem. Phys.*, 1965, **43**, 507–516.
- 68 D. E. Milligan and M. E. Jacox, *J. Chem. Phys.*, 1965, **43**, 4487.
- 69 H. Duan, J. Liu, M. Xu, Y. Zhao, X. Ma, J. Dong, X. Zheng, J. Zheng, C. S. Allen, M. Danaie, Y. Peng, T. Issariyakul, D. Chen, A. I. Kirkland, J. C. Buffet, J. Li, S. C. E. Tsang and E. M. O'Hare, *Nat. Catal.*, 2019, **2**, 1078–1087.
- 70 K. Honkala, A. Hellman, I. N. Remediakis, A. Logadottir, A. Carlsson, S. Dahl, C. H. Christensen and J. K. Nørskov, *Science*, 2005, **307**, 555–558.
- 71 C. Fernandez, N. Bion, E. M. Gaigneaux, D. Duprez and P. Ruiz, *J. Catal.*, 2016, **344**, 16–28.
- 72 S. Hagen, R. Barfod, R. Fehrmann, C. J. H. Jacobsen, H. T. Teunissen and I. Chorkendorff, *J. Catal.*, 2003, **214**, 327–335.
- 73 C. D. Zeinalipour-Yazdi, J. S. J. Hargreaves and C. R. A. Catlow, *J. Phys. Chem. C*, 2018, **122**, 6078–6082.
- 74 C. D. Zeinalipour-Yazdi, J. S. J. Hargreaves, S. Laassiri and C. R. A. Catlow, *Phys. Chem. Chem. Phys.*, 2018, **20**, 21803–21808.
- 75 G. Kresse and J. Hafner, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1993, **47**, 558.
- 76 P. E. Blöchl, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1994, **50**, 17953.
- 77 J. P. Perdew, K. Burke and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, **77**, 3865–3868.
- 78 H. J. Monkhorst and J. D. Pack, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1976, **13**, 5188–5192.

