



Unveiling the performance and prospects of metallic chiral nanoantennas with optical gain *via* an additive laser printing scheme from research teams led by Prof. Yaoyu Cao at Institute of Photonics Technology in Jinan University, Guangzhou, China.

Great chiral fluorescence from the optical duality of silver nanostructures enabled by 3D laser printing

Chiral nanoantennas heavily resorting to artificial structures that manifest efficient radiation and tightly confined light-matter interactions simultaneously remain alluring but dauntingly challenging for the 3D laser printing technique. In this work, a photoreduction-based 3D additive laser printing scheme for producing unprecedented stereo-chiral-gain silver nanoantennas is developed to achieve a record-high luminescence anisotropic factor. This inspiring method holds great promise for enriching optical links at the nanoscale.

As featured in:



See Xiaoxuan Xu, Yaoyu Cao *et al.*, *Mater. Horiz.*, 2020, 7, 3201.

Cite this: *Mater. Horiz.*, 2020,
7, 3201Received 28th July 2020,
Accepted 23rd September 2020

DOI: 10.1039/d0mh01207f

rsc.li/materials-horizons

Great chiral fluorescence from the optical duality of silver nanostructures enabled by 3D laser printing†

Hongjing Wen,[†] Shichao Song,[†] Fei Xie,^a Bin Wang,^b Jian Xu,^a Ziwei Feng,^a Shiyu Wu,^a Jing Han,^a Bai-Ou Guan,^a Xiaoxuan Xu,^{*b} Yaoyu Cao^{†*} and Xiangping Li[†]

Featured by prominent flexibility and fidelity in producing sophisticated stereoscopic structures transdimensionally, three-dimensional (3D) laser printing techniques have vastly extended the toolkit for delivering diverse functional devices. Yet chiral nanoemitters heavily resorting to artificial structures that manifest efficient emission and tightly confined light–matter interactions simultaneously remain alluring but dauntingly challenging for this technique at this moment. In this study, we assert that the chiral photoluminescence is implemented from silver nanostructures with optical duality in one go *via* a two-fold three-dimensional laser printing scheme. Such laser printing protocol allows the highly desired duality by simultaneously producing uniformly distributed fluorescent silver nanoclusters and aggregated plasmonic silver nanoparticles to tightly confine chiral interactions at the nanoscale. A helical emitter of 550 nm helix-diameter as fabricated has seen a record-high luminescence anisotropic factor with the absolute value up to 0.58, which is two orders of magnitude greater than fluorescent chiral silver clusters. This method holds great promise for future versatile applications in chiroptical nanodevices.

New concepts

The exceptional capabilities of 3D laser printing techniques have been continuously explored to extend the toolkits for advancing transdimensional photonic and optoelectronic applications in the past few decades. Nevertheless, the limitation arising from the lack of multifunctional materials and the corresponding printing protocols greatly bars the efforts in the subwavelength scale for elaborately delivering the chiral regulation of electromagnetic waves over the short-wavelength bands, which is highly desirable in the fields of frontier optics and photonics. Chiral nanoemitters heavily resorting to artificial structures that manifest efficient emission and tightly confined light–matter interactions simultaneously remain alluring but dauntingly challenging for this technique at this moment. In this work, we have developed a 3D laser printing technique for realizing unprecedented stereo chiral luminescent silver nanostructures comprising plasmonic nanostructures and emissive clusters in one go. The as-fabricated helical silver emitter of 550 nm helix-diameter, as a representative of 3D chiral structure family, has seen a record-high luminescence anisotropic factor with an absolute value up to 0.58, which is two orders of magnitude greater than that of fluorescent chiral silver clusters (10^{-3}). We believe that our work could greatly inspire the advance of 3D laser printing approach for exploring its applications in producing functional nanodevices.

Introduction

Chiral nanoemitters currently have attracted drastically increasing research interests for their abilities to underpin cutting-edge applications spanning the advanced optical and photonics,^{1–4,41,42} such as manipulating energy transfer among topologically configured photonic systems⁵ and controlling communication with spin information.⁶ Such functionalities

and applications intensely rely upon implementing strong light–matter interactions in the nanoscale,^{7,41} which requires extremely confined interacting space to achieve demanding chiral luminescence that is not always applicable to the natural chiral materials with a common anisotropic factor at the level of 0.001.⁸ Consequently, the advance of such chiral light sources preferably seeks artificial materials generated through a deterministic nanofabrication technique with considerable printing freedom in favor of offering efficient emitters and tight light–matter interaction confinement at the same time.

3D laser printing, as one of the most important and fascinating technological innovations,^{9–12} has proven to be an indispensable micro/nanofabrication technique to shape multiple materials by employing their intrinsic optical nonlinear responses,^{13–17} such as multi-photon photoredox (MPP)¹⁶ and

^a Guangdong Provincial Key Laboratory of Optical Fiber Sensing and Communications, Institute of Photonics Technology, Jinan University, Guangzhou 511443, P. R. China. E-mail: yaoyucao@jnu.edu.cn

^b The Key Laboratory of Weak-Light Nonlinear Photonics, Ministry of Education, School of Physics, Nankai University, Tianjin 300071, China. E-mail: xuxx@nankai.edu.cn

† Electronic supplementary information (ESI) available. See DOI: 10.1039/d0mh01207f

‡ These authors contributed equally to this work.





Fig. 1 Stereo silver nanocluster-based structure via 3D laser printing. (a) Schematic of the formation of fluorescent silver helical structures in the agarose matrix via 532 nm femtosecond laser printing and the chiral fluorescence generated from the silver structures excited by 532 nm continuous wave laser. (b) Dark-field images of a 3-turn helical structure with a radius of 5 μm and a pitch distance of 5 μm in the agarose matrix. The top view of the helix is on the left, while the side view is on the right. The scale bars are 10 μm . (c) Confocal fluorescence images corresponding to the 3D spiral structure of (b) in top view (left) and side view (right) at a certain focal plane. The scale bars are 10 μm . (d) TEM image of a single silver dot composed of SNCs (with sizes below 10 nm) and SNPs (with sizes over 10 nm) with different sizes in agarose. The scale bar is 100 nm. (e) Size statistical distribution of SNCs inside the silver dotted structure in (d). The nano-entities with an intense fluorescence effect below 2 nm account for ~20% out of the total SNCs. (f) Standard deviation (SD) and the root mean square (RMS) of the scattering intensity variance along the silver line fabricated in agarose with different mass-to-volume ratios (with details shown in Fig. S3 (ESI[†])). Insets are the corresponding dark-field images of the lines as printed. The scale bars are 10 μm .

To investigate the optical irradiation properties of the luminescent silver structures, silver dots composed of SNCs and SNPs as elementary building blocks were adopted. As shown in Fig. 2a, the luminescence and scattering intensities of a dotted structure produced with the 532 nm-fs laser beam of power (P_{1p}) 1 mW were measured *in situ* with the spectral range of 600 nm to 800 nm (red line). The emission lifetime of the silver dot was gauged below 0.5 ns, which implies a fast luminescence process (Fig. S4a (ESI[†])). The bright fluorescence occurring in the whole printing region reveals that the SNCs spread over the silver dot as shown in the fluorescence image captured *via* the confocal microscope. In the meantime, the scattering spectrum of the silver dot shows the light can be strongly scattered in the same range as a result of surface plasmon effect. The measured scattering peak virtually coincides with the simulation result, where the broader scattering band in the experimental spectrum can be attributed to the effective silver dot composed of varisized SNPs that can be seen in Fig. S4(b and c) (ESI[†]). Moreover, the polarization of fluorescence from the silver dot was also studied. A linear polarizer (LP) was added into the fluorescence-collecting system to manifest the polarization characteristic of emission through changing the analyzer angles.³⁶ To avoid the disturbance from the analyzing system, rhodamine 6G (R6G) with unpolarized fluorescence was introduced into the agarose matrix system as a reference. Consequently, the relative intensity variation of fluorescence (V_f) emitted from the silver dot with the analyzer rotation angle

θ can be defined as $V_f = (I_{\text{dot}}(\theta) - I_{\text{R6G}}(\theta)) / (I_{\text{dot}}(0^\circ) - I_{\text{R6G}}(0^\circ))$, where $I_{\text{dot}}(0^\circ)$ and $I_{\text{R6G}}(0^\circ)$ are the fluorescence intensities of the dot and R6G reference with an initial polarization analyzer angle of 0° , respectively. $I_{\text{dot}}(\theta)$ and $I_{\text{R6G}}(\theta)$ denote the fluorescence intensities of the dot and R6G reference with a rotated angle θ , respectively. As depicted in Fig. 2b, the virtually unchanged V_f value at around 1 measured at ~630 nm represents that the structure possesses an unpolarized electromagnetic response, indicating the silver nanocluster fluorescence of non-polarizing characteristic (the measured fluorescence spectra with different polarization angles θ can be seen in Fig. S5 (ESI[†])).

To further explore the fluorescence and scattering intensity with regard to the size of a single pixel as fabricated, a series of dotted structures were realized with different laser powers P_{1p} ranging from 0.6 to 1.4 mW. In addition, the feature sizes of the silver dotted structure measured using the dark-field images can be found in the range from 380 nm to 830 nm. In effect, the fluorescence intensities were positively correlated with the dimensions of silver dots, as shown in Fig. 2c. In the meantime, we can find that the variance in scattering intensity follows a similar tendency, indicating a reinforced ability of light manipulation with the increase in the printing power, where the measured dark-field images of silver dotted structures corresponding to fluorescence spectra are presented in Fig. S6a (ESI[†]). As shown in Fig. 2d, a virtually linear relevance between the fluorescence intensity, the scattering intensity and





Fig. 2 Optical duality of silver nanopatterns. (a) Scattering spectrum and fluorescence spectrum excited by 532 nm CW laser of a silver dotted structure. The insets depict the dark-field image and the confocal fluorescence microscopic image of the silver dotted structure fabricated in agarose with a laser power (P_{ip}) of 1 mW and an exposure time of 80 ms. The scale bars are 2 μm . (b) Relative variation V of fluorescence intensity emitted from silver dots with different polarization angles. (c) Fluorescence emission spectra of silver nanodots printed with different P_{ip} (from 0.6 to 1.4 mW). (d) The corresponding fluorescence intensity (red ball scatters) at a wavelength of 630 nm (black dot line in (c)), the scattering intensity (green ball scatters) and dot diameter (blue ball scatters) under different printing powers. (e) Dark-field image of a 4×4 silver dot lattice with a printing power of 1 mW and exposure time of 80 ms for each dot. In addition, the corresponding scattering intensities along the two white dashed line marks are depicted in the nether figures, which show favorable uniformity of the lattice structure. The scale bar is 5 μm . (f) Fluorescence image of the 4×4 silver dot lattice; the corresponding fluorescence intensities of the two white marked areas are depicted in the nether figures, which show reasonable uniformity of photoluminescence. The scale bar is 5 μm .

the silver dot size can be found with the increase in the printing power from 0.8 mW to 1.2 mW, revealing a single photon characteristic for the generation of silver dots as well as the corresponding optical properties in the particular printing power region. Fluorescence emission spectra of a silver nanodot in the agarose matrix obtained with CW laser excitation can be seen in Fig. S6(b and c) (ESI[†]). In addition, the accumulation rate of the dot size and the related optical responses can be found to be slowing down with the further increase in printing laser power, which may arise from the depletion of the silver salts in the fabrication region.

In order to investigate the uniformity of the fluorescence and the surface plasmon-based scattering from silver structures, we fabricated a 4×4 silver dot lattice with a laser power of 1 mW and an exposure time of 80 ms. The corresponding dark-field image (Fig. 2e) and fluorescence image (Fig. 2f) measured by confocal fluorescence microscopy reveal a homogenous feature for the dot

pattern. As it mainly comes from the SNPs, the steady high scattering intensity from dot to dot reflects the glorious uniformity between each dot unit and a powerful light manipulation ability of assembled SNPs as produced resorting to the surface plasmon effect, which can be obtained through the dashed mark line 1 and 2. Additionally, the uniformity of fluorescence is estimated through the dashed mark line 3 and 4, and emission intensity fluctuations are less than 10%, which further confirms the favorable homogeneity of SNCs as produced simultaneously.

Harnessing multiphoton absorption characteristic, silver ions in the agarose hydrogel are photoreduced to form spatially resolved arbitrary silver structures by the computer-aided printing with assembled SNPs and SNCs for effective light manipulation and fluorescence, respectively. In the meantime, the fluorescence intensity of the demonstrated structures can also be regulated by adjusting fabrication parameters such as the laser intensity. As shown in Fig. 3a, dark-field image (left upper green graphs) and confocal fluorescence microscope image (left nether red graphs) of the 2D dolphin pattern confirm the feasibility of the steady patterning. Besides, the right side shows the variation of scattering intensity and fluorescence intensity from the patterns depending on the printing power corresponding to the subregions in the left side. In this case, the fluorescence of the corresponding pattern was excited by 532 nm CW laser with an excitation power of 200 μW so as to ensure that the fluorescence will not be ablated. With a multilayer point-by-point



Fig. 3 Structuring and patterning of 3D fluorescent silver nanocluster-based structures. (a) A dolphin pattern fabricated by three different printing powers (1.0 mW for the subregion I, 0.8 mW for the subregion II and 0.6 mW for the subregion III). In the left side, the left upper green graphs (false-color images) are the dark-field scattering image and the left nether red ones are the confocal fluorescence image. The right side shows the variation in the scattering intensity and fluorescence intensity from the patterns depending on the printing power corresponding to the subregions in the left side. (b) Dark-field (left) and fluorescence (right) images of three layers of silver patterns printed with a layer spacing of 5 μm . (c) Dark-field (left) and fluorescence (right) images of the 3D cubic structure fabricated in the agarose matrix on side view and top view, respectively. (d) Fluorescence intensity distribution tracing the white short lines marked at eight positions on the top of the cubic structure in (c). All the scale bars are 5 μm .



printing approach, a homogeneous layered structure with an interlayer spacing of 5 μm can be explicitly fabricated and resolved in both dark-field images and confocal fluorescence microscope images, presented in Fig. 3b. Furthermore, by implementing the 3D vector scanning scheme, a cubic scaffold with continuous sides can be readily achieved, as shown in Fig. 3c. The corresponding dark-field images in the perspective view and top view indicate the high continuity of the stereo structure as a result of accurately assembling SNPs as supposed. The confocal images in perspective view are acquired by stitching layer records (the detailed layer-by-layer scanning images can be found in Fig. S7 (ESI[†])). While a bit fluctuation of confocal fluorescence intensity in the perspective view comes from the image mosaic errors during the multilayer scanning, the fluorescence intensity distribution in the top view reveals reasonable uniformity for the same layer. Herein, eight lines are marked in the top view of the confocal fluorescence image to verify the uniformity of the 3D continuous structures. As shown in Fig. 3d, the fluctuation of fluorescence peak intensity is less than 10%, indicating considerable continuity and uniformity of the stereo structure, which is in favor of achieving versatile fluorescent nanostructures.

As a representative three-dimensional structure with chirality, the helix possesses vast polarization manipulation capabilities for realizing circular dichroism (CD) and optical rotations.^{4,37} Taking full advantages of the chirality of the helical structure and photoluminescence of SNPs, fluorescence chiral structures can be realized in agarose by utilizing the joint characteristics from the inherent structural uniqueness of SNP spiral lines and fluorescence spectrum attribute of SNPs. To characterize the chirality of the helical structure, CD is defined as the difference between the fluorescence intensity with left-handed circular polarization (LCP) and right-handed circular polarization (RCP), which can be calculated using the following equation:

$$\text{CD} = T_{\text{LCP}}(\lambda) - T_{\text{RCP}}(\lambda) \quad (1)$$

where λ is the light wavelength and T denotes the transmitted fluorescence light intensity. In addition, the anisotropic factor g defined as the differential circular transmitted fluorescence intensity normalized by the average fluorescence intensity is given as follows:³⁸

$$g = \frac{2(T_{\text{LCP}}(\lambda) - T_{\text{RCP}}(\lambda))}{T_{\text{LCP}}(\lambda) + T_{\text{RCP}}(\lambda)} \quad (2)$$



Fig. 4 Chiral fluorescence of silver nanocluster-based helical nanostructures. (a) Top-view scattering image of a silver nanocluster-based helical structure ($n = 2$) captured using a confocal microscope. (b) Linewidth of the spiral line for the helical structure (obtained at the FWHM) was measured as ~ 200 nm in the horizontal orientation. (c) Scattering image of the side view of the helical structure. (d) Linewidth of the spiral line of the helical structure was measured as ~ 340 nm in the longitudinal direction. (e) Experimental results of CD for single silver nanoemitters with the helix turns ranging from 2 to 4. The insets are the scattering images of the cross-section profiles. (f) Calculated CD values normalized to the emission intensity of the dipoles used in the FDTD method (the inset is the simulation model set up with the same parameters obtained in experiments: helix diameter of 550 nm and pitch of 550 nm in the z direction). The corresponding models in calculations are shown in insets, and the green plane represents the measured plane with respect to (e). (g) Measured anisotropic factor spectra for single silver nanoemitters obtained with different turns of the helical structures. All the scale bars are 1 μm .



Agarose gel

First, 0.7 g of agarose powder (gel strength (1%) 750 g cm⁻², gelling temperature 37 ± 1.5 °C) and 10 mL ultrapure water were mixed in a glass container and heated until a clear viscous agarose gel solution was formed. Then, hot gel was spread in a Petri dish at 25 °C for 10 min until the gel solidified completely. Approximately 1 mm-thick square gel used for the subsequent laser printing was obtained from the gel block using a sharp blade.

DSI aqueous solution

Silver nitrate (0.35 g) was weighed into a glass container and an appropriate amount of ultrapure water (1.03 mL) was added to obtain a 2 mol L⁻¹ silver nitrate solution. Ammonium solution (NH₃: 25%) was gradually added to the silver nitrate solution using a pipette. When the mixed solution of silver nitrate and ammonia solution became clear and transparent (ammonia water needs ~550 µL), the dropwise addition was stopped to obtain the DSI aqueous solution with a silver ion concentration of 1.31 mol L⁻¹. Then, the configured DSI aqueous solution was diluted to obtain a DSI aqueous solution with a concentration of 0.1 mol L⁻¹ for the experiment.

NDSS solution: 0.1 mol L⁻¹ NDSS solution was prepared from 0.07 g of NDSS solid powder (CAS: 30377-07-2, > 98.0%) and 2.70 mL of ultrapure water.

Three-dimensional laser printing

The printing setup was employed to produce transdimensional structures in a fluorescent silver nanocluster/agarose matrix system. A femtosecond laser beam from a 532 nm-wavelength femtosecond laser with a repetition of 80 MHz and a pulse width of 210 fs was directly focused onto the sample mounted on a piezo multi-axis stage (P-563.3CD, Physik Instrumente (PI) GmbH & Co. KG) through an oil immersion objective lens (×100, NA = 1.4, Olympus). The size of the focused printing laser spot was estimated at ~232 nm, calculated by the formula, spot size $D = 0.61 \times \lambda_{ip}/NA$, where λ_{ip} is the wavelength of laser beam.³⁹

Helix structure printing method: Firstly, morphological parameters of expected chiral fluorescent structures were converted into the discrete 3D coordinates through a layer slicing method. Then, the converted coordinates were invoked by the controlling system of the piezo multi-axis stage (P-563.3CD, Physik Instrumente (PI) GmbH & Co. KG). After that, the 3D helix structures can be produced via the point-by-point laser printing strategy.

A CCD camera (MER-132-43U3M-L, Daheng) that provides a bright-field microscope-magnified view in the visible light region was used to monitor the fabrication process of the structures.

Measurement of fluorescence spectra

The sample was immersed in deionized water to remove the excess silver ions and then placed on the piezo multi-axis stage to be precisely positioned using a CCD camera. Therefore, the fluorescence emission spectra were recorded *in situ* from the

silver nanostructures using the spectrometer (SR-ASZ-0103, Andor). By introducing the combination of a linear polarizer and an achromatic quarter-wave plate (200–800 nm), the received fluorescence spectra can be separated into left-handed and right-handed circular polarization.⁴⁰ Herein, in order to distinguish the dark-field images, the fluorescence images were processed with pseudo color according to their raw values.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This research was supported by National Key R&D Program of China (Grant No. 2018YFB1107200), National Natural Science Foundation of China (NSFC) (Grant No. 61605061, 61875073), Guangdong Provincial Innovation and Entrepreneurship Project (Grant No. 2016ZT06D081), Natural Science Foundation of Guangdong Province (Grant No. 2016A030313088), Guangdong Basic and Applied Basic Research Foundation (Grant No. 2019A1515110385) and the Fundamental Research Funds for the Central Universities.

Notes and references

- 1 L. Lu, J. D. Joannopoulos and M. Soljacic, *Nat. Photonics*, 2014, **8**, 821.
- 2 M. Hentschel, M. Schaferling, X. Y. Duan, H. Giessen and N. Liu, *Sci. Adv.*, 2017, **3**, e1602735.
- 3 P. Lodahl, S. Mahmoodian, S. Stobbe, A. Rauschenbeutel, P. Schneeweiss, J. Volz, H. Pichler and P. Zoller, *Nature*, 2017, **541**, 473.
- 4 Z. G. Liu, H. F. Du, J. F. Li, L. Lu, Z. Y. Li and N. X. Fang, *Sci. Adv.*, 2018, **4**, eaat4436.
- 5 M. Pu, X. Li, X. Ma, Y. Wang, Z. Zhao, C. Wang, C. Hu, P. Gao, C. Huang, H. Ren, X. Li, F. Qin, J. Yang, M. Gu, M. Hong and X. Luo, *Sci. Adv.*, 2015, **1**, e1500396.
- 6 R. Farshchi, M. Ramsteiner, J. Herfort, A. Tahraoui and H. T. Grahm, *Appl. Phys. Lett.*, 2011, **98**, 162508.
- 7 A. O. Govorov, Z. Y. Fan, P. Hernandez, J. M. Slocik and R. R. Naik, *Nano Lett.*, 2010, **10**, 1374.
- 8 Y. Luo, C. Chi, M. L. Jiang, R. P. Li, S. Zu, Y. Li and Z. Y. Fang, *Adv. Opt. Mater.*, 2017, **5**, 1700040.
- 9 A. J. Capel, R. P. Rimington, M. P. Lewis and S. D. R. Christie, *Nat. Rev. Chem.*, 2018, **2**, 422.
- 10 H. Xia, J. A. Wang, Y. Tian, Q. D. Chen, X. B. Du, Y. L. Zhang, Y. He and H. B. Sun, *Adv. Mater.*, 2010, **22**, 3204.
- 11 S. K. Saha, D. Wang, V. H. Nguyen, Y. N. Chang, J. S. Oakdale and S. C. Chen, *Science*, 2019, **366**, 105.
- 12 Y. J. Liu, H. Wang, J. F. Ho, R. C. Ng, R. J. H. Ng, V. H. Hall-Chen, E. H. H. Koay, Z. G. Dong, H. L. Liu, C. W. Qiu, J. R. Greer and J. K. W. Yang, *Nat. Commun.*, 2019, **10**, 4340.
- 13 P. I. Dietrich, M. Blaicher, I. Reuter, M. Billah, T. Hoose, A. Hofmann, C. Caer, R. Dangel, B. Offrein, U. Troppenz,



- M. Moehrle, W. Freude and C. Koos, *Nat. Photonics*, 2018, **12**, 241.
- 14 A. Camposeo, L. Persano, M. Farsari and D. Pisignano, *Adv. Opt. Mater.*, 2019, **7**, 1800419.
- 15 B. E. Kelly, I. Bhattacharya, H. Heidari, M. Shusteff, C. M. Spadaccini and H. K. Taylor, *Science*, 2019, **363**, 1075.
- 16 Y. Y. Cao, N. Takeyasu, T. Tanaka, X. M. Duan and S. Kawata, *Small*, 2009, **5**, 1144.
- 17 S. Tabrizi, Y. Y. Cao, B. P. Cumming, B. H. Jia and M. Gu, *Adv. Opt. Mater.*, 2016, **4**, 529.
- 18 P. W. Wu, W. Cheng, I. B. Martini, B. Dunn, B. J. Schwartz and E. Yablonovitch, *Adv. Mater.*, 2000, **12**, 1438.
- 19 L. Yang, D. D. Qian, C. Xin, Z. J. Hu, S. Y. Ji, D. Wu, Y. L. Hu, J. W. Li, W. H. Huang and J. R. Chu, *Opt. Lett.*, 2017, **42**, 743.
- 20 Q. Geng, D. E. Wang, P. F. Chen and S. C. Chen, *Nat. Commun.*, 2019, **10**, 2179.
- 21 Z. S. Gan, Y. Y. Cao, R. A. Evans and M. Gu, *Nat. Commun.*, 2013, **4**, 2061.
- 22 D. Oran, S. G. Rodrigues, R. X. Gao, S. Asano, M. A. Skylar-Scott, F. Chen, P. W. Tillberg, A. H. Marblestone and E. S. Boyden, *Science*, 2018, **362**, 1281.
- 23 D. W. Yee, M. L. Lifson, B. W. Edwards and J. R. Greer, *Adv. Mater.*, 2019, **31**, 1901345.
- 24 M. D. Turner, G. E. Schroder-Turk and M. Gu, *Opt. Express*, 2011, **19**, 10001.
- 25 I. Sakellari, X. H. Yin, M. L. Nesterov, K. Terzaki, A. Xomalis and M. Farsari, *Adv. Opt. Mater.*, 2017, **5**, 1700200.
- 26 P. Kunwar, J. Hassinen, G. Bautista, R. H. A. Ras and J. Toivonen, *ACS Nano*, 2014, **8**, 11165.
- 27 I. Diez and R. H. A. Ras, *Nanoscale*, 2011, **3**, 1963.
- 28 A. Mooradian, *Phys. Rev. Lett.*, 1969, **22**, 185.
- 29 J. G. Zhang, S. Q. Xu and E. Kumacheva, *Adv. Mater.*, 2005, **17**, 2336.
- 30 A. Royon, K. Bourhis, M. Bellec, G. Papon, B. Bousquet, Y. Deshayes, T. Cardinal and L. Canioni, *Adv. Mater.*, 2010, **22**, 5282.
- 31 J. P. Wilcoxon and B. L. Abrams, *Chem. Soc. Rev.*, 2006, **35**, 1162.
- 32 W. Y. Li, J. Xu, Q. B. Zhou, S. Wang, Z. W. Feng, D. J. Hu, X. P. Li and Y. Y. Cao, *Nanoscale*, 2018, **10**, 21910.
- 33 V. Amendola, O. M. Bakr and F. Stellacci, *Plasmonics*, 2010, **5**, 85.
- 34 Z. Han, X. Y. Dong, P. Luo, S. Li, Z. Y. Wang, S. Q. Zang and T. C. W. Mak, *Sci. Adv.*, 2020, **6**, eaay0107.
- 35 J. F. Zhou, M. F. Zhou and R. A. Caruso, *Langmuir*, 2006, **22**, 3332.
- 36 L. P. Liu, D. Yang, W. P. Wan, H. Yang, Q. H. Gong and Y. Li, *Nanophotonics*, 2019, **8**, 1087.
- 37 J. K. Gansel, M. Thiel, M. S. Rill, M. Decker, K. Bade, V. Saile, G. von Freymann, S. Linden and M. Wegener, *Science*, 2009, **325**, 1513.
- 38 X. T. Kong, L. K. Khorashad, Z. M. Wang and A. O. Govorov, *Nano Lett.*, 2018, **18**, 2001.
- 39 L. H. V. Wang and S. Hu, *Science*, 2012, **335**, 1458.
- 40 T. Y. Han, S. Zu, Z. W. Li, M. L. Jiang, X. Zhu and Z. Y. Fang, *Nano Lett.*, 2018, **18**, 567.
- 41 Y. L. Hu, H. W. Yuan, S. L. Liu, J. C. Ni, Z. X. Lao, C. Xin, D. Pan, Y. Y. Zhang, W. L. Zhu, J. W. Li, D. Wu and J. R. Chu, *Adv. Mater.*, 2020, **32**, 2002356.
- 42 Z. X. Lao, Y. Y. Zheng, Y. C. Dai, Y. L. Hu, J. C. Ni, S. Y. Ji, Z. Cai, Z. J. Smith, J. W. Li, L. Zhang, D. Wu and J. R. Chu, *Adv. Funct. Mater.*, 2020, **30**, 1909467.
- 43 X. J. Huang, Q. Y. Guo, D. D. Yang, X. D. Xiao, X. F. Liu, Z. G. Xia, F. J. Fan, J. R. Qiu and G. P. Dong, *Nat. Photonics*, 2020, **14**, 82.
- 44 H. A. Houck, P. Muller, M. Wegener, C. Barner-Kowollik, F. E. Du Prez and E. Blasco, *Adv. Mater.*, 2020, **32**, 2003060.

