


Cite this: *Nanoscale*, 2023, **15**, 16002

Extraordinary optical transmittance generation on Si₃N₄ membranes†

Salvatore Macis,^{a,b} Maria Chiara Paolozzi,^a Annalisa D'Arco,^a Federica Piccirilli,^c Veronica Stopponi,^d Marco Rossi,^e Fabio Moia,^f Andrea Toma^f and Stefano Lupi^{a,d}

Metamaterials are attracting increasing attention due to their ability to support novel and engineerable electromagnetic functionalities. In this paper, we investigate one of these functionalities, *i.e.* the extraordinary optical transmittance (EOT) effect based on silicon nitride (Si₃N₄) membranes patterned with a periodic lattice of micrometric holes. Here, the coupling between the incoming electromagnetic wave and a Si₃N₄ optical phonon located around 900 cm⁻¹ triggers an increase of the transmitted infrared intensity in an otherwise opaque spectral region. Different hole sizes are investigated suggesting that the mediating mechanism responsible for this phenomenon is the excitation of a phonon-polariton mode. The electric field distribution around the holes is further investigated by numerical simulations and nano-IR measurements based on a Scattering-Scanning Near Field Microscope (s-SNOM) technique, confirming the phonon-polariton origin of the EOT effect. Being membrane technologies at the core of a broad range of applications, the confinement of IR radiation at the membrane surface provides this technology platform with a novel light-matter interaction functionality.

Received 14th June 2023,
Accepted 21st September 2023

DOI: 10.1039/d3nr02834h

rsc.li/nanoscale

1. Introduction

Metamaterials are a class of artificially engineered systems exhibiting exotic electromagnetic and transport properties not available in natural materials.^{1–3} Interestingly, the electromagnetic and transport response of these media to external stimuli can be engineered at will, going beyond some of the limitations encountered when using natural materials. For these reasons, metamaterials are of particular importance in optics and photonics.^{4–8} Although less developed compared to plasmonic (electron-based) metamaterials, phononic metamaterials have been recently attracting increasing attention allowing, for instance, the control of the phonon propagation and heat transport at a microscopic level.^{9–12} Moreover, they are

employed in several applications, working as mechanical filters,¹³ beam steerers, and lenses,¹⁴ reaching a similar level of feasible applications as plasmonic metamaterials do. One of the striking advantages concerning artificial materials relies on the possibility to manipulate electromagnetic radiation at a sub-wavelength scale, looking for field concentration and enhanced optical transmission.^{15,16} Indeed, highly localized fields in the vicinity of films can be beneficial for performing sensing studies, intensively investigated in nanophotonics.^{17,18} Although plasmonics has been devoting great attention to this kind of research, drawbacks are not missing. Indeed, in metallic nanostructures, the capability to concentrate light at sub-diffraction scales is efficient at near-infrared and visible frequencies, but in the infrared and terahertz (THz) range high attenuation due to inherent material absorption is experienced.^{19–21} Even noble metals, such as silver and gold, are scarcely efficient in this spectral range, which strongly affects the realization of such applications. Although the use of unconventional materials like graphene,^{22–25} topological insulators,²⁶ and high temperature superconductors^{27,28} may mitigate this effect, an alternative way to obtain efficient field confinement and enhancement at IR frequencies consists in exploiting another kind of collective excitation: the surface phonon polariton (SPhP).²⁹ Using polar dielectric materials, a coupling between electromagnetic radiation and optical phonons at infrared frequencies can be obtained in a way similar to both propagating and localized surface plasmons in

^aDepartment of Physics, Sapienza University, Piazzale Aldo Moro 5, 00185 Rome, Italy. E-mail: salvatore.macis@uniroma1.it

^bINFN – Laboratori Nazionali di Frascati, via Enrico Fermi 54, 00044 Frascati, Rome, Italy

^cElettra – Sincrotrone Trieste S.C.p.A., S.S. 14 km-163, 5 in Area Science Park, I-34149 Basovizza, Trieste, Italy

^dIOM-CNR, Area Science Park, Strada Statale 14, km 163, 5, 34149 Basovizza, TS, Italy

^eSBAI, Department of Basic and Applied Sciences for Engineering, University of Rome “La Sapienza”, Via Scarpa 16, 00161 Rome, Italy

^fIstituto Italiano di Tecnologia, via Morego 30, Genova 16163, Italy

† Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d3nr02834h>


metals.³⁰ Advantageously, polar dielectrics allow to obtain simultaneously sub-diffraction confinement *via* a negative dielectric permittivity, and low optical losses in the THz–IR spectral range due to the small damping rate of optical phonons.³¹

In this work, we studied the Extraordinary Optical Transmittance phenomenon^{32–35} generated on phononic metamaterials obtained from a set of patterned self-standing silicon nitride (Si_3N_4) membranes. Membrane technologies show a broad range of applications embracing both industrial and fundamental research.^{36,37} Within this context, Si_3N_4 membranes offer an ultra-flat and mechanically robust support to Transmission Electron Microscopy (TEM) and Scanning Transmission Electron Microscopy (STEM) imaging, real-time chemical reactions, and crystal growth investigations. The development of the so-called *in situ/operando* spectroscopies has indeed led to major advances in functional material characterization, leveraging also on membrane-based technologies. In line with these characteristics, the possibility to confine and enhance electromagnetic (EM) waves at the membrane surface could inherently endow this technological platform with newly designed functionalities, where a stronger light–matter interaction mediated by a phonon-polariton field can play a crucial role.

In this framework, we fabricated periodic arrays of holes with different diameters d (3, 5, and 7 μm) with a lattice parameter a of 12 μm (see below) on Si_3N_4 membranes, and investigated for the first time, at least to our knowledge, their phonon-polariton properties in the IR spectral region. The fabricated metamaterial structure allows the coupling between the incoming infrared electromagnetic wave and a Si_3N_4 optical phonon around 900 cm^{-1} , generating a surface phonon polariton at the air– Si_3N_4 interface. The scattering of this SPhP and its radiative decay through the hole array explain the appearance of an EOT peak in the same spectral region. The electric field distribution around the holes has been further investigated by numerical simulations and nano-IR measurements based on a Scattering-Scanning Near Field Microscope (NEASPEC s-SNOM). Both simulations and measurements confirm the phonon-polariton origin of the EOT effect.

2. Experimental

2.1. Si_3N_4 membranes synthesis and patterning

As already mentioned above, for this study we used self-standing silicon nitride membranes, which are widely used in applications such as TEM and STEM.^{36,37} Their main advantage consists in being chemically inert and mechanically robust, thus being good candidates to make a free-standing thin metamaterial structure.

The fabrication of these suspended Si_3N_4 membranes, provided by Istituto Italiano di Tecnologia (IIT) in Genova, can be summarized in the following steps. 500 μm thick double-side polished Si(100) wafer with 500 nm low stress Low Pressure Chemical Vapor Deposition (LPCVD) Si_3N_4 film, grown on both sides, was used. An etching window was realized on the

wafer backside using standard optical lithography (Süss MicroTec MA6/BA6 mask aligner system). Before UV exposure, a S1813 positive resist was spun at 4000 rpm and baked for 1 minute at 95 °C. The exposed resist was developed in MICROPOSIT MF-319 for 45 s. The sample was then loaded into a plasma-enhanced reactive ion etching system (Sentech SI500), and processed with a 12:1 gas mixture $\text{CHF}_3:\text{O}_2$, 600 W of ICP power and 30 W of RF power. The suspended membranes were finally realized using wet-etching in KOH. Focused ion beam (FIB) machining was employed to mill the Si_3N_4 surface with a nanometric spatial resolution. The process was performed in a FEI – Dual Beam Helios Nanolab 650 machine, where Ga^+ ions were emitted with a current of 21 nA and accelerated by a voltage of 30 kV. Prior to ion milling, a 20 nm-thick Au film was evaporated by physical vapour deposition technique, in order to avoid charging effects. In this way, three patterned samples with a lattice parameter of 12 μm and 3, 5, 7 μm diameters were realized, covering a $300 \times 300 \mu\text{m}^2$ area. The process was finalized by dissolving the Au sacrificial layer in a standard etchant potassium iodide solution.

2.2. Optical measurements

Optical transmittance measurements have been performed in a spectral region including terahertz (THz), IR, Visible, and Ultraviolet (UV), by combining different light sources, detectors, and optical elements. A Bruker Vertex 70v Fourier-Transform interferometer and a Jasco V-770 Spectrophotometer have been used to cover the wide THz-UV spectral range ($150\text{--}52\,000 \text{ cm}^{-1}$) for the characterization of the unpatterned membrane. A resolution of 4 cm^{-1} was used on the THz–IR region and of 2 nm for the Visible-UV one. The Bruker interferometer coupled to a Hyperion-2000 infrared microscope (Cassegrain 15 \times objective with an illumination angle of 30° and a numerical aperture NA = 0.4) has been used to cover the THz and IR spectral range for the characterization of all the patterned samples. The use of a microscope was necessary due to the small size of the patterned area.

2.3. Simulations

Numerical simulations of the optical properties of the metamaterial array were performed through COMSOL Multiphysics *via* a finite-element method. The transmittance of the unpatterned and patterned samples was simulated in the spectral range between 400 and 1650 cm^{-1} , allowing the extraction of the electric field distribution maps in and out of resonance conditions. The Si_3N_4 metamaterial array, surrounded by air, was simulated by applying periodic boundary conditions to a unit cell of period $a = 12 \mu\text{m}$ and hole-diameter $d = 3 \mu\text{m}$, thus generating an infinite periodicity. The complex dielectric function and optical conductivity of the unpatterned sample have been used as input parameters.

2.4. Scattering-type scanning near-field optical microscopy measurements

In order to perform nano-resolved IR microscopy and AFM measurements, metallic tips (ARROW-NcPt from Nano World,



Matterhorn, Switzerland) with a diameter of about 20 nm, nominal resonance frequency of 285 kHz, and force constant of 42 N m^{-1} , were used. Measurements were performed in tapping mode at a tapping frequency Ω of 243.5 kHz. An infrared QCL tunable laser operating in the spectral region between 850 cm^{-1} and 1800 cm^{-1} was used. A nitrogen-cooled Mercury Cadmium Telluride (MCT) detector was used to detect the infrared signal. Phase and amplitude of the IR signal have been acquired directly from Neaspec acquisition software, Neascan, by lock-in demodulation of the interference signal at the 3rd-harmonic of the cantilever oscillation frequency, and by using as a reference a Si substrate. Data postprocessing was performed with Neaplotter (Neaspec), and a phase correction filter was applied in order to take into account the slight phase changes of the IR laser.

3. Results and discussion

In this work, we used four membranes with a thickness of 500 nm and a patterned area of $300 \times 300 \mu\text{m}^2$ in size. The optical transmittance $T(\omega)$ of the unpatterned Si_3N_4 membrane has been measured in a broad spectral region from 150 cm^{-1} to $32\,000 \text{ cm}^{-1}$ to fully characterize its electrodynamic response. $T(\omega)$ is shown in Fig. 1a (light blue line). The two minima below 1000 cm^{-1} correspond to phonon modes of the membrane (see discussion below), while the numerous sharp peaks at higher frequencies generate from a Fabry-Pérot effect related to the thin (500 nm) sample thickness. Above nearly $32\,000 \text{ cm}^{-1}$ the transmittance goes to zero due to the electronic optical gap of Si_3N_4 . In order to extract the dielectric

function $\epsilon(\omega)$ of the material, $T(\omega)$ has been analyzed with the ReFFIT software recurring to a Lorentz model,³⁸ and taking into account the Fabry-Pérot effect as well. The fit is shown in Fig. 1a (black empty diamond symbols) and the experimental real (light blue line) and imaginary part (black line) of $\epsilon(\omega)$ are represented in Fig. 1b in the same spectral range. Here, one can observe two phonon peaks at about 450 cm^{-1} and 900 cm^{-1} , followed by a flat $\epsilon_1 \sim 4$ region, in agreement with the absence of any electronic absorption up to the electronic gap. More specifically, the first phonon peak (at about 450 cm^{-1}) is associated with the Si-N breathing mode, whereas the second peak (at about 900 cm^{-1}) is caused by two (nearly degenerate) Si-N stretching modes.^{39,40} The absence of any electronic contribution in the infrared and a marked negative value of ϵ_1 around 900 cm^{-1} strongly indicate that Si_3N_4 is a good material candidate for studying the phonon-polariton formation.^{33,36} Three periodic arrays of circular holes with different diameters d have been fabricated onto the membranes *via* Focused Ion Beam (FIB) lithography (see section 1). In Fig. 2a optical microscope images of the samples are presented, in the case of $d = 3 \mu\text{m}$ (a), $5 \mu\text{m}$ (b), and $7 \mu\text{m}$ (c). The diameter size has been chosen to set the phononic meta-material in sub-wavelength conditions, whereas the lattice parameter has been fixed at $a = 12 \mu\text{m}$ to supply the wavevector required to excite the surface phonon-polariton at the air- Si_3N_4 interface.

Fig. 2d depicts the transmittance measurements in the phonon region for all membranes. The patterned samples show a transmittance enhancement with respect to the unpatterned one in the spectral region around 900 cm^{-1} . In order to better visualize this effect, in Fig. 2e the ratios among the





Fig. 1 (a) Experimental (light blue line) and fitted (black empty diamond symbols) transmittance of the Si_3N_4 membrane, measured in the THz-UV range. The vertical black dashed line separates the phonon absorption region (low-frequency) to the high-frequency part characterized by Fabry-Pérot fringes. (b) Real (light blue line) and imaginary (black line) parts of the dielectric function, extracted from the fitted transmittance by considering the Fabry-Pérot effect.





In order to better understand the far-field results and introduce those in the near-field (see below), numerical simulations were performed through the COMSOL Multiphysics software *via* a finite element method (see section 1). An infinite meta-material array was simulated by drawing a single unit cell and applying periodic boundary conditions to it. Putting the dielectric function and the optical conductivity of the unpatterned membrane as input parameters, the transmittance of the bare and patterned membranes was simulated under an incident plane wave polarized along y . Fig. 3a shows the normalized experimental transmittance of the patterned sample with $d =$




Fig. 3 (a) Experimental (light blue line, already reported in Fig. 2e) and simulated (black dashed line) normalized transmittance for the sample with $d = 3 \mu\text{m}$. The simulation has been performed under an incident plane wave polarized along y . (b) and (c) $|E_z|$ distribution maps on the Si_3N_4 unit cell surface (xy plane) at a fixed height equal to the membrane thickness, in (900 cm^{-1}) and out of resonance conditions (1650 cm^{-1}), respectively. The electric field values were normalized between 0 and 1. (d) $|E_z|$ value along a line of length $2d$ (where d is the hole diameter), connecting the hole center (located at $0 \mu\text{m}$) and the border of the unit cell, as shown in the corresponding inset. Light blue open circles highlight points obtained with a 200 nm spatial resolution (black dashed line is a guide for the eyes).

$3 \mu\text{m}$ (light blue line), compared with the simulated one (black dashed line). There is a good agreement between experiment and simulation. Similar results (not shown) were obtained for the other samples. In order to understand the electric field behavior along the membrane surface, a distribution map of $|E_z|$ (modulus of the electric field component along z) has been calculated. Fig. 3b and c show $|E_z|$ distribution maps on the Si_3N_4 unit cell surface (xy plane) at height z equal to the membrane thickness, in resonance (900 cm^{-1}) and out of resonance (1650 cm^{-1}) conditions, respectively. The electric field values were normalized to 1. At the resonance frequency, $|E_z|$ is strongly localized around the edge of the hole, while across and away from the hole it is almost zero. On the contrary, outside resonance, $|E_z|$ is almost zero along the whole xy plane. These results indicate electric field confinement around the holes is strongly enhanced in the resonant case through the SPhP excitation. Additional maps of $|E_x|$, $|E_y|$ and $|E_{||}| = \sqrt{|E_x|^2 + |E_y|^2}$ are shown in Fig. S2 of ESI.†

Finally, Fig. 3d shows the $|E_z|$ value (light blue open circles), obtained at 900 cm^{-1} along a line of length $2d$ (d is the hole diameter), connecting the hole center and the border of the unit cell, as shown in the corresponding inset. The curve was averaged out to obtain the same spatial resolution (200 nm) of the experimental near-field measurements that will be discussed later. As expected, the field is maximized near the hole edge, decaying exponentially far from it, as expected for evanescent waves. IR nano spatially-resolved measurements were carried out at the SISSI beamline^{44,45} through the help of an s-SNOM nano-FTIR microscope

(NEASPEC, Germany) coupled to an infrared tunable quantum cascade laser (QCL). The microscope allowed us to simultaneously perform IR and AFM imaging (see section 4).

Fig. 4 shows measurements of the scattered radiation amplitude A and phase ϕ , in resonance and out-of-resonance to the surface phonon excitation at about 900 cm^{-1} for the membrane patterned with holes of $d = 3 \mu\text{m}$. Similar data (not shown) have been obtained for the other patterned membranes. The membrane region, mapped with a spatial resolution of 200 nm , is a $12 \mu\text{m} \times 18 \mu\text{m}$ area containing three holes of the array. The scattering amplitude and phase maps are presented in Fig. 4a, divided into two columns. On the left column, maps acquired at the SPhP excitation frequency of 900 cm^{-1} (*i.e.* in resonance to the EOT peak), are shown. On the right column, maps obtained with radiation out of resonance to the SPhP excitation (at a frequency of 1650 cm^{-1}), are instead reported. Strong differences are visible between the two cases. As a matter of fact, the “out of resonance” amplitude map highlights only the morphology of the sample and the phase shows almost no variation through and away from holes. At the resonance, a strong signal variation surrounds the holes, for both amplitude and phase. These variations suggest electric field confinement due to the excitation of the SPhP, which is also present in the numerical simulations (Fig. 3b). An analogous behavior (not shown) was observed for the other two samples, with $5 \mu\text{m}$ and $7 \mu\text{m}$ holes. To better understand those maps we extracted the amplitude and phase signals as a function of the distance from the hole center, and compared them to the hole depth profile. In Fig. 4b the scat-






Fig. 4 (a) Nano-IR maps of the scattering amplitude and phase variations over the $d = 3 \mu\text{m}$ holes. On the left column, maps were obtained with infrared radiation at 900 cm^{-1} , resonating with the SPhP excitation. On the right column, maps were measured with radiation at 1650 cm^{-1} , out of resonance with the SPhP excitation. Maps were obtained from the same spatial region and, in order to reduce the background noise, were acquired by sampling the signal at the cantilever 3rd harmonic frequency. The black bar indicates a distance of $5 \mu\text{m}$ as a scale reference. (b) Amplitude and phase signals extracted from the maps in resonance (green line) and out of resonance (red line) of the SPhP excitation as a function of the distance from the hole center compared with the hole depth profile (blue line). The profiles shown were extracted from the hole in the upper right side.

tered amplitude and phase are shown, in (green line) and out of (red line) resonance conditions, together with the depth profile (blue line) as a reference. An increase in the amplitude near the edge of the hole with a strong change in the phase of $\sim \pi/2$ can clearly be seen. The amplitude curve has a very good agreement with the simulated z -component of the electric field shown in Fig. 3d. On the contrary, the amplitude curve out of resonance follows the morphology profile line with no change in its phase. These data confirm that the EOT phenomenon originates from the excitation of an SPhP at the air- Si_3N_4 interface. Noteworthy, a similar electric field confinement has been measured in nanoporous graphene, where it has been also associated with heat localization around the holes.⁴⁶

4. Conclusion

In this paper, we demonstrated that the infrared electromagnetic properties of technologically relevant Si_3N_4 membranes can be engineered through the use of surface phonon polariton formation. Arrays of circular holes have been fabricated by the Focused Ion Beam technique on 500 nm thick Si_3N_4 membranes, and different hole sizes have been investigated, suggesting that the mediating mechanism responsible for the extraordinary transmittance is the excitation of a phonon-polariton mode. The electric field distribution around the holes has been further studied by numerical simulations and IR nanometric spatially-resolved measurements through a scattering-SNOM technique, confirming the phonon-polariton origin of the EOT effect. The transmittance increase in the IR spectral range paves the way for interesting sensing appli-

cations not achievable with plasmonic metamaterials due to strong optical losses in this frequency range for conventional metals.

Author contributions

Salvatore Macis: data curation, formal analysis, investigation, methodology, software, supervision, writing – original draft preparation, writing – review, and editing. Maria Chiara Paolozzi: data curation, formal analysis, investigation, methodology, software, writing – original draft preparation, writing – review and editing. Annalisa D'Arco: investigation, supervision, writing – review and editing. Federica Piccirilli: data curation, investigation, methodology, writing – review and editing. Veronica Stopponi: investigation, methodology, writing – review and editing. Marco Rossi: funding acquisition, supervision, writing – review, and editing. Fabio Moia: methodology, sample preparation, writing – review and editing. Andrea Toma: conceptualization, funding acquisition, methodology, resources, sample preparation, supervision, writing – review, and editing. Stefano Lupi: conceptualization, data curation, formal analysis, funding acquisition, investigation, methodology, project administration, resources, supervision, writing – original draft preparation, writing – review and editing.

Conflicts of interest

There are no conflicts to declare.



Acknowledgements

We acknowledge support by the European Research Council (ERC) under the European Union's Horizon 2020 Research and Innovation Program "REPLY ERC-2020-COG Grant agreement no. 101002422". This publication was also partially supported by the PNRR project for the realization of "Infrastructure for Energy Transition and Circular Economy @ EuroNanoLab" (iENTRANCE@ENL), funded by MUR (call Research Infrastructures D. D. n. 3264-IR/2021, contract IR0000027), by PNRR project Rome Technopole, and by Prin project 2020RPEPNH. This work has been also partly performed in the framework of the Nanoscience Foundry and Fine Analysis (NFFA-MIUR) facility.

References

- 1 F. Bilotti and L. Sevgi, Metamaterials: Definitions, properties, applications, and FDTD-based modeling and simulation, *International Journal of RF and Microwave Computer-Aided Engineering*, 2012, **22**, 422–438.
- 2 Y. Liu and X. Zhang, Metamaterials: a new frontier of science and technology, *Chem. Soc. Rev.*, 2011, **40**, 2494–2507.
- 3 F. Capolino, *Theory and Phenomena of Metamaterials*, CRC Press, Taylor and Francis Book, London, 3rd edn, 2009.
- 4 W. Cai and V. Shalaev, Optical Metamaterials: Fundamentals and Applications, *Phys. Today*, 2010, **63**(9), 57.
- 5 Y. Chen, B. Ai and Z. J. Wong, Soft optical metamaterials, *Nano Converg.*, 2020, **7**, 18.
- 6 H. Chen, C. T. Chan and P. Sheng, Transformation optics and metamaterials, *Nat. Mater.*, 2010, **9**, 387–396.
- 7 A. Valipour, M. H. Kargozarfard, M. Rakhshi, A. Yaghootian and H. M. Sedighi, Metamaterials and their applications: An overview, *Proc. Inst. Mech. Eng., Part L*, 2021, 1–40.
- 8 I. I. Smolyaninova and V. N. Smolyaninova, Hyperbolic metamaterials: Novel physics and applications, *Solid-State Electron.*, 2017, **136**, 102112.
- 9 M. Nomura, R. Anufriev, Z. Zhang, J. Maire, Y. Guo, R. Yanagisawa and S. Volz, Review of thermal transport in phononic crystals, *Mater. Today Phys.*, 2022, **22**, 100613.
- 10 Z. Zhang, Y. Guo, M. Bescond, J. Chen, M. Nomura and S. Volz, Coherent thermal transport in nano-phononic crystals: An overview, *APL Mater.*, 2021, **9**, 081102.
- 11 M. Sledzinska, B. Graczykowski, J. Maire, E. ChavezAngel, C. M. Sotomayor-Torres and F. Alzina, 2D Phononic Crystals: Progress and Prospects in Hypersound and Thermal Transport Engineering, *Adv. Funct. Mater.*, 2020, **30**, 1904434.
- 12 M. Maldovan, Sound and heat revolutions in phononics, *Nature*, 2013, **503**, 209–217.
- 13 M. Kalderon, A. Paradeisiotis and I. Antoniadis, 2D Dynamic Directional Amplification (DDA) in Phononic Metamaterials, *Materials*, 2021, **14**(9), 2302.
- 14 X. Zhou, M. Badreddine Assouar and M. Oudich, Acoustic superfocusing by solid phononic crystals, *Appl. Phys. Lett.*, 2014, **105**, 233506.
- 15 J.-P. Liu, L.-L. Wang, B. Sun, H.-J. Li and X. Zhai, Enhanced optical transmission through a nano-slit based on a dipole source and an annular nano-cavity, *Opt. Laser Technol.*, 2015, **69**, 71–76.
- 16 L. Ruihua and M. Zhong, Enhanced transmission performance based on ultrathin broadband circular hole array metasurface, *Mater. Res. Express*, 2021, **8**, 025801.
- 17 T. Chen, S. Li and H. Sun, Metamaterials Application in Sensing, *Sensors*, 2012, **12**, 2742–2765.
- 18 M. L. Brongersma and P. G. Kik, *Surface plasmon nanophotonics*, Springer New York, 2010.
- 19 J. B. Khurgin and G. Sun, Scaling of losses with size and wavelength in nanoplasmonics and metamaterials, *Appl. Phys. Lett.*, 2011, **99**, 211106.
- 20 J. B. Khurgin and A. Boltasseva, Reflecting upon the losses in plasmonics and metamaterials, *MRS Bull.*, 2012, **37**, 768–779.
- 21 J. B. Khurgin, How to deal with the loss in plasmonics and metamaterials, *Nat. Nanotechnol.*, 2015, **10**, 2–6.
- 22 A. N. Grigorenko, M. Polini and K. S. Novoselov, Graphene plasmonics, *Nat. Photonics*, 2012, **6**, 749–758.
- 23 F. H. L. Koppens, D. E. Chang and F. J. García de Abajo, Graphene Plasmonics: A Platform for Strong Light-Matter Interactions, *Nano Lett.*, 2011, **11**(8), 3370–3377.
- 24 Z. Fei, A. S. Rodin, G. O. Andreev, W. Bao, A. S. McLeod, M. Wagner, L. M. Zhang, Z. Zhao, M. Thiemens, G. Dominguez, M. M. Fogler, A. H. Castro Neto, C. N. Lau, F. Keilmann and D. N. Basov, Gate-tuning of graphene plasmons revealed by infrared nano-imaging, *Nature*, 2012, **487**(7405), 82–85.
- 25 L. Tomarchio, S. Macis, A. D'Arco, S. Mou, A. Grilli, M. Romani, M. Cestelli Guidi, S. Kukunuri, S. Jeong, A. Marcelli, Y. Ito and S. Lupi, Disordered photonics behavior from terahertz to ultraviolet of a three-dimensional graphene network, *NPG Asia Mater.*, 2021, **13**, 73.
- 26 P. Di Pietro, M. Ortolani, O. Limaj, A. Di Gaspare, V. Giliberti, F. Giorgianni, N. Brahlek, N. Bansal, N. Koirala, S. Oh, P. Calvani and S. Lupi, Observation of Dirac plasmons in a topological insulator, *Nat. Nanotechnol.*, 2013, **8**, 556–560.
- 27 S. Macis, L. Tomarchio, S. Tofani, F. Piccirilli, M. Zaccagna, V. Aglieri, A. Toma, G. Rimal, S. Oh and S. Lupi, Infrared plasmons in ultrahigh conductive PdCoO₂ metallic oxide, *Commun. Phys.*, 2022, **5**, 145.
- 28 S. Macis, M. C. Paolozzi, A. D'Arco, L. Tomarchio, A. Di Gaspare and S. Lupi, Terahertz Resonators Based on YBa₂Cu₃O₇ High-Tc Superconductor, *Appl. Sci.*, 2022, **12**(20), 10242.
- 29 S. Foteinopoulou, G. C. R. Devarapu, G. S. Subramania, S. Krishna and D. Wasserman, Phonon-polaritonics: enabling powerful capabilities for infrared photonics, *Nanophotonics*, 2019, **8**(12), 2129–2175.



- 30 J. D. Caldwell, L. Lindsay, V. Giannini, I. Vurgaftman, T. L. Reinecke, S. A. Maier and O. J. Glembocki, Low-loss, infrared and terahertz nanophotonics using surface phonon polaritons, *Nanophotonics*, 2015, **4**, 44–68.
- 31 S. Adachi, *The reststrahlen region. Optical properties of crystalline and amorphous semiconductors: materials and fundamental principles*, Springer Science + Business Media New York, NY, 1999.
- 32 D. Z. A. Chen, Extraordinary optical transmission through subwavelength holes in a polaritonic silicon dioxide film, *Appl. Phys. Lett.*, 2007, **90**, 181921.
- 33 T. W. Ebbesen, H. J. Lezec, H. F. Ghaemi, T. Thio and P. A. Wolff, Extraordinary optical transmission through sub-wavelength hole arrays, *Nature*, 1998, **391**, 667–669.
- 34 M. P. van Exter, E. Altewischer and J. P. Woerdman, Coherent Polarization Transfer through Sub-wavelength Hole Arrays, *NanoNet*, 2009, 76–83.
- 35 C. Genet and T. W. Ebbesen, Light in tiny holes, *Nature*, 2007, **445**, 39–46.
- 36 T. L. Morkved, W. A. Lopes, J. Hahm, S. J. Sibener and H. M. Jaeger, Silicon nitride membrane substrates for the investigation of local structure in polymer thin films, *Polymer*, 1998, **39**, 3871–3875.
- 37 V. Lausch, P. Hermann, M. Laue and N. Bannert, Silicon nitride grids are compatible with correlative negative staining electron microscopy and tip-enhanced Raman spectroscopy for use in the detection of micro-organisms, *J. Appl. Microbiol.*, 2014, **116**(6), 1521–1530.
- 38 A. Kuzmenko, *Guide to ReFIT, Software to fit Optical Spectra*, 2018.
- 39 F. Ay and A. Aydinli, Comparative investigation of hydrogen bonding in silicon-based PECVD grown dielectrics for optical waveguides, *Opt. Mater.*, 2004, **26**, 33–46.
- 40 G. Cataldo, J. A. Beall, H.-M. Cho, B. McAndrew, M. D. Niemack and E. J. Wollack, Infrared dielectric properties of low-stress silicon nitride, *Opt. Lett.*, 2012, **37**, 20.
- 41 S. A. Maier, *Plasmonics: Fundamentals and Applications*, Springer-Verlag New York, 2007.
- 42 L. Salomon, F. Grillot, A. V. Zayats and F. de Fornel, Near-Field Distribution of Optical Transmission of Periodic Subwavelength Holes in a Metal Film, *Phys. Rev. Lett.*, 2001, **86**, 6.
- 43 P. B. Catrysse and S. Fan, Near-complete transmission through subwavelength hole arrays in phonon-polaritonic thin films, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2007, **75**, 075422.
- 44 S. Lupi, A. Nucara, A. Perucchi, P. Calvani, M. Ortolani, L. Quaroni and M. Kiskinova, Performance of SISSI, the infrared beamline of the ELETTRA storage ring, *J. Opt. Soc. Am. B*, 2007, **24**, 959–964.
- 45 P. Roy, J.-B. Brubach, P. Calvani, G. deMarzi, A. Filabozzi, A. Gerschel, P. Giura, S. Lupi, O. Marcouillé, A. Mermet, A. Nucara, J. Orphal, A. Paolone and M. Vervloet, Infrared synchrotron radiation: from the production to the spectroscopic and microscopic applications, *Nucl. Instrum. Methods Phys. Res., Sect. A*, 2001, **467–468**(1), 426–436.
- 46 D. Suzuki, T. Okamoto, J. Li, Y. Ito, T. Fujita and Y. Kawano, Terahertz and Infrared Response Assisted by Heat Localization in Nanoporous Graphene, *Carbon*, 2021, **173**, 403–409.

