

RSC Sustainability



Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: U. S. Behera, S. Poddar and H. Byun, *RSC Sustainability*, 2025, DOI: 10.1039/D5SU00575B.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the <u>Information for Authors</u>.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard Terms & Conditions and the Ethical guidelines still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



View Article Online DOI: 10.1039/D5SU00575B

Sustainability spotlight

Valorising orange peel waste through pyrolysis: advancing circular economy and energy sustainability in alignment with SDG7, SDG12, and SDG13. Agricultural biomass like orange peel waste presents a promising sustainable alternative to fossil fuels but is often underutilized. This study addresses the critical data and implementation gaps by systematically analyzing the pyrolysis of orange peel waste for the simultaneous production of pyro-char, pyro-oil, and pyro-gas—an integrated tri-product approach not previously reported. Through combined thermochemical analysis and economic modeling, the study demonstrates a payback period of only 1.3 years, substantially improving the feasibility of bioresource valorization at scale. By coupling material recovery with energy generation, the study contributes directly to SDG7 (Affordable and Clean Energy), SDG12 (Responsible Consumption and Production), and SDG13 (Climate Action). It highlights the potential of waste-to-resource strategies to support industrial symbiosis and clean energy transitions, particularly in emerging economies.

View Article Online Research Paper U00575B

Pyrolysis of Orange Peel Waste to Pyrofuels and Pyrochar: Optimization, and Techno-Economic Insights for Industrial Scale-Up

View Article Online

Abstract

Biomass presents a sustainable alternative to fossil fuels; however, it faces limitations such as high moisture content, low bulk density, and poor grindability. This study investigates the pyrolysis of waste orange peels to produce pyro-char, pyro-oil, and pyro-gas, a process that has been rarely reported in the literature. The effects of pyrolysis temperature, feedstock mass, and heating rate on the yield of these pyro-products were systematically investigated. The biomass was characterized using proximate analysis and thermogravimetric analysis (TGA), while the pyro-products were analyzed for their higher heating value (HHV), lower heating value (LHV), morphology and elemental composition via scanning electron microscopy with energydispersive X-ray spectroscopy (SEM-EDX), and chemical composition using gas chromatography mass spectrometry (GC-MS). Critical parameters influencing the pyrolysis outcomes were identified: feedstock mass (1–3 kg), temperature (573–1173 K), and heating rate (10–30 K/min). Under optimal conditions 2 kg feedstock mass, 873 K temperature, and a heating rate of 20 K/min, the theoretical yields were 26.52 wt.% pyro-char, 22.76 wt.% pyrooil, and 50.72 wt.% pyro-gas, with an overall process desirability of approximately 0.7. Experimental yields showed slight deviations, resulting in 28.12 wt.% pyro-char, 22.89 wt.% pyro-oil, and 48.99 wt.% pyro-gas, all within a ±5.7% margin of the theoretical values. The estimated payback period for the initial investment is 1.3 y at a 10% discount rate, which is considerably shorter than the previously reported 6 y period for pyro-gas and pyro-oil production. Scale-up to larger plants is expected to further reduce this duration. This study bridges the gap in comprehensive techno-economic analyses of industrial-scale waste orange peel pyrolysis by producing pyro-char, pyro-oil, and pyro-gas, a three-product yield not previously reported. It offers a sustainable approach to valorizing orange peel waste into highvalue products, aligning with Industry 5.0 principles and the United Nations 2030 Sustainable Development Goals.

Keywords: Biomass; Economic analysis; Pyrolysis; Renewable energy; Waste orange peels

View Article Online DOI: 10.1039/D5SU00575B

Sustainability spotlight

Valorising orange peel waste through pyrolysis: advancing circular economy and energy sustainability in alignment with SDG7, SDG12, and SDG13. Agricultural biomass like orange peel waste presents a promising sustainable alternative to fossil fuels but is often underutilized. This study addresses the critical data and implementation gaps by systematically analyzing the pyrolysis of orange peel waste for the simultaneous production of pyro-char, pyro-oil, and pyro-gas, an integrated tri-product approach not previously reported. Through combined thermochemical analysis and economic modeling, the study demonstrates a payback period of only 1.3 years, substantially improving the feasibility of bioresource valorization at scale. By coupling material recovery with energy generation, the study contributes directly to SDG7 (Affordable and Clean Energy), SDG12 (Responsible Consumption and Production), and SDG13 (Climate Action). It highlights the potential of waste-to-resource strategies to support industrial symbiosis and clean energy transitions, particularly in emerging economies.

1. Introduction

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

Rapid industrialization and population growth have significantly increased global energy demand, necessitating sustainable alternative energy sources to mitigate the environmental impacts associated with fossil fuel consumption ¹. Currently, fossil fuels such as coal, natural gas, and petroleum remain the primary energy sources^{2,3}; however, their prolonged use leads to serious environmental degradation and long-term sustainability concerns. As a result, there is a growing global transition toward renewable energy sources to reduce dependency on fossil fuels and address these environmental challenges. For instance, orange peel pyrolysis converts agricultural waste into pyro-products (pyro-oil, pyro-char, pyro-gas) that directly replace fossil fuel-derived materials while simultaneously reducing methane emissions and petroleum dependency across transportation, manufacturing, and pharmaceutical sectors.

Agro-based biomass has emerged as a promising renewable resource for energy View Article Online DOI: 10.1039/D5SU00575B production, offering the potential to bridge the widening supply-demand gap. Among various biomass feedstocks, orange peel waste has gained attention for producing sustainable energy products such as low-ash coke. With global orange production reaching approximately 60 million tons annually, an estimated 32 million tons of orange peel waste are generated, presenting significant environmental and waste management challenges⁴. In countries like India, this biomass is predominantly disposed of in landfills^{5,6}, further exacerbating these issues. Orange peels are rich in valuable constituents such as starch, cellulose, fat, lignin, ash, pectin, and flavonoids, making them an ideal feedstock for thermochemical conversion processes⁶. Pyrolysis is a well-established thermal degradation method used to convert biomass into valuable products. This process involves the rapid heating of biomass in an inert atmosphere at temperatures ranging from 473 K to 1273 K⁷, producing three primary products: pyro-char (solid), pyro-oil (liquid), and pyro-gas (gaseous). The yield distribution of these products is highly dependent on processing conditions, particularly temperature. The pyrolysis process is governed by several key reaction mechanisms, including decarboxylation, dehydration, and demethylation. This reaction mechanism influences the formation of pyro-char, pyro-oil, and pyro-gas. Pyro-char, a carbon-rich solid residue, is characterized by a high carbon-to-hydrogen (C/H) ratio and primarily composed of fixed carbon and ash, along with some less volatile hydrocarbons. In an investigation, Selvarajoo et al. 8 reported pyro-char yields ranging from 22% to 53% when citrus peel biomass was pyrolyzed at temperatures between 573 K and 973 K. Similarly, other study demonstrated that approximately 21 to 35 wt.% of pyro-char can be obtained from various biomass sources under comparable pyrolysis⁹. Pyro-oil is a dark brown liquid with a smoky odor and primarily consists of oxygenated hydrocarbons, including tars, oils, phenols, and waxes¹⁰. Shoo et al. 10 reported nearly 50% weight loss of biomass at 773 K for particle sizes ranging from 0.6 mm to 0.8 mm, indicating a 50% conversion into various pyrolysis products¹⁰. Chaiwong et al. ¹¹observed yields of approximately 42% pyro-oil and 33%

pyro-char from algae biomass when processed at temperatures between 773 K and 823 K.

Niew Article DOI: 10.1039/D551

Amrullah et al. 12 reported 30.97% of phenol yield at 773 K from biomass coconut shell.

Another study also reported nearly 50% increased in pyro-oil production when polyethylene terephthalate was added to the pyrolysis feed 13. These findings suggest that pyro-char, pyro-oil, and pyro-gas can be produced in relatively comparable proportions, although the exact distribution varies depending on operating conditions. Generally, the pyrolysis process is classified based on the temperature. Different pyrolysis process based on the temperature, their

advantages and disadvantages are provided in Table 1.

The pyrolysis process depends on parameters such as heating rate, temperature, residence time, and operational mode (batch or continuous)^{14,15}. The composition and yield distribution of pyrolysis products are significantly influenced by factors including biomass type, reactor configuration, temperature, feedstock and heating rate. Optimizing parameters such as temperature, feedstock and heating rate is essential to achieve a desirable balance among char, oil, and gas yields^{16–18}.

| Pyrolysis type | Temperature (°C) | Heating rate (°C/s) | Advantages | Disadvantages | References | |
|-----------------------|------------------|-----------------------|--|--|------------|--|
| Slow | 300-700 | Low (0.1-1) | Simple setup Suitable for producing stable pyro-char. High char yield Longer residence time Low liquid fuel yield Less efficiency | | 19–21 | |
| Fast | 450-700 | High (~200) | High oil yield Short residence time (<5 s) Suitable for pyro oil production | Need rapid heating and coolingComplex reactor designBio-oil is often acidic | 22–24 | |
| Flash | 600-1000 | Very high (1000-2500) | Maximum oil yieldVery short residence timeEfficient for specific chemical | High energy inputTechnical challengesNeed small particle size | | |
| Intermediate | 400-550 | Moderate (1-10) | Nearly equal formation of char and oil Flexible operation Operational flexibility and lower capital cost | May not optimize for single product Advance control conditions | 26 | |
| Vacuum | 300-600 | Low to moderate | Improve pyro oil qualityReduces secondary reaction | Requires vacuum systemLower gas yieldIncreases cost and complexity | 27 | |
| Multi-stage pyrolysis | 300 - 900 | Low to moderate | Drying of biomass (30 -150 °C) Devolatization of biomass (200 - 600 °C) | To optimize product yield Quality of the product Energy consumption Flexibility and control | 28–30 | |

Sustainability Accepted Manuscript

RSC

RSC Sustainability

Understanding the relationships between these key variables is critical for enhancing process View Article Online DOI: 10.1039/D5SU00575B efficiency and maximizing product yield. Various optimization techniques have been employed to evaluate the interdependence among process parameters. Among these, response surface methodology (RSM) is widely recognized as an effective statistical approach for process optimization. RSM employs experimental designs such as the Plackett–Burman design, Box–Behnken design, Doehlert matrix, and central composite design to systematically assess and optimize process variables ³¹. Recent studies^{32–36} have demonstrated the efficacy of RSM in optimizing pyrolysis yields from biomass, confirming its suitability for advanced process optimization.

Economic analysis plays a crucial role in process design by providing reliable estimates of capital investment and operating costs. These early-stage evaluations are essential for determining total investment and energy consumption, facilitating the scale-up of laboratory processes to industrial applications ^{37–40}. Assessing feasibility, profitability, and investment risk enables the estimation of production costs for value-added products derived from orange peels. Therefore, evaluating the economic performance including initial investment, operational cost, return on investment (ROI), net present value (NPV), and payback period is critical for determining the commercial viability of the process. Most previous studies^{8,41,42} have primarily focused on the production of single pyrolysis product, with very few investigations addressing the simultaneous generation of two or three major products, i.e., char, oil and gas ⁹. This highlights the limited availability of data necessary for scaling up the process to achieve maximum product yields and ensure economic viability. Moreover, a comprehensive techno-economic assessment of industrial-scale pyrolysis of orange peel waste remains largely unaddressed, indicating a significant gap in the practical implementation of such valorization approaches.

This study investigates the pyrolysis of orange peel waste for the simultaneous New Arius (DOI:10.1039/DSS). production of char, oil, and gas, addressing a previously unexplored aspect of biomass valorization. The response surface methodology (RSM) optimization technique was employed to enhance the yields of all three pyro-products. Product characterization was conducted using scanning electron microscopy with energy-dispersive X-ray spectroscopy (SEM-EDS) for char, gas chromatography-mass spectrometry (GC-MS) for oil, and gas chromatography (GC) for gas. A comprehensive economic evaluation incorporating net present value (NPV), internal rate of return (IRR), and payback period has been conducted, offering a unique and previously unexplored perspective on the viability of waste orange peels to valuable product processes ⁴³. Sensitivity analysis was also conducted to assess the impact of variations in operational parameters on the payback period. Beyond waste mitigation, this process supports the development of an integrated biorefinery and presents a novel model for combining waste valorization with sustainable energy and material production.

2. Material and procedure

2.1. Preparation of feedstock

Oranges typically range from 0.04 m to 0.12 m in diameter ^{44,45} and are primarily composed of water, with the remaining 13% consisting of minerals, essential oils, lipids, proteins, fibers, organic acids (such as citric and formic acids), pectin, glucosides, and pentosans⁴³. The edible portion accounts for approximately 31%–51% of the total fruit weight, while the non-edible components including segment membranes, albedo, flavedo, core, oil glands, and cuticle—make up 49%–69% of the total weight^{45,46}. This non-edible fraction is referred to as orange peel waste. Figure 1 provides an overview of the orange components: (a) anatomical parts, (b) dried peels, and (c) powdered peel. 15 kg of orange (mandarin variety) peels were collected from a local market in Haldia, West Bengal, India, for feedstock preparation. The peels were sun-dried for 14 days to reduce moisture content, followed by oven drying at 110±5 °C for

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14.

approximately 4 h. The dried peels were then ground using a mixer grinder and sieved to View Article Online achieve a particle size of 0.43 mm. The specific particle size was considered based on the literature study. These processed peels were subsequently used as feedstock in a semi-batch reactor for pyrolysis.

Page 12 of 87




Figure 1: (a) Anatomic part; (b) dried orange peel waste; (c) powdered form of dried orange peel waste used for pyrolysis.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

2.2. Experimental setup and procedure

View Article Online DOI: 10.1039/D5SU00575B

Experimental setup: The experimental pyrolysis setup is illustrated in Figure 2. Experiments were conducted in a custom-fabricated cylindrical stainless-steel (SS-314) reactor designed by Purify & Company for laboratory-scale pyrolysis. The reactor has a length of 1.7 m, with internal and external diameters of 0.1195 m and 0.2 m, respectively. It features three openings: a 0.05 m top inlet for material feeding, a 0.04 m bottom outlet for cleaning, and two additional ports connected to B24 pipes—one for nitrogen flow and the other for volatile collection. The reactor is coupled to a 0.8 kW AC heater powered by a three-phase supply and is insulated with glass wool to minimize radiative heat loss. A Ni-Cr thermocouple is installed to monitor the internal temperature. The reactor required approximately 25-113 min to heat up from ambient temperature to the desired pyrolysis temperature (573 K to 1173 K), achieving a heating rate of 8-12°C/min. After completion of the pyrolysis process, the reactor was allowed to cool naturally under continuous nitrogen flow for 150-180 min to reach ambient temperature, ensuring complete condensation of volatiles and preventing secondary reactions. These controlled heating and cooling phases were critical for maintaining consistent product yields and preventing thermal degradation of products. The outlet of the reactor is connected to a condenser operating between 8 °C and 12 °C. To maximize pyrolytic oil recovery, the condensable vapors are directed through a bent pipe submerged in a water tank containing water, ice, and salts, maintaining a temperature range of 0 to -2 °C.

Experimental procedure: A predetermined amount of dried orange peel powder was introduced into the reactor for pyrolysis. Internal reactor surface temperatures were monitored using a Ni-Cr thermocouple (i.e., TC-1, TC-2, TC-3) connected to a K-type PID controller (see Figure 2). Nitrogen gas was purged from the bottom of the reactor at a flow rate of 499.8 L/h to establish an inert atmosphere and facilitate the removal of volatile compounds. The volatiles generated from thermal decomposition were directed through a B24 stainless steel pipe, followed by

condensation in a unit maintained at 8–12 °C. A 100 L water tank, equipped with a submersible when water the submersible pump and filled with ice water, was connected to the condenser to enhance the condensation of volatiles into pyrolysis oil. Three condensers were immersed in a salt–ice mixture to maintain a temperature range of 0–2 °C, thereby maximizing oil recovery. The collected pyrolysis oil was stored in 0.025 L vials for subsequent analysis. After cooling to ambient temperature, the resulting pyrolytic char was collected in plastic packets for further study. The pyrolysis procedure for waste orange peels followed the methodology described in a previous publication¹⁴. Non-condensable gases were quantified volumetrically via downward water displacement in a 1 L measuring cylinder and subsequently transferred to a 1 L Tedlar bag for compositional analysis. Gas composition was determined using gas chromatography–mass spectrometry (GCMS-TQ8040, Shimadzu, India) to measure the gaseous components' absolute and relative concentrations (wt.%). Pyrolysis was performed at temperatures ranging from 573 K to 1173 K under atmospheric pressure (1 atm), and the product distribution was calculated using the equations provided below.

$$(Bio-char) \ yield\%(wt.\%) = \frac{weight \ of \ solid \ residue}{weight \ of \ feed} \times 100$$

$$(Bio-oil) \ yield\%(wt.\%) = \frac{weight \ of \ bio-oil}{weight \ of \ feed} \times 100$$

$$(Bio-gas) \ yield (wt.\%) = 100 - [(Bio-oil)yield + (Bio-char)yield]$$
(3)

Operational parameters: Experiments were conducted in four batches to investigate the effect of varying pyrolysis temperatures (573 K to 1173 K) on product yields. Initially, 3 kg of feedstock, sieved to a particle size of 0.43 mm, was loaded into the pyrolyzer. Nitrogen gas was then purged at a flow rate of 499.8 L/h for 90 min to ensure an oxygen-free environment. Subsequently, the reactor was heated to target temperatures of 573 K, 673 K, 773 K, 873 K,

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

973 K, 1073 K, and 1173 K. For each experimental run, a specific heating rate between 10 and View Article DOI: 10.1039/D5SI 30 K/min was selected. The reactor was heated at the chosen rate until the desired target temperature was reached and then continued to be heated at the same temperature for 60 min. An additional 15 min holding period was employed to ensure complete thermal decomposition of the feedstock. Completion of pyrolysis was indicated by the absence of vapor generation in

the water displacement apparatus. The optimal operating condition was identified as the

temperature and heating rate combination that yielded the maximum amount of pyrolysis oil.

Mass loss and product separation: Mass loss during the pyrolysis experiments was determined using a high-precision weighing balance before and after each run. The collected pyrolysis oil is a complex mixture of hydrocarbons, water, acid, and alcohol. The viscosity of pyrolysis oil is generally high. To reduce the viscosity and to purify the oil, benzene is added to the pyrolysis oil in the ratio of 10:1 (benzene: oil). The mixture was transferred to a 0.25 L separating funnel and left to stand overnight (8-10 h). This step facilitated a more precise separation of the oily phase for further purification. After standing, the lighter oil fraction was recovered through

vacuum distillation for subsequent characterization.

Evaluation of moisture, volatile ash, and fixed carbon: The moisture content, volatile matter, ash, and fixed carbon of both the sieved waste orange peel powder and pyrolysis char were determined following ASTM D3172-07a ⁴⁷. Elemental composition (C, H, N, S, and O) of the pyrolyzed powder, pyrolysis char, and pyrolysis oil was measured using a CHNS micro analyzer (TruSpec, US). This comprehensive analysis ensures accurate characterization of the feedstock and pyrolysis products, which is critical for evaluating their thermal behavior and potential applications.

Higher heating value (HHV) and lower heating value (LHV): The HHV and LHV of the pyrolyzed powder (char) were calculated using Equations (4) and (5)⁴⁸.

$$LHV\binom{MJ}{kg} = \frac{0.0041868(1+0.15[O])(7837.667[C]+33888.89(H)-\frac{O}{8})}{1000}$$
(4)
View Article Onlin DOI: 10.1039/D5SU00575

$$HHV\left(\frac{MJ}{kg}\right) = \frac{LHV + 21.97[H]}{1000} \tag{5}$$

Similarly, the HHV and LHV of pyrolysis oil were estimated using Equations (6) and (7) ^{49,50}

$$LHV\left(\frac{MJ}{kg}\right) = HHV - 218.3[H](wt.\%) \tag{6}$$

$$HHV\left(\frac{MJ}{kg}\right) = 338.2[C] + 1442.8\left(H - \frac{O}{8}\right)$$
 (7)

The HHV and LHV of the pyrolysis gases were determined using Equations (8) and (9) 51.


This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14.

$$HHV\left(\frac{MJ}{Nm^3}\right) = 12.662X_{CO} + 39.782X_{CH_4} + 12.769X_{H_2} + 58.059X_{C_2H_2} + 69.693X_{C_2H_6} + 101.242X_{C_4H_8}$$
(8)

$$LHV\left(\frac{MJ}{Nm^{3}}\right) = 12.662X_{CO} + 35.814X_{CH_{4}} + 10.788X_{H_{2}} + 56.078X_{C_{2}H_{2}} + 63.748X_{C_{2}H_{6}} + 93.215X_{C_{3}H_{8}}$$

$$(9)$$



TC-: Thermocouple; l: length

Figure 2. Experimental setup used for the pyrolysis process.

View Article Online

DOI: 10.1039/D5SU00575E

2.3. Characterization procedure

Proximate and ultimate analysis: The Proximate analysis determining moisture, volatile matter, ash, and fixed carbon was conducted on both the feedstock and pyrolysis char according to ASTM D3172-89. As previously noted, ultimate (elemental) analysis of the biomass, pyrolysis char, and pyrolysis oil was carried out using a CHNS micro analyzer (TruSpec, US) to quantify carbon, hydrogen, nitrogen, sulfur, and oxygen contents.

Thermogravimetric analysis (TGA): TGA was performed on about 11-12 mg of biomass using the TGA 400 system (PerkinElmer, USA) to investigate thermal degradation behavior. The samples were thermally decomposed at heating rates of 10 K/min, 15 K/min, 20 K/min, 25 K/min, and 30 K/min under a nitrogen atmosphere, maintained at a flow rate of 0.12 L/min.

2.4. Pyrolysis parameter optimization using design of experiments (DOE)

The operational parameters, including feedstock mass and heating rate hold direct relevance for industrial scale-up. Feedstock mass determines the reactor loading, which influences heat and mass transfer efficiency during pyrolysis, while heating rate governs the rate of thermal decomposition and secondary reactions. In large-scale systems, these parameters translate into practical considerations such as reactor design, energy input requirements, throughput capacity, and overall process stability. Therefore, their systematic evaluation at the laboratory scale provides essential insights for designing scalable and economically viable pyrolysis operations. Table 2 presents the process criteria and independent variables considered for the pyrolysis of orange peel waste. It summarizes the parameters used in the experimental design and highlights the variables adjusted during the optimization study. Figure S1 (Supplementary Information) illustrates the schematic representation of the CCD process. This offers a clear visualization of the experimental design framework and the associated optimization workflow.

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Table 2: Process criteria and independent variables considered for pyrolysis of orange spice online waste.

| Symbol | Parameter | Units | Minimum | Maximum | Coded low | Coded high | Mean | Std. dev. |
|--------|----------------------|-------|---------|---------|-----------|------------|------|--------------|
| A | Feedstock biomass | kg | 1 | 3 | -1 ↔ 1 | +1 ↔ 3 | 2 | 0.73 |
| В | Temperature | K | 573 | 1173 | -1 ↔ 573 | +1 ↔ 1173 | 873 | 217.64 |
| C | Heating rate | K/min | 10 | 30 | -1 ↔ 10 | +1 ↔ 30 | 20 | 7.25 |

Type: Numeric; Subtype: Continuous

The current study employed CCD for experimental design and RSM for process optimization to enhance process efficiency and support scale-up 52 . CCD based on the Box–Wilson model, estimates curvature by combining factorial, axial, and center points, with the parameter α defining the design space 53,54 . The successful application of CCD requires systematic analysis of experimental data and validation of the model against observed values, with adjustments made if discrepancies arise $^{55-57}$. The total number of experiments in CCD is determined using Equation (10).

$$\omega = \xi^2 + 2\xi + \psi \tag{10}$$

 ω represents the overall number of experiments, ξ represents the number of independent variables investigated, and ψ represents the total number of center point repetitions. A critical aspect of CCD is the calculation of the axial distance (α \alpha α), which defines the position of the star points in the experimental region. The design geometry, whether orthogonal, spherical, rotatable, or face-centered is further characterized by the β value. For balancing spherical and face-centered design properties, β is calculated using Equation (11).

$$\beta = \left[2^{\mathrm{m}}\right]^{0.25} \tag{11}$$

Here, m denotes the number of factors. An axial point is ensured to lie within the factor $\frac{1}{3}$ region when the beta (β) value equals 1, which is the desired configuration in CCD. The relationship between the response and the independent variables is modeled using a second-order polynomial equation given below⁵⁸:

$$D = E_o + \sum_{i=1}^k E_i F_i + \sum_{i=1}^k E_{ii} F_{ii}^2 + \sum_{i=1}^k \sum_{j=1}^k E_{ij} F_i F_j + \xi$$
(12)

In this equation, D represents the response variable, k denotes the total number of independent factors, and E_0 is the intercept. The coefficients i, ii, and ij with E correspond to the linear, quadratic, and interaction effects, respectively. Meanwhile, Fi and Fj represent the coded levels of the independent variables 59,60 .

2.4.1. Optimization employing the desirability function

In addition to the DOE, criteria from the desirability function were employed to optimize the pyrolysis parameters. This method identifies the optimal process conditions by referencing assumed ideal values for target responses, including feedstock biomass, temperature, and heating rate.

Optimization plays a critical role in achieving desirable outcomes and depends on multiple influencing factors. Ensuring consistent reproducibility requires the development and stabilization of the optimization process. Therefore, optimization was conducted by establishing well-defined objectives and benchmarks. The optimization process is governed by the following equation⁵⁹:

$$\eta(x) = \left(\prod_{i=1}^{n} t_i^{\kappa_i}\right)^{1/\sum_{\kappa_i}} = \left(t_1^{\kappa_1} \times t_2^{\kappa_2} * * * \times t_n^{\kappa_n}\right)^{1/\sum_{\kappa_i}}$$

$$\tag{13}$$

where t_i denotes the ideal range for each response, n is the number of response variables evaluated, and η (x) represents the target output after assigning individual weights to each

response. Each relevant parameter is assigned a measure (κ_i) ranging from 1(+) to 5(++-Wiew Article Online To normalize the objective function, all fundamental values are standardized or scaled to a common reference point. The desirability function ranges from 0 to 1, where 0 indicates the least favorable outcome and 1 represents the most optimal result. These values quantify how closely the response approximates the desired target. Prior to batch experiments, the desirability function is utilized to determine the experimental parameters that are most likely to yield optimal production of pyrolysis char, oil, and gas, while minimizing errors.

2.5. Pyrolysis products-characterization technique:

The surface morphology of the pyrolysis char was examined using a scanning electron microscope (JSM 5610 LV, JEOL, Japan). Prior to analysis, the adsorbent was sputter-coated with gold-palladium at a wavelength of 600 nm under high vacuum and an accelerating voltage of 20 kV. Images were captured at a magnification of 250x to characterize the sample morphology. Morphological changes in orange peel waste before and after pyrolysis were further analyzed using SEM equipped with energy-dispersive X-ray spectroscopy (SEM-EDS) capabilities¹². The GC-MS analysis of the pyrolysis oils was performed using an Agilent 6890 GC coupled with 5973 MSD and HP-5 column (2.5×10⁻⁷ m×30 m×0.00025 m). The oven was initially held at 343 K for 4 min, ramped to 573 K at a constant rate of 5 K min⁻¹, and maintained at 573 K for 30 min. For the first GC-MS analysis set, ten stock solutions of pyrolysis oil were prepared in acetone; second set was prepared in dichloromethane. Calibration curve solutions were obtained by diluting the mother solutions in the respective solvents. Following the method reported by Sfetsas et al.⁶¹, 1×10⁻⁴ L of pyrolysis oil was homogenized with 0.005 L of HPLC-grade ethyl alcohol, filtered, and injected into the system. A helium carrier gas was introduced at volumetric flow rate of 1.2×10-6 L with a constant column flow rate of 0.002 L min⁻¹. The equipment was calibrated with an ionization energy of 72 eV for component ionization. The ion source temperature was maintained at 475 K, and the

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

interface temperature at 515 K. The scanning MS range was set from 42 m/z to 802 View Article Online Pyrolytic oil components were identified at different retention times using the NIST-2017 library database. Gas chromatography (Varian Model CP-3800 GC, Conquer Scientific, US) was used to determine the chemical composition of pyrolysis gas, following the ASTM E112 procedure⁶². The GC system employed a flame ionization detector (FID) with a splitless capillary inlet. The oven was initially held at 333 K for 7 min, then ramped to 543 K at 20 K min⁻¹ and held for an additional 25 min. Detector temperatures were maintained at 433 K to analyze various gas mixtures. The identification of gas components was performed based on retention times using reference data from the NIST database.

Gas chromatography of pyrolysis oil: The composition of the pyrolysis oil was analyzed using GC-MS with an Agilent 6890 system (Agilent Technologies, USA), equipped with an HP-5 column (length: 30 m; inner diameter: 0.25 mm; film thickness: 0.25 µm) and a 5973 mass selective detector (MSD). The oven temperature was initially held at 343 K for 4 min, ramped to 573 K at a rate of 5 K/min, and maintained at that temperature for 30 min. Stock solutions of pyrolysis oil were prepared in acetone and dichloromethane, and calibration curves were generated by serial dilution. The procedure followed a method previously reported by another research group⁶¹. A mixture of 0.1 μL of pyrolytic oil and 5 mL of HPLC-grade ethyl alcohol was filtered prior to injection. A 1.2 μL aliquot was then injected into the non-polar column, using helium as the carrier gas at a constant flow rate of 2 mL min⁻¹. The ionization energy was set at 72 eV, with the ion source and interface temperatures maintained at 475 K and 515 K, respectively. Scanning was performed over an m/z range of 42 to 802. Compound identification was carried out using the NIST library database.

Gas chromatography of pyrolytic gas: The chemical composition of pyrolysis gas derived from feedstocks was analyzed using gas chromatography (Varian CP-3800 GC, Conquer Scientific, USA), following the ASTM E112 method. The system was equipped with FID and a splitless capillary inlet. The oven temperature was held at 333 K for 7 min, then increased which continue of 20 K min⁻¹, and maintained at 543 K for 25 min. The detector temperature was set at 433 K. Gas components were identified based on retention time using the NIST library as a reference.

2.6. A cost-benefit analysis of orange peel waste

Table S1 (Supplementary Information) presents the parameters used to estimate the capital and operational expenses of the process plant. The total cost of the plant was calculated using the Peters and Timmerhaus method, which incorporates Lang factors added to the projected delivery costs of major equipment components⁶³. This method is widely recognized for its accuracy and is based on an extensive review of 156 capital cost estimates. It has also been applied by Goksal 64 and Bi et al. 65. To adjust the equipment, purchase cost (EPC)66, the Chemical Engineering Plant Cost Index (CEPCI) value of 699 for the year 2022, as reported by Seider et al.⁶⁷ was used. Scaling and installation adjustment factors were applied to align the equipment costs with specific design requirements, such as capacity, volumetric flow rate, and construction material. The estimation of direct and indirect expenses followed the methodologies proposed by Chhabra et al.⁶⁸ and Seider et al.⁶⁷. The fixed capital investment cost (TCIC) was determined by summing the total plant direct cost (TPDC), total plant indirect cost (TPIC), and contractor and contingency cost (CFC). For the calculation of the overall capital investment, working capital was assumed to be 5% of the total, and startup costs were estimated at 10%. The annual operational cost of the plant includes both fixed and variable components. Fixed operational costs comprise recurring expenditures such as wages, maintenance, insurance, taxes, and overheads, while variable operational costs include raw materials, utilities, consumables, and laboratory expenses. The cost of raw materials was determined in accordance with Indian Commission standards for government-regulated prices⁶⁹. For this study, a base quantity of 23,040 kg of feedstock was considered at an annual rate of □16/kg (i.e., \$0.192/kg) in the Indian context. Electricity charges were based value of Shah and Valaki ⁷⁰ and Fodah et al. ⁷¹.

Economic performance indicators used to evaluate the feasibility of pyrolyzing orange peel waste include the payback period (PB), internal rate of return (IRR), and net present value (NPV). The discounted cash flow method described by Gujjala and Won ⁷², was used for the financial analysis, assuming an IRR of 10%. The NPV was calculated after deducting applicable taxes. Sensitivity analysis was also conducted to assess the impact of variations in operational parameters on the PB⁷³.

3. Results and discussion

3.1. Feed characterization

The proximate and ultimate analyses of orange peel waste, along with its HHV, empirical formula, and elemental composition, are summarized in Table 3 and compared with literature values. The moisture content is 9.2 wt.%, falling within the acceptable limit of 10 wt.%, thereby reducing the need for additional energy input during processing. A high volatile matter content of 78.3 wt.% promotes enhanced reactivity and devolatilization during pyrolysis, while a low ash content of 2 wt.% indicates minimal operational complications due to residue buildup. The concentrations of CHNS and O are consistent with values reported for other biomass feedstocks. Notably, low nitrogen and sulfur contents suggest reduced formation of NO_X and SO_X emissions, contributing to a more environmentally benign process. The H/C and O/C molar ratios are 2.07 and 0.72, respectively, with HHV and LHV measured at 19.87 and 18.38 MJ kg⁻¹. The empirical formula, CH_{2.07}O_{0.72}, and the corresponding molecular weight of 27.70 g mol⁻¹ indicate that the material is well-suited for pyrolysis.

Analysis Present study 75 76 77 78 Proximate analysis Moisture 9.20 0.71 7.79 12.84 6.40 5.7 9.20 Ash 2.00 3.37 4.85 2.60 4.30 3.02 2.94 Volatile substance 73.75 70.51 76.70 78.30 70.80 74.6 74.79 Fixed carbon 10.50 22.17 36.09 14.05 12.60 16.68 13.07 Ultimate analysis (wt.%) Carbon 46.42 52.78 48.65 44.51 46.6 47.0 39.71 Hydrogen 8.00 5.67 5.78 5.99 7.20 6.9 6.20 Nitrogen 0.72 0.75 2.70 1.3 0.46 0.44 1.08 Sulfur 0.50 0.11 0.22 0.50 0.09 0.60 Chlorine 0.08 0.001 43.00 Oxygen 44.56 44.56 28.75 48.20 44.71 53.03 HHV(MJ/kg) 19.87 19.49 13.89 19.02 18.32 19.43 16.83 LHV(MJ/kg) 18.38 12.65 12.83 13.35 17.65 15.35 15.30 1.88 H/C 2.07 1.29 1.43 1.62 1.86 1.76 N/C 0.00 0.00 0.00 0.00 0.00 0.02 0.00 S/C 0.00 0.00 0.00 0.00 0.00 0.00 O/C 0.72 0.63 0.44 0.81 0.69 0.71 1.00 Molecular weight 27.70 25.55 23.19 29.59 27.07 27.35 33.67 (g/mol) Empirical formula $CH_{1.29}O_{0.63}$ CH_{1.43}O_{0.44} CH_{1.62}O_{0.81} $CH_{1.76}O_{0.71}$ $CH_{2.07}O_{0.72}$ CH_{1.86}O_{0.69} $CH_{1.88}O$

View Article Online DOI: 10.1039/D5SU00575B

3.2. Effect of parameters on pyro-product

This section examines the influence of process parameters—including operational temperature, heating rate, and feedstock quantity—on the yields of pyrolysis products. The discussion focuses on how these variables individually and synergistically affect the distribution of pyrochar, pyro-oil, and pyro-gas.

3.2.1. Effect of temperature on pyro-product yield

Figure 3.a presents the variation in pyrolysis product yields—char, oil, and gas—over a 1 h duration. The yield of pyrolysis char decreases progressively with increasing temperature. In contrast, pyrolysis oil yield increases, peaking at 873 K, before subsequently declining at higher temperatures. Meanwhile, pyrolysis gas yield shows a continuous rise with temperature. These observations are consistent with prior findings reported by another research group⁷⁹, which showed similar trends within the temperature range of 573 K to 773 K. Specifically, oil and gas yields increased between 573 K and 673 K, accompanied by a reduction in char yield. Beyond 673 K, pyrolysis oil vield decreased, while gas and char yields remained relatively constant. In the present study, the increase in oil yield up to 973 K was due to enhanced devolatilization and secondary cracking of biomass, which favors liquid formation. Beyond this point, the oil yield decreased. In contrast, the gas yield kept increasing, as higher temperatures promote secondary cracking, dehydrogenation, and condensable vapors reform into permanent gases such as CO, CO₂, CH₄, and H₂. Further, higher temperatures may promote tar cracking and polymerization, reducing the amount of stable condensable liquids. This could be the reason for the observed decline in oil yield and rise in gas yield at elevated temperatures. Similarly, Bhattacharjee and Biswas⁴⁷ reported that pyrolysis char yield decreases as the temperature increases from 598 K to 898 K. The pyrolysis oil yield initially increases between 598 K and 798 K, but declines with further temperature increase, while the pyrolysis gas yield steadily increases throughout the entire temperature range. As the temperature rises, HHV and

LHV of pyrolysis char increase, whereas those of pyrolysis oil decrease. These variations are DOI: 10.1039/DSSU005758 attributed to changes in the elemental composition, namely, the relative percentages of carbon, hydrogen, and oxygen. At elevated temperatures, pyro-char formed during the primary pyrolysis stage undergoes secondary reactions, enhancing the production of liquids and gases at the expense of solid char. Conversely, lower temperatures favor higher pyro-char yields. At high temperatures, the energy supplied to the biomass may exceed the bond dissociation energy, facilitating the release of volatile compounds ¹⁷, which escape as gases and result in decreased solid char yield.

3.2.2. Effect of various heating rates on pyro-product yield


Figure 3. b illustrates the effect of heating rate (K/min) on the yield of pyrolysis products (wt.%). The char yield decreases consistently as the heating rate increases from 10 K/min to 30 K/min. At higher heating rates, biomass decomposes more rapidly into volatile compounds, leading to reduced char formation. This behavior may be attributed to the dominance of secondary pyrolysis reactions under such conditions, which favor greater gas production. The effect of heating rate on char yield is particularly pronounced at lower temperatures, where these processes are more significant ^{17,80}.


In contrast, the pyrolysis oil yield increases from 10 K/min to 20 K/min but subsequently declines as the heating rate rises to 30 K/min. Meanwhile, the pyrolysis gas yield continues to increase with rising heating rate. A similar trend in the distribution of pyrolysis products under varying heating rates has been reported in other studies ⁴⁷, with observed heating rates ranging from 25 K/min to 100 K/min.

3.2.3. Effect of feedstock on pyro-product yield

Figure 3. c illustrates the effect of feedstock biomass mass on the yield of pyrolysis products. Increasing the biomass from 1 kg to 2 kg enhances pyrolysis gas formation from 44 wt.% to

50 wt.%, likely due to improved thermal decomposition, as the greater biomass volume view Article Online facilitates more extensive conversion into gaseous products. However, further increasing the biomass to 3 kg results in a decline in gas yield to 47 wt.%, which may be attributed to heat transfer limitations within the reactor. At higher biomass loads, uniform heat penetration becomes more challenging, potentially causing incomplete pyrolysis and reduced gas formation. Additionally, increased biomass mass may lead to prolonged residence times, promoting secondary reactions such as char formation, which competes with gas generation and further contributes to the observed decline in gas yield. The production of pyrolysis oil exhibited minimal variation across the biomass range from 1 to 3 kg. Notably, although gas yield increased substantially from 1 to 2 kg, it decreased with further increase to 3 kg, emphasizing the potential impact of reactor capacity limitations. At higher feedstock volumes, incomplete thermal degradation and uneven heat distribution likely reduce overall gas output. Furthermore, higher biomass inputs may enhance char formation, thereby diminishing gas yields due to competitive product pathways. However, no existing literature is available for a direct comparison of our results regarding the effect of feedstock mass on pyrolysis outcomes. underscoring the uniqueness of our findings in this area.








Figure 3. Effect of process variables on product yield: (a) temperature; (b) heating rate; (c) feedstock mass, with sub-Figures (i), (ii), and (iii) representing char, oil, and gas yields, respectively.

3.3. Thermogravimetric analysis

Figure 4 illustrates the thermogravimetric (TG) and derivative thermogravimetry (DTG) analysis of orange peel waste at varying heating rates (10, 20 and 30 K/min). The pyrolysis process can be delineated into three distinct thermal zones, the temperature ranges of which shift with increasing heating rate. At 10 K/min, Zone I spans 303-480 K, Zone II extends from

 $480-810~K, and~Zone~III~from~810-1173~K.~For~20~K/min, the~zones~are~303-488~K, \\ 488-813_{\tiny View~Article~Online}$ K, and 813–1173 K, respectively. At 30 K/min, Zone I covers 303–490 K, Zone II extends from 490-815 K, and Zone III from 815-1173 K. Zone I primarily involves the removal of moisture and the release of volatile and semi-volatile compounds. This could be the reason why only 12% mass loss was observed in this zone. Organe peels were well dried and maximum part of the moisture have been lost during drying. Zone II corresponds to the thermal degradation of the primary biomass components—cellulose, hemicellulose, and lignin—where the maximum percentage of mass loss was recorded. In contrast, Zone III exhibited a residual mass loss of approximately 7–8%, primarily attributed to the continued decomposition of lignin and the breakdown of residual char structures. The temperature ranges of these zones broaden with increased heating rates, indicating enhanced thermal inertia and delayed devolatilization. Similarly, Koçer et al. 75 reported three degradation zones at heating rates of 10–40 K/min, with Zone I occurring below 443 K, Zone II between 443–723 K, and Zone III from 723–873 K. In their study, a lower percentage of biomass decomposition was observed in Zone I at a heating rate of 10 K/min, whereas higher heating rates (15–30 K/min) enhanced the conversion efficiency, resulting in 62–76% biomass degradation. The majority of decomposition occurred in Zone II, with Zone III contributing a smaller fraction. The degradation percentages across Zones I, II, and III were approximately $10.31 \pm 2.46\%$, $63.58 \pm 1.14\%$, and $23.63 \pm 3.15\%$, respectively. Zapata et al.⁸¹ also observed similar mass loss patterns during the pyrolysis of orange peel, with 2.73% mass loss up to 273 K, 58.07% between 422–633 K, and 36.09% from 633-858 K. Hemicellulose, cellulose, and lignin—the primary components of biomass undergo degradation primarily in Zone II, typically between 423–673 K 82. Hemicellulose, due to its lower molecular weight and thermal stability, degrades at lower temperatures, whereas cellulose, characterized by its extensive hydrogen bonding and crystalline structure, exhibits higher thermal resistance. Lignin, an amorphous, highly cross-linked polymer, demonstrates significant thermal stability and degrades gradually over a broader temperature range 83. Based

on various studies, the thermal degradation temperature ranges for key biomass components are approximately 473–533 K for hemicellulose, 533–633 K for cellulose, and 633–773 K for lignin. According to Abidi et al., ⁷⁹, initial mass loss begins at 299 K and continues until 406 K (Zone I), accounting for approximately 12.38% of the total mass loss, primarily due to the evaporation of moisture and light volatile compounds. Zone II, which spans from 407 K to 680 K, is marked by the active pyrolysis stage and accounts for approximately 50.8% of the total mass loss. This stage is characterized by the thermal degradation of pectin, hemicellulose, and cellulose. The maximum degradation temperatures for these components were reported as 435 K for pectin (2.18% mass loss), 503 K for hemicellulose, and 603 K for cellulose (19.08% mass loss) 84. Bensidhom et al. 85 identified distinct decomposition peaks during the pyrolysis of lemon peel at 433 K (9%) for pectin, 508 K (22%) for cellulose, and 601 K (8.3%) for hemicellulose. In Zone III (681–973 K), lignin undergoes slow thermal decomposition, contributing to approximately 4% mass loss at a peak degradation temperature of 735 K. This phase is considered passive pyrolysis, characterized by a relatively low rate of degradation that extends up to 973 K⁸⁶. Additional studies report the thermal degradation ranges of hemicellulose, cellulose, and lignin as 483-598 K, 598-673 K, and 673-1173 K, respectively^{87,88}. These findings are consistent with the broader understanding of biomass pyrolysis and offer valuable insight into the thermal behavior of orange peel waste during thermochemical conversion.

Sustainability Accepted Manuscript

Figure 4. TGA and DTG analysis curve showing weight loss of orange peel waste at varying heating rates. The TGA curve is the weight loss curve and DTG is the derive weight curve.

an Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14. This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence


3.4. Process scale-up analysis and feasibility evaluation


View Article Online DOI: 10.1039/D5SU00575B


Evaluating the viability of the pyrolysis process requires a comprehensive analysis of production yield, raw material influence, and production rate. To ensure a realistic assessment and accurate scale-up, the process conversion capability was varied between 0.48 and 0.87. Considering standard engineering assumptions, it is essential to scale up any production process to achieve mass production. For this purpose, the pilot-scale process was extrapolated to an industrial-scale unit using the capacity power law equations^{89,90}.


$$\frac{yield_{p_c}}{yield_{p_c}} = \left(\frac{Capacity_2}{Capacity_1}\right)^m \tag{14}$$

The $y_{ield_{p_i}}$ and $y_{ield_{p_i}}$ were production yield. The exponent 'm' in this equation represents scaling efficiency. A value of m=1 would indicate perfect linear scaling. However, in practical systems, heat and mass transfer limitations, energy requirements, and equipment design constraints prevent ideal scale-up. For this reason, previous studies have reported realistic values of 'm' between 0.48 and 0.87, where the lower end reflects stronger limitations during scale-up and the higher end indicates better efficiency, though still below ideal conditions. In the present work, this range of 'm' was adopted to model different scenarios and assess feasibility across capacities. The production yield scaling exponent 'm' varies from 0.48 to 0.87, and yield, the initial production yield was considered at 4 g. The scale-up feasibility was assessed using the defined conversion capabilities and power law, with the scaling exponent m varied between 0.48 and 0.87 to model different scaling scenarios. The process was scaled from a base capacity of 4 g/h to an industrial throughput of 4000 kg/h. Figure 5 illustrates projected product yields at varying process capacities for different scaling factors. This scaling was based on optimal pyrolysis product yields: pyro-char (0.281), pyro-oil (0.229), and pyro-gas (0.489). The results demonstrated that the production rate increased proportionally with the process capacity, validating the applicability of the power law for this scale-up analysis (see Figure 5).












Figure 5. Projected product yields from orange peel waste pyrolysis at varying process capacities for different scaling factors: (a) m = 0.48; (b) m = 0.58; (c) m = 0.68; (d) m = 0.78; (e) m = 0.87. Note: m denotes the scaling factor.

3.6. Analysis using statistical methods and development of models

View Article Online DOI: 10.1039/D5SU00575B

3.6.1. Analysis of the statistical model

Table 4 presents the experimental design for process variables and the corresponding responses outputs. The design includes twenty distinct iterations combining various levels of the process variables. The residuals, typically around ± 0.79 , indicate a close agreement between predicted and experimental results, while leverage values ranged from 0.11 to 0.79. This section outlines the experimental conditions, focusing on the effects of feedstock biomass, temperature, and heating rate on the pyrolysis product yields. The final process desirability is also discussed. The choice of 2 kg feedstock biomass was made to facilitate process scale-up and to attain optimal operating conditions.

Table 4. Experimental design involving process variables and corresponding response outputs.

| Run | Factor A | Factor B | Factor C | Respon | se 1: | Respon | nse 2: | Response | 3: |
|-----|----------|----------|----------|---------|---------|--------|--------|-----------|-------|
| | | | | pyrolys | is char | pyroly | | pyrolysis | gas |
| | | | | (wt.%) | | (wt.%) | | (wt.%) | |
| | | | | Е | T | Е | T | Е | T |
| 1 | 1 | 873 | 20 | 30.12 | 32.69 | 23.02 | 22.84 | 46.86 | 44.47 |
| 2 | 2 | 873 | 30 | 27.45 | 34.42 | 23.06 | 22.98 | 49.49 | 42.60 |
| 3 | 2 | 873 | 20 | 28.12 | 26.52 | 22.89 | 22.76 | 48.99 | 50.72 |
| 4 | 2 | 873 | 20 | 28.12 | 26.52 | 22.89 | 22.76 | 48.99 | 50.72 |
| 5 | 2 | 573 | 20 | 27.7 | 30.94 | 20.21 | 20.14 | 52.09 | 48.92 |
| 6 | 1 | 1173 | 30 | 44.55 | 42.70 | 25.33 | 25.45 | 30.12 | 31.85 |
| 7 | 3 | 873 | 20 | 28.89 | 31.12 | 22.33 | 22.89 | 48.78 | 45.99 |
| 8 | 1 | 573 | 30 | 40.89 | 39.17 | 20.13 | 20.24 | 38.98 | 40.59 |
| 9 | 2 | 873 | 20 | 28.12 | 26.52 | 22.89 | 22.76 | 48.99 | 50.72 |
| 10 | 2 | 873 | 10 | 27.89 | 25.71 | 22.01 | 22.47 | 50.1 | 51.81 |
| 11 | 1 | 1173 | 10 | 20.56 | 21.55 | 24.02 | 23.86 | 55.42 | 54.59 |
| 12 | 3 | 1173 | 10 | 20.01 | 20.53 | 24.19 | 23.99 | 55.8 | 55.48 |
| 13 | 2 | 873 | 20 | 28.12 | 26.52 | 22.89 | 22.76 | 48.99 | 50.72 |
| 14 | 3 | 1173 | 30 | 42.45 | 41.24 | 24.54 | 24.33 | 33.01 | 34.43 |
| 15 | 1 | 573 | 10 | 42.45 | 42.46 | 19.46 | 19.57 | 38.09 | 37.96 |
| 16 | 2 | 873 | 20 | 28.12 | 26.52 | 22.89 | 22.76 | 48.99 | 50.72 |
| 17 | 3 | 573 | 30 | 39.23 | 37.04 | 20.15 | 20.21 | 40.62 | 42.74 |
| 18 | 2 | 1173 | 20 | 21.02 | 22.58 | 23.89 | 24.34 | 55.09 | 53.08 |
| 19 | 3 | 573 | 10 | 40.13 | 40.78 | 21.01 | 20.80 | 38.86 | 38.42 |
| 20 | 2 | 873 | 20 | 28.12 | 26.52 | 22.89 | 22.76 | 48.99 | 50.72 |

Note: E: Experimental; T: Theoretical; A: Feedstock biomass (kg); B: Temperature (K): G: Online Heating rate (K/min)

The interactive model terms reveal the combined influence of two parameters, whereas the linear model terms describe the effect of individual parameters. A positive coefficient in the model equation indicates a synergistic effect, while a negative coefficient signifies an antagonistic effect 91. Table 5 displays the analysis of variance (ANOVA) results, including pvalues, F-values, and R² coefficients. These values reflect the outcomes of all experimental runs. The proposed model was evaluated using regression model analysis, a validated method for assessing the relationship between response data and model predictions⁹². The p-value quantifies the likelihood of observing deviations due to random chance, while the F-value represents the ratio of variances, indicating model significance. According to the Fischer Ftest, a robust and accurate model typically exhibits low p-values and high F-values^{91,93,94}. For pyrolysis char, the ANOVA yielded F-value of 10.39 and p-value of 0.05%; for pyrolysis oil, F-value of 49.41 and p-value of 0.01%; and for pyrolysis gas, F-value of 9.15 and p-value of 0.09%. These results confirm the model's efficacy and predictive accuracy. The model was significantly influenced by the quadratic terms A^2 and B^2 (p < 0.05), as well as by the linear terms A (feedstock mass), B (temperature), and C (heating rate), and the interaction terms AB, AC, and BC. The R² coefficient represents the degree of fit between the regression equation and the experimental data, with a value of 1 indicating a perfect fit and 0 indicating no correlation⁵⁸. The model demonstrated strong predictive capability, with R² and adjusted R² values of 0.81 (pyrolysis char), 0.95 (pyrolysis oil), and 0.79 (pyrolysis gas). The close agreement between adjusted R² and predicted R²—differing by less than 0.4 for pyrolysis char, 0.11 for pyrolysis oil, and 0.42 for pyrolysis gas—further supports the model's reliability and relevance.

Table 5: Analysis of variance (ANOVA) results showing p-values, F-values, and R² coefficients.

| Source | Sum of s | quares | | df | Mean so | quare | | F-value | | | p-value | | | |
|----------------------------|----------|--------|---------|----|---------|--------|--------|---------|--------|--------|---------|----------|--------|-------------|
| | С | О | G | | С | О | G | С | О | G | С | O | G | |
| Model | 1004.60 | 47.78 | 896.74 | 9 | 111.62 | 5.31 | 99.64 | 10.39 | 49.41 | 9.15 | 0.0005 | < 0.0001 | 0.0009 | significant |
| A- Feedstock biomass | 6.18 | 0.0068 | 5.78 | 1 | 6.18 | 0.0068 | 5.78 | 0.5751 | 0.0629 | 0.5304 | 0.4657 | 0.8070 | 0.4832 | |
| B- Temperature | 174.81 | 44.14 | 43.26 | 1 | 174.81 | 44.14 | 43.26 | 16.27 | 410.82 | 3.97 | 0.0024 | < 0.0001 | 0.0742 | |
| C-Heating rate | 189.49 | 0.6350 | 212.06 | 1 | 189.49 | 0.6350 | 212.06 | 17.64 | 5.91 | 19.47 | 0.0018 | 0.0354 | 0.0013 | |
| AB | 0.2211 | 0.5995 | 0.0924 | 1 | 0.2211 | 0.5995 | 0.0924 | 0.0206 | 5.58 | 0.0085 | 0.8888 | 0.0398 | 0.9284 | |
| AC | 0.0990 | 0.7750 | 1.43 | 1 | 0.0990 | 0.7750 | 1.43 | 0.0092 | 7.21 | 0.1311 | 0.9254 | 0.0229 | 0.7248 | |
| BC | 298.78 | 0.4278 | 321.82 | 1 | 298.78 | 0.4278 | 321.82 | 27.81 | 3.98 | 29.55 | 0.0004 | 0.0740 | 0.0003 | |
| A^2 | 79.62 | 0.0290 | 82.69 | 1 | 79.62 | 0.0290 | 82.69 | 7.41 | 0.2701 | 7.59 | 0.0215 | 0.6146 | 0.0203 | |
| B^2 | 0.1530 | 0.7501 | 0.2255 | 1 | 0.1530 | 0.7501 | 0.2255 | 0.0142 | 6.98 | 0.0207 | 0.9074 | 0.0246 | 0.8884 | |
| C^2 | 34.58 | 0.0038 | 33.85 | 1 | 34.58 | 0.0038 | 33.85 | 3.22 | 0.0356 | 3.11 | 0.1030 | | | |
| Residual | 107.42 | 1.07 | 108.91 | 10 | 10.74 | 0.1074 | 10.89 | | | | | | | |
| Lack of Fit | 107.42 | 1.07 | 108.91 | 5 | 21.48 | 0.2149 | 21.78 | | | | | | | |
| Pure Error | 0.0000 | 0.0000 | 0.0000 | 5 | 0.0000 | 0.0000 | 0.0000 | | | | | | | |
| Cor Total | 1112.03 | 48.86 | 1005.65 | 19 | | | | | | | | | | |

RSC Sustainability Page 38 of 87

Sustainability Accepted Manuscript

df remains the same for char, oil, and gas; C = pyrolysis char; O = pyrolysis oil; G = pyrolysis gas

Fit statistics

Char: Std. Dev.: 3.28; Mean: 31.10; C.V.%: 10.54; R²: 0.90; Adjusted R²: 0.81; Predicted R²:0.41; Adeq Precision: 9.57

Oil: Std. Dev.: 0.33; Mean: 22.53; C.V.%: 1.45; R²: 0.97; Adjusted R²: 0.95; Predicted R²: 0.84; Adeq Precision: 25.32

Gas: Std. Dev.: 3.30; Mean: 46.36; C.V.%: 7.12; R²: 0.89; Adjusted R²: 0.79; Predicted R²: 0.37; Adeq Precision: 10.12

Model Comparison Statistics:

Char: PRESS: 654.38; -2 Log Likehood: 90.38; BIC: 120.34; AICc:134.82

Oil: PRESS: 7.78; -2 Log Likehood: -1.72; BIC: 28.24; AICc:42.72

Gas: PRESS: 630.34; -2 Log Likehood: 90.65; BIC: 120.61; AICe:135.10

$$pyrolysis\ char = 105.34 - 22.57 \times A - 0.06 \times B - 2.74 \times C$$

$$+ 5.5 \times 10^{-4} \times A \times B - 0.01 \times A \times C + 2.04 \times 10^{-3} \times B \times C$$

$$+ 5.38 \times A^{2} + 2.62 \times 10^{-6} \times B^{2} + 0.04 \times C^{2}$$

$$pyrolysis\ oil = 10.43 + 1.03 \times A + 0.02 \times B + 0.04 \times C$$

$$- 9.13 \times 10^{-4} \times A \times B - 0.03 \times A \times C + 7.7 \times 10^{-5} \times B \times C$$

$$+ 0.1 \times A^{2} - 5.8 \times 10^{-6} \times B^{2} - 3.73 \times 10^{-4} \times C^{2}$$

$$pyrolysis\ gas = -15.79 + 21.54 \times A + 0.04 \times B + 2.70 \times C$$

$$+ 3.58 \times 10^{-4} \times A \times B + 0.04 \times A \times B - 2.11 \times 10^{-3} \times B \times C$$

$$(16)$$

 $-5.48 \times A^2 + 3.18 \times 10^{-6} \times B^2 - 0.04 \times C^2$

3.6.2. Process variable interactive impacts

3D and 2D surface plots were employed to illustrate the interplay among process variables, including feedstock mass, temperature, and heating rate. Figure 6 presents the combined effects of these factors on the yield of pyrolysis char (wt.%). Specifically, Figure 6a(i) and 6a(ii) display the 2D and 3D surface plots, respectively, of pyrolysis char yield as a function of feedstock mass and temperature. Figures 6b(i) and 6b(ii) illustrate the yield in relation to feedstock mass and heating rate, while Figure 6c(i) and 6c(ii) present the yield as a function of temperature and heating rate. According to the ANOVA results, the interaction term in the model exhibited a statistically significant p-value of ≈ 0.0005 . The pyrolysis char yield decreased from 42.45% to 20.01% as the feedstock mass increased from 1 to 3 kg and the temperature rose from 573 to 1173 K, indicating a notable interactive effect between these variables. This suggests a favorable correlation between feedstock mass and temperature, with pyrolysis char output being directly proportional to the values of the interactive model parameters—implying that adjusting these parameters upward or downward would yield a corresponding effect. It has been reported that biomass-derived pyrolysis char does not undergo complete carbonization at temperatures below 573 K, regardless of the heating rate. Complete carbonization typically occurs at temperatures $\geq 773 \text{ K}^{95}$. An initial increase in both feedstock mass and heating rate led to a reduction in pyrolysis char yield, reaching a minimum point; however, further increases in these factors resulted rise in char production [see Figure 6b(i) and

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

b(ii)]. These findings are consistent with previous studies reported 28% char yield from rice husk sawdust pyrolyzed at 773 K in 60 min residence time⁹⁶, and 43% char yield from rice husk pyrolysis at the same temperature in 55 min residence time⁹⁷. Variations in char yield can likely be attributed to differences in feedstock composition, underscoring the importance of selecting appropriate biomass for achieving targeted carbon black yields in specific applications. A detailed examination of the response surfaces reveals that the trends exhibit a falling ridge pattern, characteristic of the polynomial behaviour described in Equation (15) under the framework of RSM. The contour plots exhibit falling ridge patterns [Figure 6a(i) and 6b(i)] and a simple maximum [Figure 6c(i)], collectively reflecting the behaviour of a second-order polynomial response^{59,98,99}.

Figure 7 illustrates the combined effects of feedstock mass, temperature, and heating time on pyrolysis oil (wt.%) yield. Specifically, Figures 7a(i) and 7a(ii) display the 2D and 3D surface plots of pyrolysis oil yield as a function of feedstock mass and temperature. Figures 7b(i) and 7b(ii) show the 2D and 3D surface plots of pyrolysis oil yield as a function of feedstock mass and heating time. Similarly, Figures 7c(i) and 7c(ii) present the yield as the function of temperature and heating time. According to the ANOVA results, the interactive model term exhibited a highly significant p-value of < 0.0001. The pyrolysis oil yield increased from 19.46% to 24.19% when the feedstock mass was raised from 1 to 3 kg and the temperature increased from 573 to 1173 K, indicating strong positive correlation between these two variables. The yield was directly proportional to the values of the interactive parameters, implying that increasing or decreasing them would result in corresponding changes in oil output. Figures 7b(i) and 7b(ii) suggest that the response surface becomes steeper as both feedstock mass and heating time increase. Notably, no previous studies have reported this specific behaviour. A detailed examination of the trends in these plots reveals a rising ridge pattern, consistent with the polynomial form described by Equation (16) within the framework

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

of RSM. Furthermore, Figure 7a(i), 7b(i), and 7c(i) each present a monotonic surface entire characterized by a smooth, plane-like incline without significant curvature or inflection points, indicative of a second-order polynomial response 59,99.

Figure 8 illustrates the combined effects of feedstock mass, temperature, and heating time on pyrolysis gas (wt.%) yield. Specifically, Figures 8a(i) and 8a(ii) present the 2D and 3D surface plots, respectively, of pyrolysis gas yield as a function of feedstock mass and temperature. Figures 8b(i) and 8b(ii) display the 2D and 3D surface plots as a function of feedstock mass and heating time, while Figures 8c(i) and 8c(ii) show the corresponding plots for temperature and heating time. The interactive model term exhibited a statistically significant p-value of \approx 0.0009. The pyrolysis gas yield increased from 38.09% to 55.8% as the feedstock mass was increased from 1 to 3 kg and the temperature was raised from 573 to 1173 K, indicating positive correlation between feedstock mass and temperature with respect to gas production. Figures 8b(i) and 8b(ii) demonstrate a decreasing trend in pyrolysis gas yield as feedstock mass and heating time increase. This response pattern has not been previously reported in the literature. A detailed analysis of the surface plots reveals that the trends follow a rising ridge pattern, consistent with the polynomial form described in Equation (17) under RSM. Figure 8a(i) exhibit a rising ridge, Figure 8b(i) represents a minimax behaviour, and Figure 8c(i) displays a simple maximum. These surface patterns are characteristic of a second-order polynomial response98-100.

Page 42 of 87

Pyrolysis char (wt.%) 1173 (i) 45 (ii) 40 1073 -35 25 Pyrolysis char (wt.%) 973 -30 B: Temperature (K) 25 873 -6 • 20 15 773 673 1173 30 35 1073 2.5 973 873 573 A: Feedstock biomass (kg) B: Temperature (K) 1.5 2.5 2 3 573 1 A: Feedstock biomass (kg)

RSC Sustainability

Figure 6a. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis char yield (wt.%) as a function of feedstock biomass and temperature.




Figure 6b. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis char yield (wt.%) as a function of feedstock biomass and heating rate.

Sustainability Accepted Manuscript

RSC




Figure 6c. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis char yield (wt.%) as a function of heating rate and temperature.




Figure 7a. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis oil yield (wt.%) as a function of feedstock biomass and temperature.

Page 46 of 87 **RSC Sustainability**

Sustainability Accepted Manuscript




Figure 7b. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis oil yield (wt.%) as a function of feedstock biomass and heating rate.





Figure 7c. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis oil yield (wt.%) as a function of heating rate and temperature.



RSC Sustainability

Page 48 of 87

Sustainability Accepted Manuscript

Figure 8a. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis gas yield (wt.%) as a function of feedstock biomass and temperature.




Figure 8b. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis gas yield (wt.%) as a function of feedstock biomass and heating rate.

Sustainability Accepted Manuscript

RSC

Figure 8c. (i) Two-dimensional contour and (ii) three-dimensional contour plots showing pyrolysis gas yield (wt.%) as a function of heating rate and temperature.

cess Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

3.6.3. Determining ideal process parameters using desirability function methodology/possuo0575B

Several aspects of the pyrolysis experiment and their associated responses were investigated using numerical optimization in Design Expert 13 to determine the optimal batch reaction parameters. The optimization aimed to maximize the values of the previously discussed response variables through a numerical approach based on desirability criteria available within the software—namely, range, minimization/maximization, and target specifications. The desirability function in RSM quantifies how well selected process conditions fulfil multiple optimization goals, with values ranging from 0 (completely undesirable) to 1 (fully desirable). However, the optimization process may require considerable energy and time due to the extensive number of batch experiments needed to obtain reliable results. For all three pyrolysis product yields—char, oil, and gas—numerical optimization was conducted using a CCD within the RSM framework and guided by desirability function approach⁵⁸. The target values for the process parameters were feedstock biomass of 2 kg, temperature of 873 K, and a heating rate of 20 K/min. Although the design of experiments (DOE) predicted high response values, these conditions were identified as optimal within the constraints of the chosen parameter space. All pyrolysis process variables were assigned the default highest importance level (+++++), indicating a strong influence on the response variables. Each independent and dependent variable was given an equal weight of 1. Table 6a presents the target constraints for factors and responses, including the optimization goal, lower and upper limits, weights, and assigned importance. Table 6b represents final desirability based on input factors and responses. The optimized solution was obtained at 2 kg feedstock biomass, 873 K temperature, and 20 K/min heating rate, yielding 26.52 wt.% pyrolysis char, 22.76 wt.% pyrolysis oil, and 50.72 wt.% pyrolysis gas. The final composite desirability value of the process was 0.7. The associated contour plots illustrating the optimization results and minimum standard errors are shown in Figure 9 (see Figures 9a, 9b, and 9c).


Table 6: Detailed goal specification and the importance of the parameters and optimized ricle Online condition of the pyrolysis process along with desirability.

(a). Specification of factor goals, upper and lower limits, upper and lower weights, and corresponding importance levels.

| Name | Goal | Lower limit | Upper limit | Lower weight | Upper weight | Importance | |
|----------------------|----------|----------------|----------------|-----------------|-----------------|------------|--|
| A: Feedstock biomass | In range | 1 | 3 | 1 | 5 | 5 | |
| B: Temperature | In range | 573 | 1173 | 1 | 5 | 5 | |
| C: Heating rate | In range | 10 | 30 | 1 | 5 | 5 | |
| pyrolysis char | maximize | 20.01 | 44.55 | 1 | 5 | 5 | |
| pyrolysis oil | maximize | 19.46 | 25.33 | 1 | 5 | 5 | |
| pyrolysis gas | maximize | 30.12 | 55.8 | 1 | 5 | 5 | |

(b). Final desirability based on input factors (feedstock biomass, temperature, and heating rate) and responses (pyrolysis char, pyrolysis oil, and pyrolysis gas).

| Feedstock | Temperature | Heating | pyrolysis | pyrolysis | pyrolysis | Desirability |
|--------------|-------------|---------|-----------|-----------|-----------|--------------|
| biomass (kg) | (K) | rate | char | oil | gas | |
| | | (K/min) | (wt.%) | (wt.%) | (wt.%) | |
| 2 | 873 | 20 | 26.52 | 22.76 | 50.72 | 0.70 |
| | | | | | | |







Figure 9a. Optimization of pyrolysis process parameters [feedstock biomass (kg) and temperature (K)] to maximize char yield using desirability criteria and minimizing standard error: (i) optimized pyrolysis char yield outcome; (ii-iv) optimized conditions for pyrolysis char yield.







Figure 9b. Optimization of pyrolysis process parameters [feedstock biomass (kg) and heating rate (K/min)] to maximize oil yield using desirability criteria and minimizing standard error: (i) optimized pyrolysis oil yield outcome; (ii-iv) optimized conditions for pyrolysis oil yield.






Figure 9c. Optimization of pyrolysis process parameters [temperature (K) and heating rate (K/min)] to maximize gas yield using desirability criteria and minimizing standard error: (i) optimized pyrolysis gas yield outcome; (ii-iv) optimized conditions for pyrolysis gas yield.

DOI: 10.1039/D5SU00575E

3.7. Pyrolysis char characterization


This section discusses the characteristics of the pyrolysis product yield derived from orange peel waste, obtained under optimized conditions: feedstock biomass of 2 kg, pyrolysis temperature of 873 K, and a heating rate of 20 K/min. The resulting product distribution included 26.52 wt.% pyrolysis char, 22.76 wt.% pyrolysis oil, and 50.72 wt.% pyrolysis gas, with an overall process desirability of 0.70.

3.7.1. CHO and surface morphology of pyrolysis char

CHNSO study: The elemental composition, specifically carbon, hydrogen, and oxygen in pyrolysis char is critical for evaluating its potential as a fuel. An increase in carbon and hydrogen content enhances the heating value of pyro-char, whereas a higher oxygen content reduces it and promotes undesirable reactions such as polymerization. Figure 10a shows the carbon, hydrogen, and oxygen composition of pyrolysis char produced from orange peel waste. The results indicate that carbon content increases while oxygen content decreases with rising pyrolysis temperature. Hydrogen content also increases with temperature. Nitrogen content declines as the temperature increases, while sulfur content remains relatively unchanged. These findings confirm a more pronounced trend of increasing carbon and decreasing oxygen compared to previous datasets. Similar observations have been reported in the literature^{47,101–103}. Hernandez-Mena et al. ¹⁰¹ observed that that pyro-char typically contains low oxygen levels (30–47 wt.%) and elevated hydrogen and carbon contents (44–62 wt.%), making it suitable for use in gasification or combustion-based energy applications¹⁰³.

Scanning electron microscopy with energy-dispersive X-ray spectroscopy (SEM-EDX) analysis: The surface morphology and elemental composition of orange peel waste and its corresponding pyrolysis char were examined using SEM-EDX, as shown in Figure 10b. The SEM micrographs in Figure 10b (i) and Figure 10b (ii) reveal a ruptured and spongy surface

morphology. The average particle diameter increased from 2.8 μm in the raw biomass to 3.8 μm in the ra um after pyrolysis, likely due to the breakdown of complex organic structures, the formation of agglomerated compounds, and the volatilization of organic components during pyrolysis. In contrast to the findings of Elnour et al. 104, who reported pyrolysis char with randomly shaped, sharp-edged particles, the pyrolysis char in the present study exhibited a similarly random shape but without sharp edges, featuring deep channels and a more porous structure. The observed morphology, with an average particle size of 12.8 µm, suggests the potential for enhanced mechanical interlocking, as the porous structure could facilitate the infiltration of molten polymer chains ^{105,106}. Chen et al. ¹⁰⁷ reported pyrolysis char with sheet-like structures of varying sizes, smooth surfaces, and honeycomb-like voids, noting that auto decomposition occurred at higher temperatures. Their EDX mapping indicated a uniform distribution of elemental components. In the current investigation, energy-dispersive X-ray spectroscopy identified C and O as the major elements, along with impurity Ca, shown in Figure 10b(iii). The observations in this study align with those of Kordoghli et al.¹⁰⁸, who reported that highmagnification SEM revealed vibrant surface texture with clearly visible pores in both pyrolysis char and raw biomass samples.



(a)

peel waste; (iii) EDX spectrum of pyrolyzed orange peel waste.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

3.7.2. CHO study of pyrolysis-oil using gas chromatography-mass spectrometry (Control on the Control of the Con

Figure 11 presents the elemental analysis of pyrolysis oil, highlighting the effects of CHNSO content. With increasing pyrolysis temperature, the oxygen and sulfur content in the pyrolysis oil increases, while the carbon and hydrogen content decreases. These trends are consistent with findings reported by Yang et al.¹⁰⁹ in fast pyrolysis. Although that study included catalytic pyrolysis, they noted that carbon content in catalytic pyrolysis oil remained higher than in non-catalytic oil at temperatures up to 873 K. The present investigation, however, focuses solely on the non-catalytic pyrolysis of orange peel waste. Similar behaviour has been observed in the pyrolysis of other biomass feedstocks, such as paddy husk, within the 723-873 K temperature range^{109,110}. The observed increase in oxygen and hydrogen concentrations may be attributed to the loss of carbon through volatilization, resulting in the formation of non-condensable gaseous products. These fractured gaseous components tend to retain carbon, thereby reducing the carbon content in the remaining pyrolysis oil. At higher temperatures, thermal cracking becomes more pronounced, leading to the production of carbon-rich, lower molecular weight gases. Table 7 summarizes the identified compounds in the pyrolysis oil obtained at 873 K, including their retention times and potential applications. The GC-MS analysis indicates that many of the detected components incorporate oxygen within their molecular structures, which is consistent with the elevated oxygen content observed.

The underlying mechanisms responsible for the variations in oxygen and carbon content with increasing temperature may be further elucidated through a detailed stoichiometric analysis of the primary and secondary pyrolysis reactions. The pyrolysis oil obtained at 873 K exhibited a dark brown color and smoky appearance. Several new compounds were identified, including D-limonene, various decanes, phenol, benzene, and phenyl derivatives.

These constituents exhibit both aromatic and aliphatic characteristics. Due to their broad constituents applications, the presence of such compounds enhances the value proposition of converting orange peel waste into pyrolytic oil.




Figure 11. Effect of CHNSO composition on pyrolysis oil.

GC-MS analysis of the pyrolysis oil: The pyrolysis oil derived from orange peel waste was subjected to both quantitative and qualitative characterization. GC-MS analysis was performed using an Agilent 6890 system equipped with HP-5 column (0.25 μm×30 m×0.25 mm) and a 5973 mass selective detector (MSD)¹¹¹. The analysis identified several novel compounds, comprising a mixture of aromatic and aliphatic constituents. Notable compounds included D-limonene, furfural, propanol, benzene, phenyl derivatives, and cyclopentane-1-hydroxymethyl-1,3-dimethyl. These findings are in agreement with the work of Abidi et al.⁷⁹, who identified similar components such as D-limonene, acetophenone, acetic acid, glycerin, hydroquinone, levoglucosan, hexanal (4-methyl), oleic acid, and stearic acid. The presence of these compounds, many of which possess industrial relevance, underscores the potential of pyrolysis

oil as a source of value-added chemicals, further highlighting the appeal of the pyrolly \$35000575B process for biomass valorization.

Table 7. Summary of the identified compounds (based on GC-MS analysis) in pyrolysis oil obtained at 873 K, including their retention times and potential applications.

| Peaks | Retention time (min) | | | Molecular weight | 1.1 | | | | |
|-------|-------------------------|-------|--|---------------------|--|--|--|--|--|
| 1 | 2.13 | 11.89 | 1,2-Dimethyl benzene (C ₈ H ₁₀) | 106 | Printing, leather, and rubber industries ¹¹² | | | | |
| 2 | 2.81 | 8.25 | 2,3 Butanedione $(C_4H_6O_2)$ | 86 | Production from glucose by fermentation ¹¹³ | | | | |
| 3 | 3.35 | 9.52 | D-limonene $(C_{10}H_{16})$ | 136 | Cosmetic usage ¹¹⁴ | | | | |
| 4 | 4.55 | 1.89 | Acetophenon e (C ₉ H ₁₀ O ₃) | 166 | Used for the manufacture of soaps, detergents, lotions, creams, and perfumes 115 | | | | |
| 5 | 6.66 | 1.46 | (4E,6Z)-2,6- Dimethyl- 2,4,6 Octatriene $(C_{10}H_{16})$ | 136 | used as a perfume component ¹¹³ | | | | |
| 6 | 7.44 | 2.45 | Acetic acid $(C_2H_4O_3)$ | 76 | For pharmaceutical application ^{58,116} | | | | |
| 7 | 7.85 | 0.86 | 1,2,3 Trimethyl benzene (C ₉ H ₁₂) | 120 | It is derived from the C9 aromatic fraction in petroleum distillation or synthesized via toluene and xylene methylation ¹¹³ | | | | |
| 8 | 10.41 | 2.62 | 1,4 -Diethyl benzene (C ₁₀ H ₁₄) | 134 | In nanotechnology ¹¹⁷ | | | | |
| 9 | 10.62 | 8.89 | Citronellal $(C_{10}H_{18}O)$ | 154 | Used as a robust antifungal qualifier | | | | |
| 10 | 10.75 | 6.11 | Octantal (CH ₃ (CH ₂)6 | 128 | For perfume and food industries ¹¹⁹ | | | | |

CHO)

| 11 | 11.40 | 0.86 | Phenol (C ₆ H ₆ O) | 94 | Used medically to help some still sale |
|----|-------|------|---|-----|---|
| 12 | 11.53 | 1.44 | Glycerin (C ₃ H ₈ O ₃) | 92 | Used in the cosmetic industry ¹²⁰ |
| 13 | 12.51 | 1.56 | Methyl hydroquinone (C ₆ H ₆ O ₂) | 110 | For skin whitening ¹²¹ |
| 14 | 13.78 | 9.05 | Guaiacol (C ₇ H ₈ O ₂) | 124 | Precursor to various flavorants 122 |
| 15 | 14.62 | 9.96 | 4-propyl guaiacol $(C_{10}H_{14}O_2)$ | 166 | Medicinal use as an antiseptic, local anesthetic ¹²² |
| 16 | 17.86 | 2.23 | Acetosyringo ne $(C_{10}H_{12}O_4)$ | 196 | allows higher transformation efficiency in plants ¹²³ |
| 17 | 18.76 | 2.01 | Levoglucosa n (C ₆ H ₁₀ O ₅) | 162 | Synthesis of chiral polymers such as nonhydrolyzable glucose polymers 124 |
| 18 | 19.08 | 4.45 | 2.4 xylenol ($C_8H_{10}O$) | 122 | Antioxidant 113 |
| 19 | 20.35 | 1.08 | | 114 | Used as a flavoring agent ¹²⁵ |
| 20 | 22.86 | 2.85 | 4-ethyl- catechol $(C_8H_{10}O_2)$ | 138 | Perfume and pharma industries ¹¹³ |
| 21 | 24.57 | 2.45 | Heptadecane nitrile $(C_{17}H_{33}N)$ | 251 | Used as a solvent and polycarboxylic acid production ³⁴ |
| 22 | 25.99 | 1.76 | | 282 | Used for the food and cosmetic industry ¹²⁶ |
| 23 | 26.40 | 1.03 | Stearic acid (C ₁₈ H ₃₆ O ₂) | 284 | Used for the food and cosmetic industry ¹²⁶ |
| 24 | 28.60 | 1.17 | Arachic acid (C ₂₀ H ₄₀ O ₂) | 312 | Used in the pharmaceutical industry 127 |
| 25 | 30.35 | 0.98 | Monoplamiti $n (C_{19}H_{38}O_4)$ | 330 | Used in drug delivery systems ¹²⁸ |
| 26 | 32.65 | 0.83 | Squalene (C ₃₀ H ₅₀) | 410 | Used for the cosmetic industry ¹²⁹ |

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

| 27 | 33.40 | 0.66 | n- Tetracosane (C ₂₄ H ₅₀) | 338 | Used as a solvent 10 and SSU 1850 B microencapsulation 130 |
|----|-------|----------------|---|-----|---|
| 28 | 37.98 | 0.14 | β -Silosterol (C ₂₉ H ₅₀ O) | 414 | lowering cholesterol levels and improving symptoms of an enlarged prostate (BPH) ¹³¹ |
| 29 | | 1.55 | Unidentified | | - / |
| 30 | | $\Sigma = 100$ | | | |

3.7.3. GC analysis of pyrolysis gas

GC analysis of pyrolysis gas derived from orange peel waste is summarized in Table 8. The primary constituents of the pyrolysis gas include CO, CO₂, H₂, CH₄, C₂H₂, C₂H₆, C₃H₈, and NO_x. At 873 K, the gas exhibited a CO/H₂ ratio of 1:2.57, an HHV of 19.87 MJ/m³, and a LHV of 18.38 MJ/m³. These results align with previous studies¹⁴. Comparison with data reported in reference⁸⁵, in which pyrolysis was conducted at temperatures ranging from 573 K to 773 K—shows that the yields of CO, CO₂, CH₄, H₂, and N₂ varied between 10.78–59.79%, 0.12–0.68%, 0.42–3.57%, 0.46–0%, and 88.09–34.33%, respectively. The current study, performed at 873 K, observed substantial quantities of these gases, consistent with increased gas yield and composition shifts at elevated temperatures.

Table 8: GC analysis of pyrolysis gas derived from orange peel waste.

| Feedstock | N ₂ | CO ₂ | СО | CH ₄ | H ₂ | C_2H_2 | C ₂ H ₆ | C ₃ H ₈ | NO _x | CO/H ₂ |
|--------------------------|----------------|-----------------|------|-----------------|----------------|----------|-------------------------------|-------------------------------|-----------------|-------------------|
| Orange peels waste | 55.4 | 2.00 | 2.89 | 10.28 | 7.43 | 9 | 6 | 5 | 2 | 1/ 2.57 |

4. Cost estimation

4.1. Evaluation of process capital expenditures

This study evaluates the revenue potential of products derived from the pyrolysis of orange peel waste by scaling up the pilot-scale capacity to 10 kg per batch. The projected total capital expenditure for this process, which yields pyrolysis char, oil, and gas, is estimated at \$19258.69

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

(\$1 = $\square 85.39$, dated 24.05.2025). This estimate encompasses the total project cost (TPC) Very Alice Online plant direct cost (TPDC), total plant indirect cost (TPIC), contractor's profit and charges (CPC), 5% working capital, and an initial expense equal to 10% of the debt financing cost (DFC). A detailed breakdown of the required initial investment for the pyrolysis of waste orange peels is provided in Table S2 (Supplementary Information)⁶¹. The majority of capital costs \$69331.30—are attributed to machinery setup, system installation, electrical controls, site upgrades, piping, and ancillary infrastructure. Rajendran et al.⁴¹ reported that the process equipment cost (PEC) contributed 20.9% to the total cost of bio-oil production from pine sawdust using microwave pyrolysis; similarly, in the present study, PEC accounts for 17.4% of the total cost. The equipment investment for the pyrolysis process with a 10 kg/h capacity is \$ 19258.69, which is higher than that reported by Fajimi and Oboirien¹³² (i.e., \$594.312), whose study covered capacities of 30 tons/day, 60 tons/day, and 120 tons/day for fluidized, fixed, and rotary kiln bed systems, respectively. The process investment cost of the present study is comparable to that reported by Alawa et al.¹³³, for a reactor with 10 kg/h capacity. Variations in investment cost arise from country-specific factors such as tax structures, inflation and interest rates, energy tariffs, and differences in process parameters.

In summary, this investigation presents the first economic analysis of the pyrolysis process applied to orange peel waste. Equipment procurement accounted for 17.4% of the total capital expenditure, while 45.2% was allocated to installation components, including pipelines, instrumentation and control systems, electrical setups, buildings, yard improvements, and service facilities. The most significant expenses were related to reactor fabrication, the pyrolysis chamber, the cooler condenser, and the nitrogen cylinder. The initial capital investment required for the pyrolysis of orange peel waste is shown in Figure 12. The TPIC summarises 44.5% of engineering and 55.4% of building-related expenses. TPIC represents 12.9% of the capital cost, while the CFC accounts for 11.5%.

View Article Online DOI: 10.1039/D5SU00575B Equipment Installation 5% 6% 17% Crusher Contractor & contingency Drver 21% 17% Plant indirect cost ■ Pyrolyzer start-up cost **■** Separator Piping ■ Working capital 13% 16% 32% ■ Instrumentation and ■ Purchase Equipment cost Control Electrical 3%

Figure 12. Initial capital investment required for the pyrolysis of orange peel waste.

4.2. Evaluation of process operational expenses

The detailed breakdown of the operational investment cost for the pyrolysis of orange peel waste is presented in Table S3 (Supplementary Information). The operational expenses associated with the pyrolysis of orange peel waste is represented in Figure 13. Total operational expenses were amounted to \$10,163.08. Variable costs (\$10,203.08) were substantially lower than fixed costs (\$96,293.48). Among the variable expenses, utilities contributed the largest share at 58.1%, followed by raw materials (9.2%), consumables (7.9%), transportation (3.5%), and other miscellaneous costs (20.9%). The economic analysis was performed for feedstock input rates of 2 kg/h, 4 kg/h, and 10 kg/h, with 10 kg/h selected to ensure scalability and commercial feasibility.





Figure 13. Operational expenses associated with the pyrolysis of orange peel waste.

The total operational expenditure of \$20366.15 is significantly lower to those reported to the rep Selvam et al. ¹³⁴ (i.e., \$ 246,044.10) from other biomass feedstock. This investigation primarily focuses on the primary pyrolysis of orange peel waste, with a cost estimation of \$117478.04. The economic analysis is based on product generation at a laboratory scale and is intended to provide a foundational framework for scaling up the process. Due to the lack of reliable market data for pyrolysis char derived from orange peel waste, its selling price was estimated at \square 9.5/kg $(\approx \$0.11),$ based on comparable listings from previous researcher³⁷ (www.indiamart.com). The market values of pyrolysis oil and gas were considered as □95/kg (\approx \$1.11) and \square 44/kg (\approx \$0.52), respectively. The price of pyrolysis oil was adopted from the commercial biodiesel rate reported by Alawa et al. 133, while the gas price was assumed as a reasonable intermediate value due to the absence of specific market data. All product prices were based on prevailing market conditions in India.

4.3. Analyzing the profitability of pyrolyzing orange peel waste

Economists utilize the NPV metric to assess the profitability of the project. A positive NPV indicates financial viability and a high return on investment (ROI), making the project an attractive investment opportunity¹³⁵. The corresponding cash flow sheet is provided in Table S4 (Supplementary Information). Assuming an annual yield of 331,776 kg of pyro-char, pyro-oil, and pyro-gas over a 20 y operational period, with daily operations of 8 h, the projected revenue amount to \$20366.15, which is the breakeven point. Pyrolysis products have diverse applications: pyro-char can be used as a fertilizer, soil conditioner, or as an electrode material in wastewater treatment; pyro-oil is suitable for transportation due to its physicochemical similarity to conventional diesel and petrol; and pyro-gas, composed primarily of CO, CO₂, CH₄, and H₂, can serve as an eco-fuel or as a hydrogen source for sustainable energy and electricity generation¹³⁶. Therefore, price also can vary based on the applications. The present

investigation estimates a net payback period of 0.9 y at an interest rate of 7.5% and equity clear ordinary contribution of 40%, consistent with findings by Selvam et al. 134 and Chhabra et al. 68. As discount rates of 10%, 20%, and 30% are applied, the payback period increases from 1.3y to 1.8 y, and IRR also changes from 14.5% to 16%. Prior studies have reported varying financial indicators: for instance, a study on rotary kiln plant 66 achieved an ROI of 32.6%, IRR of 29%, and a payback period of 6.2 y; facility processing 50,000 t/y reported 3.6 y payback, which decreased to 1.59 y for 500,000 t/y plant. Initially, the NPV is negative at a 10% discount rate but becomes positive when the IRR reaches 33.3%, assuming 20 y operational timeframe before decommissioning. Further financial details are illustrated in Figures 14a (expenditure and income) and 14b (financial statistics for life period).






Figure 14. Orange pyrolysis plant, (a) expenditures and income, (b) financial statistics for life period.

(b)

This study emphasizes mass production, with the plant scale-up from 10 kg/h to 10000 kg/h. The projected annual profit from orange peel waste pyrolysis at varying plant capacities is illustrated in Figure 15. Application of the power law model (see Equation 14) indicates that increasing plant capacity leads to a substantial rise in annual profits. The current investigation also demonstrates a shortened payback period of approximately 2 y, highlighting the process's strong economic feasibility. Whether operated at the current capacity or through future scale-up, the process proves more advantageous than previously reported methods.




Figure 15. Projected annual profit from orange peel waste pyrolysis at varying plant capacities.

4.4. Sensitivity analysis

A sensitivity analysis was conducted to evaluate the influence of key parameters on the project's economic viability. Figure 16 illustrates the relative influence of process modifications and economic factors on the pyrolysis of orange peel waste. The baseline scenario assumed a feedstock cost of \$2968.03 annually, daily operation of 8 h, and product selling prices of \$0.11/kg for pyro-char, \$1.11/L for pyro-oil, and \$0.52/L for pyro-gas, resulting in a payback period of 1.3 y and an IRR of 14.5%. Increasing the feedstock cost to \$0.70/kg extended the payback period to 1.04 y and slightly increased the IRR to 16.68%. Conversely, reducing the feedstock cost to \$0.52/kg shortened the payback period to 0.72 y, while slightly decreasing the IRR to 11.6%, consistent with the findings of Varshney et al. 137. Among the assessed economic factors, IRR, plant scale, and waste disposal charges exhibited more pronounced effect on the minimum selling price (MSP) than feedstock cost. For example,

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

waste disposal charges of $\Box 4,326$ /ton (i.e., \$50/ton) and $\Box 8,653$ /ton (i.e., \$100/ton), redisced colors the MSP by 16.2% and 32.5%, respectively. The analysis highlights that optimizing plant scale and minimizing waste disposal charges are critical to enhancing economic feasibility, as variations in key parameters such as raw material costs and operational expenses significantly influence both NPV and MSP.




Figure 16. Tornado plot illustrating the relative impact of modifying specific processes and economic factors on orange peel waste pyrolysis.

5. Conclusion

This study presents a sustainable approach to managing waste orange peels through pyrolysis, yielding three valuable products: pyro-char, pyro-oil, and pyro-gas. Pyro-char demonstrates significant potential for industrial applications, particularly in the adsorption of hazardous substances in effluent and gas treatment processes, while pyro-oil and pyro-gas emerge as promising alternatives to fossil fuels. The study identified feedstock mass, reaction temperature, and heating rate as critical parameters influencing pyrolysis performance. Optimal conditions—comprising a feedstock mass of 2 kg, a temperature of 873 K, and a heating rate

of 20 K/min—resulted in maximum yields of 26.52 wt.% for pyro-char, 22.76 wt.% for pyro-gas, with an overall process desirability of 0.7. Experimental results produced pyro-char yield of 28.12%, pyro-oil yield of 22.89%, and pyro-gas yield of 48.99%, aligning with theoretical predictions within ±5.7% margin. The estimated payback period for the initial investment is 1.3 y, substantially shorter than the 6 y typically reported for pyrolysis gas and pyrolysis oil production. The IRR is estimated at 16%, with both positive and negative NPV scenarios considered, highlighting the process's financial sensitivity. A sensitivity analysis further affirmed the economic viability of the system. The products exhibit high volatile content, predominantly composed of hydroxyl and ether functional groups, suggesting potential for automotive fuel applications. This work underscores a sustainable pathway for converting biomass waste into value-added products, aligning with Industry 5.0 principles and advancing the United Nations 2030 sustainability goals for environmental and societal impact.

Conflicts of interest

There are no conflicts of interest to disclose.

Data availability

The data that supports the findings of this study are available in the supplementary material of this article.

Details of supporting material

Table S1: Parameters used to estimate the capital and operational expenses of the process plant.

Table S2: Details breakdown of the required initial investment for the pyrolysis of waste orange peels. This table presents the total capital costs associated with establishing a pyrolysis facility, including equipment, installation, and infrastructure.

Table S3: Breakdown of operational expenses for the pyrolysis of orange peel waste. This table provides a breakdown of annual operational costs, including labor (based on Indian wage structures), maintenance, utilities, and other recurring expenses.

Table S4: Discounted cash flows to produce pyrolysis products from orange peel waste of his countrates, offering insight into the financial feasibility of the proposed process.

Figure S1: Schematic representation of the CCD process.

Acknowledgment

This work was supported by the National Research Foundation of Korea (NRF), grant funded by the Korean government (MSIT) (No. RS-2021-NR059190).

References:

- D. V. Suriapparao, R. Vinu, A. Shukla and S. Haldar, *Bioresour. Technol.*, 2020, **302**, 122775.
- 2 S. Shafiee and E. Topal, *Energy Policy*, 2009, **37**, 181–189.
- 3 U. S. Behera and J. S. Sangwai, *Ind. Eng. Chem.*, 2021, **60**, 291–313.
- U. Michael-Igolima, S. J. Abbey, A. O. Ifelebuegu and E. U. Eyo, *Materials (Basel)*., 2023, **16**, 1092.
- 5 F. Chivrac, E. Pollet and L. Avérous, *Mater. Sci. Eng. R Reports*, 2009, **67**, 1–17.
- J. S. Yaradoddi, N. R. Banapurmath, S. V. Ganachari, M. E. M. Soudagar, A. M. Sajjan, S. Kamat, M. A. Mujtaba, A. S. Shettar, A. E. Anqi, M. R. Safaei, A. Elfasakhany, M. I. H. Siddiqui and M. A. Ali, *J. Mater. Res. Technol.*, 2022, 17, 3186–3197.
- D. Neves, H. Thunman, A. Matos, L. Tarelho and A. Gómez-Barea, *Prog. Energy Combust. Sci.*, 2011, **37**, 611–630.
- 8 A. Selvarajoo, Y. L. Wong, K. S. Khoo, W. H. Chen and P. L. Show, *Chemosphere*, 2022, **294**, 1333671.
- 9 R. Miranda, D. Bustos-Martinez, C. S. Blanco, M. H. G. Villarreal and M. E. R. Cantú, *J. Anal. Appl. Pyrolysis*, 2009, **86**, 245–251.
- 10 K. Sahoo, A. Kumar and J. P. Chakraborty, *J. Mater. Cycles Waste Manag.*, 2021, 23, 186–204.

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

- K. Chaiwong, T. Kiatsiriroat, N. Vorayos and C. Thararax, Biomass and Bioency Systocic Online 11 2013, **56**, 600–606.
- A. Amrullah, O. Farobie, G.P. Pramono, Korean J. Chem. Eng., 2022, 39, 389–397.

- 24 H. S. Choi, Y. S. Choi and H. C. Park, Korean J. Chem. Eng., 2010, 27, 1164–1169.
- 25 M. Pahnila, A. Koskela, P. Sulasalmi and T. Fabritius, *Energies*, 2023, 16, 6939.
- 26 A. Hornung, Transformation of Biomass: Theory to Practice, Wiley Online Library, 2014.

View Article Online

DOI: 10.1039/D5SU00575B

- 27 N. Bucher, Angew. Chemie, 1981, 93, 625.
- 28 A. O. Oyedun, K. L. Lam, T. Gebreegziabher and C. W. Hui, *Appl. Therm. Eng.*, 2013, **61**, 123–127.
- 29 C. Y. Yang, X. M. Yang, X. S. Lu, J. Z. Yao and W. G. Lin, *Guocheng Gongcheng Xuebao/The Chinese J. Process Eng.*, 2005, **5**, 379–383.
- 30 M. Afraz, F. Muhammad, J. Nisar, A. Shah, S. Munir, G. Ali and A. Ahmad, *Waste Manag. Bull.*, 2024, 1, 30–40.
- R. Naveenkumar and G. Baskar, *Bioresour. Technol.*, 2021, **320**, 124347.
- O. A. Fakayode and K. E. Abobi, J. Anal. Sci. Technol., 2018, 9, 20.
- A. K. Tovar, L. A. Godínez, F. Espejel, R. M. Ramírez-Zamora and I. Robles, *Waste Manag.*, 2019, **85**, 202–213.
- A. Sharma, M. Noda, M. Sugiyama, A. Ahmad and B. Kaur, *Molecules*, DOI:10.3390/molecules26154671.
- I. Kariim, Y. O. Waidi, H. Swai and T. Kivevele, *J. Anal. Appl. Pyrolysis*, 2023, 173, 106032.
- 36 N. K. Sharma, R. Savithri, A. Kamal, A. Kaur, P. Ram and R. K. Rao, *ENERGY STATISTICS India* 2021, Delhi, 2021.
- U. S. Behera, S. Poddar and H.-S. Byun, Sustain. Energy Fuels, 2025, 1–22.
- Z. Yao, D. C. Makepa, S. Poddar, M. Reinmoller, M. Bertelsen, J. Jiang, J. Tong, J. Cui,
 J. Liu and I. M. D. C. Cordeiro, *Case Stud. Therm. Eng.*, 2025, 71, 106228.
- 39 H. Park, J. Byun and J. Han, *Energy*, 2021, **230**, 120729.
- 40 C. D. Scown, N. R. Baral, M. Yang, N. Vora and T. Huntington, *Curr. Opin. Biotechnol.*, 2021, 67, 58–64.
- 41 N. Rajendran, D. Kang, J. Han and B. Gurunathan, J. Clean. Prod., 2022, **365**, 132712.
- M. Ortiz-Sanchez, J. C. Solarte-Toro, C. E. Orrego-Alzate, C. D. Acosta-Medina and C.
 A. Cardona-Alzate, *Biomass Convers. Biorefinery*, 2021, 11, 645–659.
- 43 M. Ortiz-Sanchez, J. C. Solarte-Toro, P. J. Inocencio-García and C. A. Cardona Alzate,

View Article Online

DOI: 10.1039/D5SU00575B

Enzyme Microb. Technol., 2024, 172, 110327.

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

- 44 M. Ortiz-Sanchez, C. A. C. Alzate and J. C. Solarte-Toro, *Biomass*, 2024, 4, 107–131.
- 45 M. Ladaniya, Citrus Fruit: Biology, Technology and Evaluation, Second Edition,

- 56 Zolgharnein, M. Bagtash and N. Asanjarani, J. Environ. Chem. Eng., DOI:10.1016/j.jece.2014.03.017.
- 57 R. F. Schmid, R. M. Bernard, E. Borokhovski, R. M. Tamim, P. C. Abrami, M. A. Surkes, C. A. Wade and J. Woods, *Comput. Educ.*, 2014, **72**, 271–291.
- 58 S. Halder, U. S. Behera, S. Poddar, J. Khanam and S. Karmakar, AAPS PharmSciTech,

View Article Online

DOI: 10.1039/D5SU00575B

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14.

(cc) EY-NO

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

- 2024, **25**, 16201–16221.
- 59 K. Sahoo, U. S. Behera, S. Poddar and H.-S. Byun, *Korean J. Chem. Eng.*, 2024, **41**, 2621–2638.
- A. El-Ghenymy, S. Garcia-Segura, R. M. Rodríguez, E. Brillas, M. S. El Begrani and B.
 A. Abdelouahid, *J. Hazard. Mater.*, 2012, 221–222, 288–297.
- T. Sfetsas, C. Michailof, A. Lappas, Q. Li and B. Kneale, *J. Chromatogr. A*, 2011, **1218**, 3317–3325.
- H. N. Jeong, R. H. Kwon, Y. Kim, S. H. Yoo, S. M. Yoo and C. Do Wee, *Foods*, 2023, 12, 1104.
- 63 M. Peters, K. Timmerhaus and R. West, Equipment costs Plant Design and Economics for chemical Engineers 5th Edition.
- 64 F. P. Goksal, *Heliyon*, 2022, **8**, e11669.
- 65 R. Bi, Y. Zhang, X. Jiang, H. Yang, K. Yan, M. Han, W. Li, H. Zhong, X. Tan, L. Xia, X. Sun and S. Xiang, *Energy*, 2022, **260**, 125039.
- S. Jenkins, 2019 Chemical Engineering Plant Cost Index Annual Average Chemical Engineering | Page 1, https://www.chemengonline.com/2019-chemical-engineering-plant-cost-index-annual-average/, (accessed 11 November 2024).
- W. D. Seider, R. Gani, S. Widagdo, K. M. Ng, J. D. Seider and D. R. Lewin, *Product and Process Design Principles: Synthesis, Analysis and Evaluation*, Wiley, New York, 4th edn., 2016.
- V. Chhabra, A. Parashar, Y. Shastri and S. Bhattacharya, *Ind. Eng. Chem. Res.*, 2021,60, 1473–1482.
- 69 K. Kishor, Koshi Motors & Fabrication Private Limited, https://www.indiamart.com/koshi-motors-fabrication/profile.html, (accessed 11 November 2024).
- 70 J. B. Shah and J. B. Valaki, *J. Kejuruter.*, 2022, **34**, 495–504.
- A. E. M. Fodah, M. K. Ghosal and D. Behera, *Int. J. Energy Res.*, DOI:10.1002/er.6192.
- 72 L. K. S. Gujjala and W. Won, *Bioresour. Technol.*, 2022, **364**, 128028.

- A. Arora, J. Banerjee, R. Vijayaraghavan, D. MacFarlane and A. F. Patti Dando, Carallel Online Prod., 2018, **116**, 24–34.
- J.-H. Kim, T. Lee, Y. F. Tsang, D. H. Moon, J. Lee and E. E. Kwon, *Sci. Total Environ.*,2024, 941, 173701.
- A. T. Koçer, D. Özçimen and İ. Gökalp, *Biomass Convers. Biorefinery*, 2024, **14**, 22839–22851.
- 76 K. Açıkalın, Biomass Convers. Biorefinery, 2022, 12, 501–514.
- Y. Zhu, G. Xu, W. Song, Y. Zhao, Z. Miao, R. Yao and J. Gao, *J. Energy Inst.*, 2021, 98, 172–178.
- 78 M. A. Lopez-Velazquez, V. Santes, J. Balmaseda and E. Torres-Garcia, *J. Anal. Appl. Pyrolysis*, 2013, **99**, 170–177.
- S. Abidi, A. B. H. Trabelsi and N. Boudhrioua, *J. Mater. Cycles Waste Manag.*, 2023,25, 235–248.
- 80 F. Ateş, E. Pütün and A. E. Pütün, *J. Anal. Appl. Pyrolysis*, 2004, **71**, 779–790.
- B. Zapata, J. Balmaseda, E. Fregoso-Israel and E. Torres-García, *J. Therm. Anal. Calorim.*, 2009, **98**, 309–315.
- X. Wang, Z. Hu, S. Deng, Y. Wang and H. Tan, *Environ. Prog. Sustain. Energy*, 2015,34, 923–932.
- 83 D. Mohan, C. U. Pittman and P. H. Steele, *Energy and Fuels*, 2006, **20**, 848–889.
- 84 A. K. Varma and P. Mondal, *J. Therm. Anal. Calorim.*, 2016, **124**, 487–497.
- 6. Bensidhom, A. Ben Hassen-Trabelsi, K. Alper, M. Sghairoun, K. Zaafouri and I. Trabelsi, *Bioresour. Technol.*, 2018, **247**, 363–369.
- V. Dhyani and T. Bhaskar, Renew. Energy, DOI:10.1016/j.renene.2017.04.035.
- 87 A. Aboulkas, H. Hammani, M. El Achaby, E. Bilal, A. Barakat and K. El harfi, *Bioresour. Technol.*, 2017, **243**, 400–408.
- M. Boluda-Aguilar and A. López-Gómez, *Ind. Crops Prod.*, 2013, 41, 188–197.
- 89 M. Ghodrat, J. A. Alonso, D. Hagare, R. Yang and B. Samali, Int. J. Environ. Sci.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

Techn

Technol., 2019, 16, 3721–3734.

- View Article Online DOI: 10.1039/D5SU00575B
- M. Ghodrat, M. A. Rhamdhani, G. Brooks, S. Masood and G. Corder, *J. Clean. Prod.*,
 2016, 126, 178–190.
- 91 M. T. H. Siddiqui, S. Nizamuddin, N. M. Mubarak, K. Shirin, M. Aijaz, M. Hussain and H. A. Baloch, *Waste and Biomass Valorization*, 2019, **10**, 521–532.
- 92 K. Intani, S. Latif, A. K. M. R. Kabir and J. Müller, *Bioresour. Technol.*, 2016, **218**, 541–551.
- 93 O. T. Ore and F. M. Abebiyi, *Unconv. Resour.*, 2024, **4**, 100080.
- 94 N. M. Mubarak, F. Yusof and M. F. Alkhatib, Chem. Eng. J., 2011, 168, 461–469.
- 95 A. M. Nusrat Aman, A. Selvarajoo, T. L. Lau and W. H. Chen, *Chemosphere*, 2023, 313, 137477.
- 96 S. Gupta and H. W. Kua, Sci. Total Environ., 2019, **662**, 952–962.
- 97 K. Yadav and S. Jagadevan, *Bioenergy Res.*, 2021, **14**, 964–977.
- 98 U. S. Behera, S. Poddar and H.-S. S. Byun, *J. Chem. Technol. Biotechnol.*, 2024, **99**, 1212–1224.
- 99 D. C. Montgomery, *Design and Analysis of Experiments, 10th Edition, Wiley*, Wiley Online Library, 10th edn., 2020.
- D. C. Montgomery, *Design and Analysis of Experiments*, Wiley, New York, 10th Editi.,2019.
- L. E. Hernandez-Mena., A. A. B. Pecora and A. L. Beraldo, *Chem. Eng. Trans.*, 2014,
 37, 115–120.
- 102 C. M. Santos, J. Dweck, R. S. Viotto, A. H. Rosa and L. C. de Morais, *Bioresour. Technol.*, DOI:10.1016/j.biortech.2015.07.114.
- 103 S. S. Lam, R. K. Liew, X. Y. Lim, F. N. Ani and A. Jusoh, *Int. Biodeterior. Biodegrad.*, DOI:10.1016/j.ibiod.2016.02.021.
- 104 A. Y. Elnour, A. A. Alghyamah, H. M. Shaikh, A. M. Poulose, S. M. Al-Zahrani, A. Anis and M. I. Al-Wabel, *Appl. Sci.*, 2019, **9**, 1149.

SC Sustainability Accepted Manuscript

- N. Ayrilmis, J. H. Kwon, T. H. Han and A. Durmus, *Mater. Res.*, 2015, 18, 654-659 D5SU00575B
- 106 O. Das, D. Bhattacharyya and A. K. Sarmah, J. Clean. Prod., 2016, 129, 159–168.
- Z. Chen, B. Lin, Y. Huang, Y. Liu, Y. Wu, R. Qu and C. Tang, *Sci. Total Environ.*, 2023, 862, 160860.
- 108 S. Kordoghli, E. Fassatoui, J. F. Largeau and B. Khiari, *Comptes Rendus Chim.*, 2023, **26**, 37–51.
- H. M. Yang, S. Appari, S. Kudo, J. I. Hayashi and K. Norinaga, *Ind. Eng. Chem. Res.*,
 2015, 54, 6855–6864.
- J. W. C. Tae-Seung Kim, Shinyoung Oh, Jae-Young Kim, In-Gyu Choi, *Energy*, 2014,68, 437–443.
- J. Mathias, A Beginner's Guide: How to Interpret Gas Chromatography Mass Spectrometry Results, https://www.innovatechlabs.com/newsroom/1841/how-to-interpret-gas-chromatography-mass-spectrometry-results/#:~:text=Typically%2C the y-axis%2C,at the point of retention., (accessed 4 October 2024).
- B. Blu-tack, *Identification of the substance/preparation and of the company/undertaking*, SWEDEN, 2016.
- 113 S. S. Chadwick, Ullmann's Encyclopedia of Industrial Chemistry, 2000.
- https://www.healthline.com/nutrition/grapefruit-essential-oil#TOC_TITLE_HDR_9, (accessed 24 September 2024).
- 115 N. Berova, G. A. Ellestad and N. Harada, *Ref. Modul. Chem. Mol. Sci. Chem. Eng.*, 2010, **9**, 91–146.
- 116 S. Karmakar, S. Poddar and J. Khanam, *AAPS PharmSciTech*, 2022, **23**, 25601–25623.
- 117 R. Pawlak, L. Nony, F. Bocquet, V. Oison, M. Sassi, J. M. Debierre, C. Loppacher and L. Porte, *J. Phys. Chem. C*, DOI:10.1021/jp102044u.
- P. S. Auerbach, H. J. Donner and E. A. Weiss, in *Field Guide to Wilderness Medicine*, eds. P. S. Auerbach, H. J. Donner and E. A. Weiss, Mosby. Inc, 3rd edn., 2008, pp. 453–473.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence

Open Access Article. Published on 16 Nhlangula 2025. Downloaded on 2025-11-01 11:59:14

- L. C. Becker, W. F. Bergfeld, D. V. Belsito, R. A. Hill, C. D. Klaassen, D. C. Liebler, J. G. Marks, R. C. Shank, T. J. Slaga, P. W. Snyder, L. J. Gill and B. Heldreth, *Int. J. Toxicol.*, 2019, 38, 68–228.
- 121 R. M. Giner, J. L. Ríos and S. Máñez, *Antioxidants*, 2022, 11, 343.
- N. J. Walton, M. J. Mayer and A. Narbad, 2003, DOI: 10.1016/S0031-9422(03)00149 3.
- 123 S. Marimuthu, K. Krishnamurthy, K. Karunanandham and M. Ponnusamy, *African J. Microbiol. Res.*, 2014, **8**, 2486–2491.
- 124 I. Itabaiana Junior, M. Avelar Do Nascimento, R. O. M. A. De Souza, A. Dufour and R. Wojcieszak, *Green Chem.*, 2020, 22, 5859–5880.
- 125 Z. Ahamed, J. kyu Seo, J. U. Eom and H. S. Yang, *LWT*, 2023, **188**, 115374.
- 126 H. Zhang, Z. Wang and O. Liu, J. Pharm. Anal., 2015, 15, 224.
- 127 S. Purohit, M. K. Bohra and R. Jain, *Appl. Biochem. Biotechnol.*, 2023, **195**, 2235–2251.
- 128 J. X. Jia and K. M. Wasan, *J. Pharm. Pharm. Sci.*, 2008, **11**, 45–62.
- 129 K. Paramasivan and S. Mutturi, *World J. Microbiol. Biotechnol.*, DOI:10.1007/s11274-022-03273-w.
- 130 X. Yu, C. Zhang, H. Wang, Y. Li, Y. Kang and K. Yang, *ACS Omega*, 2023, **8**, 20823–20833.
- 131 A. K. Maldhure, *Int. J. Pharma Bio Sci.*, 2015, **6**, 810–815.
- 132 L. I. Fajimi and B. O. Oboirien, *J. Mater. Cycles Waste Manag.*, 2023, **25**, 3462–3475.
- 133 B. Alawa and S. Chakma, *Environ. Sci. Pollut. Res.*, 2023, **30**, 64006–64024.
- S. M. Selvam, P. Balasubramanian, M. Chintala and L. kumar S. Gujjala, *Biomass Convers. Biorefinery*, DOI:https://doi.org/10.1007/s13399-024-06232-7.
- B. Behera, D. Laavanya and P. Balasubramanian, *Bioresour. Technol.*, 2022, **346**, 126559.

- 136 J. N.*India*137 D. V
- J. N. Ullas Krishnan, S. Poddar, T. Sriharsha, A. K. Maroli and J. Sarat Chandra Barbaroli Chandra Barbaroli Chandra Barbaroli Chandra Barbaroli Chandra Chandra Chandra Chandra Chandra Chang., 2024, 64, 393–402.
 - D. Varshney, P. Mandade and Y. Shastri, Sustain. Prod. Consum., 2019, 18, 96–114.

View Article Online DOI: 10.1039/D5SU00575B

Data availability

The data that supports the findings of this study are available in the supplementary material of this article.

Details of supporting material

Table S1: Parameters used to estimate the capital and operational expenses of the process plant.

Table S2: Details breakdown of the required initial investment for the pyrolysis of waste orange peels. This table presents the total capital costs associated with establishing a pyrolysis facility, including equipment, installation, and infrastructure.

Table S3: Breakdown of operational expenses for the pyrolysis of orange peel waste. This table provides a breakdown of annual operational costs, including labor (based on Indian wage structures), maintenance, utilities, and other recurring expenses.

Table S4: Discounted cash flows to produce pyrolysis products from orange peel waste. This table summarizes projected cash flows under various discount rates, offering insight into the financial feasibility of the proposed process.

Figure S1: Schematic representation of the CCD process.