


Cite this: *RSC Adv.*, 2023, 13, 20164

# Multicolor tunable bright photoluminescence in $\text{Ca}^{2+}/\text{Mg}^{2+}$ modified $\text{Eu}^{3+}$ doped $\text{ZnGa}_2\text{O}_4$ phosphors under UV excitation for solid state lighting applications

Monika,<sup>a</sup> R. S. Yadav,<sup>b</sup> A. Bahadur<sup>a</sup> and Shyam Bahadur Rai<sup>\*a</sup>

The  $\text{Eu}^{3+}$  doped and  $\text{Mg}^{2+}/\text{Ca}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4$  phosphor samples were synthesized by solid-state reaction method and their structural and optical properties studied. The phase, crystallinity and particles size of the phosphor samples were studied by XRD and SEM measurements. EDS analyses were used to identify the elements present in the phosphor materials. The vibrational groups present in the phosphor samples were examined by Fourier transform infrared (FTIR) measurements. Pure  $\text{ZnGa}_2\text{O}_4$  emits intense blue light under 260 nm excitation. However,  $\text{Eu}^{3+}$  doped and  $\text{Mg}^{2+}/\text{Ca}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4$  phosphor samples exhibit intense red emission under 393 nm excitation. A bluish white color is observed in these samples under 290 nm excitation. The maximum PL emission intensity is found at 0.1 mol%  $\text{Eu}^{3+}$  doping concentration. For higher concentrations, concentration quenching was observed due to dipole–dipole interaction. The emission intensity is enhanced upto 1.20 and 2.91 times on co-doping of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  via induced crystal field due to charge imbalance. The emission intensity of the phosphor is found to enhance further on annealing the samples at 873 K. Under various excitation wavelengths, color tunability was seen from blue to bluish-white to red regions. The lifetime of the  $^5\text{D}_0$  level of the  $\text{Eu}^{3+}$  ion improves via doping of  $\text{Mg}^{2+}/\text{Ca}^{2+}$  ions and it increases appreciably on annealing. The temperature dependent photoluminescence study (TDPL) reveals a thermal quenching behavior of the sample with thermal stability  $\sim 65\%$  and activation energy  $\sim 0.223$  eV in the  $\text{Eu}^{3+}/\text{Ca}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4$  phosphor sample.

Received 15th May 2023  
Accepted 26th June 2023

DOI: 10.1039/d3ra03215a

rsc.li/rsc-advances

## 1. Introduction

The rare earth doped inorganic phosphor materials are highly chemically, physically and thermally stable and yield large photoluminescence intensity on excitation with suitable wavelength. These materials have wide applications in different emerging fields, such as display devices, light emitting diodes (LEDs), color tunable devices, temperature sensing, development of new lasers, plant cultivation *etc.*<sup>1–7</sup> This is possible due to the presence of a large number of meta-stable energy levels in the rare earth ions.<sup>8–12</sup> The rare earth ions, such as  $\text{Eu}^{3+}$ ,  $\text{Tb}^{3+}$ ,  $\text{Tm}^{3+}$ ,  $\text{Dy}^{3+}$ , *etc.*, emit red, green, blue and yellow colors respectively, in different host matrices.<sup>2,3–7</sup> Thus, a combination of these rare earth ions, such as  $\text{Dy}^{3+}/\text{Eu}^{3+}$ ,  $\text{Sm}^{3+}/\text{Eu}^{3+}$ ,  $\text{Tb}^{3+}/\text{Eu}^{3+}$ , *etc.* produces color tunable photoluminescence (PL) in different host matrices depending on their concentrations and excitation wavelengths.<sup>13–16</sup> The concentration of these ions

plays a very important role in achieving color tunable emissions. This occurs due to a variation in the intensity of the emitted colors from these ions as well as energy transfer between them. Out of these rare earth ions, the  $\text{Eu}^{3+}$  ion is very promising as it gives almost pure red emission.<sup>17–20</sup> The  $\text{Eu}^{3+}$  doped phosphor materials are often used to fulfill the requirement of red components in white LEDs. However, the PL intensity of  $\text{Eu}^{3+}$  doped phosphor materials needs to be improved.

Efforts have been made by several groups and it is still required to enhance the PL emission intensity of  $\text{Eu}^{3+}$  ion in different hosts by co-doping the alkalis, alkaline earths, transition metals and rare earth ions.<sup>21–26</sup> In these cases, the PL intensity of  $\text{Eu}^{3+}$  ion is enhanced not only due to increase in crystallinity of the materials but also due to crystal field effect of the other doped ions and energy transfer to  $\text{Eu}^{3+}$  ion by other ions.<sup>13–16,21–26</sup> Yang *et al.* have prepared the novel red-emitting  $\text{Sr}_7\text{Sb}_2\text{O}_{12}:\text{Eu}^{3+}$ ,  $\text{M}^+$  ( $\text{M} = \text{Li}, \text{Na}, \text{K}$ ) phosphors and studied the effect of alkali ions on the PL intensity of  $\text{Eu}^{3+}$ .<sup>21</sup> Our group has also studied the impact of alkali doping on the PL intensity of  $\text{Eu}^{3+}$  ions in  $\text{CaTiO}_3$  phosphor.<sup>22</sup> Singh *et al.* have reported luminescent characteristics of  $\text{M}_3\text{Y}_2\text{Si}_3\text{O}_{12}:\text{Eu}^{3+}$  ( $\text{M} = \text{Ca}, \text{Mg}, \text{Sr}$

<sup>a</sup>Laser & Spectroscopy Laboratory, Department of Physics, Institute of Science, Banaras Hindu University, Varanasi 221005, India. E-mail: sbrai49@yahoo.co.in

<sup>b</sup>Department of Zoology, Institute of Science, Banaras Hindu University, Varanasi 221005, India


and Ba) and found significant enhancement in the PL emission intensity in presence of these ions.<sup>23</sup> Shi *et al.* have reported an enhancement in the PL intensity of  $\text{Eu}^{3+}$  ion in  $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$  phosphors in presence of alkali and alkaline earth metal ions.<sup>27</sup> The enhancement in PL intensity has been also observed due to charge compensation (crystal field effect), increase in crystallinity and asymmetric nature of the crystal field. Yang *et al.* have also observed that increasing the concentration of  $\text{Bi}^{3+}$  ions led to an improvement in the PL intensity of  $\text{Eu}^{3+}$  in  $\text{ZnGa}_2\text{O}_4$  phosphor, which is caused by energy transfer from  $\text{Bi}^{3+}$  to  $\text{Eu}^{3+}$  ions.<sup>28</sup> Rai *et al.* have observed enhancement in PL intensity of  $\text{Eu}^{3+}$  ion through energy transfer from  $\text{Tb}^{3+}$  to  $\text{Eu}^{3+}$  ions in  $\text{LaVO}_4$  phosphor.<sup>16</sup> However, the effect of co-doping of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  ions on the PL intensity in  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$  phosphor has not been investigated to our knowledge. Our group has found that the PL intensity of  $\text{LaVO}_4:\text{Eu}^{3+}$  phosphor was enhanced 4.5 times *via* co-doping of  $\text{Ca}^{2+}$  ion.<sup>24</sup> In the present work, the PL intensity of  $\text{Eu}^{3+}$  doped  $\text{ZnGa}_2\text{O}_4$  phosphor has been investigated in absence and presence of  $\text{Mg}^{2+}/\text{Ca}^{2+}$  ions.

The thermal stability of phosphor material is one of the desirable conditions for practical applications as it is an important parameter for a photoluminescent phosphor. The variation of PL emission intensity with temperature is a function of thermal stability of the phosphor materials.<sup>29</sup> The thermal stability of phosphor samples are compared in terms of photoluminescence emission at 423 K (150 °C) for LEDs applications as the phosphor materials deteriorate at higher temperatures and reduce its emission efficiency.<sup>30</sup> The temperature dependent PL intensity has been studied by Rajendran *et al.* in  $\text{Ba}_2\text{YV}_3\text{O}_{11}:\text{Eu}^{3+}$  phosphor and found the thermal stability of phosphor is 59.5% at 423 K.<sup>31</sup> In the case of  $\text{Ba}_2\text{LaV}_3\text{O}_{11}:\text{Eu}^{3+}$ , this value was reported to be 62% at 423 K.<sup>32</sup> The temperature-dependent PL in the  $\text{Bi}_4\text{Si}_3\text{O}_{12}:\text{Eu}^{3+}$  phosphor was also studied by Zhang *et al.*<sup>33</sup> They have found that the PL emission intensity is decreased to 50% at 398 K compared to its PL intensity at 298 K. It would be interesting to measure the thermal stability of  $\text{Eu}^{3+}$  doped and  $\text{Eu}^{3+}/\text{Ca}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4$  phosphor material.



In this work, the  $\text{Eu}^{3+}$  doped and  $\text{Mg}^{2+}/\text{Ca}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4$  phosphor materials have been synthesized through solid state reaction method at 1473 K. A small part of the prepared samples has been annealed at 873 K temperature to see the changes in structural and photoluminescence properties of the doped and co-doped samples. The X-ray diffraction (XRD), scanning electron microscopic (SEM) and energy dispersive X-ray spectroscopic (EDS) measurements have been carried out for the structural, morphological and elemental properties. The vibrational structures of the phosphor samples have been studied by Fourier transform infrared (FTIR) measurements. The  $\text{Eu}^{3+}$  doped  $\text{ZnGa}_2\text{O}_4$  phosphor sample emits bright red color along with blue color on excitation with charge transfer band (CTB) of host at 260 nm and the charge transfer band (CTB) of  $\text{Eu}^{3+}$  at 290 nm. However, on excitation with *n*-UV wavelength at 393 nm (atomic line of  $\text{Eu}^{3+}$ ), only red emission is seen due to  $\text{Eu}^{3+}$  ion. The PL intensity of  $\text{Eu}^{3+}$  doped phosphor is enhanced on co-doping of  $\text{Mg}^{2+}/\text{Ca}^{2+}$  ions. On annealing the samples at 873 K, the PL intensity of phosphor

samples was further improved. The CIE coordinates of the phosphor samples were calculated for undoped and doped samples. The lifetime of  $^5\text{D}_0$  level of  $\text{Eu}^{3+}$  ion has been measured using  $^5\text{D}_0 \rightarrow ^7\text{F}_2$  transition at 613 nm wavelength under the excitation with 393 nm. The thermal stability of the  $\text{Eu}^{3+}$  doped and  $\text{Eu}^{3+}/\text{Ca}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4$  phosphor samples were demonstrated by the temperature dependent photoluminescence (TDPL) studies. These values in the two cases were found to be 58.43% and 64.88% with activation energies 0.198 eV and 0.223 eV, respectively at 423 K.



## 2. Experimental methods

### 2.1 Synthesis

The phosphor samples have been synthesized by a solid-state reaction method at 1473 K temperature. We have used base materials as ZnO (Otto, 99.99%),  $\text{Ga}_2\text{O}_3$  (Alfa Aesar 99.9%),  $\text{Eu}_2\text{O}_3$  (Molychem, 99.99%), MgO (Himedia, 99.9%) and  $\text{CaCO}_3$  (SDFCL, 99%). These materials were weighed carefully followed by mixing in agate mortar and acetone as mixing medium. The homogenously mixed samples were put in alumina crucible and heated in an electric furnace at 1473 K temperature for 4 hours. These samples were crushed into fine powder. A small part of these samples were further annealed at 873 K temperature for 4 hours separately to see the effect of further heating. Following compositions were used for the sample preparation:



where  $x$  was taken (0.05, 0.1, 0.2, 0.5 and 1.0 mol%) the concentration of  $\text{Eu}^{3+}$ , respectively. In  $\text{Mg}^{2+}/\text{Ca}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$  phosphor samples, the compositions used were as follows:



where  $x$  was fixed at 0.1 mol% concentration and the  $y$  and  $z$  were varied as 1, 2, 3 and 5 mol% concentrations to get the optimum PL intensity. The term ' $\delta$ ' represents the excess of oxygen released during the synthesis. These phosphor samples were used for further analyses.

### 2.2 Instrumentation

The crystalline nature and phase purity of the phosphor samples were analyzed by monitoring the XRD patterns using Rigaku diffractometer (MiniFlex 600-unit and  $\text{Cu K}\alpha$  radiation with  $\lambda = 0.15406$  nm). The scanning electron microscope (SEM) (Zeiss, Evo 18 Research unit) was used to study the morphological structure of the phosphor samples. The elements present in the phosphors were verified by the energy dispersive



X-ray spectroscopic (EDS) studies. The Fourier transform infrared (FTIR) spectra were monitored to know the vibrational groups present in the phosphors using a PerkinElmer IR spectrometer (I-Frontier unit). The downshifting photoluminescence spectra of all the samples were recorded using Fluorolog-3 spectrophotometer (Horiba Jobin Yvon) attached with a 450 W Xenon lamp as a source of light (Horiba Jobin Yvon). We have also measured the lifetime of  $^5D_0$  level of  $\text{Eu}^{3+}$  ion using the same unit attached with a 25 W pulsed Xenon lamp.

### 3. Results and discussion

#### 3.1 Structural studies

**3.1.1 X-ray diffraction (XRD) measurements.** The XRD patterns of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples unannealed and annealed (at 873 K) are shown in Fig. 1(a–f). The phase of the spinel crystal is cubic. The diffraction peaks match well with standard JCPDS File No. 38-1240.<sup>2,4–7,35,36</sup> Some weak impurity peaks were also observed in the XRD patterns due to monoclinic phase of  $\beta\text{-Ga}_2\text{O}_3$ . These impurity peaks are marked with asterisk '\*' in Fig. 1. The sharpness of the diffraction peaks indicates highly crystalline nature of the prepared phosphor. When the  $\text{Mg}^{2+}/\text{Ca}^{2+}$  ions are co-doped in the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$

phosphor at  $\text{Ga}^{3+}$  site, the XRD peaks are shifted towards lower  $2\theta$  angle side. The peaks are shifted as the ionic radii of  $\text{Ca}^{2+}$  (100 pm) and  $\text{Mg}^{2+}$  (72 pm) are higher as compared to  $\text{Ga}^{3+}$  (62 pm) ion.<sup>23</sup> The shift in XRD peak position can be verified from the zoomed patterns shown in Fig. 1(a–f).

The phosphor samples annealed at 873 K temperature show an improvement in crystallinity of the materials. The average crystallite size ( $D$ ) were calculated using Debye Scherrer's formula.<sup>34–37</sup>

$$D = \frac{k\lambda}{\beta \cos \theta} \quad (\text{v})$$

where  $k$  is a constant ( $=0.89$ ),  $\beta$  is the full width at half maxima (FWHM) at a diffraction angle ( $\theta$ ) and  $\lambda$  is the wavelength of X-ray radiation. The obtained values of crystallite size are found to be 38.09, 39.06 and 41.27 nm for the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples, respectively. This shows that the crystallite size increases on co-doping of  $\text{Ca}^{2+}/\text{Mg}^{2+}$  ions. The crystallite size is further improved on annealing the samples at 873 K and the values were found to be 41.29, 42.15 and 43.19 nm, respectively. The increase in crystallite size would be supportive for enhancing the PL intensity of the phosphor samples.

We have also analyzed the dislocation density for the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples and the samples annealed at 873 K by using the following relation:<sup>7,35,36</sup>

$$\delta = \frac{1}{D^2} \quad (\text{vi})$$

The computed dislocation densities for the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$




Fig. 1 XRD patterns of (a)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  (b)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (c)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples and that of (d)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  (e)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (f)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples annealed at 873 K along with JCPDS File No. and their zoomed patterns of (311) lattice plane.





Fig. 2 Rietveld fits of XRD patterns for (a)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  (b)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (c)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor. Asterisks '\*' represents the impurity peaks due to  $\beta\text{-Ga}_2\text{O}_3$ .

**Table 1** Phase, space group, lattice parameters and unit cell volume for the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor

Sample	Phase (1)	Space group	Lattice parameters ( $\text{ZnGa}_2\text{O}_4$ )	Volume ( $\text{\AA}^3$ )	Phase (2)	Space group	Lattice parameters ( $\beta\text{-Ga}_2\text{O}_3$ )	Volume ( $\text{\AA}^3$ )
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$	Cubic	$Fd\bar{3}m$	$a = 8.3311 \text{ \AA}$ $b = 8.3311 \text{ \AA}$ $c = 8.3311 \text{ \AA}$ $\alpha = \beta = \gamma = 90^\circ$	578.24	Monoclinic	$C2/m$	$a = 12.216 \text{ \AA}$ $b = 3.0395 \text{ \AA}$ $c = 5.8084 \text{ \AA}$ $\alpha = 90^\circ$ $\beta = 103.876^\circ$ $\gamma = 90^\circ$	209.38
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$	Cubic	$Fd\bar{3}m$	$a = 8.3328 \text{ \AA}$ $b = 8.3328 \text{ \AA}$ $c = 8.3328 \text{ \AA}$ $\alpha = \beta = \gamma = 90^\circ$	578.60	Monoclinic	$C2/m$	$a = 12.222 \text{ \AA}$ $b = 3.0389 \text{ \AA}$ $c = 5.8101 \text{ \AA}$ $\alpha = 90^\circ$ $\beta = 103.865^\circ$ $\gamma = 90^\circ$	209.51
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$	Cubic	$Fd\bar{3}m$	$a = 8.3339 \text{ \AA}$ $b = 8.3339 \text{ \AA}$ $c = 8.3339 \text{ \AA}$ $\alpha = \beta = \gamma = 90^\circ$	578.81	Monoclinic	$C2/m$	$a = 12.222 \text{ \AA}$ $b = 3.0398 \text{ \AA}$ $c = 5.8117 \text{ \AA}$ $\alpha = 90^\circ$ $\beta = 103.861^\circ$ $\gamma = 90^\circ$	209.63

phosphor samples are  $6.8 \times 10^{-4}$ ,  $6.5 \times 10^{-4}$  and  $5.8 \times 10^{-4} \text{ nm}^{-2}$ , respectively. In the case of annealed samples these values are  $5.8 \times 10^{-4}$ ,  $5.6 \times 10^{-4}$  and  $5.3 \times 10^{-4} \text{ nm}^{-2}$ , respectively. This shows that the dislocation density decreases in presence of  $\text{Mg}^{2+}/\text{Ca}^{2+}$  ions thereby improve the local crystal structure, which is responsible for the enhancement of PL intensity of the phosphor materials.

The Rietveld refinements of XRD patterns for the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples have been carried out using the FullProf program and they are shown in Fig. 2(a–c). The Fig. 2(a–c) shows that the observed and calculated XRD patterns match well with each other. The lower profile represents the difference between the observed and the calculated XRD patterns, whereas the vertical bars are Bragg's positions of  $\text{ZnGa}_2\text{O}_4$  (cubic) and  $\beta$ -

**Fig. 3** SEM images of (a)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  (b)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (c)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  and particles size distribution in (d)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  (e)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (f)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphors.






Fig. 4 EDS spectra of (a)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  (b)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (c)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphors.

$\text{Ga}_2\text{O}_3$  (monoclinic) phases. The different crystallographic parameters, such as phase, space group, lattice parameters and unit cell volumes for the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples are summarized in Table 1.

**3.1.2 SEM and EDS measurements.** The SEM images of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples are shown in Fig. 3(a–c). It is clear from the figure that the particles shape is nearly spherical and agglomerated to each other. The particles size distribution has been evaluated by plotting histogram for the different phosphor samples using ImageJ software and they are shown in Fig. 3(d–f). The average particles size is found to be  $1.11\ \mu\text{m}$  for  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor, which is slightly increased on doping of  $\text{Mg}^{2+}$  ( $1.36\ \mu\text{m}$ ) and  $\text{Ca}^{2+}$  ( $1.54\ \mu\text{m}$ ) ions in the  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$  phosphor, respectively.<sup>38</sup> This clearly shows that the average particles size of the phosphor materials are increased in presence of  $\text{Mg}^{2+}/\text{Ca}^{2+}$  ions. Maurya *et al.* have also observed an increase in particles size of the  $\text{Ho}^{3+}/\text{Yb}^{3+}$  co-doped  $\text{CaZrO}_3$  phosphor after co-doping of  $\text{Mg}^{2+}$  ions and reported an enhancement in the emission intensity.<sup>38</sup> An increase in the particles size of phosphor has been also reported by Rai *et al.* in the  $\text{LaVO}_4:\text{Eu}^{3+}$  phosphor on incorporation of  $\text{Ca}^{2+}$  ion.<sup>24</sup> They have also observed an increase in the PL intensity of phosphor via  $\text{Ca}^{2+}$  doping.

Fig. 4(a–c) shows the energy dispersive X-ray spectroscopic (EDS) spectra of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples, respectively. Fig. 4(a) clearly shows the presence of Zn, Ga, Eu and O

elements in the phosphor samples. However, the incorporation of Mg and Ca elements along with these elements can be also verified by Fig. 4(b and c).

### 3.2 Optical measurements

**3.2.1 Fourier transform infrared (FTIR) measurements.** FTIR spectra of  $\text{ZnGa}_2\text{O}_4$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples were recorded in the  $400\text{--}2000\ \text{cm}^{-1}$  range and they are shown in Fig. 5. The spectra show two vibrational bands at  $419$  and  $569\ \text{cm}^{-1}$  and they are assigned to arise due to stretching vibrations of the Zn–O ( $419\ \text{cm}^{-1}$ ) and Ga–O ( $569\ \text{cm}^{-1}$ ) groups, respectively.<sup>7,35,36</sup> No impurity peaks are seen in the phosphor samples. It has been observed that there is no change in vibrational band's positions however, the absorption intensity of the Zn–O and Ga–O bands are found to increase due to doping of  $\text{Eu}^{3+}$ ,  $\text{Ca}^{2+}$  and  $\text{Mg}^{2+}$  ions.

**3.2.2 PL excitation (PLE) and PL emission measurements.** The photoluminescence excitation (PLE) spectrum of  $\text{ZnGa}_2\text{O}_4$  corresponding to  $\lambda_{\text{em}} = 434\ \text{nm}$  and the photoluminescence (PL) emission spectrum under  $260\ \text{nm}$  excitation are shown in Fig. 6. The  $260\ \text{nm}$  band is due to charge transfer band of  $\text{O}^{2-} \rightarrow \text{Ga}^{3+}$ . Upon  $260\ \text{nm}$  excitation, the emission spectrum of the  $\text{ZnGa}_2\text{O}_4$  sample emits a broad intense band ranging from  $350$  to  $550\ \text{nm}$  with the peak position maxima at  $434\ \text{nm}$ , which can be attributed to the self-activation center of the octahedral Ga–O group in the spinel lattice.<sup>1,4</sup> The emission of this self-activated phosphor sample matches well with the absorption spectrum of



plant pigments, which shows usefulness of this material for plant growth applications.<sup>39</sup>

The PL excitation spectrum of  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$  phosphor monitored in the 250–500 nm region with  $\lambda_{\text{em}} = 613$  nm is shown in Fig. 7(a). The spectrum consists of a broad band ranging from 250–350 nm along with large number of sharp peaks due to intra-configurational forbidden 4f–4f transitions of  $\text{Eu}^{3+}$  ion.<sup>40–43</sup> The broad band maxima observed at 290 nm is due to charge transfer band (CTB) of  $\text{Eu}^{3+}$  ion ( $\text{O}^{2-} \rightarrow \text{Eu}^{3+}$ ). The narrow peaks observed at 362, 375, 382, 393, 413 and 463 nm are ascribed to arise due to  ${}^7\text{F}_0 \rightarrow {}^5\text{D}_4$ ,  ${}^7\text{F}_0 \rightarrow {}^5\text{L}_8$ ,  ${}^7\text{F}_0 \rightarrow {}^5\text{L}_7$ ,  ${}^7\text{F}_0 \rightarrow {}^5\text{L}_6$ ,  ${}^7\text{F}_0 \rightarrow {}^5\text{D}_3$  and  ${}^7\text{F}_0 \rightarrow {}^5\text{D}_2$  transitions of  $\text{Eu}^{3+}$  ion, respectively.<sup>20–26,40–43</sup> Among these peaks, the excitation peaks at 393 and 463 nm appear with relatively large intensity.

Fig. 7(b) shows the PL emission spectra of  $\text{ZnGa}_2\text{O}_4:x\text{Eu}^{3+}$  phosphors (where  $x = 0.05, 0.1, 0.2, 0.5$  and  $1.0$  mol%) recorded in 350–700 nm region under the excitation with 260 nm. The spectra show the broad band ranging from 350 to 550 nm due to self-activated emission of the  $\text{ZnGa}_2\text{O}_4$  host with maxima at 434 nm superimposed with  $\text{Eu}^{3+}$  emission bands in which the bands in higher wavelength side from 550 to 700 nm are very intense. Similar results are also obtained under the excitation with CTB of  $\text{Eu}^{3+}$  at 290 nm, which is shown in Fig. 7(c). It is clear from the figure that the emission intensity of  $\text{Eu}^{3+}$  bands is better on excitation with charge transfer band (CTB) at 290 nm as compared to  $\text{ZnGa}_2\text{O}_4$  excitation band at 260 nm. It is interesting to note that the emission peaks due to  $\text{Eu}^{3+}$  at 393 nm ( ${}^5\text{L}_6 \rightarrow {}^7\text{F}_0$ ) and 463 nm ( ${}^5\text{D}_2 \rightarrow {}^7\text{F}_0$ ) transitions are also superposed on the broad emission on excitation with 260 and 290 nm wavelengths.

The intense emission peaks positioned at 577, 592, 613, 652 and 696 nm are attributed to the  ${}^5\text{D}_0 \rightarrow {}^7\text{F}_0$ ,  ${}^5\text{D}_0 \rightarrow {}^7\text{F}_1$ ,  ${}^5\text{D}_0 \rightarrow {}^7\text{F}_2$ ,  ${}^5\text{D}_0 \rightarrow {}^7\text{F}_3$  and  ${}^5\text{D}_0 \rightarrow {}^7\text{F}_4$  transitions of  $\text{Eu}^{3+}$  ion, respectively, which are clearly shown in Fig. 7(b and c).<sup>20–26,40–43</sup> Fig. 7(d) shows the PL emission spectra in the range of 500–750 nm under the excitation at 393 nm. The inset in Fig. 7(d) shows the zoomed emission spectra of  $\text{Eu}^{3+}$  in the range 500–549 nm. The emission peaks could be marked clearly at 519 and 534 nm due to  ${}^5\text{D}_1 \rightarrow {}^7\text{F}_0$  and  ${}^5\text{D}_1 \rightarrow {}^7\text{F}_1$  transitions of  $\text{Eu}^{3+}$  ion, respectively. The PL emission intensity of  $\text{Eu}^{3+}$  bands is maximum on excitation with 393 nm as compared to 290 and 260 nm. The band at 613 nm due to  ${}^5\text{D}_0 \rightarrow {}^7\text{F}_2$  transition exhibits the highest PL emission intensity for all excitation wavelengths. The emission intensity is optimum for 0.1 mol% concentration of  $\text{Eu}^{3+}$  ion.<sup>44,45</sup>

As is seen from Fig. 7, the intensity  $I_{{}^5\text{D}_0 \rightarrow {}^7\text{F}_2} \gg I_{{}^5\text{D}_0 \rightarrow {}^7\text{F}_1}$ . This clearly shows that the substitution of  $\text{Eu}^{3+}$  is at asymmetric site in the host lattice. Moreover, it is well known that the  ${}^5\text{D}_0 \rightarrow {}^7\text{F}_2$  transition of  $\text{Eu}^{3+}$  ion is due to electric dipole which obeys the selection rule  $\Delta J = \pm 2$ . Because of the absence of center of symmetry in this host matrix, such transitions are hypersensitive and affected by the local crystal field symmetry around the  $\text{Eu}^{3+}$  ion. On the other hand, the magnetic dipole transition ( ${}^5\text{D}_0 \rightarrow {}^7\text{F}_1$ ) follows the selection rule  $\Delta J = \pm 1$ , and not affected by the local crystal field.<sup>21–27</sup> The photoluminescence emission intensity of  $\text{ZnGa}_2\text{O}_4:x\text{Eu}^{3+}$  has been monitored for different concentration of  $\text{Eu}^{3+}$  (where  $x = 0.05, 0.1, 0.2, 0.5$  and




Fig. 5 FTIR spectra of  $\text{ZnGa}_2\text{O}_4$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples.

1.0 mol%). It is found that the emission intensity increases from 0.05 to 0.1 mol% and then decreases for higher concentrations due to concentration quenching. The variation of  $\text{Eu}^{3+}$  ion concentration *versus* the emission intensity for 613 nm band under the excitation at 393 nm is shown in Fig. 8(a). The concentration quenching has been observed above 0.1 mol% concentration of  $\text{Eu}^{3+}$  ion. On increasing the concentration of  $\text{Eu}^{3+}$  ion, the distance between two  $\text{Eu}^{3+}$  ions decreases, which increases the mutual interaction between the  $\text{Eu}^{3+}$  ions due to which the emission intensity of  $\text{Eu}^{3+}$  band is quenched.

The value of average critical distance between the two  $\text{Eu}^{3+}$  ions has been calculated using the relation:<sup>16,21,23,41,46,47</sup>

$$R_c = 2 \left[ \frac{3V}{4\pi X_c N} \right]^{1/3} \quad (\text{vii})$$




Fig. 6 PL excitation spectrum of  $\text{ZnGa}_2\text{O}_4$  under  $\lambda_{\text{em}} = 434$  nm and PL emission spectrum of  $\text{ZnGa}_2\text{O}_4$  phosphor under  $\lambda_{\text{ex}} = 260$  nm.






Fig. 7 (a) PL excitation spectrum of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor with  $\lambda_{\text{em}} = 613$  nm, PL emission spectra of  $\text{ZnGa}_2\text{O}_4:x\text{Eu}^{3+}$  phosphors (where  $x = 0.05, 0.1, 0.2, 0.5$  and  $1.0$  mol%) under (b)  $\lambda_{\text{ex}} = 260$  nm, (c)  $\lambda_{\text{ex}} = 290$  nm and (d)  $\lambda_{\text{ex}} = 393$  nm excitation. The inset in (d) is the zoomed PL emission spectra in the 500–549 nm range.

where  $V$  is the volume of unit cell,  $X_c$  is the critical concentration of  $\text{Eu}^{3+}$  ion and  $N$  is the number of  $\text{Eu}^{3+}$  ions occupying per unit cell in the host lattice. For the cubic spinel crystal structure,  $V = 578.81 \text{ \AA}^3$ ,  $N = 8$  and  $X_c = 0.1$  respectively.<sup>46</sup> The calculated value of  $R_c$  using these parameters is found to be  $11.13 \text{ \AA}$ . It is known that when the  $R_c$  value is less than  $5 \text{ \AA}$ , the nature of interaction between two  $\text{Eu}^{3+}$  ions is exchange interaction. However, in the present case this distance is greater than  $5 \text{ \AA}$ , therefore a multipolar interaction is the main cause of concentration quenching. The exact nature of this multipolar interaction for quenching the PL intensity can be confirmed by the following relation:<sup>16,21,23,41,46,47</sup>

$$\frac{I}{x} = \frac{k}{1 + \beta(x)^{\theta/3}} \quad (\text{viii})$$

where  $I/x$  is the PL emission intensity per activator concentration.  $k$  and  $\beta$  terms are constants for a given phosphor. The value of  $\theta$  decides the actual nature of interaction between the activator ions. If this value is near to 6, the interaction is dipole–dipole. However, if this value is  $\sim 8$  or  $10$ , the nature of

interaction will be dipole–quadrupole or quadrupole–quadrupole, respectively. The simplified form of the eqn (viii) can be written as:<sup>21,41,46,47</sup>

$$\log\left(\frac{I}{x}\right) = C - \frac{\theta}{3} \log x \quad (\text{xi})$$

where  $C$  is a constant. The term  $-\theta/3$  is the slope of the curve in between  $\log\left(\frac{I}{x}\right)$  and  $\log x$ . Fig. 8(b) shows this plot for different concentrations of  $\text{Eu}^{3+}$  ions for  $613 \text{ nm}$  under  $393 \text{ nm}$  excitation in the present case. A linear fit of this gives the slope value  $-1.48$  from which the value of  $\theta$  is found to be  $4.44$ , which is close to  $6$ . This indicates that the dipole–dipole interaction is responsible for quenching of the PL intensity of  $\text{Eu}^{3+}$  bands in  $\text{ZnGa}_2\text{O}_4$  phosphor.

**3.2.3 Effect of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  doping on the PL intensity of  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$ .** The PL emission spectra of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/y\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/z\text{Ca}^{2+}$  phosphors (where  $y/z = 1, 2, 3$  and  $5$  mol%) monitored on excitation with  $393 \text{ nm}$  are shown in Fig. 9(a and b). From the Fig. 9(a and b), it is clear that the




Fig. 8 (a) Variation of PL emission intensity versus concentration of  $\text{Eu}^{3+}$  ion in the  $\text{ZnGa}_2\text{O}_4:\text{xEu}^{3+}$  phosphor samples (where  $x = 0.05, 0.1, 0.2, 0.5$  and  $1.0$  mol%) and (b) a plot between  $\log(I/x)$  and  $\log(x)$ .




Fig. 9 PL emission spectra of (a)  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}/\text{yMg}^{2+}$  (b)  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}/\text{zCa}^{2+}$  (where  $y/z = 1, 2, 3, 5$  mol%) with  $\lambda_{\text{ex}} = 393$  nm.

$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/\text{yMg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/\text{zCa}^{2+}$  phosphors emit similar emission bands as has been observed in the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor. The PL intensity of phosphor samples initially increases up to 3 mol% concentrations of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  ions and then decrease for higher concentrations of these ions. The PL intensity is found to be maximum for 3 mol% concentrations of  $\text{Mg}^{2+}/\text{Ca}^{2+}$  ions in the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor. The PL intensity of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor is increased upto 1.20 and 2.91 times on doping of 3 mol%  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  ions, respectively. Thus, the  $\text{Ca}^{2+}$  doping yields relatively larger PL emission intensity compared to  $\text{Mg}^{2+}$  in the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor. The enhancement in PL intensity of phosphor materials has been reported in several hosts *via* incorporation of  $\text{Mg}^{2+}/\text{Ca}^{2+}$  ions.<sup>24,38,48</sup>

The increase in PL intensity of the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor *via*  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  doping is due to charge imbalance in between the triply ionized Ga and doubly ionized Mg/Ca ions. This causes a crystal field around  $\text{Eu}^{3+}$  ion, which enhances its

emission intensity. Since this field is larger in the case of  $\text{Ca}^{2+}$  ion than that of  $\text{Mg}^{2+}$  ion, the enhancement in PL intensity is more in the case of  $\text{Ca}^{2+}$  doping. The particles size of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor is improved from 1.11 to 1.36 and 1.54  $\mu\text{m}$  through  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  doping, respectively. The larger particles have large number of activator ions which also contributes to this enhancement. Meetei *et al.* have also observed an

Table 2 Asymmetry ratio ( $I_{613 \text{ nm}}/I_{592 \text{ nm}}$ ) for  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphors on excitation with 393 nm

Phosphor	Asymmetric ratio ( $I_{613 \text{ nm}}/I_{592 \text{ nm}}$ )
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$	4.29
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$	4.42
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$	5.65






Fig. 10 PL emission spectra of  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples under (a)  $\lambda_{\text{ex}} = 290$  nm and (b)  $\lambda_{\text{ex}} = 393$  nm excitation.

enhancement in PL intensity in the  $\text{YVO}_4:\text{Dy}^{3+}$  phosphor *via* doping of  $\text{Ca}^{2+}$  ion.<sup>48</sup>

The inset in Fig. 9(a) shows the asymmetry ratio of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$

phosphor samples upon 393 nm excitation, which clearly demonstrates to the enhancement in PL intensity. The asymmetry ratio of the electric dipole transition *i.e.* ( $^5\text{D}_0 \rightarrow ^7\text{F}_2$ ) to the magnetic dipole transition *i.e.* ( $^5\text{D}_0 \rightarrow ^7\text{F}_1$ ) *versus* 0.1 mol%  $\text{Eu}^{3+}$




Fig. 11 PL emission spectra of unannealed and annealed (at 873 K) (a)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ , (b)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (c)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples on excitation with  $\lambda_{\text{ex}} = 393$  nm. (d) A comparison of the PL intensity of annealed samples at 873 K.

doped and 3 mol%  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  co-doped phosphor samples for 613 nm emission band, respectively. The asymmetry ratio signifies the nature of crystal field around the  $\text{Eu}^{3+}$  ion, which is responsible for larger PL intensity. It is clear from the inset of figure that the asymmetry ratio is larger for  $\text{Ca}^{2+}$  doping compared to  $\text{Mg}^{2+}$  doping [see Table 2]. The larger value of asymmetry ratio induces larger photoluminescence in the  $\text{Ca}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$  phosphor compared to the  $\text{Mg}^{2+}$  co-doped  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$ .

Fig. 10(a) shows the PL emission spectra of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples at  $\lambda_{\text{exc}} = 290$  nm in the range 350–700 nm. It is clear from the figure that the PL emission intensity of host as well as of  $\text{Eu}^{3+}$  bands are enhanced in presence of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  ions. This is due to crystal field of these ions.<sup>23,24,38,47,48</sup> When these phosphor samples are excited with  $\lambda_{\text{exc}} = 393$  nm, the host is not excited. The emission bands are observed only due to  $\text{Eu}^{3+}$  ion in 500–750 nm range [see Fig. 10(b)]. A similar structure is also obtained in the case of 290 nm excitation; however, the PL intensity is relatively larger for  $\text{Ca}^{2+}$  doping. The PL intensity of  $\text{Eu}^{3+}$  band at 613 nm is enhanced upto 1.20 and 2.91 times for  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  doping, respectively.

**3.2.4 Effect of annealing on the PL intensity.** Fig. 11(a–c) shows the PL emission spectra of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples unannealed and annealed (at 873 K) for 4 h upon 393 nm excitation. The PL intensity of the samples is found to

enhance appreciably for the samples annealed at 873 K temperature. The PL intensity of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor is enhanced more than the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor samples.<sup>24,38,47,48</sup> Actually, the crystallinity of phosphor samples is improved on annealing at 873 K temperature, which affects the PL intensity. Sreena *et al.* have observed an improvement in the PL intensity of phosphor due to increase in crystallinity as the phosphor samples were calcined at 800 and 900 °C temperatures.<sup>49</sup> Similarly, Kaewnuama *et al.* have also found an increase in PL intensity of the  $\text{Eu}^{3+}$  doped lithium lanthanum borate phosphor prepared at higher temperatures.<sup>50</sup> A similar result has been also observed in our case.

In order to understand the change in PL intensity due to annealing, we have also compared the PL intensity of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples annealed at 873 K on excitation with 393 nm (see Fig. 11(d)). It is clear from the figure that the PL intensity of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor increases in presence of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  ions on annealing.

**3.2.5 CIE chromaticity diagram.** The CIE (Commission Internationale de E'clairage) coordinates for the  $\text{ZnGa}_2\text{O}_4$ ,  $\text{ZnGa}_2\text{O}_4:\text{xEu}^{3+}$  (where  $x = 0.05, 0.1, 0.2, 0.5$  and  $1.0$  mol%),  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphors on excitation with 260, 290 and 393 nm wavelengths have been plotted using GoCIE software and they are shown in Fig. 12(a–c). The obtained CIE coordinates for pure  $\text{ZnGa}_2\text{O}_4$  phosphor




Fig. 12 CIE diagrams of (a)  $\text{ZnGa}_2\text{O}_4$  and  $\text{ZnGa}_2\text{O}_4:\text{xEu}^{3+}$  (where  $x = 0.05, 0.1, 0.2, 0.5$  and  $1.0$  mol%) phosphors on excitation with 260 nm (b)  $\text{ZnGa}_2\text{O}_4:\text{xEu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphors on excitation with 290 nm (c)  $\text{ZnGa}_2\text{O}_4:\text{xEu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphors on excitation with 393 nm.



**Table 3** CIE coordinates for the  $\text{ZnGa}_2\text{O}_4$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphors under 260, 290 and 393 nm excitations

Phosphor	CIE coordinates (x,y) at $\lambda_{\text{ex}} = 260 \text{ nm}$	CIE coordinates (x,y) at $\lambda_{\text{ex}} = 290 \text{ nm}$	CIE coordinates (x,y) at $\lambda_{\text{ex}} = 393 \text{ nm}$
$\text{ZnGa}_2\text{O}_4$	(0.14,0.13)		
$\text{ZnGa}_2\text{O}_4:0.05\text{Eu}^{3+}$	(0.19,0.18)	(0.24,0.22)	(0.59,0.40)
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$	(0.21,0.18)	(0.26,0.24)	(0.58,0.41)
$\text{ZnGa}_2\text{O}_4:0.2\text{Eu}^{3+}$	(0.22,0.19)	(0.27,0.25)	(0.57,0.41)
$\text{ZnGa}_2\text{O}_4:0.5\text{Eu}^{3+}$	(0.22,0.19)	(0.28,0.24)	(0.57,0.42)
$\text{ZnGa}_2\text{O}_4:1.0\text{Eu}^{3+}$	(0.23,0.18)	(0.28,0.25)	(0.57,0.42)
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$		(0.24,0.25)	(0.57,0.42)
$\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$		(0.25,0.26)	(0.61,0.38)

under 260 nm excitation lies in deep blue region [see Fig. 12(a)]. On doping of different concentrations of  $x\text{Eu}^{3+}$ ,  $0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  in the  $\text{ZnGa}_2\text{O}_4$  phosphor, the CIE coordinates are tuned slightly in the blue region. The coordinates are shifted from pure blue to bluish-white regions on doping of  $x\text{Eu}^{3+}$  and co-doping of  $0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  ions in the  $\text{ZnGa}_2\text{O}_4$  phosphor upon 290 nm excitation<sup>35,36</sup> [see Fig. 12(b)].

Further, the samples glow with bright red color on excitation with 393 nm, the CIE coordinates varying in the red region for different concentrations of  $\text{Eu}^{3+}$  ions [see Fig. 12(c)]. On co-doping of  $3\text{Mg}^{2+}$  and  $3\text{Ca}^{2+}$  ions in the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor, the CIE coordinates shift from (0.57, 0.42) to (0.61, 0.38). The CIE coordinates (0.61, 0.38), are close to the National Television System Committee (NTSC) standard value for a pure red color (0.67, 0.33). From this, it is clear that the co-doping of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  ions in the  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$  phosphor not only enhances the emission intensity but also improves the color perception. This shows that the emitted color is tunable with excitation wavelengths, which are useful in display devices. The calculated values of CIE coordinates are given in Table 3.

The color purity of the phosphor samples has been calculated by using the following relation.<sup>36</sup>


$$\text{Color purity} = \frac{\sqrt{(x - x_i)^2 + (y - y_i)^2}}{\sqrt{(x_d - x_i)^2 + (y_d - y_i)^2}} \times 100\% \quad (\text{x})$$

where (x,y), ( $x_i, y_i$ ) and ( $x_d, y_d$ ) are the CIE coordinates of phosphor, the standard light source for white light and the used dominant wavelength, respectively. The value of color purity of pure  $\text{ZnGa}_2\text{O}_4$  is 85.87%. However, the color purity of the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  was calculated to 93.62% upon 393 nm excitation.

**3.2.6 Lifetime measurements.** Fig. 13(a–f) shows the decay curves for the ( $^5\text{D}_0 \rightarrow ^7\text{F}_2$ ) transition at 613 nm for  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$ ,  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples unannealed and annealed (at 873 K) on excitation with 393 nm, respectively. The decay curves were found to fit better using a bi-exponential relation.<sup>16</sup>

$$I(t) = A_1 \exp\left(-\frac{t}{\tau_1}\right) + A_2 \exp\left(-\frac{t}{\tau_2}\right) \quad (\text{xi})$$

where  $\tau_1$  and  $\tau_2$  are the larger and smaller values of decay times and other terms have their usual meaning. The average lifetime values were calculated using the relation.<sup>38</sup>



**Fig. 13** Decay curves of unannealed (a)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  (b)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (c)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples and of the annealed (d)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  (e)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Mg}^{2+}$  and (f)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor on excitation with 393 nm.



$$\tau_{av} = \frac{A_1\tau_1^2 + A_2\tau_2^2}{A_1\tau_1 + A_2\tau_2} \quad (\text{xii})$$

The average value of lifetime for  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor is found to be 0.69 ms and for the same sample annealed at 873 K; it is found as 0.71 ms. On co-doping of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  ions in the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor, the lifetime values were found to be 0.73 and 1.51 ms. When these samples were annealed at 873 K, the values of average lifetime were found to be 0.78 and 1.65 ms. From this, it is clear that the lifetime value is increased on co-doping of  $\text{Mg}^{2+}$  and  $\text{Ca}^{2+}$  ions in the  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$  phosphor sample and it is further increased in case of annealed samples. This is due to highly crystalline nature of materials with less surface defects in the case of annealed phosphor samples.

**3.2.7 Temperature dependent photoluminescence of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphors and thermal stability.** In order to analyze the thermal stability of the phosphor samples, we have monitored the temperature dependent PL emission spectra of  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples in the temperatures range 303–483 K under 393 nm excitation. As it is clear from Fig. 14(a and b), the PL emission intensity of  $\text{Eu}^{3+}$  bands reduces continuously with the rise in temperature due to thermal quenching effect.<sup>29–33</sup> The emission intensity of 613 nm emission band is reduced upto 58.43% and 64.88% at 423 K for the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  [see Fig. 14(c)] and  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  [see Fig. 14(d)], respectively as compared to their initial intensity at room temperature (303 K). From this, it is clear that the doping of  $\text{Ca}^{2+}$  ion in the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor exhibits better thermal stability as compared to the  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  phosphor. We have also calculated the activation energy as it is




Fig. 14 Variation in PL emission intensity versus temperature for 613 nm band of (a)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  and (b)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples. Relative PL intensity at different temperatures for (c)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  and (d)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples. Arrhenius plot  $\ln(I_0/I - 1)$  versus  $1/KT$  for (e)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}$  and (f)  $\text{ZnGa}_2\text{O}_4:0.1\text{Eu}^{3+}/3\text{Ca}^{2+}$  phosphor samples under the excitation at 393 nm.






Fig. 15 (a and b) Variation in FWHM of 613 nm peak for the ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup> and ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup>/3Ca<sup>2+</sup> phosphor samples with temperature.

an important parameter to characterize the thermal stability of the phosphor materials. It is well known that for better thermal stability of the phosphor materials, the activation energy should have larger value. The activation energy of phosphor samples has been also calculated using Arrhenius equation:<sup>51,52</sup>

$$I_t = \frac{I_o}{1 + c \exp\left(-\frac{E_a}{Kt}\right)} \quad (\text{xiii})$$

where  $I_o$  and  $I_t$  are the emission intensities of the phosphor samples at room temperature and at temperature ( $t$ ). The term  $E_a$  is the activation energy and  $K$  is the Boltzmann's constant. The activation energy has been calculated by plotting the graph in between  $\ln[(I_o/I) - 1]$  vs.  $1/kT$  as shown in Fig. 14(e and f). The slope of these curves gives the values of the activation energy 0.198 eV (see Fig. 14(e)) and 0.223 eV (see Fig. 14(f)) for the ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup> and ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup>/3Ca<sup>2+</sup> phosphor samples, respectively. Zhang *et al.* have obtained the value of activation energy 0.17 eV for the Eu<sup>3+</sup> doped BaZrGe<sub>3</sub>O<sub>9</sub> phosphor.<sup>51</sup> The activation energy has been also found 0.14 eV in the case of Eu<sup>3+</sup> doped Ca<sub>19</sub>Mg<sub>2</sub>(PO<sub>4</sub>)<sub>14</sub> phosphor.<sup>52</sup> It has been observed that the activation energy is much larger for the Eu<sup>3+</sup> doped and Eu<sup>3+</sup>/Ca<sup>2+</sup> co-doped ZnGa<sub>2</sub>O<sub>4</sub> phosphor samples. This reveals that the Eu<sup>3+</sup> doped and Eu<sup>3+</sup>/Ca<sup>2+</sup> co-doped ZnGa<sub>2</sub>O<sub>4</sub> phosphors show better thermal stability. Moreover, the thermal stability is increased in presence of Ca<sup>2+</sup> ion. The Ca<sup>2+</sup> co-doping plays an important role to reduce the influence of non-radiative relaxations.

It is clear from insets of Fig. 14(a and b) that the FWHM of 613 nm peak in the ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup> and ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup>/3Ca<sup>2+</sup> phosphor decreases continuously on increasing the temperature of these samples. The FWHM of the 613 nm peak in the case of ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup> phosphor decreases rapidly while in the case of ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup>/3Ca<sup>2+</sup> phosphor it decreases slowly.<sup>29</sup> Fig. 15(a and b) shows the variation in FWHM of the peaks in the ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup> and ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup>/3Ca<sup>2+</sup> phosphors as a function of temperature supplied to the samples. This reveals that the ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup>/3Ca<sup>2+</sup> phosphor is more thermally stable than

the ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup> phosphor. Thus, the doping of Ca<sup>2+</sup> in ZnGa<sub>2</sub>O<sub>4</sub>:0.1Eu<sup>3+</sup> enhances the stability of the phosphor material.

## 4. Conclusions

The Eu<sup>3+</sup> doped and Mg<sup>2+</sup>/Ca<sup>2+</sup> co-doped ZnGa<sub>2</sub>O<sub>4</sub> phosphor samples were successfully synthesized by solid-state reaction method at 1473 K. A small part of all the samples were further annealed for four hours at 873 K, which improves the PL intensity of the phosphor samples. The XRD, SEM, EDS, FTIR spectra of all the samples were monitored. The pure ZnGa<sub>2</sub>O<sub>4</sub> emits broad blue emission (350–550 nm) on UV (260 nm) excitation. However, Eu<sup>3+</sup> doped and Mg<sup>2+</sup>/Ca<sup>2+</sup> co-doped samples emit blue and red bands on 260 and 290 nm excitations. However, excitation of doped samples with 393 nm emits intense pure red color. The PL intensity of emission bands is enhanced up to 1.20 and 2.91 times *via* co-doping of Mg<sup>2+</sup> and Ca<sup>2+</sup> ions in the Eu<sup>3+</sup> doped phosphors due to increase in the crystallinity, particles size and crystal field due to charge imbalance. The blue emission due to pure ZnGa<sub>2</sub>O<sub>4</sub> sample shifts slowly towards the bluish-white and red regions for Eu<sup>3+</sup> doped and Ca<sup>2+</sup>/Mg<sup>2+</sup> co-doped ZnGa<sub>2</sub>O<sub>4</sub> phosphors on excitation with 290 and 393 nm wavelengths. For 393 nm excitation, it emits only red in all cases. The lifetime of <sup>5</sup>D<sub>0</sub> level of Eu<sup>3+</sup> ion increases on Ca<sup>2+</sup>/Mg<sup>2+</sup> doping and on annealing the sample. The temperature dependent photoluminescence (TDPL) study shows the thermal quenching behavior of the sample with thermal stability ~65% and activation energy of 0.223 eV in the Eu<sup>3+</sup>/Ca<sup>2+</sup> co-doped phosphor. Thus, the Eu<sup>3+</sup> doped and Ca<sup>2+</sup> co-doped ZnGa<sub>2</sub>O<sub>4</sub> phosphor is highly thermally stable under external temperature, which may be useful for display devices, blue LEDs, warm red LEDs and plant growth lighting applications.

## Conflicts of interest

Authors declare that there is no conflict of interest in the present study.



## Acknowledgements

Monika acknowledges to Council of Scientific and Industrial Research, India for providing financial assistance of Senior Research Fellowship (Grant No. 09/013(0826)/2018-EMR-I).

## References

- W. Yang, J. Li, B. Liu, X. Zhang, C. Zhang, P. Niu and X. Jiang, Multi-wavelength tailoring of a  $\text{ZnGa}_2\text{O}_4$  nanosheet phosphor via defect engineering, *Nanoscale*, 2018, **10**, 19039–19045.
- J.-H. Lee, H.-J. Park, K. Yoo, B.-W. Kim, J. C. Lee and S. Park, Characteristics of nano-sized  $\text{ZnGa}_2\text{O}_4$  phosphor prepared by solution combustion method and solid-state reaction method, *J. Eur. Ceram. Soc.*, 2007, **27**, 965–968.
- B. G. Tagiev, G. G. Guseinov, R. B. Dzhabbarov, O. B. Tagiev, N. N. Musaeva and A. N. Georgobiani, Synthesis and luminescent properties of  $\text{ZnGa}_2\text{S}_4$ : Eu, F and  $\text{ZnGa}_2\text{O}_4$ : Eu, F, *Inorg. Mater.*, 2000, **36**, 1189–1191.
- Monika, R. S. Yadav, A. Bahadur and S. B. Rai, Concentration and pump power-mediated color tunability, optical heating and temperature sensing via TCLs of red emission in an  $\text{Er}^{3+}/\text{Yb}^{3+}/\text{Li}^{+}$  codoped  $\text{ZnGa}_2\text{O}_4$  phosphor, *RSC Adv.*, 2019, **9**, 40092–40108.
- I. K. Jeong, H. L. Park and S. Mho, Two self-activated optical centers of blue emission in zinc gallate, *Solid State Commun.*, 1998, **105**, 179–183.
- M. Vasile, P. Vlazan, P. Sfirloaga, I. Grozescu, N. M. Avram and E. Rusu, The luminescent properties of a  $\text{ZnGa}_2\text{O}_4$  spinel doped with  $\text{Eu}^{3+}$  and  $\text{Er}^{3+}$  ions, *Phys. Scr.*, 2009, **135**, 014046.
- K.-H. Hsu, M.-R. Yang and K.-S. Chen, A study of  $\text{ZnGa}_2\text{O}_4$  phosphor prepared by the solid method, *J. Mater. Sci.: Mater. Electron.*, 1998, **9**, 283–288.
- L. Zhang, Y. Xu, X. Wu, S. Yin and H. You, Strong and pure red-emitting  $\text{Eu}^{3+}$ -doped phosphor with excellent thermal stability for warm WLEDs, *Mater. Adv.*, 2022, **3**, 2591–2597.
- J. Zhao, H. Gao, H. Xu, Z. Zhao, H. Bu, X. Cao, L. He, Z. Yang and J. Sun, Structural and photoluminescence of  $\text{Eu}^{3+}$  doped  $\text{Sr}_2\text{InTaO}_6$  red phosphor with high color purity, *RSC Adv.*, 2021, **11**, 8282–8289.
- V. G. Nosov, A. A. Betina, T. S. Bulatova, P. B. Guseva, I. E. Kolesnikov, S. N. Orlov, M. S. Panov, M. N. Ryazantsev, N. A. Bogachev, M. Y. Skripkin and A. S. Mereshchenko, Effect of  $\text{Gd}^{3+}$ ,  $\text{La}^{3+}$ ,  $\text{Lu}^{3+}$  co-doping on the morphology and luminescent properties of  $\text{NaYF}_4:\text{Sm}^{3+}$  phosphors, *Mater.*, 2023, **16**, 2157.
- N. B. Adam, J. Pisarska, M. Kuwik, T. Goryczka, M. Zubko and W. A. Pisarski, Synthesis and photoluminescent characterization of ceramic phosphors  $\text{Li}_2\text{MgGeO}_4:\text{Ln}^{3+}$  ( $\text{Ln}^{3+} = \text{Pr}^{3+}$  or  $\text{Tm}^{3+}$ ) under different excitation wavelengths, *RSC Adv.*, 2023, **13**, 12386–12393.
- K. Riwozki and M. Hasse, Wet-chemical synthesis of doped colloidal nanoparticles:  $\text{YVO}_4:\text{Ln}$  ( $\text{Ln} = \text{Eu}, \text{Sm}, \text{Dy}$ ), *J. Phys. Chem. B*, 1998, **50**, 10129–10135.
- Y. R. Parauha and S. J. Dhoble, Color-tunable luminescence, energy transfer behavior and I–V characteristics of  $\text{Dy}^{3+}$ ,  $\text{Eu}^{3+}$  co-doped  $\text{La}(\text{PO}_4)$  phosphors for WLEDs and solar applications, *New J. Chem.*, 2022, **46**, 6230–6243.
- M. Yan, G. Liu, J. Wen and Y. Wang, Blue-light-excited  $\text{Eu}^{3+}/\text{Sm}^{3+}$  co-doped  $\text{NaLa}(\text{MoO}_4)_2$  phosphors: synthesis, characterizations and red emission enhancement for WLEDs, *Mater.*, 2018, **11**, 1090.
- M. Xie, W. Ruan and J. Wang, Energy transfer, tunable photoluminescence of  $\text{Sr}_3\text{Lu}(\text{PO}_4)_3:\text{Tb}^{3+}$ ,  $\text{Eu}^{3+}$  phosphors, *J. Lumin.*, 2020, **224**, 117278.
- E. Rai, A. Roy, A. Rai, V. J. Fulari and S. B. Rai, Structural and luminescent properties and energy transfer from  $\text{Tb}^{3+}$  to  $\text{Eu}^{3+}$  in  $\text{LaVO}_4:\text{xTb}^{3+}/\text{yEu}^{3+}$  phosphors, *J. Alloys Compd.*, 2023, **937**, 168395.
- R. L. Tranquillin, L. X. Lovisa, C. R. R. Almeida, C. A. Paskocimas, M. S. Li, M. C. Oliveira, L. Gracia, J. Andres, E. Longo, F. V. Motta and M. R. D. Bomio, Understanding the white-emitting  $\text{CaMoO}_4$  Co-Doped  $\text{Eu}^{3+}$ ,  $\text{Tb}^{3+}$  and  $\text{Tm}^{3+}$  phosphor through experiment and computation, *J. Phys. Chem. C*, 2019, **123**, 18536–18550.
- B. B. Niraula and C. Rizal, Photoluminescence property of  $\text{Eu}^{3+}$  doped  $\text{CaSiO}_3$  nano-phosphor with controlled grain size, *Colloids Interfaces*, 2018, **2**(4), 52.
- A. Dwivedi, M. Srivastava, R. Upadhyay, A. Srivastava, R. S. Yadav and S. K. Srivastava, A flexible photoluminescent nanoprobe for sensitive and rapid detection of arsenic ions concentration, *Microchem.*, 2022, **127**, 106969.
- K. Indumathi, S. Tamilselvan, L. Rajasekaran, A. Duke John David, G. Shakil Muhammad, G. Ramalingam and M. Biruntha, Structural and optical properties of  $\text{Eu}^{3+}$  doped  $\text{Sr}_3\text{Gd}[\text{PO}_4]_3$  phosphor white-LED application, *Mater. Lett.*, 2022, **309**, 131371.
- W. B. Yang, F. B. Xiong, Y. Yang, H. F. Lin, X. G. Meng, E. Ma and W. Z. Zhu, A novel red-emitting  $\text{Sr}_7\text{Sb}_2\text{O}_{12}:\text{Eu}^{3+}$ ,  $\text{M}^{+}$  ( $\text{M} = \text{Li}, \text{Na}, \text{K}$ ) phosphor for warm white LED: synthesis, optical properties, and LED fabrication, *Appl. Phys. A*, 2022, **128**, 584.
- P. Singh, R. S. Yadav and S. B. Rai, Enhanced photoluminescence in a  $\text{Eu}^{3+}$  doped  $\text{CaTiO}_3$  perovskite phosphor via incorporation of alkali ions for white LEDs, *J. Phys. Chem. Solids*, 2021, **151**, 109916.
- D. Singh and S. Sheoran, Synthesis and luminescent characteristics of  $\text{M}_3\text{Y}_2\text{Si}_3\text{O}_{12}:\text{Eu}^{3+}$  ( $\text{M} = \text{Ca}, \text{Mg}, \text{Sr}$  and  $\text{Ba}$ ) nanomaterials for display applications, *J. Mater. Sci.: Mater. Electron.*, 2016, **27**, 12.
- E. Rai, R. S. Yadav, D. Kumar, A. K. Singh, V. J. Fullari and S. B. Rai, Improved photoluminescence in  $\text{Eu}^{3+}$  doped  $\text{LaVO}_4$  phosphor via co-doping of  $\text{Li}^{+}/\text{Ca}^{2+}$  ions, *J. Lumin.*, 2022, **241**, 118519.
- Q. Tang, N. Guo, Y. Xin, W. Li, B. Shao and R. Ouyang, Luminous tuning in  $\text{Eu}^{3+}/\text{Mn}^{4+}$  co-doped double perovskite structure by designing the site-occupancy strategy for solid-state lighting and optical temperature sensing, *Mater. Res. Bull.*, 2022, **149**, 111704.



- 26 E. Rai, R. S. Yadav, D. Kumar, A. K. Singh, V. J. Fullari and S. B. Rai, Influence of  $\text{Bi}^{3+}$  ion on structural, optical, dielectric and magnetic properties of  $\text{Eu}^{3+}$  doped  $\text{LaVO}_4$  phosphor, *Spectrochim. Acta, Part A*, 2020, **243**, 118787.
- 27 H. Shi, X. Y. Zhang, W. L. Dong, X. Y. Mi, N. L. Wang, Y. Li and H. W. Liu, Effect of co-doped metal cations on the properties of  $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$  phosphors synthesized by gel-combustion method, *Chin. Phys. B*, 2016, **25**, 047802.
- 28 Z. Yang, J. Liao, S. Lai, H. Wu, Z. Fan, J. Qiu, Z. Song, Y. Yang and D. Zhou, Energy transfer and photoluminescence properties in  $\text{Bi}^{3+}$  and  $\text{Eu}^{3+}$  co-doped  $\text{ZnGa}_2\text{O}_4$ , *Mater. Express*, 2013, **3**, 350–354.
- 29 J. Cui, Y. Zheng, Z. Wang, L. Cao, X. Wang, Y. Yao, M. Zhang, M. Zheng, Z. Yang and P. Li, Improving the luminescence thermal stability of  $\text{Ca}_3\text{Y}_2\text{Ge}_3\text{O}_{12}:\text{Cr}^{3+}$  based on cation substitution and its application in NIR LEDs, *Mater. Adv.*, 2022, **3**, 2772–2778.
- 30 B. Yang, Y. Feng, Q. Zhao, M. He and Y. Lv, Novel tunable green-red luminescence in  $\text{Mn}^{2+}$  doped  $\text{Ca}_9\text{Tb}(\text{PO}_4)_7$  phosphors based on the  $\text{Mn}^{2+}$  regulation and energy transfer, *Coatings*, 2020, **10**, 952.
- 31 M. Rajendran and S. Vaidyanathan, A novel highly efficient host-sensitized red emitting ( $\text{Ba}_2\text{YV}_3\text{O}_{11}:\text{Eu}^{3+}$ ) phosphor for hybrid white LEDs, *ChemistrySelect*, 2020, **5**, 5128–5136.
- 32 M. Rajendran, S. K. Samal and S. Vaidyanathan, A novel self-activated (bluish-green) and  $\text{Eu}^{3+}$  doped (red) phosphors for warm white LEDs, *J. Alloys Compd.*, 2020, **815**, 152631.
- 33 Y. Zhang, J. Xu, Q. Cui and B. Yang,  $\text{Eu}^{3+}$ -doped  $\text{Bi}_4\text{Si}_3\text{O}_{12}$  red phosphor for solid state lighting: microwave synthesis, characterization, photoluminescence properties and thermal quenching mechanisms, *Sci. Rep.*, 2017, **7**, 42464.
- 34 S. Sheoran, S. Singh, A. Mann, A. Samantilleke, B. Mari and D. Singh, Novel synthesis and Optical investigation of trivalent Europium doped  $\text{MGd}_2\text{Si}_3\text{O}_{10}$  ( $\text{M} = \text{Mg}^{2+}$ ,  $\text{Ca}^{2+}$ ,  $\text{Sr}^{2+}$  and  $\text{Ba}^{2+}$ ) nanophosphors for full-color displays, *J. Mater. NanoSci.*, 2019, **6**, 73–81.
- 35 Monika, R. S. Yadav, A. Bahadur and S. B. Rai, Near-Infrared light excited highly pure green upconversion photoluminescence and intrinsic optical bistability sensing in a  $\text{Ho}^{3+}/\text{Yb}^{3+}$  co-doped  $\text{ZnGa}_2\text{O}_4$  phosphor through  $\text{Li}^+$  doping, *J. Phys. Chem. C*, 2020, **124**, 10117–10128.
- 36 Monika, R. S. Yadav, A. Rai and S. B. Rai, NIR light guided enhanced photoluminescence and temperature sensing in  $\text{Ho}^{3+}/\text{Yb}^{3+}/\text{Bi}^{3+}$  co-doped  $\text{ZnGa}_2\text{O}_4$  phosphor, *Sci. Rep.*, 2021, **11**, 4148.
- 37 R. Kokate, P. Rohilla, S. Kaur, A. S. Rao and V. Singh, Visible emission characteristics in  $\text{Tb}^{3+}$  doped  $\text{KNa}_3\text{Al}_4\text{Si}_4\text{O}_{16}$  phosphor, *Optik*, 2021, **243**, 167391.
- 38 A. Maurya, R. S. Yadav, R. V. Yadav, S. B. Rai and A. Bahadur, Enhanced green upconversion photoluminescence from  $\text{Ho}^{3+}/\text{Yb}^{3+}$  co-doped  $\text{CaZrO}_3$  phosphor via  $\text{Mg}^{2+}$  doping, *RSC Adv.*, 2016, **6**, 113469–113477.
- 39 J. Xiang, J. Zheng, Z. Zhou, H. Suo, X. Zhao, X. Zhou, N. Zhang, M. S. Molokeev and C. Guo, Enhancement of red emission and site analysis in  $\text{Eu}^{2+}$  doped new-type structure  $\text{Ba}_3\text{CaK}(\text{PO}_4)_3$  for plant growth white LEDs, *Chem. Eng. J.*, 2019, **356**, 236–244.
- 40 H. Yao, Y. Zhang and Y. Xu, Dopant concentration-dependent morphological evolution of  $\text{Zn}_2\text{GeO}_4:\text{Mn}^{2+}/\text{Eu}^{3+}$  phosphor and optical temperature sensing performance, *J. Alloys Compd.*, 2019, **770**, 149–157.
- 41 A. Luchechko, O. Kravets, L. Kostyk and O. Tsvetkova, Luminescence spectroscopy of  $\text{Eu}^{3+}$  and  $\text{Mn}^{2+}$  ions in  $\text{MgGa}_2\text{O}_4$  spinel, *Radiat. Meas.*, 2016, **90**, 47–50.
- 42 M. Vasile, P. Vlazan and N. M. Avram, Characterization and optical properties of  $\text{ZnGa}_2\text{O}_4:\text{Eu}^{3+}$  nanophosphor grown by hydrothermal method, *J. Alloys Compd.*, 2010, **500**, 185–189.
- 43 Y.-M. Peng, Y.-K. Su and R.-Y. Yang, The charge transfer transition phenomenon and microstructure of  $\text{Eu}^{3+}$ -doped  $\text{NaCaPO}_4$  phosphors sintered with  $\text{NH}_4\text{Cl}$  flux via solid-state reaction, *Mater. Res. Bull.*, 2013, **48**, 1946–1951.
- 44 M. M. Yawalkar, G. D. Zade, V. Singh and S. J. Dhoble, Investigation of luminescence processes in  $\text{Li}_6\text{Gd}(\text{BO}_3)_3:\text{Eu}^{3+}$  phosphor, *J. Mater. Sci.: Mater. Electron.*, 2017, **28**, 180–189.
- 45 C. S. Vandana and B. H. Rudramadevi, The effect of  $\text{Mg}^{2+}$  concentration on structural and luminescent properties of  $\text{CaTiO}_3:\text{Eu}^{3+}$  phosphor, *Ferroelectrics*, 2018, **524**, 168–180.
- 46 M. K. Hussien and F. B. Dejene, Effect of  $\text{Cr}^{3+}$  doping on structural and optical property of  $\text{ZnGa}_2\text{O}_4$  synthesized by sol gel method, *Optik*, 2019, **181**, 514–523.
- 47 R. S. Yadav, S. J. Dhoble and S. B. Rai, Enhanced photoluminescence in  $\text{Tm}^{3+}$ ,  $\text{Yb}^{3+}$ ,  $\text{Mg}^{2+}$  tri-doped  $\text{ZnWO}_4$  phosphor: Three photon upconversion, laser induced optical heating and temperature sensing, *Sens. Actuators, B*, 2018, **273**, 1425–1434.
- 48 S. D. Meetei, M. D. Singh and S. D. Singh, Facile synthesis, structural characterization, and photoluminescence mechanism of  $\text{Dy}^{3+}$  doped  $\text{YVO}_4$  and  $\text{Ca}^{2+}$  co-doped  $\text{YVO}_4:\text{Dy}^{3+}$  nano-lattices, *J. Appl. Phys.*, 2014, **115**, 204910.
- 49 T. S. Sreena, P. P. Rao, K. N. Ajmal and A. K. V. Raj, Influence of morphology on luminescence properties of xenotime-type phosphors  $\text{NaYP}_2\text{O}_7:\text{Eu}^{3+}$  synthesized via solid state and citrate-gel routes, *J. Mater. Sci.: Mater. Electron.*, 2018, **9**, 7458–7467.
- 50 E. Kaewnuama and J. Kaewkhao, Synthesis-temperature effect on the luminescence under light and UV excitation of  $\text{Eu}^{3+}$  doped lithium lanthanum borate phosphor, *Mater. Today: Proc.*, 2018, **5**, 15086–15091.
- 51 Q. Zhang, X. Wang, X. Ding and Y. Wang, A potential red-emitting phosphor  $\text{BaZrGe}_3\text{O}_9:\text{Eu}^{3+}$  for WLED and FED applications: Synthesis, structure, and luminescence properties, *Inorg. Chem.*, 2017, **56**, 6990–6998.
- 52 G. Zhu, Z. Ci, Y. Shi, M. Que, Q. Wang and Y. Wang, Synthesis, crystal structure and luminescence characteristics of a novel red phosphor  $\text{Ca}_{19}\text{Mg}_2(\text{PO}_4)_{14}:\text{Eu}^{3+}$  for light emitting diodes and field emission displays, *J. Mater. Chem. C*, 2013, **1**, 5960–5969.

