


PCCP

Physical Chemistry Chemical Physics

rsc.li/pccp



ISSN 1463-9076

PAPER

Alexander Kandratsenka *et al.*

An experimentally validated neural-network potential
energy surface for H-atom on free-standing graphene
in full dimensionality



Cite this: *Phys. Chem. Chem. Phys.*,
2020, 22, 26113

An experimentally validated neural-network potential energy surface for H-atom on free-standing graphene in full dimensionality†

Sebastian Wille,^{ab} Hongyan Jiang,^a Oliver Bünermann,^{cd}
Alec M. Wodtke,^{acd} Jörg Behler^{bd} and Alexander Kandratsenka^{id}*^a

We present a first principles-quality potential energy surface (PES) describing the inter-atomic forces for hydrogen atoms interacting with free-standing graphene. The PES is a high-dimensional neural network potential that has been parameterized to 75 945 data points computed with density-functional theory employing the PBE-D2 functional. Improving over a previously published PES [Jiang *et al.*, *Science*, 2019, **364**, 379], this neural network exhibits a realistic physisorption well and achieves a 10-fold reduction in the RMS fitting error, which is 0.6 meV per atom. The chemisorption barrier is 172 meV, which is lower than that of the REBO-EMFT PES (260 meV). We used this PES to calculate about 1.5 million classical trajectories with carefully selected initial conditions to allow for direct comparison to results of H- and D-atom scattering experiments performed at incidence translational energy of 1.9 eV and a surface temperature of 300 K. The theoretically predicted scattering angular and energy loss distributions are in good agreement with experiment, despite the fact that the experiments employed graphene grown on Pt(111). Compared to previous calculations, the agreement with experiments is improved. The remaining discrepancies between experiment and theory are likely due to the influence of the Pt substrate only present in the experiment.

Received 28th June 2020,
Accepted 4th September 2020

DOI: 10.1039/d0cp03462b

rscl.li/pccp

1 Introduction

H-Atom chemisorption to graphene is relevant to hydrogen storage,¹ the catalytic formation of molecular hydrogen in the interstellar medium² and—because hydrogenation of graphene can induce a band-gap—two-dimensional semiconductor materials.³ Recently, a full-dimensional PES was reported⁴ using first principles energies obtained from Embedded Mean-Field Theory (EMFT)^{5–7} to parameterize a second generation Reactive Empirical Bond Order (REBO) function.⁸ Using classical and semi-classical dynamics calculations, qualitative agreement was obtained with H-atom scattering experiments carried out at incidence translational energies E_i of 1.9 and 1 eV.

Furthermore, the trajectories provided an atomic scale movie at the femtosecond time scale showing the formation of a covalent chemical bond.⁴ The sticking probability could also be calculated using the REBO-EMFT PES and compared well with experiment at $E_i = 1$ eV. This suggests that the REBO-EMFT PES is the best available representation of interatomic forces in the H/graphene system.

Despite the progress made in that work, two problems remained. First, the EMFT data was derived from a model of free-standing graphene, while the experiment was carried out on graphene that had been grown on Pt(111).⁴ To account for the influence of Pt in the simulations, a Lennard-Jones (LJ) interaction model with the Pt substrate was included for each atom in the graphene layer. This improved agreement with experiment, suggesting the influence of the substrate may be important. Unfortunately, it is unclear how to reparameterize the analytical REBO-EMFT PES from first-principles energies that include the Pt substrate. Therefore, the role of the substrate remains uncertain. The second problem concerns the fitting error (7 meV per atom) as the REBO function is not flexible enough to closely reproduce electronic structure data.⁴ This complicates the evaluation of the quality of different electronic structure methods, since the fitting error can easily be larger than the energy differences between the methods

^a Department of Dynamics at Surfaces, Max-Planck-Institute for Biophysical Chemistry, Am Fassberg 11, 37077 Göttingen, Germany.
E-mail: akandra@mpi-bpc.mpg.de

^b Institute for Physical Chemistry, Theoretische Chemie, Georg-August University of Göttingen, Tammannstraße 6, 37077 Göttingen, Germany

^c Institute for Physical Chemistry, Georg-August University of Göttingen, Tammann-straße 6, 37077 Göttingen, Germany

^d International Center for Advanced Studies of Energy Conversion, Georg-August University of Göttingen, Tammannstraße 6, 37077 Göttingen, Germany

† Electronic supplementary information (ESI) available. See DOI: 10.1039/d0cp03462b



being compared. Clearly, a full-dimensional first-principles PES where fitting errors are small and where the role of the Pt substrate is included would be a significantly better approach to this problem. For both of these problems a solution is offered by atomistic potentials employing machine learning (ML) methods.

In recent years, ML potentials have become a promising new approach to construct PESs of first-principles quality.^{9,10} They have a uniquely flexible functional form that allows the accurate reproduction of reference data sets obtained in electronic structure calculations, without sacrificing the efficiency needed when they are repetitively evaluated in large-scale molecular dynamics (MD) simulations. ML potentials have been developed for many systems. These include free-standing¹¹ and multi-layer graphene¹² as well as graphite^{12–14} and amorphous carbon,¹⁵ which are closely related to this work. A frequently used type of machine learning potential suitable for large condensed systems is the high-dimensional neural network potential energy surface (HDNN-PES) method proposed by Behler and Parrinello in 2007.¹⁶

In this paper, we present the first HDNN-PES for H atoms interacting with free standing graphene, which we validate against data obtained from H and D scattering experiments using graphene grown on Pt(111), experiments that are similar to those recently reported elsewhere.¹⁷ Compared to the REBO-EMFT PES,⁴ we achieve substantially reduced fitting errors without sacrificing computational performance. Using MD, we show that experimentally obtained H/D-atom energy loss and angular distributions are faithfully reproduced. We demonstrate the improvement represented by the HDNN-PES by comparing the new results to MD simulations done with the previously reported REBO-EMFT PES.⁴ The remaining deviations between experiment and theory likely reflect the absence of the Pt substrate in our simulations; however, the influence of the substrate on the scattering distributions appears to be relatively small.

2 Experimental methods

The experimental apparatus has been described in detail in ref. 18. H/D-atoms are generated by photodissociating a supersonic molecular beam of hydrogen/deuterium iodide with a KrF excimer laser producing atoms with incidence energy of 1.9 eV. A small fraction of these atoms passes through two differential pumping stages, enter the ultra-high vacuum chamber and collide with the graphene sample grown *in situ* on a Pt(111) substrate. The sample is held on a six-axis manipulator, allowing variation of the incidence angle θ_i . Recoiling atoms are excited to a long lived Rydberg state ($n = 34$) by two laser pulses at 121.5 nm and 365 nm *via* a two-step excitation. These neutral atoms travel 25 cm in a field-free region and pass a detector aperture before they are field-ionized and detected by a multi-channel plate detector. The arrival time is recorded by a multi-channel scaler. The rotatable detector allows data to be recorded at various scattering angles θ_s . The graphene sample

is epitaxially grown on a clean Pt(111) substrate by dosing ethylene (partial pressure 3×10^{-8} mbar) at 700 °C for 15 minutes.

3 Computational methods

3.1 HDNN-PES

High-dimensional neural network potentials (HDNN-PESs)¹⁶ have been the first type of ML potential enabling the simulations of large condensed systems. In this approach, the total potential energy E_{tot} of the system is constructed as a sum of atomic energy contributions,

$$E_{\text{tot}} = \sum_{\mu=1}^{N_{\text{atoms}}} E_{\mu}, \quad (1)$$

depending on the local chemical environment defined by a cutoff radius R_c , typically in the range between 6 and 10 Å. The positions of all neighboring atoms inside the cutoff spheres are described by sets of atom-centered many-body symmetry functions.¹⁹ The resulting vector of symmetry function values for each atom represents a structural fingerprint that is used as input for an atomic neural network yielding atomic energy contribution E_{μ} into the total energy (1). The functional forms of the symmetry functions ensure the necessary invariance of PES with respect to translations and rotations of the system as well as permutations of like atoms. The atomic neural networks are feed-forward neural networks and contain a large number of weight parameters, which serve as fitting parameters for the HDNN-PES. Each element in the system is modeled by a separate atomic neural network with a specific architecture and values of the weight parameters calculated once for each atom of the respective element in the system. The values of these parameters are determined in an iterative optimization process by minimizing the errors of the energies and forces for a reference data set of representative structures obtained from electronic structure calculations, typically density-functional theory. Additional structures that may be required in the reference set in regions of the PES that are not well sampled can be suggested by an automatic procedure employing a committee of HDNN-PESs and a comparison of predicted energies and forces²⁰ leading to a self-consistent and unbiased generation of the data set. Once a set of weight parameters accurately reproducing the reference data has been found, the PES undergoes a series of careful validation steps.²¹ Then, the HDNN-PES is ready for applications. For all the details about the HDNN-PES method, the determination of the weight parameters and its validation procedures, the interested reader is referred to several recent reviews^{21–23}

3.2 Density functional theory calculations

The Vienna *ab initio* simulation package (VASP) version 5.3.5^{24–27} has been employed for the reference electronic structure calculations to generate the training set for the HDNN-PES. Density functional theory (DFT) at the generalized gradient approximation (GGA) level of theory using the Perdew–Burke–Ernzerhof (PBE)²⁸






Fig. 1 Primitive cell containing two C-atoms used to create the 3×4 graphene slab. Important high-symmetry sites are indicated by small white balls. This figure and the ones showing surface structures of graphene are created using OVITO version 2.9.0.³³

exchange–correlation functional with a plane-wave basis has been used in combination with Grimme D2 van der Waals (vdW) corrections.²⁹ We made use of the Projector Augmented Wave (PAW)^{27,30} approach to model the core and valence electron interactions. The kinetic energy cutoff has been set to 400 eV. The Monkhorst–Pack scheme³¹ with a $8 \times 8 \times 1$ Γ -centered k -point mesh for the 3×4 surface cell has been used to sample the surface Brillouin zone. With two atoms per primitive unit cell, the slab consists of 24 carbon atoms in total and is $8.55 \text{ \AA} \times 7.40 \text{ \AA}$ in size (see Fig. 1). 3D periodic boundary conditions have been applied with $13 \text{ \AA}$ vacuum perpendicular to the graphene sheet to ensure that the periodic images of the surfaces are non-interacting and that hydrogen atoms can be included at a maximum separation of $6 \text{ \AA}$ from the surface. We included spin polarization in the electronic structure calculations, and partial occupations have been treated by applying the tetrahedron method with Blöchl corrections^{30,32} using the default value of 0.2 eV as the smearing parameter. The threshold for the change in energy between iteration steps when relaxing the electronic degrees of freedom has been 10^{-5} eV .

3.3 Generating the reference structures

The iterative procedure described in detail elsewhere³⁴ was used to generate the reference data. Briefly, step by step new DFT energies and forces are added for geometries where the HDNN-PES fit does not show the desired accuracy or covers the full configurational space. These geometries are identified by comparing the results of several generated HDNN-PESs with differing network structures. The reference data set is then extended with the additional data until convergence is reached.

The initial data set consists of energies and forces obtained from DFT calculations for about 6×10^4 reference configurations, which were picked up from: (i) *ab initio* molecular dynamics (AIMD) trajectories simulating H-atom scattering from graphene at incidence energy of 1.9 eV and incidence angles of 34° and 52° at surface temperatures of 300 K and 600 K ; (ii) geometries close to the minimum energy path to adsorption, where the H-atom was put at the lateral position of the C-atom and the z -coordinates

were varied over a range of $-0.8 \text{ \AA} \leq z_{\text{H}} \leq 5.8 \text{ \AA}$ and $-0.8 \text{ \AA} \leq z_{\text{C}} \leq 1.0 \text{ \AA}$, respectively, with $0.025 \text{ \AA}$ step and without structures with $r_{\text{CH}} < 0.6 \text{ \AA}$, whereas the remaining C-atoms were kept at their equilibrium positions; (iii) graphene geometries chosen randomly from an AIMD trajectory thermalized at 300 K with H-atom over the surface. The position of the H-atom is chosen randomly over the whole simulation cell where the z -coordinate ranges from 1 to $6 \text{ \AA}$. The configuration with a C–H distance of $6 \text{ \AA}$ and a fully relaxed graphene surface was used as the asymptotic energy reference. This structure is our energy zero point.

The HDNN-PESs fitted to the initial reference data set were then improved on the set of about 1.5×10^4 configurations obtained from MD simulations of H-atom scattering from a graphene sheet at incidence energy of 1.9 eV in the wide range of incidence angles (from 0° to 90° in 10° step) as well as at incidence energy of 6 eV and normal incidence angle with surface temperatures of 0 K and 600 K starting over high-symmetry sites shown in Fig. 1. Moreover, we also trained the HDNN-PESs on the configurations taken from equilibrium MD simulations of the graphene surface in the wide range of temperatures from 0 K to 2000 K . The high-temperature configurations are useful, since the surface can be heated locally in the neighborhood of the collision site.

In total, the final HDNN-PES was trained on the reference data set of $75\,945$ configurations.

3.4 Construction of the neural network potential

The HDNN-PES has been constructed using the RuNNer^{21,22,35} code. The atomic neural network's architecture consists of two hidden layers with 15 neurons per layer providing the energies both for hydrogen and carbon atoms. The parameters of symmetry functions¹⁹ are listed in Table S1 of ESI.† The symmetry function values have been rescaled to the range from 0 to 1 . Randomly selected 90% of the reference data were used to train the NN, whereas the remaining 10% were used as an independent test set to validate the fit and to check for overfitting. The NN weight parameters were determined from the DFT energies and forces employing the adaptive global extended Kalman filter.³⁶ The initial values of the weight parameters have been chosen randomly in the interval from -1 to 1 . For the weights, a preconditioning scheme was applied to reduce the initial root-mean-square error (RMSE).²¹ The training data in each of the 200 iterations (epochs) of the fit were presented in a random order to reduce the probability of getting trapped in local minima.

3.5 Molecular dynamics simulations details

MD simulations of H-atom scattering from graphene were performed using MDT2 code³⁷ developed to study atomic scattering from various surfaces.^{4,38,39} The RuNNer subroutines implementing the HDNN-PES providing the energies and forces were integrated into the MDT2 code. All the results shown in this paper have been obtained from MD simulations carried out using the RuNNer-MDT2 interface.

MD simulations of the H/D scattering from graphene have been carried out in the *NVE* ensemble using the standard






Fig. 4 Potential energies from AIMD and HDNN-PES trajectories with $E_i = 1.9$ eV, $\theta_i = 34^\circ$ and $\phi_i = 0^\circ$. The two trajectories were launched with identical initial conditions and both traverse the chemisorption well before returning to the gas phase after a single bounce. The distance of closest approach is below $r_{CH} = 1.4$ Å. Movies of the two trajectories can be found in the ESI.†

experiment below. Fig. 4 shows the potential energy change along the trajectory while Fig. 5 shows the H atom motion in the trajectory in a perspective drawing. The trajectories obtained with these two approaches are nearly identical—note that if the fitting were perfect they would be identical. We now turn to the question: how well is the experiment reproduced by classical MD on the new HDNN-PES.

Fig. 6 and 7 show comparisons between experiment and theory for H and D scattering from graphene, respectively. In both figures, panels (A–C) show experimentally derived angle-resolved energy loss distributions represented as heat maps for three values of the incidence polar angle θ_i indicated with red numbers on the polar axes. The energy loss is the fraction of the incidence kinetic energy of the projectile E_i and the kinetic




Fig. 5 The same two trajectories as in Fig. 4—AIMD (red) and HDNN-PES (blue). The H-atom's initial position is shown as a cyan colored ball. The divergence between the two trajectories is due to residual error in the NN fit to the DFT data. A "side view" of the trajectories can be found in the ESI.†




Fig. 6 Comparing theory with experiment for H-scattering from graphene at incidence kinetic energy $E_i = 1.9$ eV. The energy loss is the fraction of E_i and the kinetic energy of the H-atom after its collision with the surface E_s . Experimental distribution are shown in panels (A–C) along with theoretical distribution found from MD simulations using the HDNN-PES (D–F) and the REBO-EMFT PES from ref. 4 (G–I). The red labeled ticks indicate both the incidence and specular scattering angles. The integrated signals of panel A, D and G are normalized to 1. The number of trajectories used for the plots are shown in Table S2 in the ESI.†

energy after its collision with the surface E_s . Panels (D–F) show theoretically predicted distributions derived with the HDNN-PES





Fig. 7 Comparing theory with experiment for D-scattering from graphene at $E_i = 1.9$ eV. Experimental distribution are shown in panels (A–C) along with theoretical distribution found from MD simulations using the HDNN-PES (D–F). The number of trajectories used for the plots are shown in Table S2 in the ESI.†

The quality of the results can be more clearly seen in angle-integrated energy loss distributions shown in Fig. 8. Here, the H and D energy loss distributions have in each case been normalized to the integrated scattering intensity of the $\theta_i = 59.5^\circ$ distributions. The integrated scattering intensity drops off too rapidly with decreasing incidence angle, reflecting the overestimation of out-of-plane scattering in MD simulations, which is likely related to either to inaccuracies of the DFT data or the



The theoretically predicted D-atom energy loss for the transient bond-forming channel matches experiment remarkably well—see in particular panel D—but the H energy loss is smaller than experimental observation. We note that this is consistent with possible electronically non-adiabatic dynamics where the H atom energy loss is larger than that of the D-atom due to its higher velocity.

The theoretical distributions are remarkably close to those seen in experiment. They accurately capture the branching between a quasi-elastic channel that samples only the physisorption well and a high-energy-loss channel that results from trajectories that

traverse the chemisorption well. The simulations also capture subtle differences between H and D scattering seen in experiment that appear as broadening of the angular distribution at specific values of θ_i . These results suggest that for scattering at 1.9 eV, neglecting the Pt substrate in the model of scattering dynamics does not introduce large errors.

We do, however, still see systematic differences between experiment and theory. These may be due to failure of the classical or Born–Oppenheimer approximations or both. It is, of course, possible that improved electronic structure data as well as a proper inclusion of the influence of the Pt substrate could explain the remaining discrepancies between experiment and theory. While the present work is only a first step, it demonstrates a crucial milestone toward developing a first principles quality PES that includes the influence of the metal substrate.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

We thank the DFG for financial support *via* the SFB 1073 projects A04 and C03 (Project No. 217133147). We gratefully acknowledge the funding of this project by computing time provided by the DFG project INST186/1294-1 FUGG (Project No. 405832858). AK acknowledges European Research Council (ERC) under the European Union's Horizon 2020 research and innovation programme (grant agreement no. 833404). Open Access funding provided by the Max Planck Society.

Notes and references

- 1 L. Schlapbach and A. Züttel, *Nature*, 2001, **414**, 353–358.
- 2 L. Hornekaer, A. Baurichter, V. Petrunin, D. Field and A. Luntz, *Science*, 2003, **302**, 1943–1946.
- 3 R. Balog, B. Jorgensen, L. Nilsson, M. Andersen, E. Rienks, M. Bianchi, M. Fanetti, E. Laegsgaard, A. Baraldi, S. Lizzit, Z. Sljivancanin, F. Besenbacher, B. Hammer, T. G. Pedersen, P. Hofmann and L. Hornekaer, *Nat. Mater.*, 2010, **9**, 315–319.
- 4 H. Jiang, M. Kammler, F. Ding, Y. Dorenkamp, F. R. Manby, A. M. Wodtke, T. F. Miller, III, A. Kandratsenka and O. Bünermann, *Science*, 2019, **364**, 379–382.
- 5 M. E. Fornace, J. Lee, K. Miyamoto, F. R. Manby and T. F. Miller, III, *J. Chem. Theory Comput.*, 2015, **11**, 568–580.
- 6 F. Ding, T. Tsuchiya, F. R. Manby and T. F. Miller, III, *J. Chem. Theory Comput.*, 2017, **13**, 4216–4227.
- 7 F. Ding, F. R. Manby and T. F. Miller, III, *J. Chem. Theory Comput.*, 2017, **13**, 1605–1615.
- 8 D. Brenner, O. Shenderova, J. Harrison, S. Stuart, B. Ni and S. Sinnott, *J. Phys.: Condens. Matter*, 2002, **14**, 783–802.
- 9 J. Behler, *J. Chem. Phys.*, 2016, **145**, 170901.
- 10 F. Noé, A. Tkatchenko, K.-R. Müller and C. Clementi, *Annu. Rev. Phys. Chem.*, 2020, **71**, 361–390.
- 11 P. Rowe, G. Csányi, D. Alfè and A. Michaelides, *Phys. Rev. B*, 2018, **97**, 054303.
- 12 M. Wen and E. B. Tadmor, *Phys. Rev. B*, 2019, **100**, 195419.
- 13 R. Z. Khaliullin, H. Eshet, T. D. Kühne, J. Behler and M. Parrinello, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, **81**, 100103.
- 14 R. Z. Khaliullin, H. Eshet, T. D. Kühne, J. Behler and M. Parrinello, *Nat. Mater.*, 2011, **10**, 693–697.
- 15 V. L. Deringer and G. Csányi, *Phys. Rev. B*, 2017, **95**, 094203.
- 16 J. Behler and M. Parrinello, *Phys. Rev. Lett.*, 2007, **98**, 146401.
- 17 H. Jiang, X. Tao, M. Kammler, F. Ding, A. M. Wodtke, A. Kandratsenka, T. F. Miller III and O. Bünermann, 2020, arXiv:2007.03372 [physics.chem-ph].
- 18 O. Bünermann, H. Jiang, Y. Dorenkamp, D. J. Auerbach and A. M. Wodtke, *Rev. Sci. Instrum.*, 2018, **89**, 094101.
- 19 J. Behler, *J. Chem. Phys.*, 2011, **134**, 074106.
- 20 N. Artrith and J. Behler, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2012, **85**, 045439.
- 21 J. Behler, *Int. J. Quantum Chem.*, 2015, **115**, 1032–1050.
- 22 J. Behler, *Angew. Chem., Int. Ed.*, 2017, **56**, 12828.
- 23 J. Behler, *J. Phys.: Condens. Matter*, 2014, **26**, 183001.
- 24 G. Kresse and J. Furthmüller, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1996, **54**, 11169.
- 25 G. Kresse, *J. Non-Cryst. Solids*, 1995, **192–193**, 222–229.
- 26 G. Kresse and J. Furthmüller, *Comput. Mater. Sci.*, 1996, **6**, 15–50.
- 27 G. Kresse and D. Joubert, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1999, **59**, 1758–1775.
- 28 J. P. Perdew, K. Burke and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, **77**, 3865–3868.
- 29 S. Grimme, *J. Comput. Chem.*, 2006, **27**(15), 1787–1799.
- 30 P. E. Blöchl, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1994, **50**, 17953–17979.
- 31 H. J. Monkhorst and J. D. Pack, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1976, **13**, 5188–5192.
- 32 P. E. Blöchl, O. Jepsen and O. K. Andersen, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1994, **49**, 16223–16233.
- 33 A. Stukowski, *Modell. Simul. Mater. Sci. Eng.*, 2010, **18**, 015012.
- 34 N. Artrith and J. Behler, *Phys. Rev. B*, 2012, **85**, 045439.
- 35 J. Behler, *RuNNer – A Neural Network Code for High-Dimensional Potential-Energy Surfaces*, Universität Göttingen, 2020, <http://www.uni-goettingen.de/de/560580.html>.
- 36 T. B. Blank and S. D. Brown, *J. Chemom.*, 1994, **8**, 391–407.
- 37 D. J. Auerbach, S. M. Janke, M. Kammler, S. Kandratsenka and S. Wille, *Molecular Dynamics Tian Xia 2 (MDT2)*; program for simulating the scattering of atoms and molecules from a surface (GitHub repository), 2020, Available at https://github.com/akandra/md_tian2.
- 38 S. M. Janke, D. J. Auerbach, A. M. Wodtke and A. Kandratsenka, *J. Chem. Phys.*, 2015, **143**, 124708.
- 39 O. Bünermann, H. Jiang, Y. Dorenkamp, A. Kandratsenka, S. M. Janke, D. J. Auerbach and A. M. Wodtke, *Science*, 2015, **350**, 1346–1349.
- 40 M. P. Allen and D. J. Tildesley, *Computer Simulation of Liquids*, Clarendon Press, USA, 1st edn, 1989.



- 41 W. C. Swope, H. C. Andersen, P. H. Berens and K. R. Wilson, *J. Chem. Phys.*, 1982, **76**, 637.
- 42 D. Frenkel and B. Smit, *Understanding Molecular Simulation: From Algorithms to Applications*, Academic Press, San Diego, 2nd edn, 2002.
- 43 H. C. Andersen, *J. Chem. Phys.*, 1980, **72**, 2384.
- 44 E. Ghio, L. Mattera, C. Salvo, F. Tommasini and U. Valbusa, *J. Chem. Phys.*, 1980, **73**, 556–561.
- 45 M. Bonfanti, R. Martinazzo, G. F. Tantardini and A. Ponti, *J. Phys. Chem. C*, 2007, **111**, 5825–5829.

